



WEATHER 5010

SEALING & BONDING

NEUTRAL SEALANT

RESIBOND WEATHER 5010 is a single-component, neutral-cure, weather-resistant silicone sealant. It is an excellent sealant for exterior applications like ACP and uPVC profile joint sealing. It is specifically designed for general glazing and weather sealing in curtain walls and building facades.

Exterior | Excellent weatherability



UV & water
resistant



Long-lasting
performance



Crack
resistant

FEATURES AND BENEFITS



Low modulus – with
extension/compression
capability



Primerless adhesion



Excellent resistance
to ageing



Easy tooling and soft
extrudable properties



Service temperature
-40°C to 200°C


AREAS OF APPLICATION



Exterior sealing
applications of glazing
stone, uPVC doors
and windows



Exterior sealing
and bonding ACP



Elevated
glass to glass sealing



Weather sealing
in curtain wall and
building facades

TECHNICAL DATA

PROPERTIES	TESTING STANDARD	SPECIFICATION		UNIT
Colour	-	Clear, Black, White, Brown and Grey		-
Uncured – 25°C, 50% R.H				
Paste density	ASTM D 1475	Black, White Brown and Grey	Clear	
		1.35-1.45	0.99-1.1	g/cc
Skin formation time	-	20-30		Min
Tack-free time	ASTM C 679-15	180		Min
Cured 7 days – 25°C, 50% R.H.				
Elongation	ASTM D 412	>600		%
Hardness (Shore-A)	ASTM D 2240	18-25		-
Tensile strength	ASTM D 412	>10		kg/cm²

HOW TO USE

Preparation:

The substrate areas that will be in contact with the sealant must be clean, dry and free of all loose material such as dust, dirt, rust, oil and other contaminants. Non-porous substrates should be cleaned with a solvent and a clean, lint-free cotton cloth. Remove residual solvent before it evaporates with a fresh, clean, and dry cloth.

Masking:

Masking will ensure a clean, neat appearance and reduce cleanup by protecting surrounding areas from excess sealant.

Applying:

Cut the nozzle at 45° and screw it onto the cartridge, and place it into the caulking gun. Air-operated or hand-operated caulking guns can be used. Apply sealant into the base of the joint so that it fills the joint, wetting both sides. Do not simply lay a bead on the surface, as the sealant will not penetrate the joint under its own weight.

Tooling:

Tool the surface of the joint immediately after sealant application to provide a smooth, even finish and to ensure the sealant wets the sides of the joint. A tool with a convex profile is recommended to keep the sealant within the joint. After a skin has formed, do not disturb the joint for 24 hrs.

RESTRICTIONS ON USE

Not recommended for structural bonding.

SHELF LIFE

Usable life is 12 months in the original packaging. For more information, refer to the package.

STORAGE

Store properly in a dry and well-ventilated place below 30°C.

PACKING INFORMATION

280 ml cartridge
600 ml sausage

HANDLING PRECAUTIONS

Test it before use. The user is responsible to conduct property test before using it to confirm that the sealant produces satisfactory results. Especially for the surface, which is difficult to adhere to and coated substrates, the cohesiveness should be tested. Be careful when applying at extreme temperatures. When the substrate surface temperature exceeds 50°C, rapid curing or bubble formation may occur. When the temperature is below 5°C, the curing process may be slower. Ensure the surface is clean and dry before application.

Remove any moisture or condensation
with a dry cloth or heat blower.

IMPORTANT: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.



ASTRAL LIMITED

Registered Office: 207/1, 'Astral House',
B/h Rajpath Club, Off S.G. Highway,
Ahmedabad-380059, Gujarat, India. +91 79 6621 2000
F: +91 79 6621 2121 | CIN: L25200GJ1996PLC029134

E-mail: customercare@astraladhesives.com
Website: www.astraladhesives.com
Website: www.resibond.com



MORE
CONVENIENCE



FASTER
FEEDBACK



ADDRESS TO
TECHNICAL QUERY

Experience A Better Connect With The Company

EXCLUSIVELY FOR OUR CHANNEL
PARTNERS and CUSTOMERS

Visit us at:

wecare.astraladhesives.com