

# TRU PU PURA 1K

Polyurethane Based Liquid Applied Waterproofing Compound

ASTRAL

# TRUBUILD™

TECHNICAL DATA SHEET VER NO. N.1

## PRODUCT DESCRIPTIONS

**Tru PU Pura 1K** is a single-component, ready-to-use, pure polyurethane-based, liquid applied waterproofing membrane. It has excellent waterproofing properties and can be applied by brush & roller. It is ideal for waterproofing of terrace, roofs, balconies, bridges, podium and canals, etc.



### FEATURES & ADVANTAGES



#### EXCELLENT BOND STRENGTH

- Single component, hence ready to apply.
- Liquid applied membrane, hence easy to use.
- Excellent waterproofing properties.
- Good crackbridging ability.
- Root resistant.



#### CRACK BRIDGING



#### EXCELLENT WATERPROOFING

- Excellent bond strength, hence good durability.
- Excellent adhesion to metal & concrete.
- Seamless coating, hence no joint.



#### READY TO APPLY

## AREAS OF APPLICATION



- Waterproofing of balconies, terraces, sloppy roofs, bridges, etc.
- Waterproofing of podium, tunnels, deck area & canals, etc.

## PACKAGING



## METHOD OF APPLICATION

### SURFACE PREPARATION

**Surface Preparation:** Surface preparation should be done by cleaning, removing dust, dirt, oil, grease and loose particles. Maximum permissible moisture content in concrete should be <5%. Higher humidity may modify the curing performance of Tru PU Pura 1K, which may affect the final finish. Repair the cracks with PMM using Trubuild SBR 333. In case of metal, remove rust from surfaces by using proper power tool to remove the rust & scaling. Surface should be free from oil, grease, dust and loose particles.

**Priming:** The concrete surface should be primed with Trubuild Primesure EPMI at an application rate of 80-100 sqft./L and then allow it to reach touch dry conditions. Consumption of primer may vary and it depends upon the substrate porosity.

**Coatings:** After opening the bucket, stir Tru PU Pura 1K with low-speed mechanical stirrer before use. Pour Tru PU Pura 1K to the primed substrate and spread with roller or brush. It is highly recommended to restrict maximum WFT of 0.5-0.6mm thickness in each layer. Allow it to cure for 24 hours and apply consecutive layer at same recommended thickness and consumption (not later than 48 hours).

**Curing:** Recommended air curing for at least 7 days for getting desirable properties.

## TECHNICAL PROPERTIES

| S.NO. | PROPERTIES                                  | UNIT                 | STANDARD          | RESULTS                                    |
|-------|---------------------------------------------|----------------------|-------------------|--------------------------------------------|
| 01.   | Appearance                                  | -                    | -                 | Opaque                                     |
| 02.   | Colour                                      | -                    | -                 | Red, Grey, White (subject to availability) |
| 03.   | Shore A                                     | -                    | In house          | 60                                         |
|       | Solid                                       | %                    | ASTM C 836:2018   | >85                                        |
|       | Low temp, crack bridging @ 3.2 mm extension |                      | ASTM C 1305:2016  | No cracking                                |
|       | Adhesion in peel after water immersion      | N                    | ASTM C 794:2018   | 26                                         |
|       | Tensile strength                            | N/mm <sup>2</sup>    | ASTM D 412:2016   | >2                                         |
|       | Elongation                                  | %                    | ASTM D 412:2016   | >500                                       |
|       | Density at @25°C                            | gm/cc                | In house          | 1.45                                       |
|       | Cure time                                   |                      | In house          | 7 days                                     |
|       | Water vapour transmission                   | g/m <sup>2</sup> day | ASTM E 96:2022    | 19.4                                       |
|       | Resistant to water @ 5 bar pressure         | mm                   | EN 1239-8:2019    | Pass                                       |
|       | Root penetration                            |                      | CEN/TS 14416:2014 | No root penetration                        |

**Confirms requirements of ASTM C 836:2018**

## PROTECTION SCREED

Use minimum 100/120 GSM geotextile fabric to lay over fully cured Tru PU Pura 1K as separation layer. Protect the coating with – 20/25 grade concrete screed at minimum thickness of 35 mm and at 1:100 slope toward drain outlet. Make angle fillet at the time of screed application using Trubuild SBR 333, polymer modified mortar at all junctions. Control joints shall be provided along the length and breadth of the entire screed area by using a saw cutting machine within 18-24 hours of application of the screed. The panel size of 3.25 m x 3.25 m is recommended with a maximum panel size of 15 m<sup>2</sup>, or as specified by consultant/engineer. All joints shall be filled with Trubuild Sealmaster Flexi.

## HANDLING PRECAUTIONS

Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For more detail, please refer MSDS.

## STORAGE

Container should be stored in dry and cool rooms. Protect the material against moisture and direct sunlight. Storage temperature should be 20 to 30°C. Products should remain in their original, unopened container.

## CLEANING

Application equipment should be thoroughly cleaned after use with toluene/ xylene but if it dries on the tool, the tool needs to be cleaned by mechanical means. Spillages should be absorbed with sand, vermiculite or similar substrates and be disposed in accordance with local regulations.

## THEORETICAL COVERAGE

Approx 1.5 -1.6 KG to achieve 1 mm DFT persq.mtr.

**NOTE:** Coverage may vary due to porosity and undulation of the substrate.

## SHELF LIFE

12 months from the date of manufacturing.

**DISCLAIMER:** This technical data sheet replaces all previous versions of it from the immediate effect. The information, and, in particular, the recommendations relating to the application and end-use of Astral Ltd, construction chemical products, are given in good faith based on our knowledge and experience of the products when properly stored, handled and applied under suitable favourable conditions in accordance with application instructions recommended in product technical data sheet. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. For the products on which company is offering warranty, please refer to warranty document to know entire terms and conditions. The same can be availed on request or from company website. The values mentioned in the above tables in technical data sheet are obtained in controlled lab conditions when tested properly by competent laboratory. Tolerance up to five to ten percentage on the lower side from the above values are allowable. Astral Ltd. reserves the right to change the properties of its products without notice. The end user of the product must test the product's suitability for the intended application and purpose. Astral Ltd will not bear any responsibilities on the product failure if it is wrongly positioned or if improper application methodology is adopted by the user or the applicator. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local product technical data sheet for the product concerned, copies of which will be supplied on request. No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, customer is responsible for determining whether products and the information in this document are appropriate for the customer's use and for ensuring that the customer's workplace, and disposal practices are in compliance with applicable laws and other governmental enactments.