

SEALMASTER FLEXI

MS Polymer Hybrid Sealant Compound

ASTRAL

TRUBUILD™

TECHNICAL DATA SHEET VER NO. N.1

PRODUCT DESCRIPTIONS

Trubuild Sealmaster Flexi is a high quality, single-component, elastomeric joint sealant based on MS-Polymer. Once applied, the compound reacts with atmospheric moisture to form a tough and durable elastic seal.

FEATURES & ADVANTAGES



HIGH ADHESIVE STRENGTH

- High adhesive strength on most substrates
- Superior mechanical properties
- Permanently elastic after cure
- UV resistant



PAINTABLE



UV AND WEATHER RESISTANT

- Excellent weather resistance
- Can be painted
- Does not contain isocyanates, hence safe



ELASTIC




AREAS OF APPLICATION



• For gap filling. • Sealing control and expansion joint. • Bonding of metals, glass, ceramics.

PACKAGING



METHOD OF APPLICATION

- Step-1:** Clean the application area and make it dry & free from grease and detergents.
- Step-2:** Mask adjacent surfaces for neat application.
- Step-3:** Cut tip of sausage and put into the sausage gun. Consider your required bead width and remove an appropriate section from the end of the nozzle.
- Step-4:** Apply sealant in continuous, steady flow. Push the sealant ahead in the nozzle contacting both sides of joint so it is completely filled.
- Step-5:** Smoothen sealant surface immediately after application before skin forms using a spatula dipped in mild detergent.
- Step-6:** Remove the masking tape before sealant skins. Excess sealant should be removed immediately with a clean cloth dampened in mineral turpentine.

TECHNICAL PROPERTIES

S.NO.	PROPERTIES	STANDARDS	RESULTS
01.	Physical state	-	Viscous paste
02.	Appearance	-	Opaque
03.	Colour	-	White, black, grey
04.	Density (gm/cc)	-	1.35-1.50
05.	Tensile strength (MPA)	ASTM D 412: 2016	2.14
06.	Elongation (%)	ASTM D 412: 2016	> 500
07.	Shore A	ASTM D 2240: 2015	34
08.	MAF	ASTM C 719: 2014	±50%
09.	Depth cure		Approx. 1-2 mm/Day
10.	Effects of heat ageing	ASTM C 1246:2017	No cracking and chalking
11.	Stain and colour change	ASTM C 510:2016	No staining and no colour change
12.	Tack free	ASTM C 679:2015	No transfer of test specimen to the polythene film @ 72 hrs.
13.	Adhesion-in-peel strength (N)	ASTM C 794:2018	74.2 N (cohesive failure with in the sealant and no adhesive bond loss b/w adhesive and substrate)

HANDLING PRECAUTIONS

Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and used. For additional information please read Material Safety Data Sheets.

THEORETICAL COVERAGE

• For width 5 mm and depth 5 mm, approx. coverage will be 26 RMT/kg.

NOTE: Coverage will depend upon the size of the groove. Always test the product for suitability before use.

STORAGE

Product should be stored in a dry place in its original, properly closed sausage packing at temperature between 2 - 40°C. Chemical should be consumed once opened.

SHELF LIFE

12 months from the date of manufacturing

DISCLAIMER: This technical data sheet replaces all previous versions of it from the immediate effect. The information, and, in particular, the recommendations relating to the application and end-use of Astral Ltd, construction chemical products, are given in good faith based on our knowledge and experience of the products when properly stored, handled and applied under suitable favourable conditions in accordance with application instructions recommended in product technical data sheet. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. For the products on which company is offering warranty, please refer to warranty document to know entire terms and conditions. The same can be availed on request or from company website. The values mentioned in the above tables in technical data sheet are obtained in controlled lab conditions when tested properly by competent laboratory. Tolerance up to five to ten percentage on the lower side from the above values are allowable. Astral Ltd. reserves the right to change the properties of its products without notice. The end user of the product must test the product's suitability for the intended application and purpose. Astral Ltd will not bear any responsibilities on the product failure if it is wrongly positioned or if improper application methodology is adopted by the user or the applicator. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local product technical data sheet for the product concerned, copies of which will be supplied on request. No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, customer is responsible for determining whether products and the information in this document are appropriate for the customer's use and for ensuring that the customer's workplace, and disposal practices are in compliance with applicable laws and other governmental enactments.