
THAI POLYMER SUPPLY

POM-C (Polyoxymethylene)

COLORS: BLACK , WHITE



Product characteristics

High chemical resisstance
High dimensional stability
Low moisture absorption

Typical fields ofapplication

Mechanical engineering
Electrical and Electronic industries
Medical technology
industrial assembly fixture

	Test method	Value
General properties	**ASTM**	
specific Gravity (g/cm^3)	D792	1.41
Water absorption 24 hrs (%)	D570	0.2
Mechanical properties		
Tensile strength	D638	11000
Tensile modulus (psi)	D638	450000
Tensile Elongation at Break (%)	D638	30
Flexural strength (psi)	D790	13000
Flexural modulus (psi)	D790	450000
compressive strength (psi)	D695	16000
compressive modulus (psi)	D695	450000
hardness Rockwell	D785	89/122
IZOD Notched impact (fi-lb/in)	D256	1
Thermal properties		
coefficient of thermal expansion(x 10^{-5} in/in/°F)	D696	4.7
Heat deflection temperature (°F/°C)@264 psi	D648	250/121
Melting temperature (°F/°C)	D3418	347/175
max operating temperature (°F/°C)	-	180/82
thermal conductivity(BTU-in/ft^2-hr-°F)	C177	2.5
flammability rating	UL94	HB
Electrical properties		
Dielectric strength (V/mil) short time,1/8" thk	D149	450
Dielectric constant at 1 MHz	D150	3.7
Dissipation Factor at 1 MHz	D150	0.0005
volume resistivity (0hm-cm) at 50% RH	D257	10^5

THAIPOLYMER

THAIPOLYMER