| GAUTAM SOLAR | Gautam Solar Private Limited | Document No. | GSPL/IPQC/IPC/003 |
|---|---|---|---|
| | | Issue Date | 01/12/2024 |
| | IPQC Check Sheet | Rev. No./Rev.Date | 01/30-02-2025 |

Date :- 21-02-2026 Time :- 8:41 PM Shift Night Po.no.:-

| Sr.No. | Stage | Check point | Quantum of Check: Sample Size | Quantum of Check: Frequency | Acceptance Criteria | Monitoring Result | | | | | Remarks,if any |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | | No. of Holes/ Holes dimension | once | Per shift | 3 hole with dimension 12mm±0.5mm | 3 Hole, 12.00mm, 12.01mm, 12.00mm | | | | | |
| 11 | Auto Busbar Flatten (If Applicable) | Visual Inspection | 5 pieces | per shift | No cracks/ breaks in busbar &properly flattened without bending and twisting | OK | OK | OK | OK | OK | |
| 12 | Pre lamination EL &Visual inspection | EL Inspection and Visual inspection | 5 pieces | per shift | Pre EL Inspection Criteria | S.No | GS04890KG0 442663542 | | | | |
| | | | | | | S.No | GS04890KG0 442663544 | | | | |
| | | | | | | S.No | GS04890KG0 442663546 | | | | |
| | | | | | Pre EL Visual Criteria | S.No | GS04890KG0 442663548 | | | | |
| | | | | | | S.No | GS04890KG0 442663556 | | | | |
| 13 | String Rework Station | cleaning of rework station/Soldering iron and sponge | once | per shift | Rework Station should be Clean/Sponge should be Wet | Clean and wet | | | | | |
| | | Soldering Iron Temp. | once | per shift | 400±30°C | Time: 8:45 PM 424°C | | | | | |
| 14 | Module Rework Station | Method of Rework | once | per shift | As per WI (GSPL/P/WI/012) | Manual | | | | | |
| | | Cleaning of Rework station/Soldering iron sponge | once | per shift | Rework Station should be Clean/Sponge should be Wet | Clean | | | | | |
| | | Soldering Iron Temp. | once | per shift | 400±30°C | Time: 8:48 PM 426°C | | | | | |
| 15 | Laminator | Monitoring of Laminator Process parameter | once | per shift | Process Parameter of jinchen Laminator | OK | | | | | |
| | | Cleaning of Diaphragm/release sheet | once | 24h | Diaphragm/Release sheet should be clean,No EVA residue is allowed | Clean | | | | | |