GAUTAM SOLAR

Gautam Solar Private Limited

IPQC Check Sheet

Document No.	GSPL/IPQC/IPC/003
Issue Date	01/12/2024
Rev. No./Rev.Date	01/30-08-2025

Date :- 21-02-2026 Time :- 8:30 PM Shift Night. Po.no.:-

Sr.No.	Stage	Check point	Quantum of Check: Sample Size	Quantum of Check: Frequency	Acceptance Criteria	Monitoring Result					Remarks,if any
		Peel of Test b/w: EVA/Backsheet EVA/EPE/POE to Glass	All position	All laminators to be coverd in a month	E/G ≥60N/cm E/B≥60N/cm	Refer Document GSPL/IPQC/QC/001					
		Gel Content Test			75to 95%	Refer Document GSPL/IPQC/QC/001					
16	Auto Tape Removing (If Applicable)	Visual Check after Lamination	5 pieces	per shift	Check Tape Removing Should be smooth and No visual bubble Should be found.	—	—	—	—	—	Manually.
17	Auto Edge Trimming	Trimming Quality	5 pieces	per shift	Excess layer from the glass edge should be removed,Uneven Trimming not allowed	S.No.	GS04890KG0442662958				
						S.No.	GS04890KG0442662959				
						S.No.	GS04890KG0442663001				
						S.No.	GS04890KG0442662983				
						S.No.	GS04890KG0442662979				
		Trimming Blade life cycle	once	per month	Worn out not allowed						
18	90° Visual inspection	Visual Inspection	5 pieces	per shift	Post Lam Visual Inspection Criteria	S.No	GS04890KG0442662917				
						S.No	GS04890KG0442662976				
						S.No	GS04890KG0442662921				
						S.No	GS04890KG0442662989				
						S.No	GS04890KG0442662987				
19	Framing	Glue uniformity & continuity in frame groove	1 set	per shift	Should be uniform,Back sealing should be proper	uniform and Continue.					
		Short Side Glue Weight	once	Per shift	Fill as per Specification	Refer Document GSPL/IPQC/QC/011					
		Long Side Glue Weight	once	Per shift							
		Anodizing Thickness	once	Per shift	≥15 micron	18.2 Micron.					