GAUTAM SOLAR	Gautam Solar Private Limited	Document No.	GSPL/IPQC/IPC/003
		Issue Date	01/12/2024
	IPQC Check Sheet	Rev. No./Rev.Date	01/30-08-2025

Date :- 8-03-2026 | Time :- 8:30 | Shift Night | Po.no.:-

Sr.No.	Stage	Check point	Quantum of Check: Sample Size	Quantum of Check: Frequency	Acceptance Criteria	Monitoring Result					Remarks,if any
		Peel of Test b/w: EVA/Backsheet EVA/EPE/POE to Glass	All position	All laminators to be coverd in a month	E/G ≥60N/cm E/B≥60N/cm	Refer Document GSPL/IPQC/QC/001					
		Gel Content Test			75to 95%	Refer Document GSPL/IPQC/QC/001					
16	Auto Tape Removing (If Applicable)	Visual Check after Lamination	5 pieces	per shift	Check Tape Removing Should be smooth and No visual bubble Should be found.	ok	ok	ok	ok	ok	
17	Auto Edge Trimming	Trimming Quality	5 pieces	per shift	Excess layer from the glass edge should be removed,Uneven Trimming not allowed	S.No.	GS04830T43542559738				ok
						S.No.	GS04830T43542560951				ok
						S.No.	GS04830T43542559673				ok
						S.No.	GS04830T43542559598				ok
						S.No.	GS04830T43542559605				ok
		Trimming Blade life cycle	once	per month	Worn out not allowed	20 days					
18	90° Visual inspection	Visual Inspection	5 pieces	per shift	Post Lam Visual Inspection Criteria	S.No	GS04830T43542559680				ok
						S.No	GS04830T43542559901				ok
						S.No	GS04830T43542560956				ok
						S.No	GS04830T43542560959				ok
						S.No	GS04830T43542560955				ok
19	Framing	Glue uniformity & continuity in frame groove	1 set	per shift	Should be uniform,Back sealing should be proper	ok					
		Short Side Glue Weight	once	Per shift	Fill as per Specification	Refer Document GSPL/IPQC/QC/011					
		Long Side Glue Weight	once	Per shift							
		Anodizing Thickness	once	Per shift	≥15 micron	18.5 micron					

Scanned with OKEN Scanner