

ABS-132GWS-G12 705W - 725W

Topcon Half Cut PV Module

Glass/White Back Sheet -Silver Frame



MAXIMUM POWER OUTPUT



OUTPUT POSITIVE TOLERANCE

Guaranteed 0~+10W positive tolerance ensures power output reliability.

23.3%

MAXIMUM EFFICIENCY



KEY FEATURES



LOW SYSTEM COST

Higher yield per surface area, lower BOS costs, higher power classes, and an efficiency rate of up to 23.34%.



EXTREME WEATHER RATING

High-tech aluminum alloy frame, certified for high snow (5400 Pa) and wind loads (2400 Pa).



ADVANCED MODULE TECHNOLOGY

Highest reliability & enhanced crack tolerance MBB module



ALL-WEATHER TECHNOLOGY Optimal

Yields, whatever the weather, with low-light and temperature behaviour.



BETTER TEMPERTURE COEFFICIENT


Lower temperature coefficient (Pmax): -0.30%/°C, increases energy yield in hot climate



ENDURING HIGH PERFORMANCE

Anti LID and Anti PID Technology. Under long-term production safety conditions, the limited power degradation caused by the PID effect is guaranteed.

LINEAR PERFORMANCE WARRANTY



30 Years

30-year Warranty for Extra Linear Power Output



12-year Warranty for Materials and Processing $(1^{st} \text{ year} \le 1.0\%, 2^{nd} \sim 30^{th} \text{ years} \le 0.40\% / \text{ year})$

HE IDEAL SOLUTION FOR









Residential

Commercial

Utility

COMPREHENSIVE CERTIFICATES

IEC 61215 | IEC 61730 | IEC 61701 | IEC 62716 | IEC 60068-2-68











UL 61730 | MCS | CEC | ISO 9001 | ISO 14001 | ISO 45001

ADVANTAGES







A RELIABLE INVESTMENT

Products up to 725Wp, 30 years of performance warranty.



ENCOURAGING INNOVATION

Innovative, prestigious, European production technology

ABS-132GWS-G12-705-725W

ENGINEERING DRAWINGS & TECHNICAL PARAMETERS



ELECTRICAL CHARACTERISTICS (STC/NOCT)


Models	Maximum Rating Power (Pmax) (W)		Open Circuit Voltage (Voc) (V)		Maximum Power Voltage (Vmp) (V)		Short Circuit Current (Isc) (A)		Maximum Power Current (Imp) (A)		Module Efficiency (EFF)(%)
	STC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT	
ABS-132GWS-G12-705	705	527.0	47.06	44.25	40.57	37.85	18.10	14.61	17.43	13.96	22.70%
ABS-132GWS-G12-710	710	530.7	47.17	44.35	40.66	37.94	18.14	14.64	17.54	14.05	22.86%
ABS-132GWS-G12-715	715	534.4	47.22	44.40	40.71	37.98	18.17	14.66	17.59	14.09	23.02%
ABS-132GWS-G12-720	720	538.2	47.34	44.51	40.81	38.08	18.21	14.69	17.69	14.17	23.18%
ABS-132GWS-G12-725	725	541.9	47.44	44.60	40.90	38.16	18.23	14.71	17.79	14.25	23.34%


^{*}Standard Test Condition (STC): Cell Temperature 25 °C, Irradiance 1000 W/m², AM 1.5, Nominal module operating temperature (NMOT): Air mass AM 1.5, Irradiance 800W/m², temperature 20 °C, windspeed 1 m/s. Reduction in efficiency from 1000W/m² to 200W/m² at 25 °C: 3.5 ± 2% *Values without tolerance are typical numbers. Measurement tolerance: ± 3%```


MECHANICAL DATA

Solar Cell	Topcon 210 x 105 mm G12,18BB
No.of cells	132 (6×22)
Dimensions	2384 mm x 1303 mm x 33 mm (93.85" x 51.30" x 1.29" inch)
Weight	35 kg / 77.16 lbs.(±3%)
Front Glass	3.20 mm, High Transmission, Low Iron, Tempered ARC Glass
Cell Encapsulation	EPE(Expanded polyethylene) & EVA (Ethylene-Vinyl-Acetate)
Back Sheet	White Back Sheet
Frame	Silver Anodized Aluminum Alloy Type 6005T6 , Silver Color
Junction Box	IP68, I500VDC, 3 Bypass Diodes
Connectors Type	IP68 MC4 Compatible
Cable	400mm or 1300 mm, 4mm ²
Package Configuration	33 pcs Per Pallet, 594 pcs per 40' FT container

DIMENSIONS OF PV MODULE (mm)













OPERATING CONDITION


Mechanical Load	5400 Pa
Maximum System Voltage	1500VDC
Series Fuse Rating	30 A
Operating Temperature	-40 to 85 °C
Safety application class	Class II
Fire Rating	Class C

TEMPERATURE CHARACTERISTICS


Nominal Module Operating Temperature	43°C ± 2°C
Temperature Coefficient of Isc	+0.05 % / °C
Temperature Coefficient of Voc	-0.25 % / °C
Temperature Coefficient of Pmax	-0.30 % / °C

IV-CURVES

CURRENT-VOLTAGE CURVE UNDER DIFFERENT IRRADIANCE



CURRENT-VOLTAGE CURVE UNDER DIFFERENT WORKING TEMPERATURES



The Graphs are for reference purpose only. Please consult Abundance technical team for further clarifications.