

ABS-144GGS-M10 585W - 610W Topcon Half Cut PV Module

Glass/Glass-Silver Frame



MAXIMUM POWER OUTPUT



OUTPUT POSITIVE TOLERANCE

Guaranteed 0~+10W positive tolerance ensures power output reliability.

23.6%

MAXIMUM EFFICIENCY

KEY FEATURES



LOW SYSTEM COST

Higher yield per surface area, lower BOS costs, higher power classes, and an efficiency rate of up to 23.61%.



EXTREME WEATHER RATING

High-tech aluminum alloy frame, certified for high snow (5400 Pa) and wind loads (2400 Pa).



ADVANCED MODULE TECHNOLOGY

Highest reliability & enhanced crack tolerance MBB module



ALL-WEATHER TECHNOLOGY Optimal

Yields, whatever the weather, with low-light and temperature behaviour.



BETTER TEMPERTURE COEFFICIENT

Lower temperature coefficient (Pmax): -0.30%/°C, increases energy yield in hot climate



ENDURING HIGH PERFORMANCE

Anti LID and Anti PID Technology. Under long-term production safety conditions, the limited power degradation caused by the PID effect is guaranteed.

HE IDEAL SOLUTION FOR

LINEAR PERFORMANCE WARRANTY

ADDED VALUE FROM WARRANTY

vears



100% **99%**

95%

90%

30 Years





30-year Warranty for Extra Linear Power Output

12-year Warranty for Materials and Processing

 $(1^{st} \text{ year} \le 1.0\%, 2^{nd} \sim 30^{th} \text{ years} \le 0.40\% / \text{ year})$



87 40%

Residential

Commercial

Utility

ADVANTAGES



are 100% made in

the Emirates.





A RELIABLE INVESTMENT Products up to 725Wp, 30 years of performance warranty.



ENCOURAGING INNOVATION

Innovative, prestigious, European production technology

COMPREHENSIVE CERTIFICATES

IEC 61215 | IEC 61730 | IEC 61701 | IEC 62716 | IEC 60068-2-68












UL 61730 | MCS | CEC | ISO 9001 | ISO 14001 | ISO 45001

ABS-144GGS-M10-585-610W

ENGINEERING DRAWINGS & TECHNICAL PARAMETERS

ELECTRICAL CHARACTERISTICS (STC/NOCT)



42.01

45.03

BI-FACIAL OUTPUT-BACKSIDE POWER GAIN

456.0


Models		ABS-144GGS- M10-585	ABS-144GGS- M10-590	ABS-144GGS- M10-595	ABS-144GGS- M10-600	ABS-144GGS- M10-605	ABS-144GGS- M10-610
10%	Power	644	649	655	660	666	671
	Eff	24.91%	25.12%	25.34%	25.55%	25.76%	25.98%
15%	Power	673	679	684	690	696	702
	Eff	26.04%	26.27%	26.49%	26.71%	26.93%	27.16%
20%	Power	702	708	714	720	726	732
	Eff	27.18%	27.41%	27.64%	27.87%	28.10%	28.34%
25%	Power	731	738	744	750	756	763
	Eff	28.31%	28.55%	28.79%	29.03%	29.28%	29.52%

MECHANICAL DATA

ABS-144GGS-M10-610

Solar Cell	Topcon 182.2 x 91.88 mm M10,16BB		
No.of cells	144 (6×24)		
Dimensions	2278 mm x 1134 mm x 30 mm (89.69" x 44.65" x 1.18" inch)		
Weight	32 kg / 70.54 lbs.(±3%)		
Front Glass	2.0 mm, High Transmission, Low Iron, Tempered ARC Glass		
Cell Encapsulation	EPE(Expanded polyethylene) & EVA (Ethylene-Vinyl-Acetate)		
Back Glass	2.0 mm Semi Tempered Glass with Glaze		
Frame	Silver Anodized Aluminum Alloy Type 6005T6, Silver Color		
Junction Box	IP68, 1500VDC, 3 Bypass Diodes		
Connectors Type	IP68 MC4 Compatible		
Cable	400mm or 1300 mm, 4mm ²		
Package Configuration	36 pcs Per Pallet, 720 pcs per 40' FT container (Two pallets=One stack)		

DIMENSIONS OF PV MODULE (mm)



OPERATING CONDITION

Mechanical Load	5400 Pa
Maximum System Voltage	I500VDC
Series Fuse Rating	25 A
Operating Temperature	-40 to 85 °C
Safety application class	Class II
Fire Rating	Class C


23.61%


TEMPERATURE CHARACTERISTICS

Nominal Module Operating Temperature	43°C ± 2°C
Temperature Coefficient of Isc	+0.05 % / °C
Temperature Coefficient of Voc	-0.25 % / °C
Temperature Coefficient of Pmax	-0.30 % / °C

IV-CURVES

CURRENT-VOLTAGE CURVE UNDER DIFFERENT IRRADIANCE





The Graphs are for reference purpose only. Please consult Abundance technical team for further clarifications.

^{*}Standard Test Condition (STC): Cell Temperature 25 °C, Irradiance 1000 W/m², AM 1.5, Nominal module operating temperature (NMOT): Air mass AM 1.5, Irradiance 800W/m², temperature 20 °C, windspeed 1 m/s. Reduction in efficiency from 1000W/m² to 200W/m² at 25 °C: 3.5 ± 2%.

*Values without tolerance are typical numbers. Measurement tolerance: ± 3%