

ABS-132GGB-G12R 610W – 630W Topcon Half Cut PV Module

Glass/Glass-Black Frame



MAXIMUM POWER OUTPUT



OUTPUT POSITIVE TOLERANCE

Guaranteed 0~+10W positive tolerance ensures power output reliability.



MAXIMUM EFFICIENCY



KEY FEATURES



LOW SYSTEM COST

Higher yield per surface area, lower BOS costs, higher power classes, and an efficiency rate of up to 23.30%.



EXTREME WEATHER RATING

High-tech aluminum alloy frame, certified for high snow (5400 Pa) and wind loads (2400 Pa).



ADVANCED MODULE TECHNOLOGY

Highest reliability & enhanced crack tolerance MBB module



ALL-WEATHER TECHNOLOGY Optimal

Yields, whatever the weather, with low-light and temperature behaviour.



BETTER TEMPERTURE COEFFICIENT


Lower temperature coefficient (Pmax): -0.30%/°C, increases energy yield in hot climate



ENDURING HIGH PERFORMANCE

Anti LID and Anti PID Technology. Under long-term production safety conditions, the limited power degradation caused by the PID effect is guaranteed.

LINEAR PERFORMANCE WARRANTY



Product warranty
30
Years

30-year Warranty for Extra Linear Power Output



12-year Warranty for Materials and Processing (1st year ≤ 1.0%, 2nd~30th years ≤ 0.40% / year)

THE IDEAL SOLUTION FOR









Residential

Commercial

Off-Grid

Utility

COMPREHENSIVE CERTIFICATES

IEC 61215 | IEC 61730 | IEC 61701 | IEC 62716









UL 61730 | CEC | ISO 9001 | ISO 14001 | ISO 45001

ADVANTAGES



the Emirates.





A RELIABLE INVESTMENT
Products up to 725Wp, 30
years of performance
warranty.



ENCOURAGING INNOVATION

Innovative, prestigious, European production technology

ABS-132GGB-G12R-610-630W

ENGINEERING DRAWINGS & TECHNICAL PARAMETERS



ELECTRICAL CHARACTERISTICS (STC/NOCT)

Models	Maximum Rating Power (Pmax) (W)		Open Circuit Voltage (Voc) (V)		Maximum Power Voltage (Vmp) (V)		Short Circuit Current (Isc) (A)		Maximum Power Current (Imp) (A)		Module Efficiency (EFF)(%)
	STC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT	
ABS-132GGB-G12R-610	610	456.0	47.09	44.27	40.60	37.88	15.67	12.65	15.09	12.08	22.56%
ABS-132GGB-G12R-615	615	459.7	47.20	44.38	40.69	37.96	15.70	12.67	15.18	12.16	22.75%
ABS-132GGB-G12R-620	620	463.4	47.30	44.47	40.77	38.04	15.75	12.71	15.27	12.23	22.93%
ABS-132GGB-G12R-625	625	467.2	47.41	44.58	40.87	38.13	15.78	12.73	15.35	12.29	23.12%
ABS-132GGB-G12R-630	630	470.9	47.47	44.63	40.92	38.18	15.81	12.76	15.40	12.33	23.30%

^{*}Standard Test Condition (STC): Cell Temperature 25 °C, Irradiance 1000 W/m², AM 15, Nominal module operating temperature (NMOT): Air mass AM 15, Irradiance 800W/m², temperature 20°C, windspeed 1 m/s. Reduction in efficiency from 1000W/m² to 200W/m² at 25°C: $3.5 \pm 2\%$. *Values without tolerance are typical numbers. Measurement tolerance: ± 3%


BI-FACIAL OUTPUT-BACKSIDE POWER GAIN

Models		ABS-132GGB-G12R- 610	ABS-132GGB-G12R- 615	ABS-132GGB-G12R- 620	ABS-132GGB-G12R- 625	ABS-132GGB-G12R- 630
10%	Power	671	677	682	688	693
10%	Eff	24.82%	25.02%	25.23%	25.43%	25.63%
15%	Power	702	707	713	719	725
15/0	Eff	25.95%	26.16%	26.37%	26.59%	26.80%
20%	Power	732	738	744	750	756
20%	Eff	27.08%	27.30%	27.52%	27.74%	27.96%
25%	Power	763	769	775	781	788
	Eff	28.20%	28.44%	28.67%	28.90%	29.13%

MECHANICAL DATA

Solar Cell	Topcon 182 x 105 mm G12R ,16BB				
No.of cells	132 (6×22)				
Dimensions	2384 mm x 1134 mm x 30 mm (93.85" x 44.64" x 1.18" inch)				
Weight	33 kg / 72.75 lbs.(±3%)				
Front Glass	2.0 mm, High Transmission, Low Iron, Tempered ARC Glass				
Cell Encapsulation	EPE(Expanded polyethylene) & EVA (Ethylene-Vinyl-Acetate)				
Back Glass	2.0 mm Semi Tempered Glass with Glaze				
Frame	Black Anodized Aluminum Alloy Type 6005T6 , Black Color				
Junction Box	IP68, 1500VDC, 3 Bypass Diodes				
Connectors Type	IP68 MC4 Compatible				
Cable	400mm or 1300 mm, 4mm ²				
Package Configuration	36 pcs Per Pallet, 720 pcs per 40' FT container (Two pallets=One stack)				

DIMENSIONS OF PV MODULE (mm)



OPERATING CONDITION


Mechanical Load	5400 Pa
Maximum System Voltage	1500VDC
Series Fuse Rating	30 A
Operating Temperature	-40 to 85 °C
Safety application class	Class II
Fire Rating	Class C

TEMPERATURE CHARACTERISTICS


Nominal Module Operating Temperature	43°C ± 2°C
Temperature Coefficient of Isc	+0.05 % / °C
Temperature Coefficient of Voc	-0.25 % / °C
Temperature Coefficient of Pmax	-0.30 % / °C

IV-CURVES

CURRENT-VOLTAGE CURVE UNDER DIFFERENT IRRADIANCE



CURRENT-VOLTAGE CURVE UNDER DIFFERENT WORKING TEMPERATURES



The Graphs are for reference purpose only. Please consult Abundance technical team for further clarifications.