检测报告

Test Report

报告编号：A01JCR0224501ER1 第 1 页 共 7 页
Report No: A01JCR0224501ER1 Page 1 of 7

委托单位 Applicant	：	佛山市南海万磊建筑涂料有限公司 Foshan city Nanhai Wanlei Building Paint Co.,Ltd
地址 Address	：	广东省佛山市南海区松岗万石工业区 Wanshi Industrial Zone, Songgang, Nanhai District, Foshan City, Guangdong Province

样品信息：(以下测试样品及样品信息由客户提供)
The following sample and sample information was submitted by the behalf of the client

样品名称 Sample Name	:	微水泥 Micro cement
样品数量 Quantity	:	1 组 1 group
批号 Batch number	:	/
其他信息 Other information	:	样品编号： A01JCR0224501 Sample number： A01JCR0224501
样品状态 Sample Status	:	符合测试要求 Normal
样品接收日期 Sample Received Date	:	2025.05.22
样品检测日期 Sample Testing Period	:	2025.05.22~2025.07.23
判定依据 Judgment criteria	:	**T/CECS 10192-2022《聚合物微水泥》 T/CECS 10192-2022《Polymer micro-cement》**
检测项目 Test Item	:	**详见下页 See next page for details**
检测结论 Test Result	:	**详细信息参见下页。 Refer to following pages.**

编 制 Edited by : Hua cheng kai   审 核 Reviewed by: Pang Yinchuan
批 准 Approved by: Chen Quan   日 期 Date : 2025.08.07

chenquan
授权签字人 Authorized Signatory   No.319741532

苏州市华测检测技术有限公司 江苏省苏州市相城区澄阳路3286号Center
Testing International (Suzhou) Co., Ltd No.3286,Chengyang Road, Xiangcheng District, Suzhou , Jiangsu,China

检测报告
Test Report

检测项目及方法

Test Item & Test Method

1. 外观质量
   Appearance quality
   T/CECS 10192-2022《聚合物微水泥》第 6.4 条
   T/CECS 10192-2022《Polymer micro-cement》Article 6.4
2. 施工性
   Constructability
   T/CECS 10192-2022《聚合物微水泥》第 6.5 条
   T/CECS 10192-2022《Polymer micro-cement》Article 6.5
3. 耐人工气候老化性，400h
   Resistance to artificial climate aging，400h
   GB/T 1865-2009《色漆和清漆 人工气候老化和人工辐射曝露 滤过的氙弧辐射》*
   GB/T 1865-2009《Paints and varnishes-Artificial weathering and exposure to artificial radiation-Exposure to filtered xenon-arc radiation》*
   GB/T 1766-2008《色漆和清漆 涂层老化的评级方法》*
   GB/T 1766-2008《Paints and varnishes-Rating schemes of degradation of coats》*
4. 涂层耐温变性（3 次循环）
   Coating temperature resistance (3 cycles)
   T/CECS 10192-2022《聚合物微水泥》第 6.10 条
   T/CECS 10192-2022《Polymer micro-cement》Article 6.10
5. 抗冲击性
   Impact resistance
   T/CECS 10192-2022《聚合物微水泥》第 6.11 条
   T/CECS 10192-2022《Polymer micro-cement》Article 6.11
6. 吸水量（2h）
   Water absorption capacity (2 hours)
   T/CECS 10192-2022《聚合物微水泥》第 6.12 条
   T/CECS 10192-2022《Polymer micro-cement》Article 6.12
7. 抗压强度
   Compressive strength
   T/CECS 10192-2022《聚合物微水泥》第 6.13 条
   T/CECS 10192-2022《Polymer micro-cement》Article 6.13
8. 粘结强度
   Bonding strength
   JG/T 157-2009《建筑外墙用腻子》*
   JG/T 157-2009《Putty for exterior wall》*

9. 耐磨性

Wear resistance

T/CECS 10192-2022《聚合物微水泥》第 6.15 条

T/CECS 10192-2022《Polymer micro-cement》Article 6.15

本页以下空白

To be continued

检测报告

Test Report

<table>
<tr><th>序号
No.</th><th colspan="2">检测项目
Test Item</th><th>单位
Unit</th><th>技术要求
Technical Requirement</th><th>检测结果
Test Result</th><th>单项评定
Individual Conclusion</th></tr>
<tr><td>1</td><td colspan="2">外观质量
Appearance quality</td><td>—</td><td>粉料应为均匀、无结块的粉末；液料经搅拌后应均匀、无沉淀
The powder should be uniform and free of lumps；The liquid material should be uniform and free of sediment after stirring</td><td>粉料为均匀、无结块的粉末；液料经搅拌后均匀、无沉淀
The powder is uniform and free of lumps；The liquid material is uniform and free of sediment after stirring</td><td>合格
Pass</td></tr>
<tr><td>2</td><td colspan="2">施工性
Constructability</td><td>—</td><td>施涂无障碍
Barrier-free application</td><td>施涂无障碍
Barrier-free application</td><td>合格
Pass</td></tr>
<tr><td rowspan="3">3</td><td rowspan="3">耐人工气候老化性，400h
Resistance to artificial climate aging，400h</td><td>外观
Appearance</td><td>—</td><td>不起泡、不剥落、无裂纹
No bubbling, no peeling, no cracks</td><td>不起泡、不剥落、无裂纹
No bubbling, no peeling, no cracks</td><td rowspan="3">合格
Pass</td></tr>
<tr><td>粉化/级
Pulverization</td><td>级
level</td><td>0</td><td>0</td></tr>
<tr><td>变色（白色和浅色）/级
Color change (white and light colors)</td><td>级
level</td><td>≤1</td><td>0</td></tr>
<tr><td>4</td><td colspan="2">涂层耐温变性（3 次循环）
Coating temperature resistance (3 cycles)</td><td>—</td><td>无异常
No abnormal</td><td>无异常
No abnormal</td><td>合格
Pass</td></tr>
<tr><td>5</td><td colspan="2">抗冲击性
Impact resistance</td><td>—</td><td>无开裂或脱离底板
No cracking or detachment from the bottom plate</td><td>无开裂，无脱离底板
No cracking，no detachment from the bottom plate</td><td>合格
Pass</td></tr>
</table>

检测报告

Test Report

序号 No.	检测项目 Test Item		单位 Unit	技术要求 Technical Requirement	检测结果 Test Result	单项评定 Individual Conclusion
6	吸水量（2h） Water absorption capacity (2 hours)		g	≤2	0.69	合格 Pass
7	抗压强度 Compressive strength		MPa	≥8	9.8	合格 Pass
8	粘结强度 Bonding strength	标准状态 Standard state	MPa	≥1.0	2.1	合格 Pass
		冻融循环后（5 次循环） After freeze-thaw cycles (5 cycles)	MPa	≥0.6	1.9	
9	耐磨性 Wear resistance		mm^3	≤400	127	合格 Pass

备注*：1.试件制备配合比例，干粉：微乳：水=16：4：2（质量比）；

2. 外观质量、施工性、涂层耐温变性（3 次循环）、抗冲击性、吸水量（2h）、抗压强度、耐磨性项目不在 CNAS 认可范围内。外观质量、施工性、涂层耐温变性（3 次循环）、抗冲击性、吸水量（2h）、抗压强度、耐磨性项目结果/结论所依据的合格评定活动不在认可范围内；

3. 本报告对原报告（报告编号：A01JCR0224501E）“*”处进行修改且加盖 CNAS 章，并替换原报告 A01JCR0224501E，自本报告签发之日起，原报告 A01JCR0224501E 作废。

Note*: 1.The fit ratio for specimen preparation ， Powder: Emulsion: water=16:4:2(Mass ratio).

2. The Appearance quality、Constructability、Coating temperature resistance (3 cycles)、Impact resistance、Water absorption capacity (2 hours)、Compressive strength、Wear resistance project is not within the scope of CNAS accreditation. The qualification assessment activities on which the results/conclusions of the Appearance quality、Constructability、Coating temperature resistance (3 cycles)、Impact resistance、Water absorption capacity (2 hours)、Compressive strength、Wear resistance project are based are not within the scope of recognition.

3.This report modifies the "*" section of the original report (Report Number: A01JCR0224501E), affixing the CNAS seal, and replaces the original report A01JCR0224501E. As of the date of issuance of this report, the original report A01JCR0224501E is invalidated.

本页以下空白

To be continued

检测报告

Test Report

样品图片

Photo of the sample

A01JCR0224501

1. 报告无批准人签字、检验检测专用章及报告骑缝章，或经涂改，以及复印报告未加盖红色检验检测专用章均视作无效。
   The report without the signature of the approver, the special seal for inspection and testing, and the report saddle seal, or with alterations, as well as copies of the report without the red special seal for inspection and testing, shall be deemed invalid.
2. 未经本公司批准，不得部分复制或部分引用本报告。
   Without the approval of our company, partial reproduction or partial citation of this report is not allowed.
3. 样品及样品信息由申请者提供，申请者应对其真实性负责，CTI 未核实其真实性。
   The samples and sample information are provided by the applicant, who is responsible for their authenticity. CTI has not verified their authenticity.
4. 本报告检测结果仅对受检样品负责。
   The test results in this report are only responsible for the tested samples.
5. 不得擅自使用检测结果进行不当宣传。
   Do not use the test results for improper promotion without authorization.
6. 如果对检测结果有异议，应于收到报告之日起 7 个工作日内提出，逾期不予受理。
   If there are any objections to the test results, they should be raised within 7 working days from the date of receiving the report, and will not be accepted after the deadline.

7. 扫描报告首页二维码或登陆官方网站 https://mycti.cti-cert.com 输入报告编号和报告首页验证码，即可查询报告真伪；如有疑问，请联系邮箱:info@cti-cert.com。

Scan the QR code on the homepage of the report or log in to the official website https://mycti.cti-cert.com Enter the report number and report homepage verification code to check the authenticity of the report; If you have any questions, please contact email: info@cti-cert.com .

如未加盖 CMA 标识，本报告出具的数据结果仅供科研、教学、企业内部质量控制、企业产品研发等目的用，不具有对社会的证明作用。

8.如未加盖 CMA 标识，本报告出具的数据结果仅供科研、教学、企业内部质量控制、企业产品研发等目的用，不具有对社会的证明作用。

If the CMA logo is not affixed, the data results issued in this report are only for scientific research, teaching, internal quality control of enterprises, product development and other purposes, and do not have a certification effect on society.

*** 报告结束 ***

*** End of Report ***