DESCRIPTION

MULTI PAINT MPB-852 is a two component amine cured epoxy body coat formulated as a high build epoxy b0ody coat for concrete floor. Good adhesion of this body coat for porous substrate with properly selected top coat forms a general protective coating system for concrete floor. it can be applied as a filler for the hairline cracks / small concrete damage.

It is suitable for heavy duty floor in :

- Workshop
- Hospital
- Pharmaceutical factory
- Food and beverage production area
- Hotel, etc

ADVANTAGES

- Excellent bonding strength
- Easy to apply
- Low odor, solvent free system

PRODUCT DATA

Type : Two component solvent less amine cured epoxy body coat

Color : Grey

Finish : Matt

Solid by Volume (mixture) : ±75%

Specific Grafity (mixture) : ±1.45 gr/cc

Material Consumption : 0.2 – 0.25 kg-set/m² (depend on porosity of substrate condition)
Flash Point : ±99 °C

Drying Time :

- Surface Dry : 3 hours (30 °C)

- Hard Dry : 6 hours (30 °C)

- Full Cure : 7 days (30 °C)

Bonding Strength : >2.5N/mm2 concrete failure (by ASTM D-4541)

Packaging : 5 and 20kg-set

Storage Stability : One year in cool and dry storage and in original not opened box.

Mixing Ratio by Weight : Comp A : B = 5 : 1 w/w
Pot Life : 30 minutes in 30 °C

Application Method : Metal trowel, rubber squegee

Re-coating Interval (30 °C) : 12 - 16 hours until 7 days

Application Temperature : 10 - 35 °C

Humidity Maximum : 80 % RH

Provide adequate ventilation during application and drying

INSTRUCTION FOR USE

Surface Preparation

Compressive strength of concrete floor not less than 25 N/mm2 in more than 28 days. Moisture content should be less than 5% and the surface temperature must be at least 3 °C above current dew temperature. Remove oil contaminants using industrial grade detergent or degreasing compound as chemical cleaning and mechanical cleaning

Application Procedure

Skin Contact : Use a low speed electrical mixer to stir comp. A slowly before mixing. Mix one set MULTI PAINT MPB-852 SF (with mixing ratio comp.A : B = 5 : 1 by weight) until mixture is homogeneous at least for 2 minutes. Poured mixed material approx
0.2 – 0.25 kg-set/m² onto to the substrate and spread mixture using metal trowel or rubber squegee. Allow curing time 12 - 16 hours (overnight) before applying next step. As an epoxy filler for concrete patching repair or big holes, can be mixed with talc or quartz sand. MULTI PAIINT MPB-852 : talc or quartz sand is 1 : 3-4 by weight. Let it dry 8 -12 hours for next application step.

RECOMMENDED COATING SYSTEM

1. PRIMER :MPP-851 clear
2. BODY COAT :MPB-852
3. TOP COAT :MPT-953 Color

SAFETY PRE CAUTIONS

MULTI PAINT MPB-952 does not contain any material with heavy metals such as lead. Avoid contact with the skin and eyes. Wear suitable protective clothing such as overalls, goggles, dust masks and gloves. Use barrier cream. This product is flammable. Do not smoke. Use only explosion proof equipment. Do not breathe vapor or spray.

First Aid Skin Contact : Wash off thoroughly with plenty of water immediately. If irritation occurs, seek medical advice. Eye Contact : Rinse immediately with plenty of clean water. Seek medical advice. Inhalation : Move person to fresh air, loosen collar and avoid exertion. Keep patient rested and give artificial respiration.

CLEANING

MULTI PAINT MPB-852 should be removed from tools and equipments with MULTI PAINT Epoxy Thinner immediately after use. Hardened material can only be removed mechanically.