DESCRIPTION

MULTI PAINT MPP-851 is two component solventless modified poly amido amine cured epoxy self levelling floor primer. It has good adhesion to concrete, good abrasive resistance and good resistance against alkali, acid, solvent, and other chemicals.

USES

It is suitable for heavy duty floor in :

- Workshop
- Hospital
- Pharmaceutical factory
- Food and beverage production area
- Hotel, etc

ADVANTAGES

- Gloss Finish, easily cleaned
- Easy application
- Smooth and seamless
- Good Chemical and mechanical resistance

PRODUCT DATA

Type : Two Component solventless modified poly amido amine cured epoxy self levelling primer

Color : Clear, milky

Finish : Glossy

Specific gravity (mix) : 1,4 gr/ml

Solid by volume (mix): 92,3 %

Material consumption : 0,15 – 0,2 kg/m²

Flash point : 30°C

Drying Time :

- Surface Dry : 1 Hours (30°C)
- Hard Dry : 5-6 Hours (30°)
- Full Cure : 6-7 days (30°C)

Shore D. Hardness : 85 (7 days) ASTM D.2240

Compressive Strength : >50 N/mm² (28 days)

Bonding Strenght : 1,5 N/mm² (Concrete Failure) ASTM D-4541

Packaging : 5 kg/set, 20kg/set

Storage stability : 12 months. If stored in cool and dry place with original container

APPLICATION

Mixing ratio (by weight) : Component A Component B (4 : 1)

Pot Life : 25 – 30 minutes (30°C)

Application method : Rubber, roll and squeegee

Thinner : Thinner Epoxy

Thickness minimum : 100 micron, DFT

Recoating Interval : 5-6 Hours (30°C)

Application Temperature : 20°C - 35°C

Humidity maximum : 80%

SURFACE PREPARATION

- Age of concrete should be more than 28 days or moisture content should be less than 5 %
- Minimum K-200 for type of concrete
- Surface must be clean and free from oil, grease, water and others contaminants
- Remove oil, grease, and others contaminants by scrubbing with detergent or mechanical cleaning

INSTRUCTION FOR USE

Apply primer coat MPP-851 with material consumption 0,15-0,2 kg/m² using squeegee and paint roller. Allow it to curing time 6-8 hours

PT. MULTI ARTHA KREASINDO
TRADING BAHAN KIMIA | TRADING & MANUFACTURE CAT | JASA PENGECATAN
Integrity In Every Formula, Prosperity In Every Solution

RECOMMENDED COATING SYSTEM

1. MPP-851 clear
2. Body Coat MPB-852
3. MPT-870 Color

SAFETY PRE CAUTIONS

First Aid

Skin Contact : Wash of troughly with plenty of water. If irritation occurs seek medical advice

Eye Contact : Rinse Immediately with plenty of clean water. Seek medical advice.

Inhalation : Remove person to fresh air and loosen collar. Keep patient rested and give artificial respiration.

CLEANING

MULTI PAINT MPP-851 should be removed from tools and equipment with epoxy thinner immerdeantely after use.

PT. MULTI ARTHA KREASINDO
TRADING BAHAN KIMIA | TRADING & MANUFACTURE CAT | JASA PENGECATAN
Integrity In Every Formula, Prosperity In Every Solution