DESCRIPTION

MULTI PAINT TOP COAT MPT-870 is two component solventless modified cyclo alifatic amine cured epoxy self smoothing and self levelling floor topping. It has good adhesion to concrete, good abrasive resistance and good resistance against alkali, acid, solvent, and other chemicals.

USES

It is suitable for heavy duty floor in :

- Workshop
- Hospital
- Pharmaceutical factory
- Food and beverage production area
- Hotel, etc

ADVANTAGES

- Gloss Finish, easily cleaned
- Easy application
- Smooth and seamless
- Good Chemical and mechanical resistance

PRODUCT DATA

Type : Two Component solventless modified cyclo alifatic amine cured epoxy self levelling and self smoothing floor top coat

Color : As shown in the color card and customize

Finish : Glossy

Specific gravity (mix) : 1,45 gr/ml

Solid by volume (mix): 90,2 %

Material consumption : 0,5 kg/m² (For 500 mc thickness) 1 kg/m² (For 1 mm thickness)

Flash point : 30°C

Drying Time :

- Surface Dry : 2 Hours (30°C)
- Hard Dry : 16 Hours (30°
- Full Cure : 6-7 days (30°C)

Shore D. Hardness : 95 (7 days) ASTM D.2240

Compressive Strength : >50 N/mm² (28 days)

Bonding Strenght : 1,5 N/mm² (Concrete Failure) ASTM D-4541

Abrasion Resistance : 1000 mg, 1000 cycles (Asim D-4060, CS.17 wheel)

Packaging : 5 kg/set, 20kg/set

Storage stability : 12 months. If stored in cool and dry place with original container

Chemical Resistance :

- Sulphuric acid 10%-40% : Good
- Acetic acid 10% : Fair
- Nitric acid 10% : Color changed
- Ammonia : Good
- Salt : Good
- Water : Good
- Oil : Good
- Gasoline : Good
- Caustic soda 100% : Good
- Sugar solution : Good
- Alcohol : Good
- Xylene : Good
- Toluene : Good

APPLICATION

Mixing ratio (by weight) : Component A Component B (4 : 1)

Pot Life : 25 – 30 minutes (30°C)

Application method : Rubber squeegee, rubber roll and spike roll

Thinner : Thinner Epoxy

Thickness minimum : 500 micron, DFT

Recoating Interval : 10-12 Hours (30°C)

Application Temperature : 20°C - 35°C

Humidity maximum : 80%

SURFACE PREPARATION

- Age of concrete should be more than 28 days or moisture content should be less than 5 %
- Minimum K-200 for type of concrete
- Surface must be clean and free from oil, grease, water and others contaminants
- Remove oil, grease, and others contaminants by scrubbing with detergent or mechanical cleaning

INSTRUCTION FOR USE

- PRIMER
  Apply primer coat MPP-851 with material consumption 0,15-0,2 kg/m² using squeegee and paint roller. Allow it to curing time 6-8 hours
- CRACKS TREATMENT
  Apply epoxy mortar MPM mix quartz sand. Use metal trowel
- TOP COAT
  Apply finish coat MPT-870 use low speed stirrer mixer. Stir component A and Component B for at least 2 minutes until the mixing is homogeneous. Poured the material approx. 0,7 – 0,8 kg/m² (for thickness 500 micron) to the substrate using squeegee and spike roll. Protect the coated area for at least 16 hours.

RECOMMENDED COATING SYSTEM

1. MPP-851 clear
2. Body Coat MPB-852
3. MPT-870 Color

SAFETY PRE CAUTIONS

First Aid

Skin Contact : Wash of troughly with plenty of water. If irritation occurs seek medical advice

Eye Contact : Rinse Immediately with plenty of clean water. Seek medical advice.

Inhalation : Remove person to fresh air and loosen collar. Keep patient rested and give artificial respiration.

CLEANING

MULTI PAINT MPT-870 should be removed from tools and equipment with epoxy thinner immerdeantely after use.