DESCRIPTION

MULTI PAINT COATING 75% MPT 871 Finish is high build Topcoat epoxy flooring formulated with 75% epoxy resin and well-graded silica, pigment to provide high impact, abrasion resistance and excellent adhesion to different surfaces. Suitable for application on high build heavy duty, chemically resistant in production areas, shoes production, pharmaceutical production, helmet production, workshops, showrooms, kitchens, car parking, traffic decks, water treatment plants and other areas with chemical spillage.

USES

It is suitable for heavy duty floor in :

- Workshop
- Hospital
- Pharmaceutical factory
- Food and beverage production area
- Hotel, etc

ADVANTAGES

• High impact resistance

• Hard wearing and abrasion resistant

• High chemical and oil resistance

• Low maintenance costs

• Easy clean

• Glossy finish surface

PRODUCT DATA

Type : Two Component solventless modified alifatic amine cured and self smoothing floor top coat

Color : As shown in the color card and customize

Finish : Glossy

Specific gravity (mix) : 1,1 – 1,2 Kg/Litre Solid by volume (mix): 75 %

Material consumption :
0,1 – 0,15 kg/m² (6.6 m² / kg) For 200 mc thickness
1,5 – 1,6 kg/m² (0.62 m² / kg) For 500 mc thickness

Flash point : 30°C

Drying Time :

- Dust Free ± 2 Hours at 25 C°
- Hard Dry ± 12 Hours at 25 C°
- Fully Cured ± 24 Hours at 25 C°

Shore D. Hardness : 95 (7 days)

Compressive Strength : >50 N/mm² (28 days)

Bonding Strenght : 1,5 N/mm² (Concrete Failure)

Abrasion Resistance : 1000 mg, 1000 cycles

Packaging : 5 kg/set, 20kg/set

Load Capacity If Dry : ± 500 kg

Storage stability : 12 months. If stored in cool and dry place with original container

Chemical Resistance :

- Sulphuric acid 10%-40% : Good
- Acetic acid 10% : Fair
- Nitric acid 10% : Color changed
- Ammonia : Good
- Salt : Good
- Water : Good
- Oil : Good
- Gasoline : Good
- Caustic soda 100% : Good
- Sugar solution : Good
- Alcohol : Good

- Xylene : Good
- Toluene : Good

APPLICATION

Mixing ratio (by weight) : Component A Component B (3 : 1)

Pot Life : 25 – 30 minutes (30°C)

Application method : Rubber squeegee, rubber roll and spray

Thinner : Thinner Epoxy

Thickness minimum : 200 micron, DFT

Recoating Interval : 10-12 Hours (30°C)

Application Temperature : 20°C - 35°C

Humidity maximum : 80%

SURFACE PREPARATION

- Age of concrete should be more than 28 days or moisture content should be less than 5 %
- Minimum K-200 for type of concrete
- Surface must be clean and free from oil, grease, water and others contaminants
- Remove oil, grease, and others contaminants by scrubbing with detergent or mechanical cleaning

INSTRUCTION FOR USE

- PREIMER
  Apply primer coat MPP-851 with material consumption 0,1-0,15 kg/m² using spray and paint roller. Allow it to curing time 6-8 hours
- CRACKS TREATMENT
  Apply epoxy mortar MPM mix quartz sand. Use metal trowel
- TOP COAT
  Apply finish coat MPT-871 use low speed stirrer mixer. Stir component A and Component B for at least 2 minutes until the mixing is homogeneous. Poured the material approx. 0,1 – 0,15 kg/m² (for thickness 200 micron) to the substrate using spray and paint roll. Protect the coated area for at least 16 hours.

RECOMMENDED COATING SYSTEM

1. MPP-851
2. Body Coat MPB-852
3. MPT-871 Color

SAFETY PRE CAUTIONS

First Aid

Skin Contact : Wash of troughly with plenty of water. If irritation occurs seek medical advice

Eye Contact : Rinse Immediately with plenty of clean water. Seek medical advice.

Inhalation : Remove person to fresh air and loosen collar. Keep patient rested and give artificial respiration.

CLEANING

MULTI PAINT MPT-871 should be removed from tools and equipment with epoxy thinner immerdeantely after use.