TECHNICAL DATA SHEET

EPOXY COATING SF

PRODUCT DESCRIPTION

Epoxy Coating SF – MPU-875 2K is a high performance solvent-free epoxy coating formulated with selected epoxy resins and high quality curing agents to provide excellent adhesion, chemical resistance, and durable protection. This system is designed for use as a protective coating on concrete and steel surfaces in industrial and commercial environments.

Suitable for application in factories, warehouses, pharmaceutical plants, food processing areas, workshops, parking areas, water treatment facilities, and other areas exposed to mechanical wear and chemical spillage.

MIXING RATIO

- 4 Parts Epoxy Coating SF Base by volume
- 1 Part Hardener by volume
- Do not dilute (Solvent Free system)

TECHNICAL INFORMATION

o Color and Texture	: By request
o Specific Gravity 25º C	: ± 1.45 – 1.60 Kg/kg
o Volume Solids	: ± 100 %
o Pot Life	: ± 30 – 45 minutes at 25º C after mixing
o Coverage Theoretical	: ± 0,3 – 0,4 m²/kg @ 300 micron DFT
o Drying Time :	
Dust Free	: ± 3 – 5 hours at 25º C
Hard Dry	: ± 12 – 16 hours at 25º C
Fully Cured	: ± 5 – 7 days at 25º C

- Recommended DFT : 100 – 300 microns
- Standard Packing : 20 Kg / set (Base + Hardener)
- Supplied in separate containers as Base and Hardener

ADVANTAGES

- Solvent free (low VOC)
- High build coating system
- Excellent adhesion to concrete and steel
- High abrasion and impact resistance
- Superior chemical resistance
- Seamless and hygienic finish
- Easy to clean and maintain

APPLICATION METHOD

SURFACE PREPARATION

All surfaces must be clean, dry, and free from laitance, oil, grease, dust, and other contaminants that may affect adhesion. Concrete surfaces should be mechanically prepared to achieve a suitable surface profile.

MECHANICAL ABRASION

Surface preparation is carried out using mechanical methods such as grinding, shot blasting, or scarifying. Diamond grinders are recommended to remove weak layers and contaminants while creating a good bonding profile.

APPLICATION OF MIXING

The entire contents of the hardener container must be poured into the base container. Mix thoroughly for at least 3 – 5 minutes using a slow speed electric mixer equipped with a suitable mixing paddle. Ensure all materials are properly blended and no unmixed material remains on the sides or bottom of the container.

APPLICATION OF EPOXY COATING

Immediately after mixing, pour the material onto the prepared surface. Spread evenly using a notched trowel or rubber squeegee to achieve the desired thickness.

Follow by back rolling using a spike roller to remove entrapped air and ensure uniform distribution.

Apply within the pot life of the material. Ensure primer layer (if applied) is tack free before application of the coating layer. Additional layers may be applied depending on system requirements.