

# SHINY

Based on N130 Shira fabric  
Colour Card 2023

**HY**  
Hung Ten Knitting & Dyeing Co., Ltd.



● Color dyed with a particular sensitive dyestuff that might create a "blue stains" effect in conditions of high humidity and temperature.  
This effect can be eliminated: machine wash the garment with soap at 30°C, delicate tumbler dry or hang to dry.



Shiny

## N130 SHIRA

Applications > Swimwear > Beachwear


Polyamide	Elastane
80%	20%
Weight (±5%)	Width (+3%/-2%)
190 g/m <sup>2</sup>	285 g/m lin.
Courses	Wales
46/cm	26/cm
Tolerance for composition (standard ASTM)	
±3%	
Dimensional Change of fabric after HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	
Max	Max
-5%	-5%
Width	Length
Resistance to pilling ASTM D 3512-Random tumble at 30 minutes photographic rating STD	
4 to 4.5	
Ultraviolet Protection Factor (U.P.F.) AATCC 183-2010	
50+	
Stretch to dynamometer (±15%) ASTM D 4964 - LOAD 20 LBS	
115%	210%
Width	Length
(min 98% - max 132%)	(min 179% - max 242%)
30%	50%
50%	70%
70%	30%
Modulus % elongation (30% - 50% - 70%)	
0.4-1.0	1.0-1.8
1.0-1.8	2.0-3.6
0.0-0.4	0.4-0.8
0.4-0.8	0.8-1.6
Width Lbs	
Length Lbs	
Care labelling codes	
W	X
X	W
W	X
X	W



UV  
protection



extra  
comfort



two way  
stretch



perfect  
fit



high chlorine  
resistance