



● Color dyed with a particular sensitive dyestuff that might create a "blue stains" effect in conditions of high humidity and temperature.  
This effect can be eliminated: machine wash the garment with soap at 30°C, delicate tumbler dry or hang to dry.

\* Fluorescent Colours

\*

Polyamide	Elastane
80%	20%
Weight 195 g/m <sup>2</sup>	Width +3%/-2% 293 g/m lin.
Courses 46/cm	Wales 26/cm
Dimensional Change of fabric after HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	Tolerance for composition (standard ASTM) 150 cm
Resistance to pilling ASTM D 3512 Random tumble at 30 minutes photographic rating STD	-3% Max -5% Width -5% Length
Ultraviolet Protection Factor (U.P.F.) AATCC 183-2010	4 to 4.5 50+
Stretch to dynamometer (+15%) ASTM D 4964 - LOAD 20 LBS	110% Width 215% Length (min 94% - max 127%) (min 18% - max 247%)
Modulus % elongation (30% - 50% - 70%)	30% 50% 70% Width Lbs 3.10 10.20 2.2-4.0 0.8-0.2 0.3-1.0 10.15 Length Lbs
Care labelling codes	    

