TICK the lines you want (they turn yellow), then SAVE and send this file back to us.

Client name:

HIPCO
HAMMOUD INTERNATIONAL PAPER SAL.
PAPER & BOARD

AVAILABLE OFFSHORE - متوفر في الخارج

Stocklot Report

Reference: SL157-K-CKB-DPLX-27.10.2026
27 OCTOBER 2026

TOTAL AVAILABLE	SUBSTANCE RANGE	MILL (معمل)
378.13 MT	135 - 285 GSM	BILLERUD

#	QUALITY	GSM	SIZE (CM)	TONS
	REELS			378.13 MT
	CROWNBOARD PRESTIGE			304.91 MT
1	CROWNBOARD PRESTIGE	230	71 cm	7.35
2	CROWNBOARD PRESTIGE	230	76 cm	12.94
3	CROWNBOARD PRESTIGE	230	85 cm	3.36
4	CROWNBOARD PRESTIGE	230	96 cm	27.45
5	CROWNBOARD PRESTIGE	230	162.5 cm	92.76
6	CROWNBOARD PRESTIGE	230	202 cm	10.51
7	CROWNBOARD PRESTIGE	260	122.8 cm	60.81
8	CROWNBOARD PRESTIGE	285	99.2 cm	9.63
9	CROWNBOARD PRESTIGE	285	104 cm	8.82
10	CROWNBOARD PRESTIGE	285	115 cm	20.70
11	CROWNBOARD PRESTIGE	285	129 cm	14.98
12	CROWNBOARD PRESTIGE	285	133.2 cm	4.32
13	CROWNBOARD PRESTIGE	285	140.6 cm	19.63
14	CROWNBOARD PRESTIGE	285	144.8 cm	8.74
15	CROWNBOARD PRESTIGE	285	146 cm	2.92
	CLC/C DUPLEX			31.55 MT
16	CLC/C DUPLEX	282	153 cm	15.67
17	CLC/C DUPLEX	282	153.5 cm	7.50
18	CLC/C DUPLEX	282	161.5 cm	8.38
	CLC/M DUPLEX			10.36 MT
19	CLC/M DUPLEX	221	157.1 cm	6.26
20	CLC/M DUPLEX	221	157.4 cm	4.09
	LIQUID LC			9.26 MT
21	LIQUID LC	240	163 cm	9.26
	CLC/C DUPLEX 290 MN			8.23 MT
22	CLC/C DUPLEX 290 MN	282	161.8 cm	8.23
	DUPLEX			7.24 MT
23	DUPLEX	135	130.6 cm	5.45
24	DUPLEX	139	129.6 cm	1.80
	CLC/C DUPLEX 150 MN			6.59 MT
25	CLC/C DUPLEX 150 MN	242	157.1 cm	6.59
	TOTAL			**378.13**

BILLERUD

Billerud CrownBoard Prestige "New"

Tentative - Technical Data Sheet

Metric



Fully coated top side
Top: Bleached chemical pulp
Middle: Bleached CTMP reinforced with bleached chemical pulp
Bottom: Bleached chemical pulp
Light coated reverse side

Product description

CrownBoard Prestige® combines strength and printability in a unique way. The strong, stiff and tough board gives top performance throughout the product range. A high-white, coated surface offers outstanding print results giving the packaging a sophisticated visual appearance that enhances the contents. CrownBoard Prestige® is made out of 100% strong fresh fibres. Produced in Sweden.

Certification

Our mills are certified in accordance with ISO 9001, ISO 14001, ISO 45001, ISO 50001, FSSC 22000.
PEFC CoC and FSC® CoC Certification is available. The product is in compliance with FDA and BfR regarding food contact applications, for restriction and limitations ask your Billerud sales representative.
Recyclable in accordance with EN 13430:2004 and EN 13431:2004.

Property	Unit	Method	Tolerance							
Basis weight	**g/m²**	**ISO 536**	**±4%**	**215**	**230**	**260**	**285**	**310**	**335**	**365**	**395**
Thickness microns	**µm**	**ISO 534**	**±4% or max ±20µm**	**290**	**305**	**355**	**405**	**455**	**505**	**555**	**605**
Caliper points	**pt**		**±4%**	**11.4**	**12.0**	**14.0**	**15.9**	**17.9**	**19.9**	**21.9**	**23.8**
Bending resistance, L&W 15º MD	mN	ISO 2493	-15%	172	212	300	430	550	650	840	1070
Bending resistance, L&W 15º CD	mN	ISO 2493	-15%	82	101	150	230	290	355	460	580
Z-strength	kPa	ISO 15754	280	350	350	350	350	350	350	350	350
CIE Whiteness TS		ISO 11475	min 120	125	125	125	125	125	125	125	125
CIE Whiteness RS		ISO 11475	min 97	102	102	102	102	102	102	102	102
Smoothness, PPS-10 TS	µm	ISO 8791-4	max 1.5	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
Smoothness, Bendtsen RS	ml/min	ISO 8791-2	max 900, 1300*	500	500	500	500	500	500	500	500
Cobb 60" TS	g/m²	ISO 535	max 60	35	35	35	35	35	35	35	35
Cobb 60" RS	g/m²	ISO 535	max 60	35	35	35	35	35	35	35	35
Moisture content	%	ISO 287	±1	7.3	7.4	7.4	7.5	7.7	7.9	8.1	8.3

- Issued on the 12th of August, 2025.
- Values may be subject to change without notice.
- Testing climate 23ºC, 50% RH.
- Billerud production units are certified according to FSC® and PEFC Chain of Custody standards, which both demonstrate traceability.
  License codes: FSC-C004906, FSC-C108771, PEFC/05-33-135 and PEFC/05-33-114
- FSC® and PEFC certified products are available on request.
- Min/max property values are lower resp. upper limit values for 95% confidence interval of the tested properties and are based on measurements on tambour basis.
- During the converting process, especially the bending stiffness values might be influenced negatively.

*) For 335 - 395 g/m²