TICK the lines you want (they turn yellow), then SAVE and send this file back to us.

Client name:

HIPKO
HAMMOUD INTERNATIONAL PAPER SAL.
PAPER & BOARD

# AVAILABLE OFFSHORE - متوفر في الخارج

Stocklot Report

Reference: SL196-FBB-11.11.2026
11 NOVEMBER 2026

**TOTAL AVAILABLE**
**53.166 MT**

**SUBSTANCE RANGE**
**400 - 450 GSM**

| # | QUALITY | GSM | SIZE (CM) | TONS |
|---|---|---|---|---|
| | ***REELS*** | | | **38.56 MT** |
| | ***PANKASEAL FBB*** | | | **19.74 MT** |
| ☐ | 1 PANKASEAL FBB | 410 | 98 cm | 19.74 |
| | ***PANKAMAX HS FBB*** | | | **18.82 MT** |
| ☐ | 2 PANKAMAX HS FBB | 400 | 156 cm | 18.82 |
| | ***SHEETS*** | | | **14.61 MT** |
| | ***PANKABRITE FBB*** | | | **14.61 MT** |
| ☐ | 3 PANKABRITE FBB | 450 | 80 x 120 cm | 14.61 |
| | **TOTAL** | | | **53.17** |

This offer is subject to prior sale and stock confirmation. Prices and availability may change without notice.



## PankaSeal Uncoated folding boxboard (UC2)

### Technical specifications

#### Typical technical values for PankaSeal

| Property / Unit | Tolerance | | | | | | | Standards |
|---|---|---|---|---|---|---|---|---|
| Grammage, g/m² | ±4% | 300* | 350* | 370[1] | 430 | 460 | 500 | ISO 536 |
| Thickness, µm | ±5% | 500 | 620 | 700 | 840 | 900 | 1000 | ISO 534 |
| Moisture, % | ±1.5 | 8.0 | 8.5 | 8.5 | 9.0 | 9.0 | 9.0 | ISO 287 |
| Surface Smoothness, Bendtsen, ml/min | | 500 | 600 | 700 | 800 | 800 | 900 | ISO 7891-2 |
| Bending moment Taber 15º MD, mNm | -15% | 27.0 | 47.0 | 56.1 | 75.3 | 98.7 | 110.0 | ISO 2493 |
| Bending moment Taber 15º CD, mNm | -15% | 11.0 | 19.1 | 22.9 | 30.7 | 38.3 | 48.5 | |

[1]Grammage produced upon special request only, minimum production volume 10 tonnes
*Grammage available only in reels

#### Properties not related to grammage

| Property / Unit | Tolerance | Values | Standards |
|---|---|---|---|
| ISO Brightness C/2º, % | ±1.5 | 75 | ISO 2470-1 |
| Scott Bond, J/m² | >120 | 130 | TAPPI 569 |
| Cobb 180 s top, g/m² | < 70 | 50 | ISO 535 |
| Cobb 180 s reverse, g/m² | < 70 | 50 | ISO 535 |

**Tailor-made substances can be produced upon request, minimum production volume 20 tonnes**

All properties according to Pankakoski Mill measurements tested in manufacturing conditions
Test climate 23ºC / 50%RH (according to ISO 187). Tolerances based upon 95% confidence limits, apply to reel average.
In order to verify, reel average shall be based on 5 single measurements randomly sampled within the reel. These averages will be for at least 19 of 20 reels within the specification limits.

## PankaMax Solid groundwood board with maximized bulk

### Technical specifications

#### Typical technical values for PankaMax

| Property / Unit | Tolerance | | | | | | | | | Standards |
|---|---|---|---|---|---|---|---|---|---|---|
| Grammage, g/m² | ±5% | 290* | 370[1] | 400 | 460[1] | 480[1] | 520[1] | 570 | 630 | ISO 536 |
| Thickness, µm | ±5% | 750 | 970 | 1050 | 1200 | 1260 | 1350 | 1500 | 1650 | ISO 534 |

[1]Grammage produced upon special request only, minimum production volume 10 tonnes
*Grammage available only in reels

#### Properties not related to grammage

| Property / Unit | Tolerance | Values | Standards |
|---|---|---|---|
| Moisture, % | ±1.5 | 7.5 | ISO 287 |
| Scott Bond, J/m² | > 90 | 100 | TAPPI 569 |
| Cobb 30 min top, g/m² | < 100 | 90 | ISO 535 |
| Cobb 30 min reverse, g/m² | < 100 | 90 | ISO 535 |
| pH of Aqueous Extract | | 7.5 – 10.0 | ISO 6588 |
| Alkali Reserve, mol/kg | | > 0.4 | ISO 10716 |

**Produced all fiber layers hard sized as standard, Cobb 30 min < 90 g/m²**

**Tailor-made substances can be produced upon request, minimum production volume 20 tonnes**

All properties according to Pankakoski Mill measurements tested in manufacturing conditions
Test climate 23ºC / 50%RH (according to ISO 187). Tolerances based upon 95% confidence limits, apply to reel average.
In order to verify, reel average shall be based on 5 single measurements randomly sampled within the reel. These averages will be for at least 19 of 20 reels within the specification limits.

## PankaBrite Fully coated folding box board (GC2)

### Technical specifications

#### Typical technical values for PankaBrite

| Property / Unit | Tolerance | | | | | | | | | | | | Standards |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Grammage, g/m² | ±4% | 275 | 300 | 325 | 350 | 375 | 400 | 425 | 450 | 475 | 500 | 550 | ISO 536 |
| Thickness, µm | ±5% | 460 | 510 | 560 | 610 | 670 | 720 | 770 | 830 | 885 | 940 | 1030 | ISO 534 |
| Moisture, % | ±1.5 | 8.5 | 8.5 | 8.5 | 8.5 | 9.0 | 9.0 | 9.0 | 9.0 | 9.5 | 9.5 | 9.5 | ISO 287 |
| Bending moment Taber 15º MD, mNm | -15% | 20.0 | 26.3 | 32.5 | 39.5 | 46.4 | 55.4 | 65.1 | 74.8 | 86.5 | 97.6 | 123.9 | ISO 2493 |
| Bending moment Taber 15º CD, mNm | -15% | 8.8 | 12.1 | 14.9 | 17.9 | 21.1 | 25.2 | 29.5 | 33.9 | 39.1 | 44.1 | 55.9 | |

#### Properties not related to grammage

| Property / Unit | Tolerance | Values | Standards |
|---|---|---|---|
| ISO Brightness C/2º, %, top | ±1.5 | 85 | ISO 2470-1 |
| Colour CIELAB L * C/2˚, top | | 93.5 | ISO 5631-1 |
| Colour CIELAB a * C/2˚, top | | 0.7 | ISO 5631-1 |
| Colour CIELAB b * C/2˚, top | | 0.5 | ISO 5631-1 |
| Surface Smoothness, PPS 10, µm | ±0.3 | 1.0 | ISO 8791-4 |
| Gloss 75º, top % | >40 | 40 | ISO 8254-1 |
| Scott Bond, J/m² | >110 | 110 | TAPPI 569 |

**On request all fiber layers hard sized, Cobb 180 s < 50 g/m²**

All properties according to Pankakoski Mill measurements tested in manufacturing conditions
Test climate 23ºC / 50%RH (according to ISO 187). Tolerances based upon 95% confidence limits, apply to reel average.
In order to verify, reel average shall be based on 5 single measurements randomly sampled within the reel. These averages will be for at least 19 of 20 reels within the specification limits.