



CENTRE FOR MATERIALS FOR ELECTRONICS TECHNOLOGY (C-MET)  
SHORNUR ROAD, ATHANI (PO), THRISSUR - 680 771.

Fax: 0487-201347  
Phone: 0487-201157

### TEST REPORT

Test report No.:	Customer Ref.: Nil
Name of the Customer: M/s. Excel Earthings Thrissur	Date of receipt of sample: 04.01.2010
Code:	Date of completion of testing: 15.01.2010
Batch No.	Date of reporting: 15.01.2010

Packing  
Sample identification/description:

### TEST RESULTS

Summary of results: (for details see enclosed sheets)


Total number of samples: 2

Sheet resistance of

1. Excel Earthing compound :  $2.89 \times 10^6 \Omega^*$
2. Charcoal :  $52.5 \times 10^6 \Omega^*$

\* The samples were made slurry using double distilled water and casted to sheet form and dried at Room temperature for 24 hrs. The resistance was measured by two probe method.

Seema A  
Analyst / Engineer.

  
Authorized signatory

Subject to terms and conditions in overleaf.

