


Heraeus

# PALACOS® MV

Medium viscosity, radiopaque bone cement





# PALACOS® MV

**EN**      **Instructions for use**  
            **Working times**  
            (Revision status: 05/2014)

**ZH**      **使用说明书**  
            **加工时间**  
            (修订状态: 2014 年 5 月)

**3**  
**6**

**第7页**  
**第10页**

66057815/06048



EN

# PALACOS®MV

## Properties – Composition

**PALACOS®MV** is a radiopaque, quick-setting bone cement and exhibits low initial viscosity. It is obtained by mixing a polymer powder component with a liquid monomer component. Zirconium oxide has been added to the cement powder as an X-ray contrast medium. The sterile-filtrated monomer component is supplied in an amber glass ampoule and comes in a sterile blister pack. The polymer powder component is supplied in a double sterile packaging. The inner polyethylene sachet which contains the powder component is wrapped in an additional polyethylene sachet; both sachets were sterilized with ethylene oxide. The polyethylene sachets are contained in a non-sterile protective aluminium packaging. Chlorophyll (Typ E141) has been used to obtain the green colour of **PALACOS®MV** in order to ensure clear visibility of the cement at the operating site. After mixing, a plastic dough is obtained which is filled into the bone as an anchoring medium. The cement which then hardens in the bone allows stable fixation of the endoprostheses. The stress forces resulting from motions are transferred via the cement coating widely onto the bone.

## Intended use

**PALACOS®MV** is a radiopaque cement-like substance which allows the implantation and fixation of prostheses in the bone.

## Indications

**PALACOS®MV** is indicated for the fixation of prostheses in the bone in partial and total arthroplastic surgery of the hip, knee or other joints.

## Contraindications

**PALACOS®MV** must not be used during pregnancy or nursing. In cases of known hypersensitivity to the constituents of the bone cement **PALACOS®MV** must not be used.

## Warning information – Side effects

**PALACOS®MV** has not been evaluated with regard to spinal surgery. In some cases, the use of this cement beyond the listed indications in spine surgery resulted in serious, life-threatening complications. Cases of pulmonary embolism, respiratory and cardiac insufficiency and death have been reported.

Prior to using **PALACOS®MV** the surgeon should be familiar with its properties, handling and application during arthroplastic surgery. It is also recommended for surgeons to practice mixing, handling and application of **PALACOS®MV** prior to the use. Precise knowledge is also required, if mixing systems and syringes are used for the application of the cement. The monomer liquid is highly volatile and flammable; accordingly, suitable precautionary measures should be taken for use in the operating room. The monomer is also a powerful lipid solvent and should not come into direct contact with the body. When working with the monomer or the cement, gloves must be worn to ensure adequate protection against the penetration of the monomer (methyl methacrylate) into the skin. PVP (three-layer polyethylene, ethylene-vinyl alcohol-copolymer, polyethylene) and Viton/Butyl gloves have proven to provide good protection over an extended period. Wearing two pairs of gloves has also proved to offer adequate protection. The use of latex or polystyrene-butadiene gloves, however, must be avoided. Please request the confirmation of your

Composition	PALACOS®MV 1x40
	<b>1 sachet of 44.0 g powder contains:</b>
Poly (methyl acrylate, methyl methacrylate)	38.3 g
Zirconium dioxide	5.3 g
Benzoyl peroxide	0.4 g
	<b>1 ampoule with 20 ml liquid contains:</b>
Methyl methacrylate	18.4 g
N,N-Dimethyl-p-toluidine	0.4 g
Other constituents	In the powder: colourant E141 In the liquid: colourant E141, hydroquinone



glove supplier whether the respective gloves are suitable for use with **PALACOS® MV**.

The monomer vapors may irritate the respiratory tract and the eyes and possibly damage the liver. Skin irritations have been reported, which must be attributed to the contact with the monomer.

Manufacturers of soft contact lenses recommend the removal of the lenses in the presence of harmful or irritating vapors. Since contact lenses are permeable to liquids and gases, they should not be worn in the operating room if methyl methacrylate is used.

#### Precautionary measures

Blood pressure, pulse and breathing must be carefully monitored during and immediately after implanting the bone cement. Any significant change of these vital signs must be immediately responded to with adequate measures.

If **PALACOS® MV** is used for a total hip endoprosthesis, the proximal part of the medullary (bone marrow) canal of the femur and the acetabulum need to be thoroughly cleaned, aspirated and dried.

To reduce the considerable increase in pressure in the intraosseous area during the implantation of the prosthesis, it is recommended to use suction drainage. If pulmonary, cardiovascular complications arise, monitoring and – in some cases – even increasing the blood volume may be required. In case of acute respiratory insufficiency, anaesthesiological measures should be taken.

#### Undesired effects

Frequently, a temporary drop in blood pressure immediately after the implantation of the bone cement and the endoprosthesis has been observed. Rare cases of hypotension, including anaphylactic shock, followed by cardiac arrest and sudden death have been reported. The following, additional undesired effects of the use of methyl methacrylate bone cement have been observed:

Thrombophlebitis, superficial wound infection, deep wound infection, pulmonary embolism, haemorrhage and haematoma, trochanter bursitis, loosening or displacement of the prosthesis, trochanter detachment.

Other side effects observed: heterotopic bone regeneration, myocardial infarction, temporary cardiac arrhythmia, cerebrovascular accident.

#### Interactions

Not known for **PALACOS® MV**.

#### Incompatibilities

Aqueous solutions (e.g. containing antibiotics) must not be added to the bone cement since they considerably impair the mechanical properties of the cement.

#### Dosing and preparation

A single dose is prepared by mixing the entire content of a powder sachet with one ampoule. The quantity to be used depends on the respective surgical operation and the technique employed. Before the beginning of the operation, at least one additional dose of **PALACOS® MV** should be readily available. Each dose is prepared separately.

The following is required to prepare the bone cement:

Sterile working surface, porcelain or stainless steel bowls, sterile mixing spoons or porcelain or stainless steel spatulas or a sterile vacuum mixing system.

The protective aluminium packaging, the outer non-sterile polyethylene sachet and the blister pack of the ampoules should be opened by an assistant in a way to maintain sterility. The sterile polyethylene sachet and the ampoule are placed under aseptic conditions on a sterile table. Sterile conditions must be ensured when opening the polyethylene sachet and the ampoule.

#### Application

Two different methods can be used for mixing:

Manual mixing

Mixing under vacuum

#### Manual mixing

The liquid is poured into a bowl and the powder is added. Do not open the ampoule over the mixing device to prevent contamination of the cement with glass fragments. Then the mixture is stirred carefully for 30 sec.

If the dough-like mass no longer sticks to the rubber gloves, it can be processed. The application time depends on the material and room temperature. If the required consistency is obtained, the cement can be applied. To ensure adequate fixation, the prosthesis should be implanted and stabilized within the given time until the bone cement has hardened completely. Surplus cement must be removed as long as it is still soft.

If additional cement is needed during the operation, another sachet of powder can be mixed with one ampoule of liquid as described above. The kneadable mass which is obtained must be applied to the previously applied cement before it hardens. It is always required to mix the entire content of a sachet with the entire content of an ampoule.

#### Mixing under vacuum

To obtain a bone cement with reduced porosity, the components are mixed under vacuum. For this purpose an airtight closed system and rapid build-up of sufficient vacuum in the mixing equipment are required (absolute pressure: approx. 200 mbar). The stirring times for mixing under vacuum and mixing without vacuum are identical (30 sec). For details of the mixing method refer to the instructions of the mixing system used.



**Storage**

Do not store above 25 °C (77 °F).

**Shelf life/Sterility**

The shelf life is 3 years. The expiration date is printed on the folded box, the protective aluminium packaging and the inner sachet. **PALACOS® MV** must not be used after the expiration date. The contents of unused but opened or damaged packs must be discarded and must not be resterilized. **PALACOS® MV** has been sterilized with ethylene oxide gas and must not be resterilized. The polymer powder must not be used if it exhibits yellow discoloration.


Manufacturer: Heraeus Medical GmbH  
Registered office address: Philipp-Reis-Straße 8/13,  
61273 Wehrheim, Germany  
Manufacturing address: Philipp-Reis-Straße 8/13,  
61273 Wehrheim, Germany  
Telephone: +49 (0) 6181.35-3399  
Fax: +49 (0) 6181.35-3366  
Website: www.heraeus-medical.com

After sale-service agent:  
LandMover Medical & Technology (Beijing) Co., Ltd.  
Address: Room 606, 6th Floor, Building 2, No. 106,  
Majiapu east road, Fengtai District, Beijing, China  
Tel: +86 10 5803 1636  
Fax: +86 10 5803 1636 EXT 804


License number: CFDA (I)20113651097 (更)  
Product Standard: YZB/GER 0761-2011



### Working times for manual mixing (not pre-chilled bone cement)



### Working times for vacuum mixing (not pre-chilled bone cement)



■ Mixing ① ■ Waiting ② ■ Application ③ ■ Setting ④

Test conditions: Not pre-chilled vacuum mixing system PALAMIX®, 55% humidity.



ZH

## PALACOS® MV

**性质-成分**

**PALACOS® MV**为一种不透辐射的快凝骨水泥，呈微小的初始粘性。其制备方法为将一聚合体粉末状成分与一液状单体成分相混合。氧化锆已被作为X线造影剂加入该骨粉。该经无菌过滤的单体成分供货时以琥珀玻璃安瓿瓶装，外加有无菌泡罩包装，其经环氧乙烷灭菌。

粉末状的聚合体成分以双层无菌包装的形式供应。即在一个内层聚乙烯小袋中装粉末状成分，在其外再包一个聚乙烯小袋，这两个小袋均已用环氧乙烷灭菌。在这两个小袋外加有非无菌保护性铝包装。

叶绿素（索引号：E141）被用来使**PALACOS® MV**变成绿色，以使该水泥在手术区域上清晰可见。

混合后，形成了一种面团状可塑物质，其被作为锚固剂注入骨。该水泥然后在骨内固化，从而使内假体被稳定地固定住。在活动时产生的压应力通过水泥层被大面积地施加于骨上。

**使用意图**

**PALACOS® MV**为一种不透辐射的水泥状物质，其有助于将假体植入并固定于骨内。

**适应症**

适用于关节置换术植入假体的内固定。

**禁忌症**

在怀孕期或哺乳期禁用**PALACOS® MV**。并在已知对骨水泥**PALACOS® MV**的成分过敏的病例中禁用。

**警示信息—副作用**

未在脊椎手术方面对**PALACOS® MV**做过评价。在针对上述适应症之外的病症的脊椎手术中使用该水泥可导致严重的危及生命的并发症，已有肺栓塞、呼吸功能不全、心功能不全乃至死亡的报道。

在使用**PALACOS® MV**之前，外科医生应熟悉其在关节造形术中的性质、处理方法和应用。建议外科医生在使用**PALACOS® MV**之前，练习混合、处理和施用。如果在施用水泥时使用混合系统和注射器，需要了解详尽的有关知识。。单体液体具有高度的挥发性和易燃性，因此在手术室内应采用适当的预防措施。该单体液也是强脂溶剂，不应与身体直接接触。当用处理单体液或水泥时，应戴上手套以充分地防止单体（甲基丙烯酸甲酯）渗入皮肤。由三层聚乙烯、乙烯-乙醇共聚物、聚乙烯和氟橡胶（Viton®）/丁基制成的手套经长时间的检验，已被证明可提供充分的保护。但必须避免仅戴乳胶或聚苯乙烯-丁二烯手套。请要求您的手套供应商确认有关手套是否适用于**PALACOS® MV**。

成分	PALACOS® MV 1x40
	每小袋中的44,0 g粉中含有：
聚（丙烯酸甲酯、甲基丙烯酸甲酯）	38.3 g
二氧化锆	5.3 g
过氧苯甲酰	0.4 g
	每安瓿瓶中的20 ml 液体中含有：
甲基丙烯酸甲酯	18.4 g
N,N-二甲基-对甲苯胺	0.4 g
其它成分：	在粉中：着色剂 E141； 在液体中：着色剂 E141、对苯二酚。



单体汽可刺激呼吸道和眼，可能对肝造成损害。已有因与单体接触而引起的皮肤炎症的报道。

软性隐形眼镜的生产厂家建议在有害或刺激性气体存在的情况下去除镜片。因为液体和气体可渗透过隐形眼镜的镜片，如使用甲基丙烯酸甲酯，不得在手术室内戴隐形眼镜。

### 预防措施

应在植入骨水泥时或紧接植入水泥后仔细监测血压、脉搏和呼吸。如果这些生命标志有任何显著的变化，必须立刻采取适当的措施。

如果将PALACOS® MV用于全髓内假体，需要将大腿骨和髌骨的髓管的近端部分彻底清洗，并吸出液体然后将其干燥。

在植入假体时，为了降低骨内相当大的压力增加，建议使用抽吸引流。如果发生肺、心血管并发症，需要监测血量，在一些病例中甚至可能需要增加血量。在急性呼吸功能不全的情况下，应采取麻醉措施。

### 不良反应

经常在植入骨水泥和内假体后立即观察到暂时的血压降低。据报道在一些罕见的病例中有伴随过敏反应的血压过低，这些过敏反应包括过敏性休克、心跳骤停和猝死等。

下列使用甲基丙烯酸甲酯骨水泥后产生的其它不良反应已被观察到：

血栓性静脉炎、表面伤口感染、深度伤口感染、肺栓塞、出血和血肿、转子粘液囊炎、假体松动与移位和转子脱离。

观察到的其它副作用：异位成骨、心肌梗塞、短暂性心律不齐和脑血管事件。

### 相互作用

对PALACOS® MV尚无资料。

### 不亲和性

勿将水溶液（例如含抗生素的）加入骨水泥，因为这些水溶液会相当大地损害水泥的力学性质。

### 剂量和制备

将一装粉的小袋中全部内容物与一个安瓿内的液体相混合以制备一剂。使用剂量取决于相应手术和所

采用的技术。在手术开始前，必须准备至少一剂备用的PALACOS® MV。每一剂应单独制备。

下列为制备骨粉所需要的条件：

无菌工作台面、瓷或不锈钢碗、无菌搅拌勺、瓷或不锈钢调药刀或一无菌真空混合系统。

应由助手以保持无菌的方法打开保护性铝包装、外层非无菌聚乙烯小袋和安瓿的泡罩包装。无菌聚乙烯小袋和安瓿应在无菌条件下放置地无菌工作台上。并应保证在无菌状况下打开聚乙烯小袋和安瓿。

### 施用

两个不同的方法可用于混合，

手动混合；

真空下混合。

### 手动混合

将液体倾倒入碗中，再加入粉。请勿在混合设备上方便打开安瓿，以防骨水泥被玻璃碎片污染。然后仔细地搅拌混合物30秒。

当面团状物质不再粘在橡胶手套上，可对其进行加工。施用持续时间取决于材料和室温。当达到需要的稠度后，可以施用该水泥。为了保证充分地固定假体，必须在一定的时间内将其植入并使其保持固定，直到骨水泥彻底固化。必须将溢出的骨水泥在其未凝固前清除。如果在操作中需要额外的水泥，将另一小袋中的粉与一安瓿中的液体如上述混合。将得到的可塑性物质在其变硬前加入已施用的水泥中。必须总是将一个口袋中的全部内容物与一个安瓿中的全部内容物混合。

### 真空下混合

为了得到多孔性较低的骨水泥，将骨水泥成分在真空下混合。为了这个目的，必须有一个气密性系统，并在混合系统中快速建立足够的真空（绝对压力：约200 mbar）。在真空下混合的搅拌时间（30 s）与非真空下混合的相同。混合方法详见所采用的混合系统的使用说明





### 储存

勿储存在高于25°C (77°F)的温度下。


### 储存期/无菌状态

该产品有效期三年。过期日期被印在折叠的盒、保护性铝包装和内层小袋上。过期后，PALACOS® R不能使用。未使用过的、但已打开或损坏的包装必须丢弃，不能再对其进行灭菌。聚合物粉如已呈黄色，不能再使用。


生产厂家：Heraeus Medical GmbH  
注册地址：Philipp-Reis-Straße 8/13,  
61273 Wehrheim, Germany  
生产地址：Philipp-Reis-Straße 8/13,  
61273 Wehrheim, Germany  
电话：+49 (0) 6181.35-3399  
传真：+49 (0) 6181.35-3366  
网址：www.heraeus-medical.com

售后服务机构：雷德睦华医药科技（北京）有限公司  
地址：北京市丰台区马家堡东路106号2号楼6层606室  
电话：010-58031636  
传真：010-58031636转804  
医疗注册号：国食药监械（进）字2011第3651097号（更）  
注册产品标准编号：YZB/GER 0761-2011

### 手动混合的工作时间(非预冷骨水泥)



### 真空混合的工作时间(非预冷骨水泥)



■ 搅拌期 ① ■ 粘丝期 ② ■ 粘丝期 ③ ■ 面团期 ④

测试条件: 未预冷, 使用PALAMIX真空混合 55% 湿度

# SYMBOLS



Manufacturer



Sterilized using aseptic processing techniques



Sterilized using ethylene oxide



Consult instructions for use



Keep away from sunlight



Keep dry



Do not store above 25 °C (77 °F)



Do not re-use



Do not re-sterilize



Catalogue number



Use by date



Batch code



Flammable liquid – Flashpoint 10 °C



Causes skin irritation

# Heraeus



EN Do not use if the product sterilization barrier or its packaging is compromised.  
ZH 若发现无菌环境遭破坏或包转破损，则禁止使用。

**REF** 66055192



Heraeus Medical GmbH  
Philipp-Reis-Straße 8/13  
61273 Wehrheim, Germany  
[www.heraeus-medical.com](http://www.heraeus-medical.com)

PALACOS® is a trademark of Heraeus Medical GmbH.

## CE 0123