

Enhancement Due to Photonic Coupling in Nanocavity Structures

```
Bumbia, Amal;
Abudayyeh, Hamza;
Liu, Zhida;
Li, Xiaoqin
```

Department of Physics UT

Austin



Outline and Key Concepts

Quantum emitters

(plasmonic) cavities

Transition Metal Dichalcogenide

nanocubes


Our Sample

Dark-field spectroscopy

Photoluminescence




How do quantum emitters work?






Why can a nanoscale quantum emitter can have emitting behavior?






What is the interplay between quantum emitters and cavities?






Nanocube

 shorten the lifetime of exciton emission via plasmonic nanostructures (nanocubes)





TMD - Transition Metal Dichalcogenide





What are the effects of weak coupling between plasmonic nanocavities and excitons?



How does plasmon-exciton coupling effect emission

enhancement?




The Sample



Material: Monolayer TMD Film-Cube Separation: 8-9 nm cavity Au nanocubes TMD (70-100 nm) **TMD** gold foil






Dark-field Spectroscopy


- white light scattering by nanocavities
- measure plasmonic resonances





Focusing on a single nanocube point


Emission spectrum of a nanocube







Hyperspectral Spatial Image

- well localized points with nanocubes
- intensity coming out of these points is enhanced












Photoluminescence (PL)

- excite sample at different wavelengths
- measure exciton resonances
- longer wavelengths enhanced
- greater, non-uniform intensity enhancement along nanocubes
- overlap between the wavelengths where plasmonic resonances and enhancement occur





Future Applications

- insight to optical properties of quantum emitters
- manipulate emitters by altering their EM environment
- enhance previously weak emissions
- nanophotonic devices
- manipulating light-matter interaction at the nanoscale




Acknowledgements

I would like to thank Dr. Hamzah Abudayyeh and Dr. Xiaoqin Li for giving me the opportunity to work on this project.



HIDDEN SLIDES







Coupling parameters:

- emitter's decay in free space \$\Gamma _0\$\\
- cavity's loss rate \$\kappa\$\\
- emitter-cavity coupling coefficient \$g\$\\

This is dependent on the overlap of the photonic cavity and the resonances of the 2-level system. Due to the interplay between the photonic cavity and the system, we are able to enhance some processes at the expense of others. For instance, if the resonances of the plasmonic cavity are vertical, they selectively enhance dipole emitters with a vertical dipole. Not only are we increasing the lifetime, but we are also altering our characterization and probability of the emission.

Cavities can impact emitters in a few ways:

- decay rate enhancement --- The weak coupling of a 2-level emitter to a cavity leads to the modification of the spontaneous emission rate. The emitter can have multiple radiative modes and some nonradiative processes
- emission redirection --- the intrinsic radiation pattern of a quantum emitter is omnidirectional, making it hard to collect emitted photons. Cavities can redirect the emission to the desired optical mode with an efficiency \$\eta_{NA}\$. Different modes can have different efficiencies.
- absorption enhancement --- cavities alter the absorption cross-section of the emitter which causes absorption enhancement and lowers the saturation power needed from the pump laser.



Weak Coupling Regime

We are concerned with the weak coupling regime \$g < \kappa\$, \$\Gamma 0\$. Here, the photon is released by an excited emitter due to spontaneous emission and lost to far-field radiation modes leaving the cavity in a vacuum state. In this case, the cavity becomes the system's environment and results in a modified decay rate \$\Gamma = F \Gamma _0\$ where \$F = \frac{3}{4\pi ^2} Q \frac{\lambda ^3}{V}\$ (Purcell factor represents the shortening of lifetimes; losses ensure that it is not directly related to the number of emitted photons), \$Q \approx \frac{1}{\kappa}\$ (cavity quality factor), and the cavity mode volume \$\frac{V}{\lambda ^3}\$. The advantage of the weak coupling regime is that for emitted photons, the probability that they will be reabsorbed by the emitter is low compared to the likelihood of the photon escaping the cavity.



Methods

- Use AFM to confirm nanocubes
- Pick nanocube points of interest
- Map their plasmonic resonances using dark-field spectroscopy
- Use PL to graph enhancement due to exciton emission Does an overlap between the plasmonic resonances and exciton excitation exist?