

Table 0: Preview of Enriched Anode Dataset with 12 Extended Features

formula	E_ads_DFT_eV	band_gap	formation_energy	energy_hull	bulk_modulus	shear_modulus	young_modulus	mean_atomic_mass	mean_electronegativity	pugh_ratio	poisson_ratio
LiCr9O27	-7.102	1.902	-1.705	2.573	22.910	12.050	30.757	24.511	2.941	1.901	0.276
LiBi4F20	-6.823	1.589	-1.805	0.085	35.210	24.410	59.484	48.913	3.546	1.442	0.218
GaSe	-4.932	0.725	-0.582	0.029	33.000	21.140	52.261	74.341	2.180	1.561	0.236
VS2	-4.869	0.000	-0.942	2.099	49.360	29.910	74.651	38.357	2.263	1.650	0.248
PF5	-4.392	7.356	-2.573	0.000	13.990	7.430	18.937	20.994	3.682	1.883	0.274
VSe	-4.287	0.000	-0.515	1.656	93.160	20.690	57.792	64.951	2.090	4.503	0.397
ZrS2	-4.226	0.911	-1.686	1.837	44.090	31.870	77.046	51.785	2.163	1.383	0.209
ZrO2	-4.204	3.914	-3.642	1.487	178.770	46.680	128.827	41.074	2.737	3.830	0.380