

Table 3. Top 10 Screened Host Anode Materials from CGCNN Multi-Property Evaluation

Rank	Formula	E_ads (eV)	Eg (eV)	Ef (eV/at)	K (GPa)	G (GPa)	Score
1	C	-2.673	3.462	0.196	412.421	462.367	0.720
2	FeOF	-2.115	0.133	-1.673	172.056	95.724	0.676
3	HoBrO	-2.183	3.489	-2.968	48.625	20.644	0.644
4	TmBrO	-2.171	4.465	-3.003	49.086	29.286	0.639
5	Rb2F	-2.006	0.016	-1.885	22.908	4.241	0.630
6	YClO	-1.518	1.898	-2.630	73.658	42.931	0.629
7	NbC	-1.824	0.064	-0.393	295.005	192.619	0.617
8	Mg2SiO4	-2.768	3.912	-2.729	193.481	102.894	0.615
9	CuMoO4	-2.001	0.034	-1.589	131.549	59.215	0.603
10	VOF	-2.761	0.490	-2.472	88.902	52.932	0.602