

Formula	Actual Eg (eV)	Predicted Eg (eV)	Difference	Abs Error
NiS2	0.0	0.217	0.217	0.217
SnSe	0.47	0.52	0.05	0.05
MnO	0.18	0.253	0.073	0.073
Co3O4	0.0	0.04	0.04	0.04
Ni2P	0.0	0.052	0.052	0.052
MnS	0.0	0.0	0.0	0.0
ZnS	2.02	1.952	-0.068	0.068
TiO2	2.68	2.728	0.048	0.048
NiO	2.3	2.139	-0.161	0.161
Ni2P	0.0	0.059	0.059	0.059