

Formula	Actual G (GPa)	Predicted G (GPa)	Difference	Abs Error
NiS2	19.582	15.724	-3.857	3.857
SnSe	20.91	21.883	0.973	0.973
MnO	54.115	50.304	-3.811	3.811
Co3O4	65.0	57.809	-7.191	7.191
Ni2P	38.15	45.859	7.709	7.709
MnS	29.955	34.955	5.0	5.0
ZnS	33.288	22.154	-11.134	11.134
TiO2	74.663	79.824	5.161	5.161
NiO	52.573	58.773	6.2	6.2
Ni2P	38.15	32.707	-5.443	5.443