

| Formula | Actual Formation Energy (eV/atom) | Predicted Formation Energy (eV/atom) | Difference | Abs Error |
|---------|-----------------------------------|--------------------------------------|------------|-----------|
| NiS2    | -0.334                            | -0.403                               | -0.07      | 0.07      |
| SnSe    | -0.482                            | -0.49                                | -0.008     | 0.008     |
| MnO     | -1.313                            | -1.289                               | 0.023      | 0.023     |
| Co3O4   | -1.109                            | -1.099                               | 0.01       | 0.01      |
| Ni2P    | -0.432                            | -0.421                               | 0.011      | 0.011     |
| MnS     | -0.494                            | -0.445                               | 0.048      | 0.048     |
| ZnS     | -0.887                            | -0.882                               | 0.004      | 0.004     |
| TiO2    | -3.25                             | -3.211                               | 0.038      | 0.038     |
| NiO     | -0.636                            | -0.616                               | 0.02       | 0.02      |
| Ni2P    | -0.432                            | -0.461                               | -0.03      | 0.03      |