

Top Candidate Host Materials

Rank	Formula	E _g (eV)	E _f (eV/at)	K (GPa)	G (GPa)	E _{ads} (eV)	Composite Score
1	WB2	0.0	-1.5	310.0	180.0	2.722	0.772
2	MoC	0.0	-0.17	306.843	145.583	2.89	0.653
3	Co3O4	0.0	-1.109	186.5	65.0	5.572	0.644
4	Ti3O5	0.0	-3.178	170.0	68.0	2.596	0.642
5	Mo2C	0.0	-0.149	293.87	147.8	2.782	0.641
6	Ti4O7	0.0	-2.773	175.0	70.0	2.136	0.603
7	ZnO	0.72	-1.592	143.802	44.627	4.57	0.525
8	MnO	0.18	-1.313	184.99	54.115	2.593	0.506
9	TiO2	2.68	-3.25	159.067	74.663	3.348	0.477
10	Ni3P	0.0	-0.405	195.0	68.0	2.112	0.466