

Sample Preview of Integrated Matched Polysulfide Adsorption Dataset

Formula	Adsorbate	E _g (eV)	E _f (eV/at)	E _{hull} (eV)	K (GPa)	G (GPa)	E _{ads} (eV)
TiO2	S8	2.68	-3.25	1.47	159.067	74.663	3.84
TiO2	Li2S8	2.68	-3.25	1.47	159.067	74.663	2.67
TiO2	Li2S6	2.68	-3.25	1.47	159.067	74.663	3.08
TiO2	Li2S4	2.68	-3.25	1.47	159.067	74.663	3.67
TiO2	Li2S2	2.68	-3.25	1.47	159.067	74.663	3.48
Ti4O7	S8	0.0	-2.773	0.04	175.0	70.0	0.91
Ti4O7	Li2S8	0.0	-2.773	0.04	175.0	70.0	1.67
Ti4O7	Li2S6	0.0	-2.773	0.04	175.0	70.0	2.23
Ti4O7	Li2S4	0.0	-2.773	0.04	175.0	70.0	2.82
Ti4O7	Li2S2	0.0	-2.773	0.04	175.0	70.0	3.05