

Dataset Sample Preview — 5 Core Physical Target Properties

Formula	Adsorbate	Eg (eV)	Ef (eV/at)	Ehull (eV)	K (GPa)	G (GPa)	E_ads (eV)
TiO2	S8	2.680	-3.250	1.470	159.067	74.663	3.840
TiO2	Li2S8	2.680	-3.250	1.470	159.067	74.663	2.670
TiO2	Li2S6	2.680	-3.250	1.470	159.067	74.663	3.080
TiO2	Li2S4	2.680	-3.250	1.470	159.067	74.663	3.670
TiO2	Li2S2	2.680	-3.250	1.470	159.067	74.663	3.480
Ti4O7	S8	0.000	-2.773	0.040	175.000	70.000	0.910
Ti4O7	Li2S8	0.000	-2.773	0.040	175.000	70.000	1.670
Ti4O7	Li2S6	0.000	-2.773	0.040	175.000	70.000	2.230
Ti4O7	Li2S4	0.000	-2.773	0.040	175.000	70.000	2.820
Ti4O7	Li2S2	0.000	-2.773	0.040	175.000	70.000	3.050