

Actual Bulk Modulus	Predicted Bulk Modulus	Difference	Abs Error	
NiS2	51.997	51.76	-0.237	0.237
SnSe	34.192	39.066	4.874	4.874
MnO	184.99	201.151	16.161	16.161
Co3O4	186.5	181.923	-4.577	4.577
Ni2P	184.18	178.515	-5.665	5.665
MnS	57.85	55.252	-2.598	2.598
ZnS	72.298	73.401	1.103	1.103
TiO2	159.067	155.471	-3.596	3.596
NiO	194.387	198.577	4.191	4.191
Ni2P	184.18	191.866	7.686	7.686