

Formula	Actual K (GPa)	Predicted K (GPa)	Difference	Abs Error
Mo2C	293.87	302.05	8.18	8.18
VSe	90.687	94.116	3.43	3.43
NiS2	51.997	61.314	9.317	9.317
Co3O4	186.5	180.343	-6.157	6.157
Ni2P	184.18	202.429	18.249	18.249
MnS	57.85	44.696	-13.154	13.154
Co3O4	186.5	178.376	-8.124	8.124
TiO2	159.067	160.074	1.007	1.007
NiO	194.387	190.879	-3.507	3.507
Ni2P	184.18	179.182	-4.998	4.998