

Formula	Actual G (GPa)	Predicted G (GPa)	Difference	Abs Error
Mo2C	147.8	143.424	-4.376	4.376
VSe	51.75	56.749	4.999	4.999
NiS2	19.582	26.558	6.976	6.976
Co3O4	65.0	66.14	1.14	1.14
Ni2P	38.15	32.581	-5.569	5.569
MnS	29.955	40.382	10.427	10.427
Co3O4	65.0	62.395	-2.605	2.605
TiO2	74.663	68.827	-5.836	5.836
NiO	52.573	56.092	3.519	3.519
Ni2P	38.15	29.661	-8.489	8.489