

Formula	Actual Ef (eV/at)	Predicted Ef (eV/at)	Difference	Abs Error
Mo2C	-0.149	-0.09	0.059	0.059
VSe	-0.515	-0.618	-0.103	0.103
NiS2	-0.334	-0.312	0.021	0.021
Co3O4	-1.109	-0.988	0.12	0.12
Ni2P	-0.432	-0.455	-0.024	0.024
MnS	-0.494	-0.388	0.105	0.105
Co3O4	-1.109	-1.059	0.05	0.05
TiO2	-3.25	-3.191	0.058	0.058
NiO	-0.636	-0.548	0.087	0.087
Ni2P	-0.432	-0.483	-0.052	0.052