

Formula	Actual Ef (eV/at)	Predicted Ef (eV/at)	Difference	Abs Error
NiS2	-0.334	-0.403	-0.07	0.07
SnSe	-0.482	-0.49	-0.008	0.008
MnO	-1.313	-1.289	0.023	0.023
Co3O4	-1.109	-1.099	0.01	0.01
Ni2P	-0.432	-0.421	0.011	0.011
MnS	-0.494	-0.445	0.048	0.048
ZnS	-0.887	-0.882	0.004	0.004
TiO2	-3.25	-3.211	0.038	0.038
NiO	-0.636	-0.616	0.02	0.02
Ni2P	-0.432	-0.461	-0.03	0.03