EUROPEAN INDUSTRIAL POLYMER SUPPLY

SUSPENSION PVC RESIN

PRIME EXTRUSION GRADES: ZHONGTAI SG-5 & SINOPEC S-1000

Zagros Vitosha Bulgaria EOOD is an international petrochemical and polymer distribution company registered in the Republic of Bulgaria (European Union). We supply 100% prime virgin Suspension Polyvinyl Chloride (S-PVC) resins directly from tier-one global producers to European profile extruders, pipe manufacturers, and compounding plants.

Key Supply Advantages:

- **Certified Prime Virgin Resin:** Guaranteed batch-to-batch consistency with K-Value 65–68.
- **Strict EU Compliance:** Residual VCM < 1.0 ppm (exceeding EU REACH safety standards).
- **Multi-Modal Delivery:** Direct ocean containers to **CIF Gdansk (Poland)**, **CIF Constanta (Romania)**, **CIF Varna/Burgas**, and **FCA Bulgaria Warehouse**.
- **Independent Inspection:** Pre-shipment quality & loading verification by **SGS / Bureau Veritas**.



Executive Comparative Matrix — Prime Suspension PVC Grades

Technical / Commercial Metric	Zhongtai SG-5 (Extrusion & Profile Grade)	Sinopec S-1000 (High-Purity Pipe & Profile Grade)
Manufacturer & Origin	Xinjiang Zhongtai Chemical Co., Ltd. (P.R. China)	Sinopec Qilu Petrochemical Corp. (P.R. China)
CAS Registry / HS Code	CAS: 9002-86-2 | EU Taric / HS Code: 3904 10 00	CAS: 9002-86-2 | EU Taric / HS Code: 3904 10 00
K-Value & Viscosity Number	**K-Value: 66 – 68 (Typical: 67)** | Viscosity: 118 – 127 mL/g	**K-Value: 65 – 67 (Typical: 66.5)** | Viscosity: 107 – 118 mL/g
Apparent Bulk Density	>= 0.55 g/mL (Typical Batch: 0.56 g/mL)	>= 0.53 g/mL (Typical Batch: 0.54 g/mL)
Whiteness & Residual VCM	Whiteness: >= 82% (160 C, 10m) | **Residual VCM: < 1.0 ppm**	Whiteness: >= 83% (160 C, 10m) | **Residual VCM: < 1.0 ppm**
Primary Industrial Applications	uPVC window & door multi-chamber profiles, rigid sewage & drainage pipes, siding, fencing, technical profiles.	High-speed window profiles, pressure water pipes, rigid calendered sheets, electrical cable conduits & fittings.
Standard Export Packaging	25 kg kraft composite bags on shrink-wrapped pallets / 1,000 kg FIBC	25 kg kraft composite bags on shrink-wrapped pallets / 1,000 kg FIBC

ISO 9001 & 14001 CERTIFIED Produced by Tier-1 state & public petrochemical complexes with full batch traceability.	**EU REACH COMPLIANT** Residual VCM monomer < 1.0 ppm; supplied with 16-section European GHS SDS.	**SGS / BV PRE-SHIPMENT QC** Independent third-party laboratory testing & container loading supervision available.	**EU REGISTERED SUPPLIER** Zagros Vitosha Bulgaria EOOD EIK: 208619412 | VAT: BG208619412

1. Zhongtai SG-5 — Suspension PVC Resin Technical Dossier

MANUFACTURER: XINJIANG ZHONGTAI CHEMICAL CO., LTD. | STANDARD: GB/T 5761-2018 | K-VALUE: 67

No.	Test Parameter	Unit	Standard (SG-5)	COA Batch Result	Verdict
1	**K-Value**	-	66 - 68	**67.0**	**PASS**
2	**Viscosity Number**	mL/g	118 - 127	**122**	**PASS**
3	**Apparent Bulk Density**	g/mL	>= 0.55	**0.56**	**PASS**
4	**Volatile Matter (inc. water)**	%	<= 0.40	**0.25**	**PASS**
5	**Sieve Residue (0.25 mm)**	%	<= 2.0	**0.3**	**PASS**
6	**Sieve Residue (0.063 mm)**	%	<= 6.0	**3.5**	**PASS**
7	**Fish Eyes Count**	pcs/400cm 2	<= 30	**15**	**PASS**
8	**Whiteness (160 C, 10 min)**	%	>= 75	**82**	**PASS**
9	**Residual VCM Monomer**	ppm	<= 5.0	**< 1.0**	**PASS**
10	**Impurity Particle Count**	pcs	<= 16	**8**	**PASS**
11	**Water Extract Conductivity**	uS/cm	<= 100	**80**	**PASS**
12	**Residual Inhibitor (Pe)**	ppm	Conforms	**Conforms**	**PASS**



KEY EXTRUSION & PROCESSING BENEFITS

- **Window & Door Profile Excellence:** Ideal particle porosity guarantees homogeneous mixing with Ca-Zn stabilizers, TiO2, and acrylic impact modifiers.
- **Superior Dry-Blend Flow:** High apparent density (0.56 g/mL) maximizes extruder screw feeding efficiency and output torque stability.
- **High Thermal Whiteness:** 82% whiteness index ensures bright, UV-stable architectural profiles without yellowing during high-shear extrusion.
- **Compatible Equipment:** Optimized for KraussMaffei, Battenfeld-Cincinnati, Reifenhauser, and Greiner profile extrusion lines.

RECOMMENDED EXTRUSION TEMPERATURE PROFILE (CONICAL TWIN-SCREW)

- **Barrel Zone 1:** 165 – 175 C | **Zone 2:** 175 – 185 C | **Zone 3:** 180 – 188 C | **Adapter & Die Head:** 185 – 195 C | **Target Melt Temp:** 190 – 198 C

REFERENCE uPVC PROFILE FORMULATION (PER 100 PHR SG-5)

- **Ca-Zn Stabilizer:** 3.5–4.2 phr | **ACR Impact Modifier:** 5.5–6.5 phr | **Processing Aid:** 1.5 phr | **Treated CaCO3:** 8–15 phr | **Rutile TiO2:** 4.0 phr

2. Sinopec S-1000 — Suspension PVC Resin Technical Dossier

MANUFACTURER: SINOPEC QILU PETROCHEMICAL | STANDARD: GB/T 5761-2018 | K-VALUE: 66.5

No.	Test Parameter	Unit	Standard (S-1000)	COA Batch Result	Verdict
1	**K-Value**	-	65 - 67	**66.5**	**PASS**
2	**Viscosity Number**	mL/g	107 - 118	**112**	**PASS**
3	**Apparent Bulk Density**	g/mL	>= 0.53	**0.54**	**PASS**
4	**Volatile Matter (inc. water)**	%	<= 0.40	**0.20**	**PASS**
5	**Sieve Residue (0.25 mm)**	%	<= 2.0	**0.2**	**PASS**
6	**Sieve Residue (0.063 mm)**	%	<= 6.0	**3.0**	**PASS**
7	**Fish Eyes Count**	pcs/400cm 2	<= 30	**10**	**PASS**
8	**Whiteness (160 C, 10 min)**	%	>= 75	**83**	**PASS**
9	**Residual VCM Monomer**	ppm	<= 5.0	**< 1.0**	**PASS**
10	**Impurity Particle Count**	pcs	<= 16	**6**	**PASS**
11	**Water Extract Conductivity**	uS/cm	<= 100	**60**	**PASS**
12	**Melting / Decomposition**	deg C	~160 / >200	**Conforms**	**PASS**



TECHNICAL ADVANTAGES OF SINOPEC S-1000

- **Ultra-Low Fish Eye Count (10 pcs/400cm2):** Mirror-smooth surface finish for high-gloss window profiles, pressure pipes, and rigid sheets.
- **Exceptional Electrical Insulation:** Low water extract conductivity (60 uS/cm) ideal for electrical conduits and fittings.
- **Superior Purity & Whiteness (83%):** Minimal impurity count (6 pcs) guarantees zero black spots on continuous extrusion runs.
- **GHS SDS & EU REACH Compliant:** Non-hazardous cargo; Residual VCM < 1.0 ppm; 12-month shelf life.

HIGH-SPEED DRY-BLEND MIXING PROTOCOL (SINOPEC S-1000)

• **Hot Mixer Discharge:** 118 – 125 C | **Cold Mixer Discharge:** < 42 C | **Dry-Blend Apparent Density:** >= 0.56 g/mL | **Vacuum Calibration:** -0.04 to -0.08 MPa

APPLICABLE EUROPEAN END-PRODUCT STANDARDS

• **EN 12608:** uPVC Window & Door Profiles | **EN ISO 1452:** Pressure Water Pipes | **EN 1401:** Underground Drainage | **IEC 61386:** Electrical Conduits

Packaging, European Logistics & Corporate Contact

DIRECT CONTAINER SHIPPING & BONDED WAREHOUSE DISTRIBUTION ACROSS EUROPE

Logistics & Supply Parameter	Operational Specification
Standard Bag Packaging	25 kg net weight kraft composite bags with inner PE moisture barrier, shrink-wrapped on fumigated wooden pallets.
Industrial Bulk Packaging	1,000 kg / 1,200 kg PP woven Jumbo Bags (FIBC) with top/bottom spouts.
Container Loading Capacity	• **20ft FCL:** 17.0 - 20.0 MT • **40ft HC FCL:** 25.0 - 26.5 MT (Optimized payload)
CIF Maritime Ports	• **CIF Gdansk Port, Poland** • **CIF Constanta Port, Romania** • **CIF Varna / Burgas Ports, Bulgaria**
FCA Warehouse Delivery	**FCA Bulgaria** (Bonded warehouse dispatch in Sofia / Plovdiv / Burgas for immediate TIR truck loading).
Supply Capacity	Trial batches from **20 MT** up to regular contractual deliveries of **500 - 1,500+ MT/month**.



ZAGROS VITOSHA BULGARIA EOOD — CORPORATE & COMMERCIAL DESK

Registered European Union Petrochemical & Polymer Distribution Enterprise | Republic of Bulgaria (EU)

EXECUTIVE MANAGEMENT

- **Farhad Kohkan**
  Managing Director / CEO
- **Amirhossein Tahani**
  Procurement Director

EU CORPORATE CREDENTIALS

- **Company:** Zagros Vitosha Bulgaria EOOD
- **Jurisdiction:** Republic of Bulgaria (EU)
- **UIC / EIK Code: 208619412**
- **EU VAT Number: BG208619412**

DIRECT COMMERCIAL CONTACT

- **Tel / WhatsApp 1: +359 88 970 0004**
- **WhatsApp / Direct 2: +359 87 794 4353**
- **Official Email: zvbulgaria@gmail.com**
- **Corporate Website: https://zvbt.eu**

SCAN FOR WEBSITE
https://zvbt.eu

DIRECT WHATSAPP
+359 88 970 0004