



QUALITY CONTROL LABORATORY CORDITE FACTORY, ARUVANKADU TEST REPORT

No:21/TR/QC(LAB)/GL/ACRYLIC/05/25-26

Date:05/09/2025

NOMENCLATURE : ACRYLIC RAYON CLOTH GR- B
 CONDITION OF THE SAMPLE : GOOD
 REFERENCE NUMBER : QC S&P (MI) 25MI370
 REFERENCE DATE : 24/08/2025
 SPECIFICATION : IND/ME/973 (a) : 2016
 LAB ITEM NO : GL-1208/25-26
 LAB ITEM NO DATE : 24/08/2025
 DATE OF PERFORMANCE OF THE TEST FROM : 24/08/2025
 DATE OF PERFORMANCE OF THE TEST TO : 05/09/2025

Sl. No	TEST CLAUSE	RESULTS	SPECIFICATION LIMIT	TEST METHOD
1	Description	PASSES	The material shall be woven of acrylic viscose rayon yarn spun from a blend of fibres containing 85 % minimum polyacrylonitrile and viscose fibres.	-
2	Colour	WHITE	White , off White or as per S.O	Visual examination
3	Width	1.17	As per S.O	-
4	Visual examination (Permissible deffects) , Major	NO DEFECTS PASSES	2 Max.	APPENDIX A
5	Visual examination (Permissible deffects) , Combined (Major + Minor but not containing more than 2 major deffects)	NO DEFECTS PASSES	7 Max.	APPENDIX A
6	Ether Soluble matter % by mass	3	10 Max.	APPENDIX B
7	Starch % by mass	4	Min 2 ; Max 6	APPENDIX C
8	Acrylic fibre content % by mass	55	Min 50 ; Max 60	APPENDIX D
9	pH of water extract	8.5	Min 5 ; Max 9	APPENDIX E
10	Acidity as CH ₃ COOH % (If pH of water extract is 5.0 to 7.0)	NIL	0.1 Max.	APPENDIX F
11	Alkalinity as Na ₂ CO ₃ % (If pH of water extract is 7.0 to 9.0)	0.1	0.1 Max.	APPENDIX F
12	Ash % by mass	0.2	2.0 Max.	APPENDIX G
13	Halogen content	NIL	Nil	APPENDIX H
14	Moisture / Regain % by mass	5	10 Max.	JSG 0114 METHOD 4
15	Mass in g/m ²	301	Min 280 ; Max 310	JSG 0114 METHOD 1
16	Threads/cm, Warp	20	18 Min.	-
17	Threads/cm, Weft	20	18 Min.	-
18	Breaking Strength N, Warp	1170	960 Min.	APPENDIX J
19	Breaking Strength N, Weft	970	960 Min.	APPENDIX J
20	Elongation at break % , Warp	24	25 Max.	-
21	Elongation at break % , Weft	15	25 Max.	-

Note:

- Results reported related only to the item/sample tested
- Report shall not be reproduced except in full without prior written permission of Group Officer
- Specification are mentioned wherever applicable
- Tests are done in respect of clauses required by user/consignee.
- Column whichever is not applicable may be treated as canceled.
- Sample is not drawn by Quality Control Laboratory.

Tested By : N.VINOTH KUMAR, R.ESWARI

Report Generated by : VINOTH KUMAR N

Sampled By : DEEPA KRISHNA

Remarks : NIL

DO/QC(S&P)

 Digitally Approved By
MURUKESAN.P
DO/QC(LAB)

 Digitally Verified By
GOPAL B.
OIC/QC(LAB)