AEX's Heat Shrink Rain Sheds are used for extending the creepage path for the Medium Voltage Cable Termination, thereby saving the length of the Cable and compacting the Switchgear cabinet size required for this purpose. The Rain sheds are suitable for the termination of the complete range of XLPE and PILC types of Cables.

They also restrict the continuity of water during the monsoon causing electrical short circuits.

The Rain Sheds are made from Non-tracking Cross-linked halogen-free Polyolefin material that offers abiding service reliability.

The inside-coated butyl rubber-based red mastic sealant seals each Rain Shed to the Cable insulation. This Mastic sealant is Non-tracking, waterproof and electrical insulating.

KEY FEATURES AND BENEFITS:

- Resistant to tracking and erosion.
- UV and weather-resistant.
- Resistant to common fluids and solvents.
- Excellent electrical performance.
- Halogen-free.
- Suitable for Indoor as well as Outdoor application.
- Quick and easy to install.
- Unlimited Shelf life.

Technical Properties

Test Description	Typical Value	Test Method
Tensile Strength	8 MPa (Min.)	ASTM D638
Elongation	300% (Min.)	ASTM D638
Accelerated ageing	150°C for 168 hrs.	ASTM D2671
Tensile Strength	7 MPa (Min.)	ASTM D638
Elongation	250% (Min.)	ASTM D638
Hardness	35 (Shore D)	ASTM D2240
Water Absorption	1% (Max.)	ASTM D570
Low Temp. Flexibility (-40°C for 4 hrs)	No Cracking	ASTM D2671
Shrink Temperature	125°C	IEC 216
Continuous Operating Temp.	-40 to +115°C	IEC 216
Di-electric Strength	12 kV/mm. (min.)	ASTM D149
Volume Resistivity	1 x 10^{14} Ohm.cm (min.)	ASTM D257



Selection Chart

Product Code	D (min.)	d (min.)	H (min.)	T (±10%)	S (min.)	A (min.)
ACES 1	41.0	13	33	2.5	94	20
ACES 2	55.0	18	40	3.5	124	20
ACES 3	75.0	28	40	3.5	141	20
ACES 6S	120.0	50	50	4.5	200	20
ACES 6	150.0	50	45	4.5	200	20

D: Supplied Dia., d: Free Recovered Dia.,
T: Total Thickness after free recovery.
All dimensions are in mm