



Heat Shrink Wraparound Sleeve



Wraparound Sleeves is a Cross-linked polyolefin Tubes which is folded around the Cables, zipped up with a Stainless Steel Channel and then heat shrunk.

Hot Melt Sealant provides complete environmental sealing.


High resistance to UV rays, chemicals, corrosion, fungus, etc.

KEY FEATURES AND BENEFITS:

- Hot melt adhesive lining / Mastic for tight insulation and protection against moist penetration under the heat shrink layer.
- Complete environmental protection and insulation.
- Resistance to weathering, UV rays, Chemicals and Solvents.
- Excellent resistance to vibration, impact, abrasion, corrosive fluids, dis-bonding, organic & bio-deterioration.
- Protect against weather conditions and aggressive underground factors.
- Custom dimensions, thickness, length & colours available on request.
- Can be supplied with or without adhesive
- The product code shall remain the same also for the customized length / with or without adhesive
- Shrink Temperature 125°C.
- Conforms to IEC 60684-3-247 standard.
- Meets IP 68 (Ingress Protection)
- REACH and RoHS compliant

APPLICATION:

- Cable Repair
- Protection of Cable Joint



Product Dimensions

Product Code	D Min.	d Max.	T ±10%
AWS 55 / 8	55	8	2.7
AWS 76 / 18	76	18	2.7
AWS 105 / 28	105	28	2.7
AWS 140 / 35	140	35	2.7
AWS 190 / 46	190	46	2.7
AWS 240 / 50	240	50	2.7

All dimensions are in mm

D - Dia. Supplied; d - Dia. Free Recovered;
T - Thickness after Free Recovery;

Technical Properties

Test Description	Typical Value	Test Method
Tensile Strength	16 N/mm ² (min.)	ASTM D638
Elongation	350% (min.)	ASTM D638
Water Absorption	0.50% (max.)	ASTM D570
Density	0.8 - 1.2 gm/cm ³	ASTM D792
Longitudinal Change	+/- 10 Shore D	ASTM D2671
Hardness	45 +/- 10 Shore D	ASTM D2240
Thermal Ageing		
Tensile Strength	14 N/mm ² (min.)	ASTM D638
Elongation	300% (min.)	ASTM D638
Di-electric Strength	12 kV/mm. (min.)	ASTM D149
Volume Resistivity	1x10 ¹² Ohm.cm (min.)	ASTM D257
UV Resistance	No Cracking	ASTM G154