



AEX's rigid Red Barrier Board Sheet (ARBB) is a non-structural, interphase barrier for switchgear applications. The ARBB board is made from a high-quality Polyolefin material that has excellent track resistance, especially following flash-overs. It can be easily fabricated into a shape.

The use of ARBB barriers allows switchgear cabinets to be protected against interphase flash-overs that can be caused by contaminants, moisture and animals. It has excellent tracking resistant properties.

As the barrier board is UV resistant, it is also suitable for outdoor applications. These boards are damage resistant from solvents, mechanical impact, and general wear and tear usage.

Machining properties allow boards to be cut and drilled for mounting without the need of any special safety equipment. The innovative cross-linking polymer withstands power-arcs without compromising its physical shape.

The high temperature resistant material can be wiped clean after power-arc events resulting in no visible effects of surface damages.

KEY FEATURES AND BENEFITS:

- High Dielectric strength
- Exceptional insulation and long-term reliability even at high continuous operating temperatures
- Excellent mechanical strength and impact resistance
- Prevent Busbar from chemical corrosion effected by strong acid, alkali, etc.
- Flame retardant and Halogen-free
- UV and weather-resistant
- Tracking resistance in compliance with IEC 112
- Resistant to bacteria and fungi
- Suitable for Indoor as well as Outdoor application
- Quick and easy to install. No special tools or skills needed.
- Unlimited Shelf life
- Conforms to specifications: IEC 60684-3 / ENATS 09-13, RoHS 2011/65/EU & 2015/863/EU Compliant

Technical Properties

Test Description	Typical Value	Test Method
Tensile Strength	10 N/mm ² (min.)	ASTM D638
Elongation	350% (min.)	ASTM D638
Water Absorption	0.50% (max.)	ASTM D570
Density	1.2 gm/cm ³	ASTM D792
Hardness	45 +/- 10 Shore D	ASTM D2240
UV Resistance	No Cracking	ASTM G154
Thermal Ageing		
Tensile Strength	8 N/mm ² (min.)	ASTM D638
Elongation	300% (min.)	ASTM D638
Di-electric Strength	12 kV/mm. (min.)	ASTM D149
Volume Resistivity	1x10 ¹² Ohm.cm (min.)	ASTM D257