UNIFLOOR SF

PROTECTIVE

TECHNICAL DATA

Polyamine cured highly resistance solvent free dust proofing epoxy topcoat with excellent adhesion properties on all types of Steel , wood, concrete and cement floors and walls after preparing by suitable primer

DESCRIPTION

- **UNIFLOOR SF** is a two-component highly performance, polyamine cured solvent free epoxy topcoat with excellent adhesion properties .used for flooring application and for wide range of other applications.
- **UNIFLOOR SF** is excellent adhesive and bonding topcoat used to avoid the problem of scratching concrete and other applied sufaces
- Work as porosity sealing compound, adhesion improver and bonding agent on concrete, mortar and steel.
- **UNIFLOOR SF** has very good durability, covering and reinforcing properties for concrete.

COLOURS AND GLOSS

- **UNIFLOOR SF** is two-component epoxy topcoat (A) & (B) when mixed together produces a fluid pigmented liquid.
- **UNIFLOOR SF** is available in different others high opaque color (grey, yellow, white etc…)

PROPERTTIES & BASIC DATA AT 23°C

Application Methods	Airless, brush and roller
Pot life	2 hours
Dry to touch	4 hours
Dry to handle	24 hours
Dry to recoat	20 hours min
Fully cured	7 days max
Color	pigmented
Solids by volume	100 %
Specific gravity	1.3± 0.04
Viscosity	200 sec (Flow cup no 4/ 25 C DIN 532)
Flash Point	42°C

WHERE TO USE

- **UNIFLOOR SF** can be used as a topcoat for indoors sports surface and play yards
- **UNIFLOOR SF** can be used as a topcoat for playing courts, walkways and tennis courts
- Used for Jogging tracks and multi-purpose athletic courts.
- Used to seal porosity & as concrete reinforcing agent for concrete, natural stone, cementations renderings, mortar and asbestos cement.
- Used interior surfaces, above or below grade
- **UNIFLOOR SF** also can be used as a bonding agent for the following overlays:
  - Epoxy mortar screeds.
  - Epoxy self-leveling floor toppings

ADVANTAGES

- Excellent adhesion to damped concrete with a very good adhesion to all types of substrates.
- Very good cohesion forces and excellent bonding properties on steel, mortar and iron.
- Easy to apply and good penetration.
- Can be applied at low temperature
- Can be applied on vertical and horizontal surfaces

- Excellent mechanical properties and very high adhesive strengths (tensile strength, shear strength, and flexural strength)
- Has no solvent, which makes it more safe system.
- High compressive strength.

SYSTEMSPECIFICATION

FLOORING SYSTEM

INSTRUCTIONS FOR USE

- **UNIFLOOR SF** is pre-patched component (no excess thinner to be added)
- Excess thinner will reduce bonding and sealing properties.

▪▪1 RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- **UNIFLOOR SF** can be applied at various weather conditions but ideal applications carried out in a hot weather, where the Minimum application temperature is 5ºC, so do not apply when temperature is 5ºC or going to fall below 5ºC within 24 hours.
- The substrate to be properly prepared and clean.

▪▪2 SURFACE PREPARATION

- As with all coating systems, surface preparation is of prime importance.
- All substrate surfaces must be properly prepared, clean, free from oil, grease, or any loosely adhering material.
- Vacuum cleaning is necessary
- Remove efflorescence, mineral salts, fungus and form treatment by an appropriate method.
- If the concrete surface is defective or has excess laitance, it must be cut to a sound base by an appropriate method.
- All surfaces must be as true and flat as possible, repair surface defects where necessary.
- Any steel in the application area should be exposed around its full circumference and thoroughly cleaned to remove all loose scale and corrosion deposits either by mechanical properties like sand blaster or mechanical abrasive like chipping or whip sand blasting or by using a suitable rust remover
- UNIGUARD RO PRIMER or UNIZINC primer should be used as corrosion inhibitor to prevent interior corrosion to insure ideal bonding with the **UNIFLOOR SF**

Smooth or new substrate should be mechanically roughened to provide

- adhesion & bonding properties.

▪▪3 MIXING

- Add the hardener into the resin container and then thoroughly mix using a low electric drill or manually until obtaining a uniform color using a low speed mixer or manually.
- After mixing, allow material to stand for 2 Min to allow entrained air to escape.
- No extra thinner should be added
- When mixing the temperature of the base and hardener should be at least above 5ºC

▪▪4 APPLICATION

- **UNIFLOOR SF** is normally applied with brush or roller.
- Air spray application is recommended for large areas and can be applied for any numbers of coats.
- Spread a layer of **UNIFLOOR SF** on the substrate surface and level it out by brush or roller.
- Leave the first coat to start dry (2-3 hours).
- If the substrate surface still require another layer.
- Apply the second coat of **UNIFLOOR SF** as soon as possible before tacking free to ensure proper adhesion between layers
- If the substrate surface is good primed enough with one layer, apply the first coat of flooring system as soon as possible, to ensure proper adhesion between layers.
- High film thickness applied of **UNIFLOOR SF** is not recommended.
- High film thickness applied of **UNIFLOOR SF** will slow down the curing and will cause in bad adhesion and may be cracking.

PRECAUTIONS

- Minimum age of concrete: 3 - 6 weeks, depending on climate.

- Maximum ambient and substrate temperature: +30°C.
- Minimum ambient and substrate temperature: +10°C.
- Maximum relative humidity: 85%
- Moisture content of substrate: <4%
- No thinner to be added.
- Excess thinner will reduce durability, bonding properties, adhesion.

PACKAGING:

UNISEALER SF is available in 5 & 20 kg tow pack (A+B)

THEORETICAL COVERAGE

- Depending on type of application, porosity of surface and consistency required, two coats is the minimum recommended application.
- Approx. 0.25 kg/m² for first coat consumption.
- 0.18 - 0.2 kg/ m² (175 microns D.F.T.).

STORAGE

UNISEALER SF has shelf life of 1 year when store in its original unopened packs in proper conditions under cover, out of direct sunlight and protected from extremes of temperature and humid environmental and free from heat and frost.

CLEANING

UNISEALER SF should be removed from tools & equipment immediately after application by cleaning with UNIEAST CLEENING THINNER
Hardened material can only be removed mechanically

HEALTH AND SAFETY

- All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations
- Prior to use, obtain, consult and read well the Material Safety Data Sheet for this product and follow all precautionary notices.
- Take precautions to avoid inhalation of spray mist, skin, mucous membrane and eye contact by the use of safety equipment (gloves, goggles, face masks, barrier creams etc.) and other personal protection.
- If skin comes in contact, it should be thoroughly flushed and washed with fresh water and proprietary cleanser and soap
- Eyes should be cautiously washed with fresh water or proprietary wash and medical attention obtained
- Don't use solvents for skin cleaning
- Equipment and tools to be cleaned immediately after use with clean water
- Don't dispose of water or soil but according to local regulations
- **UNISEALER SF** is nontoxic according to health and safety codes.
- **UNISEALER SF** is non-hazardous.
- Keep labeled until decontaminated