

SECTION 09 90 00

PAINTS AND COATINGS

05/11

PART 1 GENERAL

1.1 REFERENCES

The publications listed below form a part of this specification to the extent referenced. The publications are referred to within the text by the basic designation only.

AMERICAN CONFERENCE OF GOVERNMENTAL INDUSTRIAL HYGIENISTS (ACGIH)

ACGIH 0100 (2001; Supplements 2002-2008)
Documentation of the Threshold Limit
Values and Biological Exposure Indices

ASME INTERNATIONAL (ASME)

ASME A13.1 (2007) Scheme for the Identification of
Piping Systems

ASTM INTERNATIONAL (ASTM)

ASTM C920 (2011) Standard Specification for
Elastomeric Joint Sealants

ASTM D235 (2002; R 2007) Mineral Spirits (Petroleum
Spirits) (Hydrocarbon Dry Cleaning Solvent)

ASTM D2824 (2006) Aluminum-Pigmented Asphalt Roof
Coatings, Non-Fibered, Asbestos Fibered,
and Fibered without Asbestos

ASTM D4214 (2007) Standard Test Method for Evaluating
the Degree of Chalking of Exterior Paint
Films

ASTM D4263 (1983; R 2005) Indicating Moisture in
Concrete by the Plastic Sheet Method

ASTM D4444 (2008) Use and Calibration of Hand-Held
Moisture Meters

ASTM D523 (2008) Standard Test Method for Specular
Gloss

ASTM D6386 (2010) Standard Practice for Preparation
of Zinc (Hot-Dip Galvanized) Coated Iron
and Steel Product and Hardware Surfaces
for Painting

ASTM E2129	(2010) Standard Practice for Data Collection for Sustainability Assessment of Building Products
ASTM F 1869	(2011) Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride
GREENGUARD ENVIRONMENTAL INSTITUTE (GEI)	
GEI	Greenguard Standards for Low Emitting Products
MASTER PAINTERS INSTITUTE (MPI)	
MPI 1	(Oct 2009) Aluminum Paint
MPI 10	(Oct 2009) Exterior Latex, Flat, MPI Gloss Level 1
MPI 101	(Oct 2009) Epoxy Anti-Corrosive Metal Primer
MPI 107	(Oct 2009) Rust Inhibitive Primer (Water-Based)
MPI 108	(Oct 2009) High Build Epoxy Coating, Low Gloss
MPI 11	(Oct 2009) Exterior Latex, Semi-Gloss, MPI Gloss Level 5
MPI 113	(Oct 2009) Exterior Pigmented Elastomeric Coating (Water Based)
MPI 116	(Oct 2009) Epoxy Block Filler
MPI 119	(Oct 2009) Exterior Latex, Gloss
MPI 13	(Oct 2009) Exterior Solvent-Based Semi-Transparent Stain
MPI 134	(Oct 2009) Galvanized Primer (Waterbased)
MPI 138	(Oct 2009) Interior High Performance Latex, MPI Gloss Level 2
MPI 139	(Oct 2009) Interior High Performance Latex, MPI Gloss Level 3
MPI 140	(Oct 2009) Interior High Performance Latex, MPI Gloss Level 4
MPI 141	(Oct 2009) Interior High Performance Latex MPI Gloss Level 5
MPI 144	(Oct 2009) Institutional Low Odor / VOC

	Interior Latex, MPI Gloss Level 2
MPI 145	(Oct 2009) Institutional Low Odor / VOC Interior Latex, MPI Gloss Level 3
MPI 146	(Oct 2009) Institutional Low Odor/VOC Interior Latex, MPI Gloss Level 4
MPI 147	(Oct 2009) Institutional Low Odor / VOC Interior Latex, Semi-Gloss, MPI Gloss Level 5
MPI 151	(Oct 2009) Interior W.B. Light Industrial Coating, MPI Gloss Level 3
MPI 153	(Oct 2009) Interior W.B. Light Industrial Coating, Semi-Gloss, MPI Gloss Level 5
MPI 154	(Oct 2009) Interior W.B. Light Industrial Coating, Gloss, MPI Gloss Level 6
MPI 16	(Oct 2009) Exterior Latex-Based Solid Hide Stain
MPI 161	(Oct 2009) Exterior W.B. Light Industrial Coating, MPI Gloss Level 3
MPI 163	(Oct 2009) Exterior W.B. Light Industrial Coating, Semi-Gloss, MPI Gloss Level 5
MPI 164	(Oct 2009) Exterior W.B. Light Industrial Coating, Gloss, MPI Gloss Level 6
MPI 19	(Oct 2009) Inorganic Zinc Rich Primer
MPI 2	(Oct 2009) Aluminum Heat Resistant Enamel (up to 427 C and 800 F)
MPI 21	(Oct 2009) Heat Resistant Enamel, Gloss (up to 205 degrees C and 400 degrees F), MPI Gloss Level 6
MPI 22	(Oct 2009) Aluminum Paint, High Heat (up to 590 degrees C and 1100 degrees F.
MPI 23	(Oct 2009) Surface Tolerant Metal Primer
MPI 26	(Oct 2009) Cementitious Galvanized Metal Primer
MPI 27	(Oct 2009) Exterior / Interior Alkyd Floor Enamel, Gloss
MPI 31	(Oct 2009) Polyurethane, Moisture Cured, Clear Gloss
MPI 39	(Oct 2009) Interior Latex-Based Wood Primer

MPI 4	(Oct 2009) Interior/Exterior Latex Block Filler
MPI 42	(Oct 2009) Latex Stucco and Masonry Textured Coating
MPI 44	(Oct 2009) Interior Latex, MPI Gloss Level 2
MPI 45	(Oct 2009) Interior Alkyd Primer Sealer
MPI 46	(Oct 2009) Interior Enamel Undercoat
MPI 47	(Oct 2009) Interior Alkyd, Semi-Gloss, MPI Gloss Level 5
MPI 48	(Oct 2009) Interior Alkyd, Gloss, MPI Gloss Level 6
MPI 49	(Oct 2009) Interior Alkyd, Flat, MPI Gloss Level 1
MPI 5	(Oct 2009) Exterior Alkyd Wood Primer
MPI 50	(Oct 2009) Interior Latex Primer Sealer
MPI 51	(Oct 2009) Interior Alkyd, Eggshell, MPI Gloss Level 2
MPI 52	(Oct 2009) Interior Latex, MPI Gloss Level 3
MPI 54	(Oct 2009) Interior Latex, Semi-Gloss, MPI Gloss Level 5
MPI 56	(Oct 2009) Interior Oil Modified Urethane Clear Gloss
MPI 57	(Oct 2009) Interior Oil Modified Urethane Clear Satin
MPI 59	(Oct 2009) Interior/Exterior Floor Enamel, Low Gloss
MPI 6	(Oct 2009) Exterior Latex Wood Primer
MPI 60	(Oct 2009) Interior/Exterior Latex Floor Paint, Low Gloss
MPI 68	(Oct 2009) Interior/Exterior Latex Floor Enamel, Gloss
MPI 7	(Oct 2009) Exterior Oil Wood Primer
MPI 71	(Oct 2009) Polyurethane, Moisture Cured, Clear, Flat

MPI 72	(Oct 2009) Polyurethane, Two Component, Pigmented, Gloss
MPI 77	(Oct 2009) Epoxy Gloss
MPI 79	(Oct 2009) Alkyd Anti-Corrosive Metal Primer
MPI 8	(Oct 2009) Exterior Alkyd, Flat, MPI Gloss Level I
MPI 9	(Oct 2009) Exterior Alkyd, Gloss, MPI Gloss Level 6
MPI 90	(Oct 2009) Interior Wood Stain, Semi-Transparent
MPI 94	(Oct 2009) Exterior Alkyd, Semi-Gloss, MPI Gloss Level 5
MPI 95	(Oct 2009) Quick Drying Primer for Aluminum

SCIENTIFIC CERTIFICATION SYSTEMS (SCS)

SCS	Scientific Certification Systems (SCS) Indoor Advantage
SCS SP-01	(2000) Environmentally Preferable Product Specification for Architectural and Anti-Corrosive Paints

THE SOCIETY FOR PROTECTIVE COATINGS (SSPC)

SSPC Guide 6	(2004) Guide for Containing Surface Preparation Debris Generated During Paint Removal Operations
SSPC Guide 7	(2004; E 2004) Guide to the Disposal of Lead-Contaminated Surface Preparation Debris
SSPC PA 1	(2000; E 2004) Shop, Field, and Maintenance Painting of Steel
SSPC PA Guide 3	(1982; E 1995) A Guide to Safety in Paint Application
SSPC Paint 18	(1982; E 2004) Chlorinated Rubber Intermediate Coat Paint
SSPC QP 1	(1998; E 2004) Standard Procedure for Evaluating Painting Contractors (Field Application to Complex Industrial Structures)
SSPC SP 1	(1982; E 2004) Solvent Cleaning

SSPC SP 10/NACE No. 2	(2007) Near-White Blast Cleaning
SSPC SP 12/NACE No.5	(2002) Surface Preparation and Cleaning of Metals by Waterjetting Prior to Recoating
SSPC SP 2	(1982; E 2004) Hand Tool Cleaning
SSPC SP 3	(1982; E 2004) Power Tool Cleaning
SSPC SP 6/NACE No.3	(2007) Commercial Blast Cleaning
SSPC SP 7/NACE No.4	(2007) Brush-Off Blast Cleaning
SSPC VIS 1	(2002; e 2004) Guide and Reference Photographs for Steel Surfaces Prepared by Dry Abrasive Blast Cleaning
SSPC VIS 3	(2004) Guide and Reference Photographs for Steel Surfaces Prepared by Hand and Power Tool Cleaning
SSPC VIS 4/NACE VIS 7	(1998; E 2000; E 2004) Guide and Reference Photographs for Steel Surfaces Prepared by Waterjetting

U.S. ARMY CORPS OF ENGINEERS (USACE)

EM 385-1-1	(2008; Errata 1-2010; Changes 1-3 2010; Changes 4-6 2011) Safety and Health Requirements Manual
------------	---

U.S. DEPARTMENT OF DEFENSE (DOD)

MIL-PRF-680	(2010; Rev C) Degreasing Solvent
MIL-STD-101	(1970; Rev B) Color Code for Pipelines & for Compressed Gas Cylinders

U.S. ENVIRONMENTAL PROTECTION AGENCY (EPA)

EPA Method 24	(2000) Determination of Volatile Matter Content, Water Content, Density, Volume Solids, and Weight Solids of Surface Coatings
---------------	---

U.S. FEDERAL AVIATION ADMINISTRATION (FAA)

FAA AC 70/7460-1	(2007; Rev K) Obstruction Marking and Lighting
------------------	--

U.S. GENERAL SERVICES ADMINISTRATION (GSA)

FED-STD-313	(Rev D; Am 1) Material Safety Data, Transportation Data and Disposal Data for Hazardous Materials Furnished to Government Activities
-------------	--

U.S. GREEN BUILDING COUNCIL (USGBC)

LEED

(2002; R 2005) Leadership in Energy and
Environmental Design(tm) Green Building
Rating System for New Construction
(LEED-NC)

U.S. NATIONAL ARCHIVES AND RECORDS ADMINISTRATION (NARA)

29 CFR 1910.1000 Air Contaminants

29 CFR 1910.1001 Asbestos

29 CFR 1910.1025 Lead

29 CFR 1926.62 Lead

1.2 SUBMITTALS

The following shall be submitted in accordance with Section 01 33 00
SUBMITTAL PROCEDURES:

The current MPI, "Approved Product List" which lists paint by brand, label, product name and product code as of the date of contract award, will be used to determine compliance with the submittal requirements of this specification. The Contractor may choose to use a subsequent MPI "Approved Product List", however, only one list may be used for the entire contract and each coating system is to be from a single manufacturer. All coats on a particular substrate must be from a single manufacturer. No variation from the MPI Approved Products List is acceptable.

Samples of specified materials may be taken and tested for compliance with specification requirements.

SD-02 Shop Drawings

Piping identification

Submit color stencil codes

SD-03 Product Data

Coating

Manufacturer's Technical Data Sheets

Indicate VOC content.

SD-04 Samples

Color

Submit manufacturer's samples of paint colors. Cross reference color samples to color scheme as indicated.

SD-07 Certificates

Applicator's qualifications

Qualification Testing laboratory for coatings

SD-08 Manufacturer's Instructions

Application instructions

Mixing

Detailed mixing instructions, minimum and maximum application temperature and humidity, potlife, and curing and drying times between coats.

Manufacturer's Material Safety Data Sheets

Submit manufacturer's Material Safety Data Sheets for coatings, solvents, and other potentially hazardous materials, as defined in **FED-STD-313**.

SD-10 Operation and Maintenance Data

Coatings:

Preprinted cleaning and maintenance instructions for all coating systems shall be provided.

SD-11 Closeout Submittals

1.3 APPLICATOR'S QUALIFICATIONS

1.3.1 Contractor Qualification

Submit the name, address, telephone number, FAX number, and e-mail address of the contractor that will be performing all surface preparation and coating application. Submit evidence that key personnel have successfully performed surface preparation and application of coatings on on a minimum of five similar projects within the past two years. List information by individual and include the following:

- a. Name of individual and proposed position for this work.
- b. Information about each previous assignment including:

Position or responsibility

Employer (if other than the Contractor)

Name of facility owner

Mailing address, telephone number, and telex number (if non-US) of facility owner

Name of individual in facility owner's organization who can be

contacted as a reference

Location, size and description of structure

Dates work was carried out

Description of work carried out on structure

1.4 QUALITY ASSURANCE

1.4.1 Field Samples and Tests

The Contracting Officer may choose up to two coatings that have been delivered to the site to be tested at no cost to the Government. Take samples of each chosen product as specified in the paragraph "Sampling Procedures." Test each chosen product as specified in the paragraph "Testing Procedure." Products which do not conform, shall be removed from the job site and replaced with new products that conform to the referenced specification. Testing of replacement products that failed initial testing shall be at no cost to the Government.

1.4.1.1 Sampling Procedure

The Contracting Officer will select paint at random from the products that have been delivered to the job site for sample testing. The Contractor shall provide [one quart](#) samples of the selected paint materials. The samples shall be taken in the presence of the Contracting Officer, and labeled, identifying each sample. Provide labels in accordance with the paragraph "Packaging, Labeling, and Storage" of this specification.

1.4.1.2 Testing Procedure

Provide Batch Quality Conformance Testing for specified products, as defined by and performed by MPI. As an alternative to Batch Quality Conformance Testing, the Contractor may provide [Qualification Testing](#) for specified products above to the appropriate MPI product specification, using the third-party laboratory approved under the paragraph "Qualification Testing" laboratory for coatings. The qualification testing lab report shall include the backup data and summary of the test results. The summary shall list all of the reference specification requirements and the result of each test. The summary shall clearly indicate whether the tested paint meets each test requirement. Note that Qualification Testing may take 4 to 6 weeks to perform, due to the extent of testing required.

Submit name, address, telephone number, FAX number, and e-mail address of the independent third party laboratory selected to perform testing of coating samples for compliance with specification requirements. Submit documentation that laboratory is regularly engaged in testing of paint samples for conformance with specifications, and that employees performing testing are qualified. If the Contractor chooses MPI to perform the Batch Quality Conformance testing, the above submittal information is not required, only a letter is required from the Contractor stating that MPI will perform the testing.

1.5 REGULATORY REQUIREMENTS

1.5.1 Environmental Protection

In addition to requirements specified elsewhere for environmental protection, provide coating materials that conform to the restrictions of the local Air Pollution Control District and regional jurisdiction. Notify Contracting Officer of any paint specified herein which fails to conform.

1.5.2 Lead Content

Do not use coatings having a lead content over 0.06 percent by weight of nonvolatile content.

1.5.3 Chromate Content

Do not use coatings containing zinc-chromate or strontium-chromate.

1.5.4 Asbestos Content

Materials shall not contain asbestos.

1.5.5 Mercury Content

Materials shall not contain mercury or mercury compounds.

1.5.6 Silica

Abrasive blast media shall not contain free crystalline silica.

1.5.7 Human Carcinogens

Materials shall not contain **ACGIH 0100** confirmed human carcinogens (A1) or suspected human carcinogens (A2).

1.6 PACKAGING, LABELING, AND STORAGE

Paints shall be in sealed containers that legibly show the contract specification number, designation name, formula or specification number, batch number, color, quantity, date of manufacture, manufacturer's formulation number, manufacturer's directions including any warnings and special precautions, and name and address of manufacturer. Pigmented paints shall be furnished in containers not larger than 5 gallons. Paints and thinners shall be stored in accordance with the manufacturer's written directions, and as a minimum, stored off the ground, under cover, with sufficient ventilation to prevent the buildup of flammable vapors, and at temperatures between 40 to 95 degrees F. Do not store paint, polyurethane, varnish, or wood stain products with materials that have a high capacity to adsorb VOC emissions. Do not store paint, polyurethane, varnish, or wood stain products in occupied spaces.

1.7 SAFETY AND HEALTH

Apply coating materials using safety methods and equipment in accordance with the following:

Work shall comply with applicable Federal, State, and local laws and regulations, and with the ACCIDENT PREVENTION PLAN, including the Activity Hazard Analysis as specified in GOVERNMENT SAFETY REQUIREMENTS and in Appendix A of **EM 385-1-1**. The Activity Hazard Analysis shall include

analyses of the potential impact of painting operations on painting personnel and on others involved in and adjacent to the work zone.

1.7.1 Safety Methods Used During Coating Application

Comply with the requirements of [SSPC PA Guide 3](#).

1.7.2 Toxic Materials

To protect personnel from overexposure to toxic materials, conform to the most stringent guidance of:

- a. The applicable [manufacturer's Material Safety Data Sheets](#) (MSDS) or local regulation.
- b. [29 CFR 1910.1000](#).
- c. [ACGIH 0100](#), threshold limit values.
- d. The appropriate OSHA standard in [29 CFR 1910.1025](#) and [29 CFR 1926.62](#) for surface preparation on painted surfaces containing lead. Additional guidance is given in [SSPC Guide 6](#) and [SSPC Guide 7](#). Refer to drawings for list of hazardous materials located on this project. Contractor to coordinate paint preparation activities with this specification section.

1.8 ENVIRONMENTAL CONDITIONS

Comply, at minimum, with manufacturer recommendations for space ventilation during and after installation. Isolate area of application from rest of building when applying high-emission paints or coatings.

1.8.1 Coatings

Do not apply coating when air or substrate conditions are:

- a. Less than [5 degrees F](#) above dew point;
- b. Below [50 degrees F](#) or over [95 degrees F](#), unless specifically pre-approved by the Contracting Officer and the product manufacturer. Under no circumstances shall application conditions exceed manufacturer recommendations.

1.8.2 Post-Application

Vacate space for as long as possible after application. Wait a minimum of 48 hours before occupying freshly painted rooms. Maintain one of the following ventilation conditions during the curing period, or for 72 hours after application:

- a. Supply 100 percent outside air 24 hours a day, unless humidity level is high enough to prohibit proper drying of paint. If high humidity is a problem, condition space as recommended by manufacturer.
- b. Supply airflow at a rate of 6 air changes per hour, when outside temperatures are between [55 degrees F](#) and [85 degrees F](#) and humidity is between 30 percent and 60 percent.

- c. Supply airflow at a rate of 1.5 air changes per hour, when outside air conditions are not within the range stipulated above.

1.10 SCHEDULING

Allow paint, polyurethane, varnish, and wood stain installations to cure prior to the installation of materials that adsorb VOCs, including gypsum board, carpets, ceiling panels, and similar materials.

1.11 COLOR SELECTION

Colors of finish coats shall be as indicated or specified. Where not indicated or specified, colors shall be selected by the Contracting Officer. Manufacturers' names and color identification are used for the purpose of color identification only. Named products are acceptable for use only if they conform to specified requirements. Products of other manufacturers are acceptable if the colors approximate colors indicated and the product conforms to specified requirements.

Tint each coat progressively darker to enable confirmation of the number of coats.

Color, texture, and pattern of wall coating systems shall be as directed by Contracting Officer. Colors stated in drawings and specifications are typically for reference only and final selection shall be by Contracting Officer.

1.12 LOCATION AND SURFACE TYPE TO BE PAINTED

1.12.1 Painting Included

Where a space or surface is indicated to be painted, include the following unless indicated otherwise.

- a. Surfaces behind portable objects and surface mounted articles readily detachable by removal of fasteners, such as screws and bolts.
- b. New factory finished surfaces that require identification or color coding and factory finished surfaces that are damaged during performance of the work.
- c. Existing coated surfaces that are damaged during performance of the work.

1.12.1.1 Exterior Painting

Includes new surfaces, existing coated surfaces, and existing uncoated surfaces, of the building and appurtenances. Also included are existing coated surfaces made bare by cleaning operations.

1.12.1.2 Interior Painting

Includes new surfaces, existing uncoated surfaces, and existing coated surfaces of the buildings and appurtenances as indicated and existing coated surfaces made bare by cleaning operations. Where a space or surface is indicated to be painted, include the following items, unless indicated otherwise.

- a. Exposed columns, girders, beams, joists, and painted metal deck; and
- b. Other contiguous surfaces.

1.12.2 Painting Excluded

Do not paint the following unless indicated otherwise.

- a. Surfaces concealed and made inaccessible by panelboards, fixed ductwork, machinery, and equipment fixed in place.
- b. Surfaces in concealed spaces. Concealed spaces are defined as enclosed spaces above suspended ceilings, furred spaces, attic spaces, crawl spaces, elevator shafts and chases.
- c. Steel to be embedded in concrete.
- d. Copper, stainless steel, aluminum, brass, and lead except existing coated surfaces.
- e. Hardware, fittings, and other factory finished items.
- f. The exposed underside of galvanized roof decking if it has not been previously painted.
- g. Pre-finished surfaces.

1.12.3 Mechanical and Electrical Painting

Includes field coating of interior and exterior new and existing surfaces.

- a. Where a space or surface is indicated to be painted, include the following items unless indicated otherwise.
 - (1) Exposed piping, conduit, and ductwork;
 - (2) Supports, hangers, air grilles, and registers;
 - (3) Miscellaneous metalwork and insulation coverings.
- b. Do not paint the following, unless indicated otherwise:
 - (1) New zinc-coated, aluminum, and copper surfaces under insulation
 - (2) New aluminum jacket on piping
 - (3) New interior ferrous piping under insulation.

1.12.3.1 Fire Extinguishing Sprinkler Systems

Clean, pretreat, prime, and paint fire extinguishing sprinkler systems including valves, piping, conduit, hangers, supports, miscellaneous metalwork, and accessories. Apply coatings to clean, dry surfaces, using clean brushes. Clean the surfaces to remove dust, dirt, rust, and loose mill scale. Immediately after cleaning, provide the metal surfaces with one coat primer per schedules. Shield sprinkler heads with protective

covering while painting is in progress. Upon completion of painting, remove protective covering from sprinkler heads. Remove sprinkler heads which have been painted and replace with new sprinkler heads. Provide primed surfaces with the following:

- a. Piping in Unfinished Areas: Provide primed surfaces with one coat of red alkyd gloss enamel applied to a minimum dry film thickness of 1.0 mil in attic spaces, spaces above suspended ceilings, crawl spaces, pipe chases, mechanical equipment room, and spaces where walls or ceiling are not painted or not constructed of a prefinished material.
- b. Piping in Finished Areas: Provide primed surfaces with two coats of paint to match adjacent surfaces, except provide valves and operating accessories with one coat of red alkyd gloss enamel applied to a minimum dry film thickness of 1.0 mil. Provide piping with 2 inch wide red enamel bands or self-adhering red plastic bands spaced at maximum of 20 foot intervals throughout the piping systems.

1.12.4 Exterior Painting of Site Work Items

Field coat the following items:

<u>New Surfaces</u>	<u>Existing Surfaces</u>
a. None	None
b. _____	_____
c. _____	_____

1.12.6 Definitions and Abbreviations

1.12.6.1 Qualification Testing

Qualification testing is the performance of all test requirements listed in the product specification. This testing is accomplished by MPI to qualify each product for the MPI Approved Product List, and may also be accomplished by Contractor's third party testing lab if an alternative to Batch Quality Conformance Testing by MPI is desired.

1.12.6.3 Coating

A film or thin layer applied to a base material called a substrate. A coating may be a metal, alloy, paint, or solid/liquid suspensions on various substrates (metals, plastics, wood, paper, leather, cloth, etc.). They may be applied by electrolysis, vapor deposition, vacuum, or mechanical means such as brushing, spraying, calendaring, and roller coating. A coating may be applied for aesthetic or protective purposes or both. The term "coating" as used herein includes emulsions, enamels, stains, varnishes, sealers, epoxies, and other coatings, whether used as primer, intermediate, or finish coat. The terms paint and coating are used interchangeably.

1.12.6.4 DFT or dft

Dry film thickness, the film thickness of the fully cured, dry paint or coating.

1.12.6.5 DSD

Degree of Surface Degradation, the MPI system of defining degree of surface degradation. Five (5) levels are generically defined under the Assessment sections in the MPI Maintenance Repainting Manual.

1.12.6.6 EPP

Environmentally Preferred Products, a standard for determining environmental preferability in support of Executive Order 13101.

1.12.6.7 EXT

MPI short term designation for an exterior coating system.

1.12.6.8 INT

MPI short term designation for an interior coating system.

1.12.6.9 micron / microns

The metric measurement for 0.001 mm or one/one-thousandth of a millimeter.

1.12.6.10 mil / mils

The English measurement for 0.001 in or one/one-thousandth of an inch, equal to 25.4 microns or 0.0254 mm.

1.12.6.11 mm

The metric measurement for millimeter, 0.001 meter or one/one-thousandth of a meter.

1.12.6.12 MPI Gloss Levels

MPI system of defining gloss. Seven (7) gloss levels (G1 to G7) are generically defined under the Evaluation sections of the MPI Manuals. Traditionally, Flat refers to G1/G2, Eggshell refers to G3, Semigloss refers to G5, and Gloss refers to G6.

Gloss levels are defined by MPI as follows:

<u>Gloss Level</u>	<u>Description</u>	<u>Units at 60 degrees</u>	<u>Units at 85 degrees</u>
G1	Matte or Flat	0 to 5	10 max
G2	Velvet	0 to 10	10 to 35
G3	Eggshell	10 to 25	10 to 35

<u>Gloss Level</u>	<u>Description</u>	<u>Units at 60 degrees</u>	<u>Units at 85 degrees</u>
G4	Satin	20 to 35	35 min
G5	Semi-Gloss	35 to 70	
G6	Gloss	70 to 85	
G7	High Gloss		

Gloss is tested in accordance with [ASTM D523](#). Historically, the Government has used Flat (G1 / G2), Eggshell (G3), Semi-Gloss (G5), and Gloss (G6).

1.12.6.13 MPI System Number

The MPI coating system number in each Division found in either the MPI Architectural Painting Specification Manual or the Maintenance Repainting Manual and defined as an exterior (EXT/REX) or interior system (INT/RIN). The Division number follows the CSI Master Format.

1.12.6.14 Paint

See Coating definition.

1.12.6.15 REX

MPI short term designation for an exterior coating system used in repainting projects or over existing coating systems.

1.12.6.16 RIN

MPI short term designation for an interior coating system used in repainting projects or over existing coating systems.

PART 2 PRODUCTS

2.1 MATERIALS

Conform to the [coating](#) specifications and standards referenced in PART 3. Submit [manufacturer's technical data sheets](#) for specified [coatings](#) and solvents. Comply with applicable regulations regarding toxic and hazardous materials.

PART 3 EXECUTION

3.1 PROTECTION OF AREAS AND SPACES NOT TO BE PAINTED

Prior to surface preparation and coating applications, remove, mask, or otherwise protect, hardware, hardware accessories, machined surfaces, radiator covers, plates, lighting fixtures, public and private property, and other such items not to be coated that are in contact with surfaces to be coated. Following completion of painting, workmen skilled in the trades

involved shall reinstall removed items. Restore surfaces contaminated by coating materials, to original condition and repair damaged items.

3.4 SURFACE PREPARATION

Remove dirt, splinters, loose particles, grease, oil, disintegrated coatings, and other foreign matter and substances deleterious to coating performance as specified for each substrate before application of paint or surface treatments. Oil and grease shall be removed prior to mechanical cleaning. Cleaning shall be programmed so that dust and other contaminants will not fall on wet, newly painted surfaces. Exposed ferrous metals such as nail heads on or in contact with surfaces to be painted with water-thinned paints, shall be spot-primed with a suitable corrosion-inhibitive primer capable of preventing flash rusting and compatible with the coating specified for the adjacent areas.

3.4.1 Additional Requirements for Preparation of Surfaces With Existing Coatings

Before application of coatings, perform the following on surfaces covered by soundly-adhered coatings, defined as those which cannot be removed with a putty knife:

- a. Test existing finishes for lead before sanding, scraping, or removing. If lead is present, refer to paragraph Toxic Materials.
- b. Wipe previously painted surfaces to receive solvent-based coatings, except stucco and similarly rough surfaces clean with a clean, dry cloth saturated with mineral spirits, [ASTM D235](#). Allow surface to dry. Wiping shall immediately precede the application of the first coat of any coating, unless specified otherwise.
- c. Sand existing glossy surfaces to be painted to reduce gloss. Brush, and wipe clean with a damp cloth to remove dust.
- d. The requirements specified are minimum. Comply also with the [application instructions](#) of the paint manufacturer.
- e. Previously painted surfaces specified to be repainted or damaged during construction shall be thoroughly cleaned of all grease, dirt, dust or other foreign matter.
- f. Blistering, cracking, flaking and peeling or other deteriorated coatings shall be removed.
- g. Chalk shall be removed so that when tested in accordance with [ASTM D4214](#), the chalk resistance rating is no less than 8.
- h. Slick surfaces shall be roughened. Damaged areas such as, but not limited to, nail holes, cracks, chips, and spalls shall be repaired with suitable material to match adjacent undamaged areas.
- i. Edges of chipped paint shall be feather edged and sanded smooth.
- j. Rusty metal surfaces shall be cleaned as per SSPC requirements. Solvent, mechanical, or chemical cleaning methods shall be used to provide surfaces suitable for painting.

- k. New, proposed coatings shall be compatible with existing coatings.

3.4.2 Existing Coated Surfaces with Minor Defects

Sand, spackle, and treat minor defects to render them smooth. Minor defects are defined as scratches, nicks, cracks, gouges, spalls, alligatoring, chalking, and irregularities due to partial peeling of previous coatings. Remove chalking by sanding so that when tested in accordance with [ASTM D4214](#), the chalk rating is not less than 8.

3.4.3 Removal of Existing Coatings

Remove existing coatings from the following surfaces:

- a. Surfaces containing large areas of minor defects;
- b. Surfaces containing more than 20 percent peeling area; and
- c. Surfaces where rust shows through existing coatings.
- d. Surfaces designated by the Contracting Officer.

3.4.4 Substrate Repair

- a. Repair substrate surface damaged during coating removal;
- b. Sand edges of adjacent soundly-adhered existing coatings so they are tapered as smooth as practical to areas involved with coating removal; and
- c. Clean and prime the substrate as specified.

3.5 PREPARATION OF METAL SURFACES

3.5.1 Existing and New Ferrous Surfaces

- a. Ferrous Surfaces including Shop-coated Surfaces and Small Areas That Contain Rust, Mill Scale and Other Foreign Substances: Solvent clean or detergent wash in accordance with [SSPC SP 1](#) to remove oil and grease. Where shop coat is missing or damaged, clean according to [SSPC SP 2](#), [SSPC SP 3](#), [SSPC SP 6/NACE No.3](#), or [SSPC SP 10/NACE No. 2](#). Brush-off blast remaining surface in accordance with [SSPC SP 7/NACE No.4](#); Water jetting to [SSPC SP 12/NACE No.5](#) WJ-4 may be used to remove loose coating and other loose materials. Use inhibitor as recommended by coating manufacturer to prevent premature rusting. Shop-coated ferrous surfaces shall be protected from corrosion by treating and touching up corroded areas immediately upon detection.
- b. Surfaces With More Than 20 Percent Rust, Mill Scale, and Other Foreign Substances: Clean entire surface in accordance with [SSPC SP 6/NACE No.3](#) /[SSPC SP 12/NACE No.5](#) WJ-3 or [SSPC SP 10/NACE No. 2](#)/[SSPC SP 12/NACE No.5](#) WJ-2.
- c. Metal Floor Surfaces to Receive Nonslip Coating: Clean in accordance with [SSPC SP 10/NACE No. 2](#) or [SSPC SP 12/NACE No.5](#) WJ-2.

3.5.2 Final Ferrous Surface Condition:

For tool cleaned surfaces, the requirements are stated in [SSPC SP 2](#) and [SSPC SP 3](#). As a visual reference, cleaned surfaces shall be similar to photographs in [SSPC VIS 3](#).

For abrasive blast cleaned surfaces, the requirements are stated in [SSPC SP 7/NACE No.4](#), [SSPC SP 6/NACE No.3](#), and [SSPC SP 10/NACE No. 2](#). As a visual reference, cleaned surfaces shall be similar to photographs in [SSPC VIS 1](#).

For waterjet cleaned surfaces, the requirements are stated in [SSPC SP 12/NACE No.5](#). As a visual reference, cleaned surfaces shall be similar to photographs in [SSPC VIS 4/NACE VIS 7](#).

3.5.3 Galvanized Surfaces

- a. New or Existing Galvanized Surfaces With Only Dirt and Zinc Oxidation Products: Clean with solvent, steam, or non-alkaline detergent solution in accordance with [SSPC SP 1](#). If the galvanized metal has been passivated or stabilized, the coating shall be completely removed by brush-off abrasive blast. New galvanized steel to be coated shall not be "passivated" or "stabilized" If the absence of hexavalent stain inhibitors is not documented, test as described in [ASTM D6386](#), Appendix X2, and remove by one of the methods described therein.
- b. Galvanized with Slight Coating Deterioration or with Little or No Rusting: Water jetting to [SSPC SP 12/NACE No.5](#) WJ3 to remove loose coating from surfaces with less than 20 percent coating deterioration and no blistering, peeling, or cracking. Use inhibitor as recommended by the coating manufacturer to prevent rusting.
- c. Galvanized With Severe Deteriorated Coating or Severe Rusting: Water jet to [SSPC SP 12/NACE No.5](#) WJ3 degree of cleanliness. Or, spot abrasive blast rusted areas as described for steel in [SSPC SP 6/NACE No.3](#), and waterjet to [SSPC SP 12/NACE No.5](#), WJ3 to remove existing coating.

3.5.4 Non-Ferrous Metallic Surfaces

Aluminum and aluminum-alloy, lead, copper, and other nonferrous metal surfaces.

Surface Cleaning: Solvent clean in accordance with [SSPC SP 1](#) and wash with mild non-alkaline detergent to remove dirt and water soluble contaminants.

3.5.5 Terne-Coated Metal Surfaces

Solvent clean surfaces with mineral spirits, [ASTM D235](#). Wipe dry with clean, dry cloths.

3.5.6 Existing Surfaces with a Bituminous or Mastic-Type Coating

Remove chalk, mildew, and other loose material by washing with a solution of [1/2 cup](#) trisodium phosphate, [1/4 cup](#) household detergent, [one quart](#) 5 percent sodium hypochlorite solution and [3 quarts](#) of warm water.

3.6 PREPARATION OF CONCRETE AND CEMENTITIOUS SURFACE

3.6.1 Concrete and Masonry

- a. Curing: Concrete, stucco and masonry surfaces shall be allowed to cure at least 30 days before painting, except concrete slab on grade, which shall be allowed to cure 90 days before painting.
- b. Surface Cleaning: Remove the following deleterious substances.
 - (1) Dirt, Chalking, Grease, and Oil: Wash new and existing uncoated surfaces with a solution composed of 1/2 cup trisodium phosphate, 1/4 cup household detergent, and 4 quarts of warm water. Then rinse thoroughly with fresh water. Wash existing coated surfaces with a suitable detergent and rinse thoroughly. For large areas, water blasting may be used.
 - (2) Fungus and Mold: Wash new, existing coated, and existing uncoated surfaces with a solution composed of 1/2 cup trisodium phosphate, 1/4 cup household detergent, 1 quart 5 percent sodium hypochlorite solution and 3 quarts of warm water. Rinse thoroughly with fresh water.
 - (3) Paint and Loose Particles: Remove by wire brushing.
 - (4) Efflorescence: Remove by scraping or wire brushing followed by washing with a 5 to 10 percent by weight aqueous solution of hydrochloric (muriatic) acid. Do not allow acid to remain on the surface for more than five minutes before rinsing with fresh water. Do not acid clean more than 4 square feet of surface, per workman, at one time.
 - (5) Removal of Existing Coatings: For surfaces to receive textured coating MPI 42, remove existing coatings including soundly adhered coatings if recommended by textured coating manufacturer.
- c. Cosmetic Repair of Minor Defects: Repair or fill mortar joints and minor defects, including but not limited to spalls, in accordance with manufacturer's recommendations and prior to coating application.
- d. Allowable Moisture Content: Latex coatings may be applied to damp surfaces, but not to surfaces with droplets of water. Do not apply epoxies to damp vertical surfaces as determined by ASTM D4263 or horizontal surfaces that exceed 3 lbs of moisture per 1000 square feet in 24 hours as determined by ASTM F 1869. In all cases follow manufacturers recommendations. Allow surfaces to cure a minimum of 30 days before painting.

3.6.2 Gypsum Board, Plaster, and Stucco

- a. Surface Cleaning: Plaster and stucco shall be clean and free from loose matter; gypsum board shall be dry. Remove loose dirt and dust by brushing with a soft brush, rubbing with a dry cloth, or vacuum-cleaning prior to application of the first coat material. A damp cloth or sponge may be used if paint will be water-based.
- b. Repair of Minor Defects: Prior to painting, repair joints, cracks, holes, surface irregularities, and other minor defects with patching plaster or spackling compound and sand smooth.

- c. Allowable Moisture Content: Latex coatings may be applied to damp surfaces, but not surfaces with droplets of water. Do not apply epoxies to damp surfaces as determined by [ASTM D4263](#). New plaster to be coated shall have a maximum moisture content of 8 percent, when measured in accordance with [ASTM D4444](#), Method A, unless otherwise authorized. In addition to moisture content requirements, allow new plaster to age a minimum of 30 days before preparation for painting.

3.6.3 Existing Asbestos Cement Surfaces

Remove oily stains by solvent cleaning with mineral spirits, [MIL-PRF-680](#), [ASTM D235](#). Remove loose dirt, dust, and other deleterious substances by brushing with a soft brush or rubbing with a dry cloth prior to application of the first coat material. Do not wire brush or clean using other abrasive methods. Surfaces shall be dry and clean prior to application of the coating.

3.7 PREPARATION OF WOOD AND PLYWOOD SURFACES

3.7.1 New, Existing Uncoated, and Existing Coated Plywood and Wood Surfaces, Except Floors:

- a. Wood surfaces shall be cleaned of foreign matter.

Surface Cleaning: Surfaces shall be free from dust and other deleterious substances and in a condition approved by the Contracting Officer prior to receiving paint or other finish. Do not use water to clean uncoated wood. Scrape to remove loose coatings. Lightly sand to roughen the entire area of previously enamel-coated wood surfaces.

- b. Removal of Fungus and Mold: Wash existing coated surfaces with a solution composed of 3 ounces (2/3 cup) trisodium phosphate, 1 ounce (1/3 cup) household detergent, 1 quart 5 percent sodium hypochlorite solution and 3 quarts of warm water. Rinse thoroughly with fresh water.
- c. Moisture content of the wood shall not exceed 12 percent as measured by a moisture meter in accordance with [ASTM D4444](#), Method A, unless otherwise authorized.
- d. Wood surfaces adjacent to surfaces to receive water-thinned paints shall be primed and/or touched up before applying water-thinned paints.
- e. Cracks and Nailheads: Set and putty stop nailheads and putty cracks after the prime coat has dried.
- f. Cosmetic Repair of Minor Defects:
 - (1) Knots and Resinous Wood and Fire, Smoke, Water, and Color Marker Stained Existing Coated Surface: Prior to application of coating, cover knots and stains with two or more coats of 3-pound-cut shellac varnish, plasticized with 5 ounces of castor oil per gallon. Scrape away existing coatings from knotty areas, and sand before treating. Prime before applying any putty over shellacked area.
 - (2) Open Joints and Other Openings: Fill with whiting putty, linseed oil putty. Sand smooth after putty has dried.

- (3) Checking: Where checking of the wood is present, sand the surface, wipe and apply a coat of pigmented orange shellac. Allow to dry before paint is applied.

- g. Prime Coat For New Exterior Surfaces: Prime coat wood doors, windows, frames, and trim before wood becomes dirty, warped, or weathered.

3.7.2 Wood Floor Surfaces, Natural Finish

- a. Initial Surface Cleaning: As specified in paragraph entitled "Surface Preparation."
- b. Existing Loose Boards and Shoe Molding: Before sanding, renail loose boards. Countersink nails and fill with an approved wood filler. Remove shoe molding before sanding and reinstall after completing other work. At Contractor's option, new shoe molding may be provided in lieu of reinstalling old. New wood molding shall be same size, wood species, and finish as the existing.
- c. Sanding and Scraping: Sanding of wood floors is specified in Section 09 64 29 WOOD STRIP FLOORING or 09 64 66 WOOD ATHLETIC FLOORING. Floors of oak or similar open-grain wood shall be filled with wood filler recommended by the finish manufacturer and the excess filler removed.
- d. Final Cleaning: After sanding, sweep and vacuum floors clean. Do not walk on floors thereafter until specified sealer has been applied and is dry.

3.7.3 Interior Wood Surfaces, Stain Finish

Interior wood surfaces to receive stain shall be sanded. Oak and other open-grain wood to receive stain shall be given a coat of wood filler not less than 8 hours before the application of stain; excess filler shall be removed and the surface sanded smooth.

3.8 APPLICATION

3.8.1 Coating Application

Painting practices shall comply with applicable federal, state and local laws enacted to insure compliance with Federal Clean Air Standards. Apply coating materials in accordance with [SSPC PA 1](#). [SSPC PA 1](#) methods are applicable to all substrates, except as modified herein.

At the time of application, paint shall show no signs of deterioration. Uniform suspension of pigments shall be maintained during application.

Unless otherwise specified or recommended by the paint manufacturer, paint may be applied by brush, roller, or spray. Use trigger operated spray nozzles for water hoses. Rollers for applying paints and enamels shall be of a type designed for the coating to be applied and the surface to be coated. Wear protective clothing and respirators when applying oil-based paints or using spray equipment with any paints.

Paints, except water-thinned types, shall be applied only to surfaces that are completely free of moisture as determined by sight or touch.

Thoroughly work coating materials into joints, crevices, and open spaces. Special attention shall be given to insure that all edges, corners, crevices, welds, and rivets receive a film thickness equal to that of adjacent painted surfaces.

Each coat of paint shall be applied so dry film shall be of uniform thickness and free from runs, drops, ridges, waves, pinholes or other voids, laps, brush marks, and variations in color, texture, and finish. Hiding shall be complete.

Touch up damaged coatings before applying subsequent coats. Interior areas shall be broom clean and dust free before and during the application of coating material.

Apply paint to new fire extinguishing sprinkler systems including valves, piping, conduit, hangers, supports, miscellaneous metal work, and accessories. Shield sprinkler heads with protective coverings while painting is in progress. Remove sprinkler heads which have been painted and replace with new sprinkler heads. For piping in unfinished spaces, provide primed surfaces with one coat of red alkyd gloss enamel to a minimum dry film thickness of 1.0 mil. Unfinished spaces include attic spaces, spaces above suspended ceilings, crawl spaces, pipe chases, mechanical equipment room, and space where walls or ceiling are not painted or not constructed of a prefinished material. For piping in finished areas, provide prime surfaces with two coats of paint to match adjacent surfaces, except provide valves and operating accessories with one coat of red alkyd gloss enamel. Upon completion of painting, remove protective covering from sprinkler heads.

- a. Drying Time: Allow time between coats, as recommended by the coating manufacturer, to permit thorough drying, but not to present topcoat adhesion problems. Provide each coat in specified condition to receive next coat.
- b. Primers, and Intermediate Coats: Do not allow primers or intermediate coats to dry more than 30 days, or longer than recommended by manufacturer, before applying subsequent coats. Follow manufacturer's recommendations for surface preparation if primers or intermediate coats are allowed to dry longer than recommended by manufacturers of subsequent coatings. Each coat shall cover surface of preceding coat or surface completely, and there shall be a visually perceptible difference in shades of successive coats.
- c. Finished Surfaces: Provide finished surfaces free from runs, drops, ridges, waves, laps, brush marks, and variations in colors.
- d. Thermosetting Paints: Topcoats over thermosetting paints (epoxies and urethanes) should be applied within the overcoating window recommended by the manufacturer.
- e. Floors: For nonslip surfacing on level floors, as the intermediate coat is applied, cover wet surface completely with almandite garnet, Grit No. 36, with maximum passing U.S. Standard Sieve No. 40 less than 0.5 percent. When the coating is dry, use a soft bristle broom to sweep up excess grit, which may be reused, and vacuum up remaining residue before application of the topcoat. For nonslip surfacing on ramps, provide MPI 77 with non-skid additive, applied by roller in accordance with manufacturer's instructions.

3.8.2 Mixing and Thinning of Paints

Reduce paints to proper consistency by adding fresh paint, except when thinning is mandatory to suit surface, temperature, weather conditions, application methods, or for the type of paint being used. Obtain written permission from the Contracting Officer to use thinners. The written permission shall include quantities and types of thinners to use.

When thinning is allowed, paints shall be thinned immediately prior to application with not more than 1 pint of suitable thinner per gallon. The use of thinner shall not relieve the Contractor from obtaining complete hiding, full film thickness, or required gloss. Thinning shall not cause the paint to exceed limits on volatile organic compounds. Paints of different manufacturers shall not be mixed.

3.8.3 Two-Component Systems

Two-component systems shall be mixed in accordance with manufacturer's instructions. Any thinning of the first coat to ensure proper penetration and sealing shall be as recommended by the manufacturer for each type of substrate.

3.8.4 Coating Systems

- a. Systems by Substrates: Apply coatings that conform to the respective specifications listed in the following Tables:

Table	
<u>EXTERIOR</u>	
Division 3.	Exterior Concrete Paint Table
Division 4.	Exterior Concrete Masonry Units Paint Table
Division 5.	Exterior Metal, Ferrous and Non-Ferrous Paint Table
Division 6.	Exterior Wood; Dressed Lumber, Paneling, Decking, Shingles Paint Table
Division 9.	Exterior Stucco Paint Table
Division 10.	Exterior Cloth Coverings and Bituminous Coated Surfaces Paint Table
<u>INTERIOR</u>	
Division 3.	Interior Concrete Paint Table
Division 4.	Interior Concrete Masonry Units Paint Table
Division 5.	Interior Metal, Ferrous and Non-Ferrous Paint Table
Division 6.	Interior Wood Paint Table

Table	
Division 10.	Interior Plaster, Gypsum Board, Textured Surfaces Paint Table

- b. Minimum Dry Film Thickness (DFT): Apply paints, primers, varnishes, enamels, undercoats, and other coatings to a minimum dry film thickness of 1.5 mil each coat unless specified otherwise in the Tables. Coating thickness where specified, refers to the minimum dry film thickness.
- c. Coatings for Surfaces Not Specified Otherwise: Coat surfaces which have not been specified, the same as surfaces having similar conditions of exposure.
- d. Existing Surfaces Damaged During Performance of the Work, Including New Patches In Existing Surfaces: Coat surfaces with the following:
 - (1) One coat of primer.
 - (2) One coat of undercoat or intermediate coat.
 - (3) One topcoat to match adjacent surfaces.
- e. Existing Coated Surfaces To Be Painted: Apply coatings conforming to the respective specifications listed in the Tables herein, except that pretreatments, sealers and fillers need not be provided on surfaces where existing coatings are soundly adhered and in good condition. Do not omit undercoats or primers.

3.9 COATING SYSTEMS FOR METAL

Apply coatings of Tables in Division 5 for Exterior and Interior.

- a. Apply specified ferrous metal primer on the same day that surface is cleaned, to surfaces that meet all specified surface preparation requirements at time of application.
- b. Inaccessible Surfaces: Prior to erection, use one coat of specified primer on metal surfaces that will be inaccessible after erection.
- c. Shop-primed Surfaces: Touch up exposed substrates and damaged coatings to protect from rusting prior to applying field primer.
- d. Surface Previously Coated with Epoxy or Urethane: Apply MPI 101, 1.5 mils DFT immediately prior to application of epoxy or urethane coatings.
- e. Pipes and Tubing: The semitransparent film applied to some pipes and tubing at the mill is not to be considered a shop coat, but shall be overcoated with the specified ferrous-metal primer prior to application of finish coats.
- f. Exposed Nails, Screws, Fasteners, and Miscellaneous Ferrous Surfaces. On surfaces to be coated with water thinned coatings, spot prime exposed nails and other ferrous metal with latex primer MPI 107.

3.10 COATING SYSTEMS FOR CONCRETE AND CEMENTITIOUS SUBSTRATES

Apply coatings of Tables in Division 3, 4 and 9 for Exterior and Interior.

3.11 COATING SYSTEMS FOR WOOD AND PLYWOOD

- a. Apply coatings of Tables in Division 6 for Exterior and Interior.
- b. Prior to erection, apply two coats of specified primer to treat and prime wood and plywood surfaces which will be inaccessible after erection.
- c. Apply stains in accordance with manufacturer's printed instructions.
- d. Wood Floors to Receive Natural Finish: Thin first coat 2 to 1 using thinner recommended by coating manufacturer. Apply all coatings at rate of 300 to 350 square feet per gallon. Apply second coat not less than 2 hours and not over 24 hours after first coat has been applied. Apply with lambs wool applicators or roller as recommended by coating manufacturer. Buff or lightly sand between intermediate coats as recommended by coating manufacturer's printed instructions.

3.12 PIPING IDENTIFICATION

Piping Identification, Including Surfaces In Concealed Spaces: Provide in accordance with MIL-STD-101. Place stenciling in clearly visible locations. On piping not covered by MIL-STD-101, stencil approved names or code letters, in letters a minimum of 1/2 inch high for piping and a minimum of 2 inches high elsewhere. Stencil arrow-shaped markings on piping to indicate direction of flow using black stencil paint.

3.13 INSPECTION AND ACCEPTANCE

In addition to meeting previously specified requirements, demonstrate mobility of moving components, including swinging and sliding doors, cabinets, and windows with operable sash, for inspection by the Contracting Officer. Perform this demonstration after appropriate curing and drying times of coatings have elapsed and prior to invoicing for final payment.

3.14 WASTE MANAGEMENT

As specified in the Waste Management Plan and as follows. Do not use kerosene or any such organic solvents to clean up water based paints. Properly dispose of paints or solvents in designated containers. Close and seal partially used containers of paint to maintain quality as necessary for reuse. Store in protected, well-ventilated, fire-safe area at moderate temperature. Place materials defined as hazardous or toxic waste in designated containers. Set aside extra paint for future color matches or reuse by the Government.

3.15 PAINT TABLES

All DFT's are minimum values. Use only materials having a minimum MPI "Environmentally Friendly" E1 or better rating based on VOC (EPA Method 24) content levels. Acceptable products are listed in the MPI Green Approved Products List, available at <http://www.specifygreen.com/APL/ProductIdxByMPInum.asp>.

3.15.1 EXTERIOR PAINT TABLES

HL4>DIVISION 3: EXTERIOR CONCRETE PAINT TABLE		
A. New and uncoated existing and Existing, previously painted concrete; vertical surfaces, including undersides of balconies and soffits but excluding tops of slabs:		
1. Latex		
New; MPI EXT 3.1A-G2 (Flat) / Existing; MPI REX 3.1A-G2 (Flat)		
Primer: MPI 10	Intermediate: MPI 10	Topcoat: MPI 10
System DFT: 3.5 mils		
New; MPI EXT 3.1A-G5 (Semigloss) / Existing; MPI EXT 3.1A-G5 (Semigloss)		
Primer: MPI 11	Intermediate: MPI 11	Topcoat: MPI 11
System DFT: 3.5 mils		
New; MPI EXT 3.1A-G6 (Gloss) / Existing; MPI REX 3.1A-G6 (Gloss)		
Primer: MPI 119	Intermediate: MPI 119	Topcoat: MPI 119
Primer as recommended by manufacturer. Topcoat: Coating to match adjacent surfaces.		
B. New and uncoated existing and Existing, previously painted concrete, textured system; vertical surfaces, including undersides of balconies and soffits but excluding tops of slabs:		
1. Latex Aggregate		
New; MPI EXT 3.1B-G2 (Flat) / Existing; MPI REX 3.1B-G2 (Flat)		
Primer: MPI 42	Intermediate: MPI 10	Topcoat: MPI 10
System DFT: Per Manufacturer		
New; MPI EXT 3.1B-G5 (Semigloss) / Existing; MPI REX 3.1B-G5 (Semigloss)		
Primer: MPI 42	Intermediate: MPI 11	Topcoat: MPI 11
System DFT: Per Manufacturer		
New; MPI EXT 3.1B-G6 (Gloss) / Existing; MPI REX 3.1B-G6 (Gloss)		

HL4>DIVISION 3: EXTERIOR CONCRETE PAINT TABLE		
Primer: MPI 42	Intermediate: MPI 119	Topcoat: MPI 119
System DFT: Per Manufacturer		
Texture - Medium. Surface preparation and number of coats in accordance with manufacturer's instructions. Topcoat: Coating to match adjacent surfaces.		
C. New and uncoated existing and Existing, previously painted concrete, elastomeric System; vertical surfaces, including undersides of balconies and soffits but excluding tops of slabs:		
1. Elastomeric Coating		
New; MPI EXT 3.1F / Existing; MPI REX 3.1F		
Primer: Per Manufacturer	Intermediate: MPI 113	Topcoat: MPI 113
System DFT: 16 mils		
Primer as recommended by manufacturer. Topcoat: Coating to match adjacent surfaces. Surface preparation and number of coats in accordance with manufacturer's instructions.		
NOTE: Apply sufficient coats of MPI 113 to achieve a minimum dry film thickness of 16 mils.		
D. New and uncoated existing and Existing, previously painted concrete: walls and bottom of swimming pools.		
1. Chlorinated Rubber		
New; / Existing;		
Primer: SSPC Paint 18	Intermediate: SSPC Paint 18	Topcoat: SSPC Paint 18
System DFT: Per Manufacturer		
NOTE: Thin first coat (primer) with 1 part of approved thinner to 4 parts of paint by volume.		
E. New and Existing Cementitious composition board (including Asbestos cement board):		

HL4>DIVISION 3: EXTERIOR CONCRETE PAINT TABLE		
1. Latex		
New; MPI EXT 3.3A-G5 (Semigloss) / Existing; MPI REX 3.3A-G5 (Semigloss)		
Primer: MPI 11	Intermediate: MPI 11	Topcoat: MPI 11
System DFT: 4.5 mils		
New; MPI EXT 3.3A-G6 (Gloss) / Existing; MPI REX 3.3A-G6 (Gloss)		
Primer: MPI 119	Intermediate: MPI 119	Topcoat: MPI 119
System DFT: 4.5 mils		
Topcoat: Coating to match adjacent surfaces.		

DIVISION 4: EXTERIOR CONCRETE MASONRY UNITS PAINT TABLE			
A. New and Existing concrete masonry on uncoated surface:			
1. Latex			
New; MPI EXT 4.2A-G1 (Flat) / Existing; MPI REX 4.2A-G1 (Flat)			
Block Filler: MPI 4	Primer: N/A	Intermediate: MPI 10	Topcoat: MPI 10
System DFT: 11 mils			
New; MPI EXT 4.2A-G5 (Semigloss) / Existing; MPI REX 4.2A-G5 (Semigloss)			

DIVISION 4: EXTERIOR CONCRETE MASONRY UNITS PAINT TABLE

Block Filler: MPI 4	Primer: N/A	Intermediate: MPI 11	Topcoat: MPI 11
System DFT: 11 mils			
New; MPI EXT 4.2A-G6 (Gloss) / Existing; MPI REX 4.2A-G6 (Gloss)			
Block Filler: MPI 4	Primer: N/A	Intermediate: MPI 119	Topcoat: MPI 119
Topcoat: Coating to match adjacent surfaces.			
B. New and Existing concrete masonry, textured system; on uncoated surface:			
1. Latex Aggregate			
New; MPI EXT 4.2B-G1 (Flat) / Existing; MPI REX 4.2B-G1 (Flat)			
Primer: MPI 42	Intermediate: MPI 42	Topcoat: MPI 10	
System DFT: Per Manufacturer			
New; MPI EXT 4.2B-G5 (Semigloss) / Existing; MPI REX 4.2B-G5 (Semigloss)			
Primer: MPI 42	Intermediate: MPI 42	Topcoat: MPI 11	
System DFT: Per Manufacturer			
New; MPI EXT 4.2B-G6 (Gloss) / Existing; MPI REX 4.2B-G6 (Gloss)			
Primer: MPI 42	Intermediate: MPI 42	Topcoat: MPI 119	
System DFT: Per Manufacturer			
Texture - Fine Medium Course. Surface preparation and number of coats in accordance with manufacturer's instructions. Topcoat: Coating to match adjacent surfaces.			
C. New and Existing concrete masonry, elastomeric System; on uncoated surface:			
1. Elastomeric Coating			
New; MPI EXT 4.2D / Existing; MPI REX 4.2D			
Primer: Per Manufacturer	Intermediate: MPI 113	Topcoat: MPI 113	
System DFT: 16 mils			

DIVISION 4: EXTERIOR CONCRETE MASONRY UNITS PAINT TABLE
Primer as recommended by manufacturer. Topcoat: Coating to match adjacent surfaces. Surface preparation and number of coats in accordance with manufacturer's instructions.
NOTE: Apply sufficient coats of MPI 113 to achieve a minimum dry film thickness of 16 mils.

DIVISION 5: EXTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE		
<u>STEEL / FERROUS SURFACES</u>		
A. New Steel that has been hand or power tool cleaned to SSPC SP 2 or SSPC SP 3		
1. Alkyd		
New; MPI EXT 5.1Q-G5 (Semigloss) / Existing; MPI REX 5.1D-G5		
Primer: MPI 23	Intermediate: MPI 94	Topcoat: MPI 94
System DFT: 5.25 mils		
New; MPI EXT 5.1Q-G6 (Gloss) / Existing; MPI REX 5.1D-G6		
Primer: MPI 23	Intermediate: MPI 9	Topcoat: MPI 9
System DFT: 5.25 mils		
B. New Steel that has been blast-cleaned to SSPC SP 6/NACE No.3:		
1. Alkyd		
New; MPI EXT 5.1D-G5 (Semigloss) / Existing; MPI REX 5.1D-G5		
Primer: MPI 79	Intermediate: MPI 94	Topcoat: MPI 94
System DFT: 5.25 mils		
New; MPI EXT 5.1D-G6 (Gloss) / Existing; MPI REX 5.1D-G6		
Primer: MPI 79	Intermediate: MPI 9	Topcoat: MPI 9

DIVISION 5: EXTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE		
System DFT: 5.25 mils		
C. Existing steel that has been spot-blasted to SSPC SP 6/NACE No.3:		
1. Surface previously coated with alkyd or latex:		
Waterborne Light Industrial Coating		
MPI REX 5.1C-G5 (Semigloss)		
Spot Primer: MPI 79	Intermediate: MPI 163	Topcoat: MPI 163
System DFT: 5 mils		
MPI REX 5.1C-G6 (Gloss)		
Spot Primer: MPI 79	Intermediate: MPI 164	Topcoat: MPI 164
System DFT: 5 mils		
2. Surface previously coated with epoxy:		
Waterborne Light Industrial		
a. MPI REX 5.1L-G5 (Semigloss)		
Spot Primer: MPI 101	Intermediate: MPI 163	Topcoat: MPI 163
System DFT: 5 mils		
MPI REX 5.1L-G6 (Gloss)		
Spot Primer: MPI 101	Intermediate: MPI 164	Topcoat: MPI 164
System DFT: 5 mils		
Pigmented Polyurethane		
b. MPI REX 5.1H-G6 (Gloss)		
Spot Primer: MPI 101	Intermediate: MPI 108	Topcoat: MPI 72

DIVISION 5: EXTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE		
System DFT: 8.5 mils		
D. New and existing steel blast cleaned to SSPC SP 10/NACE No. 2:		
1. Waterborne Light Industrial		
MPI EXT 5.1R-G5 (Semigloss)		
Primer: MPI 101	Intermediate: MPI 108	Topcoat: MPI 163
System DFT: 8.5 mils		
MPI EXT 5.1R-G6 (Gloss)		
Primer: MPI 101	Intermediate: MPI 108	Topcoat: MPI 164
System DFT: 8.5 mils		
2. Pigminted Polyurethane		
2. Pigmented Polyurethane		
MPI EXT 5.1J-G6 (Gloss)		
Primer: MPI 101	Intermediate: MPI 108	Topcoat: MPI 72
System DFT: 8.5 mils		
E. Metal floors (non-shop-primed surfaces or non-slip deck surfaces) with non-skid additive (NSA), load at manufacturer's recommendations:		
1. Alkyd Floor Enamel		
MPI EXT 5.1S-G6 (Gloss)		
Primer: MPI 79	Intermediate: MPI 27	Topcoat: MPI 27 (plus NSA)
System DFT: 5.25 mils		
<u>EXTERIOR GALVANIZED SURFACES</u>		
F. New Galvanized surfaces:		
1. Cementitious primer / Latex		

DIVISION 5: EXTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE		
MPI EXT 5.3A-G1 (Flat)		
Primer: MPI 26	Intermediate: MPI 10	Topcoat: MPI 10
System DFT: 4.5 mils		
MPI EXT 5.3A-G5 (Semigloss)		
Primer: MPI 26	Intermediate: MPI 11	Topcoat: MPI 11
System DFT: 4.5 mils		
MPI EXT 5.3A-G6 (Gloss)		
Primer: MPI 26	Intermediate: MPI 119	Topcoat: MPI 119
System DFT: 4.5 mils		
2. Waterborne Primer / Latex		
MPI EXT 5.3H-G1 (Flat)		
Primer: MPI 134	Intermediate: MPI 10	Topcoat: MPI 10
System DFT: 4.5 mils		
MPI EXT 5.3H-G5 (Semigloss)		
Primer: MPI 134	Intermediate: MPI 11	Topcoat: MPI 11
System DFT: 4.5 mils		
MPI EXT 5.3H-G6 (Gloss)		
Primer: MPI 134	Intermediate: MPI 119	Topcoat: MPI 119
System DFT: 4.5 mils		
3. Waterborne Primer / Waterborne Light Industrial Coating		
MPI EXT 5.3J-G5 (Semigloss)		
Primer: MPI 134	Intermediate: MPI 163	Topcoat: MPI 163

DIVISION 5: EXTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE		
System DFT: 4.5 mils		
MPI EXT 5.3J-G6 (Gloss)		
Primer: MPI 134	Intermediate: MPI 164	Topcoat: MPI 164
System DFT: 4.5 mils		
4. Epoxy Primer / Waterborne Light Industrial Coating		
MPI EXT 5.3K-G5 (Semigloss)		
Primer: MPI 101	Intermediate: MPI 163	Topcoat: MPI 163
System DFT: 5 mils		
MPI EXT 5.3K-G6 (Gloss)		
Primer: MPI 101	Intermediate: MPI 164	Topcoat: MPI 164
System DFT: 5 mils		
5. Pigmented Polyurethane		
MPI EXT 5.3L-G6 (Gloss)		
Primer: MPI 101	Intermediate: N/A	Topcoat: MPI 72
System DFT: 5 mils		
G. Galvanized surfaces with slight coating deterioration; little or no rusting:		
1. Waterborne Light Industrial Coating		
MPI REX 5.3J-G5 (Semigloss)		
Primer: MPI 134	Intermediate: N/A	Topcoat: MPI 163
System DFT: 4.5 mils		
2. Pigmented Polyurethane		

DIVISION 5: EXTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE		
MPI REX 5.3D-G6 (Gloss)		
Primer: MPI 101	Intermediate: N/A	Topcoat: MPI 72
System DFT: 5 mils		
H. Galvanized surfaces with severely deteriorated coating or rusting:		
1. Waterborne Light Industrial Coating		
MPI REX 5.3L-G5 (Semigloss)		
Primer: MPI 101	Intermediate: MPI 108	Topcoat: MPI 163
System DFT: 8.5 mils		
MPI REX 5.3L-G6 (Gloss)		
Primer: MPI 101	Intermediate: MPI 108	Topcoat: MPI 164
System DFT: 8.5 mils		
2. Pigmented Polyurethane		
MPI REX 5.3K-G6 (Gloss)		
Primer: MPI 101	Intermediate: MPI 108	Topcoat: MPI 72
System DFT: 5 mils		
<u>EXTERIOR SURFACES, OTHER METALS (NON-FERROUS)</u>		
I. Aluminum, aluminum alloy and other miscellaneous non-ferrous metal items not otherwise specified except hot metal surfaces, roof surfaces, and new prefinished equipment. Match surrounding finish:		
1. Alkyd		
MPI EXT 5.4F-G1 (Flat)		
Primer: MPI 95	Intermediate: MPI 8	Topcoat: MPI 8
System DFT: 5 mils		

DIVISION 5: EXTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE		
MPI EXT 5.4F-G5 (Semigloss)		
Primer: MPI 95	Intermediate: MPI 94	Topcoat: MPI 94
System DFT: 5 mils		
MPI EXT 5.4F-G6 (Gloss)		
Primer: MPI 95	Intermediate: MPI 9	Topcoat: MPI 9
System DFT: 5 mils		
2. Waterborne Light Industrial Coating		
MPI EXT 5.4G-G3 (Eggshell)		
Primer: MPI 95	Intermediate: MPI 161	Topcoat: MPI 161
System DFT: 5 mils		
MPI EXT 5.4G-G5 (Semigloss)		
Primer: MPI 95	Intermediate: MPI 163	Topcoat: MPI 163
System DFT: 5 mils		
MPI EXT 5.4G-G6 (Gloss)		
Primer: MPI 95	Intermediate: MPI 164	Topcoat: MPI 164
System DFT: 5 mils		
J. Existing roof surfaces previously coated:		
1. Aluminum Pigmented Asphalt Roof Coating		
ASTM D2824: Sufficient coats to provide not less than 8 mils of finished coating system (without asbestos fibers).		
2. Aluminum Paint		

DIVISION 5: EXTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE		
MPI REX 10.2D		
Primer: MPI 107	Intermediate: MPI 1	Topcoat: MPI 1
System DFT: 3.5 mils		
K. Surfaces adjacent to painted surfaces; Mechanical, Electrical, Fire extinguishing sprinkler systems including valves, conduit, hangers, supports, exposed copper piping, and miscellaneous metal items not otherwise specified except floors, hot metal surfaces, and new prefinished equipment. Match surrounding finish:		
1. Alkyd		
MPI EXT 5.1D-G1 (Flat)		
Primer: MPI 79	Intermediate: MPI 8	Topcoat: MPI 8
System DFT: 5.25 mils		
MPI EXT 5.1D-G5 (Semigloss)		
Primer: MPI 79	Intermediate: MPI 94	Topcoat: MPI 94
System DFT: 5.25 mils		
MPI EXT 5.1D-G6 (Gloss)		
Primer: MPI 79	Intermediate: MPI 9	Topcoat: MPI 9
System DFT: 5.25 mils		
2. Waterborne Light Industrial Coating		
MPI EXT 5.1C-G3 (Eggshell)		
Primer: MPI 79	Intermediate: MPI 161	Topcoat: MPI 161
System DFT: 5 mils		
MPI EXT 5.1C-G5 (Semigloss)		

DIVISION 5: EXTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE		
Primer: MPI 79	Intermediate: MPI 163	Topcoat: MPI 163
System DFT: 5 mils		
MPI EXT 5.1C-G6 (Gloss)		
Primer: MPI 79	Intermediate: MPI 164	Topcoat: MPI 164
System DFT: 5 mils		
L. Hot metal surfaces including smokestacks subject to temperatures up to 400 degrees F.		
1. Heat Resistant Enamel		
MPI EXT 5.2A		
Primer: MPI 21	Intermediate: Surface preparation and number of coats per manufacturer's instructions.	Topcoat: Surface preparation and number of coats per manufacturer's instructions.
System DFT: Per Manufacturer		
M. Ferrous metal subject to high temperature, up to 750 degrees F:		
1. Inorganic Zinc Rich Coating		
MPI EXT 5.2C		
Primer: MPI 19	Intermediate: Surface preparation and number of coats per manufacturer's instructions.	Topcoat: Surface preparation and number of coats per manufacturer's instructions.
System DFT: Per Manufacturer		
2. Heat Resistant Aluminum Enamel		
MPI EXT 5.2B (Aluminum Finish)		

DIVISION 5: EXTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE		
Primer: MPI 2	Intermediate: Surface preparation and number of coats per manufacturer's instructions.	Topcoat: Surface preparation and number of coats per manufacturer's instructions.
System DFT: Per Manufacturer		
N. New surfaces and Existing surfaces made bare cleaning to SSPC SP 10/NACE No. 2 subject to temperatures up to 1100 degrees F:		
1. Heat Resistant Coating		
MPI EXT 5.2D		
Primer: MPI 22	Intermediate: Surface preparation and number of coats per manufacturer's instructions.	Topcoat: Surface preparation and number of coats per manufacturer's instructions.
System DFT: Per Manufacturer		

DIVISION 6: EXTERIOR WOOD; DRESSED LUMBER, PANELING, DECKING, SHINGLES PAINT TABLE		
A. New and existing, uncoated Dressed lumber, Wood and plywood, trim, including top, bottom and edges of doors not otherwise specified:		
1. Alkyd		
MPI EXT 6.3B-G5 (Semigloss)		
Primer: MPI 7	Intermediate: MPI 94	Topcoat: MPI 94
System DFT: 5 mils		
MPI EXT 6.3B-G6 (Gloss)		
Primer: MPI 7	Intermediate: MPI 9	Topcoat: MPI 9
System DFT: 5 mils		

DIVISION 6: EXTERIOR WOOD; DRESSED LUMBER, PANELING, DECKING, SHINGLES PAINT TABLE		
2. Latex		
MPI EXT 6.3A-G1 (Flat)		
Primer: MPI 7	Intermediate: MPI 10	Topcoat: MPI 10
MPI EXT 6.3A-G5 (Semigloss)		
Primer: MPI 7	Intermediate: MPI 11	Topcoat: MPI 11
System DFT: 5 mils		
MPI EXT 6.3A-G6 (Gloss)		
Primer: MPI 7	Intermediate: MPI 119	Topcoat: MPI 119
System DFT: 5 mils		
3. Waterborne Solid Color Stain		
MPI EXT 6.3K		
Primer: MPI 7	Intermediate: MPI 16	Topcoat: MPI 16
System DFT: 4.25 mils		
B. Existing, dressed lumber, Wood and plywood, trim including top, bottom and edges of doors previously coated with an alkyd / oil based finish coat not otherwise specified:		
1. Alkyd		
MPI REX 6.3B-G5 (Semigloss)		
Primer: MPI 5	Intermediate: MPI 94	Topcoat: MPI 94
System DFT: 5 mils		
MPI REX 6.3B-G6 (Gloss)		
Primer: MPI 5	Intermediate: MPI 9	Topcoat: MPI 9
System DFT: 5 mils		
2. Latex		
MPI REX 6.3A-G1 (Flat)		

DIVISION 6: EXTERIOR WOOD; DRESSED LUMBER, PANELING, DECKING, SHINGLES PAINT TABLE		
Primer: MPI 5	Intermediate: MPI 10	Topcoat: MPI 10
System DFT: 5 mils		
MPI REX 6.3A-G5 (Semigloss)		
Primer: MPI 5	Intermediate: MPI 11	Topcoat: MPI 11
System DFT: 5 mils		
MPI REX 6.3A-G6 (Gloss)		
Primer: MPI 5	Intermediate: MPI 119	Topcoat: MPI 119
System DFT: 5 mils		
C. Existing, dressed lumber, Wood and plywood, trim, including top, bottom and edges of doors previously coated with a latex / waterborne finish coat not otherwise specified:		
1. Latex		
MPI REX 6.3L-G1 (Flat)		
Primer: MPI 6	Intermediate: MPI 10	Topcoat: MPI 10
System DFT: 5 mils		
MPI REX 6.3L-G5 (Semigloss)		
Spot Primer: MPI 6	Intermediate: MPI 11	Topcoat: MPI 11
System DFT: 4.5 mils		
MPI REX 6.3L-G6 (Gloss)		
Spot Primer: MPI 6	Intermediate: MPI 119	Topcoat: MPI 119
System DFT: 4.5 mils		
2. Waterborne Solid Color Stain		
MPI REX 6.3K (Stain)		
Spot Primer: MPI 6	Intermediate: MPI 16	Topcoat: MPI 16
System DFT: 4 mils		
D. New, Uncoated wood siding:		

DIVISION 6: EXTERIOR WOOD; DRESSED LUMBER, PANELING, DECKING, SHINGLES PAINT TABLE		
1. Semi-Transparent Stain		
MPI EXT 6.3D		
Spot Primer: N/A	Intermediate: MPI 13	Topcoat: MPI 13
System DFT: N/A		
E. Existing, previously stained wood siding:		
1. Latex		
MPI REX 6.2K-G1 (Flat)		
Primer: MPI 5	Intermediate: MPI 10	Topcoat: MPI 10
System DFT: 4.5 mils		
MPI REX 6.2K-G5 (Semigloss)		
Primer: MPI 5	Intermediate: MPI 11	Topcoat: MPI 11
System DFT: 4.5 mils		
F. Existing Uncoated or previously semitransparent stained wood siding:		
1. Semi-Transparent Stain		
MPI REX 6.3D		
Spot Primer: N/A	Intermediate: MPI 13	Topcoat: MPI 13
System DFT: Per Manufacturer		
G. Wood: Steps, platforms, floors of open porches, and with non-skid additive (NSA), load at manufacturer's recommendations.:		
1. Latex Floor Paint		
MPI EXT 6.3A-G2 (Flat)		
Primer: MPI 5	Intermediate: MPI 60 plus NSA	Topcoat: MPI 60 plus NSA
System DFT: 4.5 mils		
MPI EXT 6.5A-G6 (Gloss)		

DIVISION 6: EXTERIOR WOOD; DRESSED LUMBER, PANELING, DECKING, SHINGLES PAINT TABLE		
Primer: MPI 5	Intermediate: MPI 68 plus NSA	Topcoat: MPI 68 plus NSA
System DFT: 4.5 mils		
2. Alkyd Floor Paint		
MPI EXT 6.5B-G2 (Flat)		
Primer: MPI 59	Intermediate: MPI 59 plus NSA	Topcoat: MPI 59 plus NSA
System DFT: 5 mils		
MPI EXT 6.5B-G6 (Gloss)		
Primer: MPI 27	Intermediate: MPI 27 plus NSA	Topcoat: MPI 27 plus NSA
System DFT: 5 mils		

DIVISION 9: EXTERIOR STUCCO PAINT TABLE		
A. New and Existing stucco:		
1. Latex		
New; MPI EXT 9.1A-G1 (Flat) / Existing; MPI REX 9.1A-G2 (Flat)		
Primer: MPI 10	Intermediate: MPI 10	Topcoat: MPI 10
System DFT: 4.5 mils		
New; MPI EXT 9.1A-G5 (Semigloss) / Existing; MPI REX 9.1A-G5 (Semigloss)		
Primer: MPI 11	Intermediate: MPI 11	Topcoat: MPI 11
System DFT: 4.5 mils		
New; MPI EXT 9.1A-G6 (Gloss) / Existing; MPI REX 9.1A-G6 (Gloss)		

DIVISION 9: EXTERIOR STUCCO PAINT TABLE		
Primer: MPI 119	Intermediate: MPI 119	Topcoat: MPI 119
System DFT: 4.5 mils		
Primer as recommended by manufacturer. Topcoat: Coating to match adjacent surfaces. On existing stucco, apply primer based on surface condition.		
B. New and Existing stucco, elastomeric system:		
1. Elastomeric Coating		
New; MPI EXT 9.1C / Existing; MPI REX 9.1C		
Primer: See note below.	Intermediate: MPI 113	Topcoat: MPI 113
System DFT: 16 mils		
Provide Primer recommended by manufacturer. Topcoat: Coating to match adjacent surfaces. Surface preparation, primer and 2 coats in accordance with manufacturer's instructions.		
NOTE: Apply sufficient coats of MPI 113 to achieve a minimum dry film thickness of 16 mils.		

DIVISION 10: EXTERIOR CLOTH COVERINGS AND BITUMINOUS COATED SURFACES PAINT TABLE		
A. Insulation and surfaces of insulation coverings (canvas, cloth, paper): (Interior and Exterior Applications)		
1. Latex		
MPI EXT 10.1A-G1 (Flat)		
Primer: N/A	Intermediate: MPI 10	Topcoat: MPI 10
System DFT: 3.2 mils		
MPI EXT 10.1A-G5 (Semigloss)		
Primer: N/A	Intermediate: MPI 11	Topcoat: MPI 11

DIVISION 10: EXTERIOR CLOTH COVERINGS AND BITUMINOUS COATED SURFACES PAINT TABLE		
System DFT: 3.2 mils		
MPI EXT 10.1A-G6 (Gloss)		
Primer: N/A	Intermediate: MPI 119	Topcoat: MPI 119
System DFT: 3.2 mils		
Topcoat: Coating to match adjacent surfaces.		

3.15.2 INTERIOR PAINT TABLES

DIVISION 3: INTERIOR CONCRETE PAINT TABLE		
A. New and uncoated existing and Existing, previously painted concrete; vertical surfaces, not specified otherwise:		
1. Latex		
New; MPI INT 3.1A-G2 (Flat) / Existing; MPI RIN 3.1A-G2 (Flat)		
Primer: MPI 50	Intermediate: MPI 44	Topcoat: MPI 44
System DFT: 4 mils		
New; MPI INT 3.1A-G3 (Eggshell) / Existing; MPI RIN 3.1A-G3 (Eggshell)		
Primer: MPI 50	Intermediate: MPI 52	Topcoat: MPI 52
New; MPI INT 3.1A-G5 (Semigloss) / Existing; MPI RIN 3.1A-G5 (Semigloss)		
Primer: MPI 50	Intermediate: MPI 54	Topcoat: MPI 54
System DFT: 4 mils		
2. High Performance Architectural Latex		
New; MPI INT 3.1C-G2 (Flat) / Existing; MPI RIN 3.1J-G2 (Flat)		
Primer: MPI 50	Intermediate: MPI 138	Topcoat: MPI 138
System DFT: 4 mils		
New; MPI INT 3.1C-G3 (Eggshell) / Existing; MPI RIN 3.1J-G3 (Eggshell)		

DIVISION 3: INTERIOR CONCRETE PAINT TABLE		
Primer: MPI 50	Intermediate: MPI 139	Topcoat: MPI 139
System DFT: 4 mils		
New; MPI INT 3.1C-G4 (Satin) / Existing; MPI RIN 3.1J-G4		
Primer: MPI 50	Intermediate: MPI 140	Topcoat: MPI 140
System DFT: 4 mils		
New; MPI INT 3.1C-G5 (Semigloss) / Existing; MPI RIN 3.1J-G5 (Semigloss)		
Primer: MPI 50	Intermediate: MPI 141	Topcoat: MPI 141
System DFT: 4 mils		
3. Institutional Low Odor / Low VOC Latex		
New; MPI INT 3.1M-G2 (Flat) / Existing; MPI RIN 3.1L-G2 (Flat)		
Primer: MPI 50	Intermediate: MPI 144	Topcoat: MPI 144
System DFT: 4 mils		
New; MPI INT 3.1M-G3 (Eggshell) / Existing; MPI RIN 3.1L-G3 (Eggshell)		
Primer: MPI 50	Intermediate: MPI 145	Topcoat: MPI 145
System DFT: 4 mils		
New; MPI INT 3.1M-G4 (Satin) / Existing; MPI RIN 3.1L-G4		
Primer: MPI 50	Intermediate: MPI 146	Topcoat: MPI 146
System DFT: 4 mils		
New; MPI INT 3.1M-G5 (Semigloss) / Existing; MPI RIN 3.1L-G5 (Semogloss)		
Primer: MPI 50	Intermediate: MPI 147	Topcoat: MPI 147
System DFT: 4 mils		
B. Concrete ceilings, uncoated:		
1. Latex Aggregate		
MPI INT 3.1N		
Primer: N/A	Intermediate: N/A	Topcoat: MPI 42
System DFT: Per Manufacturer		

DIVISION 3: INTERIOR CONCRETE PAINT TABLE		
Texture - Fine Medium Coarse. Surface preparation, number of coats, and primer in accordance with manufacturer's instructions. Topcoat: Coating to match adjacent surfaces.		
C. New and uncoated existing and Existing, previously painted Concrete in toilets, food-preparation, food-serving, restrooms, laundry areas, shower areas, areas requiring a high degree of sanitation, _____ and other high-humidity areas not otherwise specified except floors:		
1. Waterborne Light Industrial Coating		
New; MPI INT 3.1L-G3 (Eggshell) / Existing; MPI RIN 3.1C-G3 (Eggshell)		
Primer: MPI 151	Intermediate: MPI 151	
System DFT: 4.8 mils		
New; MPI INT 3.1L-G5 (Semigloss) / Existing; MPI RIN 3.1C-G5 (Semigloss)		
Primer: MPI 153	Intermediate: MPI 153	Topcoat: MPI 153
System DFT: 4.8 mils		
New; MPI INT 3.1L-G6 (Gloss) / Existing; MPI RIN 3.1C-G6 (Gloss)		
Primer: MPI 154	Intermediate: MPI 154	Topcoat: MPI 154
System DFT: 4.8 mils		
2. Alkyd		
New; MPI INT 3.1D-G3 (Eggshell) / Existing; RIN 3.1D-G3 (Eggshell)		
Primer: MPI 50	Intermediate: MPI 51	Topcoat: MPI 51
System DFT: 4.5 mils		
New; MPI INT 3.1D-G5 (Semigloss) / Existing; RIN 3.1D-G5 (Semigloss)		
Primer: MPI 50	Intermediate: MPI 47	Topcoat: MPI 47
System DFT: 4.5 mils		
New; MPI INT 3.1D-G6 (Gloss) / Existing; RIN 3.1D-G6 (Gloss)		
Primer: MPI 50	Intermediate: MPI 48	Topcoat: MPI 48
System DFT: 4.5 mils		

DIVISION 3: INTERIOR CONCRETE PAINT TABLE		
3. Epoxy		
New; MPI INT 3.1F-G6 (Gloss) / Existing; MPI RIN 3.1E-G6 (Gloss)		
Primer: MPI 77	Intermediate: MPI 77	Topcoat: MPI 77
System DFT: 4 mils		
Note: Primer may be reduced for penetration per manufacturer's instructions.		
D. New and uncoated existing and Existing, previously painted concrete: walls and bottom of swimming pools.		
1. Chlorinated Rubber		
Primer: SSPC Paint 18	Intermediate: SSPC Paint 18	Topcoat: SSPC Paint 18
System DFT: Per Manufacturer		
Note: Primer may be reduced for penetration per manufacturer's instructions.		
2. Epoxy		
New; MPI INT 3.1F / Existing; MPI RIN 3.1E		
Primer: MPI 77	Intermediate: MPI 77	Topcoat: MPI 77
System DFT: 4 mils		
Note: Primer may be reduced for penetration per manufacturer's instructions.		
E. New and uncoated existing and Existing, previously painted concrete floors in following areas _____:		
1. Latex Floor Paint		
New; MPI INT 3.2A-G2 (Flat) / Existing; MPI RIN 3.3A-G2 (Flat)		
Primer: MPI 60	Intermediate: MPI 60	Topcoat: MPI 60
System DFT: 5 mils		
2. Alkyd Floor Paint		
New; MPI INT 3.2B-G2 (Flat) / Existing; MPI RIN 3.2B-G2 (Flat)		
Primer: MPI 59	Intermediate: MPI 59	Topcoat: MPI 59

DIVISION 3: INTERIOR CONCRETE PAINT TABLE		
System DFT: 5 mils		
3. Epoxy		
New; MPI INT 3.2C-G6 (Gloss) / Existing; MPI REX 3.2C-G6 (Gloss)		
Primer: MPI 77	Intermediate: MPI 77	Topcoat: MPI 77
System DFT: 5 mils		
Note: Primer may be reduced for penetration per manufacturer's instructions.		

DIVISION 4: INTERIOR CONCRETE MASONRY UNITS PAINT TABLE			
A. New and uncoated Existing Concrete masonry:			
1. High Performance Architectural Latex			
MPI INT 4.2D-G2 (Flat)			
Filler: MPI 4	Primer: N/A	Intermediate: MPI 138	Topcoat: MPI 138
System DFT: 11 mils			
MPI INT 4.2D-G3 (Eggshell)			
Filler: MPI 4	Primer: N/A	Intermediate: MPI 139	
System DFT: 11 mils			
MPI INT 4.2D-G4 (Satin)			
Filler: MPI 4	Primer: N/A	Intermediate: MPI 140	Topcoat: MPI 140
System DFT: 11 mils			
MPI INT 4.2D-G5 (Semigloss)			
Filler: MPI 4	Primer: N/A	Intermediate: MPI 141	Topcoat: MPI 141

DIVISION 4: INTERIOR CONCRETE MASONRY UNITS PAINT TABLE			
System DFT: 11 mils			
Fill all holes in masonry surface			
2. Institutional Low Odor / Low VOC Latex			
New; MPI INT 4.2E-G2 (Flat)			
Filler: MPI 4	Primer: N/A	Intermediate: MPI 144	
System DFT: 4 mils			
New; MPI INT 4.2E-G3 (Eggshell)			
Filler: MPI 4	Primer: N/A	Intermediate: MPI 145	Topcoat: MPI 145
System DFT: 4 mils			
New; MPI INT 4.2E-G4 (Satin)			
Filler: MPI 4	Primer: N/A	Intermediate: MPI 146	
System DFT: 4 mils			
New; MPI INT 4.2E-G5 (Semigloss)			
Filler: MPI 4	Primer: N/A	Intermediate: MPI 147	Topcoat: MPI 147
System DFT: 4 mils			
B. Existing, previously painted Concrete masonry:			
1. High Performance Architectural Latex			
MPI RIN 4.2K-G2 (Flat)			
Spot Primer: MPI 50	Intermediate: MPI 138		Topcoat: MPI 138

DIVISION 4: INTERIOR CONCRETE MASONRY UNITS PAINT TABLE		
System DFT: 4.5 mils		
MPI RIN 4.2K-G3 (Eggshell)		
Spot Primer: MPI 50	Intermediate: MPI 139	Topcoat: MPI 139
System DFT: 4.5 mils		
MPI RIN 4.2K-G4		
Spot Primer: MPI 50	Intermediate: MPI 140	Topcoat: MPI 140
System DFT: 4.5 mils		
MPI RIN 4.2K-G5 (Semigloss)		
Spot Primer: MPI 50	Intermediate: MPI 141	Topcoat: MPI 141
System DFT: 4.5 mils		
2. Institutional Low Odor / Low VOC Latex		
Existing; MPI RIN 4.2L-G2 (Flat)		
Spot Primer: MPI 50	Intermediate: MPI 144	Topcoat: MPI 144
System DFT: 4 mils		
Existing; MPI RIN 4.2L-G3 (Eggshell)		
Spot Primer: MPI 50	Intermediate: MPI 145	
System DFT: 4 mils		
Existing; MPI RIN 4.2L-G4 (Satin)		
Spot Primer: MPI 50	Intermediate: MPI 146	Topcoat: MPI 146
System DFT: 4 mils		
Existing; MPI RIN 4.2L-G5 (Semigloss)		
Spot Primer: MPI 50	Intermediate: MPI 147	Topcoat: MPI 147

DIVISION 4: INTERIOR CONCRETE MASONRY UNITS PAINT TABLE			
System DFT: 4 mils			
C. New and uncoated Existing Concrete masonry units in toilets, food-preparation, food-serving, restrooms, laundry areas, shower areas, areas requiring a high degree of sanitation, _____, and other high humidity areas unless otherwise specified:			
1. Waterborne Light Industrial Coating			
MPI INT 4.2K-G3(Eggshell)			
Filler: MPI 4	Primer: N/A	Intermediate: MPI 151	Topcoat: MPI 151
System DFT: 11 mils			
MPI INT 4.2K-G5(Semigloss)			
Filler: MPI 4	Primer: N/A	Intermediate: MPI 153	Topcoat: MPI 153
System DFT: 11 mils			
MPI INT 4.2K-G6(Gloss)			
Filler: MPI 4	Primer: N/A	Intermediate: MPI 154	Topcoat: MPI 154
System DFT: 11 mils			
Fill all holes in masonry surface			
2. Alkyd			
MPI INT 4.2N-G3 (Eggshell)			
Filler: MPI 4	Primer: MPI 50	Intermediate: MPI 51	Topcoat: MPI 51
System DFT: 12 mils			
MPI INT 4.2N-G5 (Semigloss)			
Filler: MPI 4	Primer: MPI 50	Intermediate: MPI 47	Topcoat: MPI 47
System DFT: 12 mils			

DIVISION 4: INTERIOR CONCRETE MASONRY UNITS PAINT TABLE

MPI INT 4.2N-G6 (Gloss)			
Filler: MPI 4	Primer: MPI 50	Intermediate: MPI 48	Topcoat: MPI 48
System DFT: 12 mils			
Fill all holes in masonry surface			
3. Epoxy			
Filler: MPI 116	Primer: N/A	Intermediate: MPI 77	Topcoat: MPI 77
System DFT: 10 mils			
Fill all holes in masonry surface			
D. Existing, previously painted, concrete masonry units in toilets, food-preparation, food-serving, restrooms, laundry areas, shower areas, areas requiring a high degree of sanitation, , and other high humidity areas unless otherwise specified:			
1. Waterborne Light Industrial Coating			
MPI RIN 4.2G-G3(Eggshell)			
Spot Primer: MPI 151	Intermediate: MPI 151		Topcoat: MPI 151
System DFT: 4.5 mils			
MPI RIN 4.2G-G5(Semigloss)			
Spot Filler: MPI 153	Intermediate: MPI 153		Topcoat: MPI 153
System DFT: 4.5 mils			
MPI RIN 4.2G-G6(Gloss)			
Spot Primer: MPI 154	Intermediate: MPI 154		Topcoat: MPI 154
System DFT: 4.5 mils			
2. Alkyd			
MPI RIN 4.2C-G3 (Eggshell)			

DIVISION 4: INTERIOR CONCRETE MASONRY UNITS PAINT TABLE		
Spot Primer: MPI 50	Intermediate: MPI 51	Topcoat: MPI 51
System DFT: 4.5 mils		
MPI RIN 4.2C-G5 (Semigloss)		
Spot Primer: MPI 50	Intermediate: MPI 47	Topcoat: MPI 47
System DFT: 4.5 mils		
MPI RIN 4.2C-G6 (Gloss)		
Spot Primer: MPI 50	Intermediate: MPI 48	Topcoat: MPI 48
System DFT: 4.5 mils		
3. Epoxy		
MPI RIN 4.2D-G6 (Gloss)		
Spot Primer: MPI 77	Intermediate: MPI 77	Topcoat: MPI 77
System DFT: 5 mils		

DIVISION 5: INTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE		
<u>INTERIOR STEEL / FERROUS SURFACES</u>		
A. Metal, Mechanical, Electrical, Fire extinguishing sprinkler systems including valves, conduit, hangers, supports, Surfaces adjacent to painted surfaces (Match surrounding finish), exposed copper piping, and miscellaneous metal items not otherwise specified except floors, hot metal surfaces, and new prefinished equipment:		
1. High Performance Architectural Latex		
MPI INT 5.1R-G2 (Flat)		
Primer: MPI 138	Intermediate: MPI 138	Topcoat: MPI 138

DIVISION 5: INTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE		
<u>INTERIOR STEEL / FERROUS SURFACES</u>		
System DFT: 5 mils		
MPI INT 5.1R-G3 (Eggshell)		
Primer: MPI 79	Intermediate: MPI 139	Topcoat: MPI 139
System DFT: 5 mils		
MPI INT 5.1R-G5 (Semigloss)		
Primer: MPI 79	Intermediate: MPI 141	Topcoat: MPI 141
System DFT: 5 mils		
2. Alkyd		
MPI INT 5.1E-G2 (Flat)		
Primer: MPI 79	Intermediate: MPI 49	Topcoat: MPI 49
System DFT: 5.25 mils		
MPI INT 5.1E-G3 (Eggshell)		
Primer: MPI 79	Intermediate: MPI 51	Topcoat: MPI 51
System DFT: 5.25 mils		
MPI INT 5.1E-G5 (Semigloss)		
Primer: MPI 79	Intermediate: MPI 47	Topcoat: MPI 47
System DFT: 5.25 mils		
MPI INT 5.1E-G6 (Gloss)		
Primer: MPI 79	Intermediate: MPI 48	Topcoat: MPI 48
System DFT: 5.25 mils		
B. Metal floors (non-shop-primed surfaces or non-slip deck surfaces) with non-skid additive (NSA), load at manufacturer's recommendations:		
1. Alkyd Floor Paint		
MPI INT 5.1U-G6 (Gloss)		

DIVISION 5: INTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE		
<u>INTERIOR STEEL / FERROUS SURFACES</u>		
Primer: MPI 79	Intermediate: MPI 27	Topcoat: MPI 27 (plus NSA)
System DFT: 5.25 mils		
2. Epoxy		
MPI INT 5.1L-G6 (Gloss)		
Primer: MPI 101	Intermediate: MPI 77	Topcoat: MPI 77 (plus NSA)
System DFT: 5.25 mils		
C. Metal in toilets, food-preparation, food-serving, restrooms, laundry areas, shower areas, areas requiring a high degree of sanitation, _____, and other high-humidity areas not otherwise specified except floors, hot metal surfaces, and new prefinished equipment:		
1. Alkyd		
MPI INT 5.1E-G3 (Eggshell)		
Primer: MPI 79	Intermediate: MPI 51	Topcoat: MPI 51
System DFT: 5.25 mils		
MPI INT 5.1E-G5 (Semigloss)		
Primer: MPI 79	Intermediate: MPI 47	Topcoat: MPI 47
System DFT: 5.25 mils		
MPI INT 5.1E-G6 (Gloss)		
Primer: MPI 79	Intermediate: MPI 48	Topcoat: MPI 48
System DFT: 5.25 mils		
2. Alkyd		
MPI INT 5.1T-G3 (Eggshell) For hand tool cleaning		
Primer: MPI 23	Intermediate: MPI 51	Topcoat: MPI 51
System DFT: 5.25 mils		
MPI INT 5.1T-G5 (Semigloss)		

DIVISION 5: INTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE		
<u>INTERIOR STEEL / FERROUS SURFACES</u>		
Primer: MPI 23	Intermediate: MPI 47	Topcoat: MPI 47
System DFT: 5.25 mils		
MPI INT 5.1T-G6 (Gloss)		
Primer: MPI 23	Intermediate: MPI 48	Topcoat: MPI 48
System DFT: 5.25 mils		
D. Ferrous metal in concealed damp spaces or in exposed areas having unpainted adjacent surfaces as follows:		
1. Aluminum Paint		
MPI INT 5.1M		
Primer: MPI 79	Intermediate: MPI 1	Topcoat: MPI 1
System DFT: 4.25 mils		
E. Miscellaneous non-ferrous metal items not otherwise specified except floors, hot metal surfaces, and new prefinished equipment. Match surrounding finish:		
1. High Performance Architectural Latex		
MPI INT 5.4F-G2 (Flat)		
Primer: MPI 95	Intermediate: MPI 138	Topcoat: MPI 138
System DFT: 5 mils		
MPI INT 5.4F-G3 (Eggshell)		
Primer: MPI 95	Intermediate: MPI 139	Topcoat: MPI 139
System DFT: 5 mils		
MPI INT 5.4F-G4 (Satin)		
Primer: MPI 95	Intermediate: MPI 140	Topcoat: MPI 140
System DFT: 5 mils		
MPI INT 5.4F-G5 (Semigloss)		

DIVISION 5: INTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE		
<u>INTERIOR STEEL / FERROUS SURFACES</u>		
Primer: MPI 95	Intermediate: MPI 141	Topcoat: MPI 141
System DFT: 5 mils		
2. Alkyd		
MPI INT 5.4J-G2 (Flat)		
Primer: MPI 95	Intermediate: MPI 49	Topcoat: MPI 49
System DFT: 5 mils		
MPI INT 5.4J-G3 (Eggshell)		
Primer: MPI 95	Intermediate: MPI 51	Topcoat: MPI 51
System DFT: 5 mils		
MPI INT 5.4J-G5 (Semigloss)		
Primer: MPI 95	Intermediate: MPI 47	Topcoat: MPI 47
System DFT: 5 mils		
MPI INT 5.4J-G6 (Gloss)		
Primer: MPI 95	Intermediate: MPI 48	Topcoat: MPI 48
System DFT: 5 mils		
F. Hot metal surfaces including smokestacks subject to temperatures up to 400 degrees F:		
1. Heat Resistant Enamel		
MPI INT 5.2A		
Primer: MPI 21	Intermediate: Surface preparation and number of coats per manufacturer's instructions.	Topcoat: Surface preparation and number of coats per manufacturer's instructions.

DIVISION 5: INTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE		
<u>INTERIOR STEEL / FERROUS SURFACES</u>		
System DFT: Per Manufacturer		
G. Ferrous metal subject to high temperature, up to 750 degrees F:		
1. Inorganic Zinc Rich Coating		
MPI INT 5.2C		
Primer: MPI 19	Intermediate: Surface preparation and number of coats per manufacturer's instructions.	Topcoat: Surface preparation and number of coats per manufacturer's instructions.
System DFT: Per Manufacturer		
2. Heat Resistant Aluminum Paint		
MPI INT 5.2B (Aluminum Finish)		
Primer: MPI 2	Intermediate: Surface preparation and number of coats per manufacturer's instructions.	Topcoat: Surface preparation and number of coats per manufacturer's instructions.
System DFT: Per Manufacturer		
H. New surfaces and made bare cleaning to SSPC SP 10/NACE No. 2 subject to temperatures up to 1100 degrees F:		
1. High Heat Resistant Coating		
MPI INT 5.2D		
Primer: MPI 22	Intermediate: Surface preparation and number of coats per manufacturer's instructions.	Topcoat: Surface preparation and number of coats per manufacturer's instructions.
System DFT: Per Manufacturer		

DIVISION 6: INTERIOR WOOD PAINT TABLE		
A. New and Existing, uncoated Wood and plywood not otherwise specified:		
1. High Performance Architectural Latex		
MPI INT 6.4S-G3 (Eggshell)		
Primer: MPI 39	Intermediate: MPI 139	Topcoat: MPI 139
System DFT: 4.5 mils		
MPI INT 6.4S-G4 (Satin)		
Primer: MPI 39	Intermediate: MPI 140	Topcoat: MPI 140
System DFT: 4.5 mils		
MPI INT 6.4S-G5 (Semigloss)		
Primer: MPI 39	Intermediate: MPI 141	Topcoat: MPI 141
System DFT: 4.5 mils		
2. Alkyd		
MPI INT 6.4B-G3 (Eggshell)		
Primer: MPI 45	Intermediate: MPI 51	Topcoat: MPI 51
System DFT: 4.5 mils		
MPI INT 6.4B-G5 (Semigloss)		
Primer: MPI 45	Intermediate: MPI 47	Topcoat: MPI 47
System DFT: 4.5 mils		
MPI INT 6.4B-G6 (Gloss)		
Primer: MPI 45	Intermediate: MPI 48	Topcoat: MPI 48
System DFT: 4.5 mils		
3. Institutional Low Odor / Low VOC Latex		
New; MPI INT 6.3V-G2 (Flat)		

DIVISION 6: INTERIOR WOOD PAINT TABLE		
Primer: MPI 39	Intermediate: MPI 144	Topcoat: MPI 144
System DFT: 4 mils		
New; MPI INT 6.3V-G3 (Eggshell)		
Primer: MPI 39	Intermediate: MPI 145	Topcoat: MPI 145
System DFT: 4 mils		
New; MPI INT 6.3V-G4		
Primer: MPI 39	Intermediate: MPI 146	Topcoat: MPI 146
System DFT: 4 mils		
New; MPI INT 6.3V-G5 (Semigloss)		
Primer: MPI 39	Intermediate: MPI 147	Topcoat: MPI 147
System DFT: 4 mils		
B. Existing, previously painted Wood and plywood not otherwise specified:		
1. High Performance Architectural Latex		
MPI RIN 6.4B-G3 (Eggshell)		
Primer: MPI 46	Intermediate: MPI 139	Topcoat: MPI 139
System DFT: 4.5 mils		
MPI RIN 6.4B-G4 (Satin)		
Primer: MPI 46	Intermediate: MPI 140	Topcoat: MPI 140
System DFT: 4.5 mils		
MPI RIN 6.4B-G5 (Semigloss)		
Primer: MPI 46	Intermediate: MPI 141	Topcoat: MPI 141
System DFT: 4.5 mils		
2. Alkyd		
MPI RIN 6.4C-G3 (Eggshell)		
Primer: MPI 46	Intermediate: MPI 51	Topcoat: MPI 51

DIVISION 6: INTERIOR WOOD PAINT TABLE		
System DFT: 4.5 mils		
MPI RIN 6.4C-G5 (Semigloss)		
Primer: MPI 46	Intermediate: MPI 47	Topcoat: MPI 47
System DFT: 4.5 mils		
MPI RIN 6.4C-G6 (Gloss)		
Primer: MPI 46	Intermediate: MPI 48	Topcoat: MPI 48
System DFT: 4.5 mils		
3. Institutional Low Odor / Low VOC Latex		
Existing; MPI RIN 6.4D-G2 (Flat)		
Primer: MPI 39	Intermediate: MPI 144	Topcoat: MPI 144
System DFT: 4 mils		
Existing; MPI RIN 6.4D-G3 (Eggshell)		
Primer: MPI 39	Intermediate: MPI 145	Topcoat: MPI 145
System DFT: 4 mils		
Existing; MPI RIN 6.4D-G4		
Primer: MPI 39	Intermediate: MPI 146	Topcoat: MPI 146
System DFT: 4 mils		
Existing; MPI RIN 6.4D-G5 (Semigloss)		
Primer: MPI 39	Intermediate: MPI 147	Topcoat: MPI 147
System DFT: 4 mils		
C. New and Existing, previously finished or stained Wood and Plywood, except floors; natural finish or stained:		
1. Natural finish, oil-modified polyurethane		
New; MPI INT 6.4J-G4 / Existing; MPI RIN 6.4L-G4		
Primer: MPI 57	Intermediate: MPI 57	Topcoat: MPI 57
System DFT: 4 mils		

DIVISION 6: INTERIOR WOOD PAINT TABLE			
New; MPI INT 6.4J-G6 (Gloss) / Existing; MPI RIN 6.4L-G6 (Gloss)			
Primer: MPI 56	Intermediate: MPI 56	Topcoat: MPI 56	
System DFT: 4 mils			
2. Stained, oil-modified polyurethane			
New; MPI INT 6.4E-G4 / Existing; MPI RIN 6.4G-G4			
Stain: MPI 90	Primer: MPI 57	Intermediate: MPI 57	Topcoat: MPI 57
System DFT: 4 mils			
New; MPI INT 6.4E-G6 (Gloss) / Existing; MPI RIN 6.4G-G6 (Gloss)			
Stain: MPI 90	Primer: MPI 56	Intermediate: MPI 56	Topcoat: MPI 56
System DFT: 4 mils			
3. Stained, Moisture Cured Urethane			
New; MPI INT 6.4V-G2 (Flat) / Existing; MPI RIN 6.4V-G2 (Flat)			
Stain: MPI 90	Primer: MPI 71	Intermediate: MPI 71	Topcoat: MPI 71
System DFT: 4 mils			
New; MPI INT 6.4V-G6 (Gloss) / Existing; MPI RIN 6.4V-G6 (Gloss)			
Stain: MPI 90	Primer: MPI 31	Intermediate: MPI 31	Topcoat: MPI 31
System DFT: 4 mils			
D. New and Existing, previously finished or stained Wood Floors; Natural finish or stained:			
1. Natural finish, oil-modified polyurethane			
New; MPI INT 6.5C-G6 (Gloss) / Existing; MPI RIN 6.5C-G6 (Gloss)			
Primer: MPI 56	Intermediate: MPI 56	Topcoat: MPI 56	
System DFT: 4 mils			
2. Natural finish, Moisture Cured Polyurethane			

DIVISION 6: INTERIOR WOOD PAINT TABLE

New; MPI INT 6.5K-G6 (Gloss) / Existing; MPI RIN 6.5D-G6 (Gloss)			
Primer: MPI 31	Intermediate: MPI 31	Topcoat: MPI 31	
System DFT: 4 mils			
3. Stained, oil-modified polyurethane			
New; MPI INT 6.5B-G6 (Gloss) / Existing; MPI RIN 6.5B-G6 (Gloss)			
Stain: MPI 90	Primer: MPI 56	Intermediate: MPI 56	Topcoat: MPI 56
System DFT: 4 mils			
4. Stained, Moisture Cured Polyurethane			
New; MPI INT 6.5J-G6 (Gloss) / Existing; MPI RIN 6.5L-G6 (Gloss)			
Stain: MPI 90	Primer: MPI 31	Intermediate: MPI 31	Topcoat: MPI 31
System DFT: 4 mils			
E. New and Existing, previously coated Wood floors; pigmented finish:			
1. Latex Floor Paint			
New; MPI INT 6.5G-G2 (Flat) / Existing; MPI RIN 6.5J-G2 (Flat)			
Primer: MPI 45	Intermediate: MPI 60	Topcoat: MPI 60	
System DFT: 4.5 mils			
New; MPI INT 6.5G-G6 (Gloss) / Existing; MPI RIN 6.5J-G6 (Gloss)			
Primer: MPI 45	Intermediate: MPI 68	Topcoat: MPI 68	
System DFT: 4.5 mils			
2. Alkyd Floor Paint			
New; MPI INT 6.5A-G2 (Flat) / Existing; MPI RIN 6.5A-G2 (Flat)			
Primer: MPI 59	Intermediate: MPI 59	Topcoat: MPI 59	
System DFT: 4.5 mils			
New; MPI INT 6.5A-G6 (Gloss) / Existing; MPI RIN 6.5A-G6 (Gloss)			

DIVISION 6: INTERIOR WOOD PAINT TABLE		
Primer: MPI 27	Intermediate: MPI 27	Topcoat: MPI 27
System DFT: 4.5 mils		
F. New and Existing, uncoated wood surfaces in toilets, food-preparation, food-serving, restrooms, laundry areas, shower areas, areas requiring a high degree of sanitation, otherwise specified:		
1. As specified in Section 09 96 59 HIGH-BUILD GLAZE COATINGS.		
2. Waterborne Light Industrial		
MPI INT 6.3P-G5 (Semigloss)		
Primer: MPI 45	Intermediate: MPI 153	Topcoat: MPI 153
System DFT: 4.5 mils		
MPI INT 6.3P-G6 (Gloss)		
Primer: MPI 45	Intermediate: MPI 154	Topcoat: MPI 154
System DFT: 4.5 mils		
3. Alkyd		
MPI INT 6.3B-G5 (Semigloss)		
Primer: MPI 45	Intermediate: MPI 47	Topcoat: MPI 47
System DFT: 4.5 mils		
MPI INT 6.3B-G6 (Gloss)		
Primer: MPI 45	Intermediate: MPI 48	Topcoat: MPI 48
System DFT: 4.5 mils		
G. Existing, previously painted wood surfaces in toilets, food-preparation, food-serving, restrooms, laundry areas, shower areas, areas requiring a high degree of sanitation, otherwise specified:		
1. As specified in Section 09 96 59 HIGH-BUILD GLAZE COATINGS.		
2. Waterborne Light Industrial Coating		
MPI RIN 6.3P-G5 (Semigloss)		

DIVISION 6: INTERIOR WOOD PAINT TABLE		
Primer: MPI 46	Intermediate: MPI 153	Topcoat: MPI 153
System DFT: 4.5 mils		
MPI RIN 6.3P-G6 (Gloss)		
Primer: MPI 46	Intermediate: MPI 154	Topcoat: MPI 154
System DFT: 4.5 mils		
3. Alkyd		
MPI RIN 6.3B-G5 (Semigloss)		
Primer: MPI 46	Intermediate: MPI 47	Topcoat: MPI 47
System DFT: 4.5 mils		
MPI RIN 6.3B-G6 (Gloss)		
Primer: MPI 46	Intermediate: MPI 48	Topcoat: MPI 48
System DFT: 4.5 mils		
H. New and Existing, previously finished or stained Wood Doors; Natural Finish or Stained:		
1. Natural finish, oil-modified polyurethane		
New; MPI INT 6.3K-G4 / Existing; MPI RIN 6.3K-G4		
Primer: MPI 57	Intermediate: MPI 57	Topcoat: MPI 57
System DFT: 4 mils		
New; MPI INT 6.3K-G6 (Gloss) / Existing; MPI RIN 6.3K-G6 (Gloss)		
Primer: MPI 56	Intermediate: MPI 56	Topcoat: MPI 56
System DFT: 4 mils		
Note: Sand between all coats per manufacturers recommendations.		
2. Stained, oil-modified polyurethane		
New; MPI INT 6.3E-G4 / Existing; MPI RIN 6.3E-G4		

DIVISION 6: INTERIOR WOOD PAINT TABLE

Stain: MPI 90	Primer: MPI 57	Intermediate: MPI 57	Topcoat: MPI 57
System DFT: 4 mils			
New; MPI INT 6.3E-G6 (Gloss) / Existing; MPI RIN 6.3E-G6 (Gloss)			
Stain: MPI 90	Primer: MPI 56	Intermediate: MPI 56	Topcoat: MPI 56
System DFT: 4 mils			
Note: Sand between all coats per manufacturers recommendations.			
3. Stained, Moisture Cured Urethane			
New; MPI INT 6.4V-G2 (Flat) / Existing; MPI RIN 6.4V-G2 (Flat)			
Stain: MPI 90	Primer: MPI 71	Intermediate: MPI 71	Topcoat: MPI 71
System DFT: 4 mils			
New; MPI INT 6.4V-G6 (Gloss) / Existing; MPI RIN 6.4V-G6 (Gloss)			
Stain: MPI 90	Primer: MPI 31	Intermediate: MPI 31	Topcoat: MPI 31
System DFT: 4 mils			
Note: Sand between all coats per manufacturers recommendations.			
I. New and Existing, uncoated Wood Doors; Pigmented finish:			
1. Alkyd			
New; MPI INT 6.3B-G5 (Semigloss)			
Primer: MPI 45	Intermediate: MPI 47		Topcoat: MPI 47
System DFT: 4.5 mils			
New; MPI INT 6.3B-G6 (Gloss)			
Primer: MPI 45	Intermediate: MPI 48		Topcoat: MPI 48
System DFT: 4.5 mils			
Note: Sand between all coats per manufacturers recommendations.			
2. Pigmented Polyurethane			

DIVISION 6: INTERIOR WOOD PAINT TABLE		
New; MPI INT 6.1E-G6 (Gloss)		
Primer: MPI 72	Intermediate: MPI 72	Topcoat: MPI 72
System DFT: 4.5 mils		
Note: Sand between all coats per manufacturers recommendations.		
J. Existing, previously painted Wood Doors; Pigmented finish:		
1. Alkyd		
New; MPI RIN 6.3B-G5 (Semigloss)		
Primer: MPI 46	Intermediate: MPI 47	Topcoat: MPI 47
System DFT: 4.5 mils		
New; MPI RIN 6.3B-G6 (Gloss)		
Primer: MPI 46	Intermediate: MPI 48	Topcoat: MPI 48
System DFT: 4.5 mils		
Note: Sand between all coats per manufacturers recommendations.		

DIVISION 9: INTERIOR PLASTER, GYPSUM BOARD, TEXTURED SURFACES PAINT TABLE		
A. New and Existing, previously painted Plaster and Wallboard not otherwise specified:		
1. Latex		
New; MPI INT 9.2A-G2 (Flat) / Existing; RIN 9.2A-G2 (Flat)		
Primer: MPI 50	Intermediate: MPI 44	Topcoat: MPI 44
System DFT: 4 mils		
New; MPI INT 9.2A-G3 (Eggshell) / Existing; RIN 9.2A-G3 (Eggshell)		
Primer: MPI 50	Intermediate: MPI 52	Topcoat: MPI 52
System DFT: 4 mils		
New; MPI INT 9.2A-G5 (Semigloss) / Existing; RIN 9.2A-G5 (Semigloss)		
Primer: MPI 50	Intermediate: MPI 54	Topcoat: MPI 54

DIVISION 9: INTERIOR PLASTER, GYPSUM BOARD, TEXTURED SURFACES PAINT TABLE		
System DFT: 4 mils		
2. High Performance Architectural Latex - High Traffic Areas		
New; MPI INT 9.2B-G2 (Flat) / Existing; MPI RIN 9.2B-G2 (Flat)		
Primer: MPI 50	Intermediate: MPI 138	Topcoat: MPI 138
System DFT: 4 mils		
New; MPI INT 9.2B-G3 (Eggshell) / Existing; MPI RIN 9.2B-G3 (Eggshell)		
Primer: MPI 50	Intermediate: MPI 139	Topcoat: MPI 139
System DFT: 4 mils		
New; MPI INT 9.2B-G5 (Semigloss) / Existing; MPI RIN 9.2B-G5 (Semigloss)		
Primer: MPI 50	Intermediate: MPI 141	Topcoat: MPI 141
System DFT: 4 mils		
3. Institutional Low Odor / Low VOC Latex		
New; MPI INT 9.2M-G2 (Flat) / Existing; MPI RIN 9.2M-G2 (Flat)		
Primer: MPI 50	Intermediate: MPI 144	Topcoat: MPI 144
System DFT: 4 mils		
New; MPI INT 9.2M-G3 (Eggshell) / Existing; MPI RIN 9.2M-G3 (Eggshell)		
Primer: MPI 50	Intermediate: MPI 145	Topcoat: MPI 145
System DFT: 4 mils		
New; MPI INT 9.2M-G4 (Satin) / Existing; MPI RIN 9.2M-G4 (Satin)		
Primer: MPI 50	Intermediate: MPI 146	Topcoat: MPI 146
System DFT: 4 mils		
New; MPI INT 9.2M-G5 (Semigloss) / Existing; MPI RIN 9.2M-G5 (Semigloss)		
Primer: MPI 50	Intermediate: MPI 147	Topcoat: MPI 147
System DFT: 4 mils		

DIVISION 9: INTERIOR PLASTER, GYPSUM BOARD, TEXTURED SURFACES PAINT TABLE		
B. New and Existing, previously painted Plaster and Wallboard in toilets, food-preparation, food-serving, restrooms, laundry areas, shower areas, areas requiring a high degree of sanitation, _____ and other high humidity areas not otherwise specified:		
1. Waterborne Light Industrial Coating		
New; MPI INT 9.2L-G5 (Semigloss) / Existing; MPI RIN 9.2L-G5 (Semigloss)		
Primer: MPI 50	Intermediate: MPI 153	Topcoat: MPI 153
System DFT: 4 mils		
2. Alkyd		
New; MPI INT 9.2C-G5 (Semigloss) / Existing; MPI RIN 9.2C-G5 (Semigloss)		
Primer: MPI 50	Intermediate: MPI 47	Topcoat: MPI 47
System DFT: 4 mils		
3. Epoxy		
New; MPI INT 9.2E-G6 (Gloss) / Existing; MPI RIN 9.2D-G6 (Gloss)		
Primer: MPI 50	Intermediate: MPI 77	Topcoat: MPI 77
System DFT: 4 mils		

3.14 PROJECT PAINT SELECTOR GUIDE

Select paints from the above tables in accordance with the following instructions. For materials or surfaces not addressed herein, provide paint in accordance with manufacturer's recommendations applicable to the material, condition, location, and previous coatings (if any) on the surface in question.

3.14.1 EXTERIOR

As applicable:

Div. 3: Concrete

General application: Elastomeric Coating

Div. 4: Concrete Masonry Units

General application: Block filler, Elastomeric Coating

Div. 5: Metal, Ferrous, and Non-Ferrous

General application: Alkyd, gloss

Galvanized surfaces: Waterborne light industrial coating, gloss

Div. 6: Wood, Dressed Lumber, Paneling, Decking, Shingles

General application: Latex, gloss

Div. 9: Stucco

General application: Elastomeric Coating

Div. 10: Cloth (interior and exterior insulation coverings)

General application: Latex, semigloss

3.14.2 INTERIOR

Div. 3: Concrete

General application: High Performance Architectural Latex*, semigloss
*if existing surface has alkyd, use alkyd, semigloss

Concrete ceilings: Latex Aggregate, Medium Texture

Sanitary, restrooms, high humidity locations: Alkyd, gloss.

Concrete floors: Polish, apply hardener, Clean and Seal

Div. 4: Concrete Masonry Units

General application: Block filler, High Performance Architectural Latex, semigloss

Sanitary, restrooms, high humidity locations: Alkyd, gloss

Div. 5: Metal, Ferrous, and Non-Ferrous

General application: High Performance Architectural Latex, gloss

Metal floors: Alkyd, gloss

Sanitary, restrooms, high humidity locations: Alkyd, gloss

Div. 6: Wood

General application and Trim: High Performance Architectural Latex, semigloss

Stained: Natural finish, oil-modified polyurethane

Wood floors: See spec section for wood flooring

Sanitary, restrooms, high humidity locations: Alkyd, gloss

Wood doors: See spec section for wood doors (if applicable)

Div. 9: Plaster, Gypsum Board, Textured Surfaces

General application: High Performance Architectural Latex, eggshell

Sanitary, restrooms, high humidity locations: Alkyd, gloss

3.14.3 GENERAL PROJECT PAINTING NOTES

The PROJECT PAINT SELECTOR GUIDE is to be followed for locations and conditions as described. For locations, surfaces, or conditions not specifically addressed, select product that is most compatible to above selections and in accordance with manufacturer's written recommendations.

If multiple products are appropriate or if there is not a readily appropriate selection, contact the Contracting Officer for a final decision.

Colors are as indicated, see finish schedule, color schedule, and related notes. See Color Schedule on drawings. Contracting Officer reserves the right to select other colors from manufacturer's standard selections. Contracting Officer shall make final decision on colors.

Contractor shall provide exterior colors in accordance with Base Exterior Appearance Program (BEAP) guidelines. Contact Contracting Officer for BEAP info. Contracting Officers reserves the right to make other color choices.

-- End of Section --