

SECTION 09 90 00

PAINTS AND COATINGS

02/21

PART 1 GENERAL

1.1 RELATED REQUIREMENTS

1.1.1 Painting Included

Where a space or surface is indicated to be painted, include the following unless indicated otherwise.

- a. Surfaces behind portable objects and surface mounted articles readily detachable by removal of fasteners, such as screws and bolts.
- b. New factory finished surfaces that require identification or color coding and factory finished surfaces that are damaged during performance of the work.
- c. Existing coated surfaces that are damaged during performance of the work.

1.1.1.1 Exterior Painting

Includes new surfaces, existing coated surfaces, and existing uncoated surfaces, of the building and appurtenances. Also included are existing coated surfaces made bare by cleaning operations.

1.1.1.2 Interior Painting

Includes new surfaces, existing uncoated surfaces, and existing coated surfaces of the building and appurtenances as indicated and existing coated surfaces made bare by cleaning operations. Where a space or surface is indicated to be painted, include the following items, unless indicated otherwise.

1.2 REFERENCES

The publications listed below form a part of this specification to the extent referenced. The publications are referred to within the text by the basic designation only.

AMERICAN CONFERENCE OF GOVERNMENTAL INDUSTRIAL HYGIENISTS (ACGIH)

ACGIH 0100

(2017; Suppl 2020) Documentation of the
Threshold Limit Values and Biological
Exposure Indices

AMERICAN SOCIETY OF MECHANICAL ENGINEERS (ASME)

ASME A13.1

(2020) Scheme for the Identification of
Piping Systems

ASTM INTERNATIONAL (ASTM)

ASTM C920	(2018) Standard Specification for Elastomeric Joint Sealants
ASTM D235	(2002; R 2012) Mineral Spirits (Petroleum Spirits) (Hydrocarbon Dry Cleaning Solvent)
ASTM D523	(2014; R 2018) Standard Test Method for Specular Gloss
ASTM D2824/D2824M	(2018) Standard Specification for Aluminum-Pigmented Asphalt Roof Coatings, Non-Fibered, and Fibered without Asbestos
ASTM D4214	(2007; R 2015) Standard Test Method for Evaluating the Degree of Chalking of Exterior Paint Films
ASTM D4263	(1983; R 2018) Standard Test Method for Indicating Moisture in Concrete by the Plastic Sheet Method
ASTM D4444	(2013; R 2018) Standard Test Method for Laboratory Standardization and Calibration of Hand-Held Moisture Meters
ASTM D6386	(2016a) Standard Practice for Preparation of Zinc (Hot-Dip Galvanized) Coated Iron and Steel Product and Hardware Surfaces for Painting
ASTM F1869	(2016a) Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride

CENTERS FOR DISEASE CONTROL AND PREVENTION (CDC)

Intelligence Bulletin 65	(2013) Occupational Exposure to Carbon Nanotubes and Nanofibers
--------------------------	---

MASTER PAINTERS INSTITUTE (MPI)

MPI 1	(2012) Aluminum Paint
MPI 2	(2012) Aluminum Heat Resistant Enamel (up to 427 C and 800 F
MPI 3	(2016) Primer, Alkali Resistant, Water Based
MPI 4	(2016) Interior/Exterior Latex Block Filler
MPI 5	(2015) Primer, Exterior Alkyd Wood
MPI 6	(2015) Primer, Exterior Latex Wood
MPI 8	(2016) Alkyd, Exterior Flat (MPI Gloss Level I)

MPI 9	(2016) Alkyd, Exterior Gloss (MPI Gloss Level 6)
MPI 10	(2016) Latex, Exterior Flat (MPI Gloss Level 1)
MPI 11	(2016) Latex, Exterior Semi-Gloss, MPI Gloss Level 5
MPI 13	(2016) Stain, Exterior Solvent-Based, Semi-Transparent
MPI 16	(2016) Stain, Exterior, Water Based, Solid Hide
MPI 17	(2016) Primer, Bonding, Water Based
MPI 19	(2012) Primer, Zinc Rich, Inorganic
MPI 21	(2012) Heat Resistant Coating, (Up to 205°C/402°F), MPI Gloss Level 6
MPI 22	(2012) Aluminum Paint, High Heat (up to 590° C/1100° F)
MPI 23	(2015) Primer, Metal, Surface Tolerant
MPI 27	(2016) Floor Enamel, Alkyd, Gloss (MPI Gloss Level 6)
MPI 31	(2012) Varnish, Polyurethane, Moisture Cured, Gloss (MPI Gloss Level 6)
MPI 38	(2016) Elastomeric Coating, Exterior, Water Based, Non-Flat
MPI 39	(2018) Primer, Latex, for Interior Wood
MPI 42	(2012) Textured Coating, Latex, Flat
MPI 44	(2016) Latex, Interior, (MPI Gloss Level 2)
MPI 45	(2016) Primer Sealer, Interior Alkyd
MPI 46	(2016) Undercoat, Enamel, Interior
MPI 47	(2016) Alkyd, Interior, Semi-Gloss (MPI Gloss Level 5)
MPI 48	(2016) Alkyd, Interior, Gloss (MPI Gloss Level 6-7)
MPI 49	(2015) Alkyd, Interior, Flat (MPI Gloss Level 1)
MPI 50	(2015) Primer Sealer, Latex, Interior

MPI 51	(2016) Alkyd, Interior, (MPI Gloss Level 3)2
MPI 52	(2016) Latex, Interior, (MPI Gloss Level 3)
MPI 54	(2016) Latex, Interior, Semi-Gloss (MPI Gloss Level 5)
MPI 56	(2012) Varnish, Interior, Polyurethane, Oil Modified, Gloss
MPI 57	(2012) Varnish, Interior, Polyurethane, Oil Modified, Satin
MPI 59	(2016) Floor Paint, Alkyd, Low Gloss
MPI 60	(2016) Floor Paint, Latex, Low Gloss
MPI 68	(2016) Floor Paint, Latex, Gloss
MPI 71	(2012) Varnish, Polyurethane, Moisture Cured, Flat (MPI Gloss Level 1)
MPI 72	(2016) Polyurethane, Two-Component, Pigmented, Gloss (MPI Gloss Level 6-7)
MPI 76	(2016) Primer, Alkyd, Quick Dry, for Metal
MPI 77	(2015) Epoxy, Gloss
MPI 79	(2016) Primer, Alkyd, Anti-Corrosive for Metal
MPI 90	(2012) Stain, Semi-Transparent, for Interior Wood
MPI 94	(2016) Alkyd, Exterior, Semi-Gloss (MPI Gloss Level 5)
MPI 95	(2015) Primer, Quick Dry, for Aluminum
MPI 101	(2016) Primer, Epoxy, Anti-Corrosive, for Metal
MPI 107	(2016) Primer, Rust-Inhibitive, Water Based
MPI 108	(2015) Epoxy, High Build, Low Gloss
MPI 113	(2018) Elastomeric, Pigmented, Exterior, Water Based, Flat
MPI 116	(2012) Block Filler, Epoxy
MPI 119	(2016) Latex, Exterior, Gloss (MPI Gloss Level 6)

MPI 120	(2020) Epoxy, High Build, Self Priming, Low Gloss
MPI 134	(2015) Primer, Galvanized, Water Based
MPI 138	(2016) Latex, Interior, High Performance Architectural, (MPI Gloss Level 2)
MPI 139	(2016) Latex, Interior, High Performance Architectural, (MPI Gloss Level 3)
MPI 140	(2016) Latex, Interior, High Performance Architectural, (MPI Gloss Level 4)
MPI 141	(2016) Latex, Interior, High Performance Architectural, Semi-Gloss (MPI Gloss Level 5)
MPI 144	(2016) Latex, Interior, Institutional Low Odor/VOC, (MPI Gloss Level 2)
MPI 145	(2016) Latex, Interior, Institutional Low Odor/VOC, (MPI Gloss Level 3)
MPI 146	(2016) Latex, Interior, Institutional Low Odor/VOC, (MPI Gloss Level 4)
MPI 147	(May 2016) Latex, Interior, Institutional Low Odor/VOC, Semi-Gloss (MPI Gloss Level 5)
MPI 149	(2016) Primer Sealer, Interior, Institutional Low Odor/VOC
MPI 151	(2016) Light Industrial Coating, Interior, Water Based (MPI Gloss Level 3)
MPI 153	(2016) Light Industrial Coating, Interior, Water Based, Semi-Gloss (MPI Gloss Level 5)
MPI 154	(2016) Light Industrial Coating, Interior, Water Based, Gloss (MPI Gloss Level 6)
MPI 161	(2016) Light Industrial Coating, Exterior, Water Based (MPI Gloss Level 3)
MPI 163	(2016) Light Industrial Coating, Exterior, Water Based, Semi-Gloss (MPI Gloss Level 5)
MPI 164	(2016) Light Industrial Coating, Exterior, Water Based, Gloss (MPI Gloss Level 6)
MPI 177	(2020) Epoxy, Semi-Gloss (MPI Gloss Level 5)
MPI 214	(2016) Latex, Exterior (MPI Gloss Level 2)

MPI ASM	(2019) Architectural Painting Specification Manual
MPI GPS-1-14	(2014) Green Performance Standard GPS-1-14
MPI GPS-2-14	(2014) Green Performance Standard GPS-2-14
MPI MRM	(2015) Maintenance Repainting Manual
SOCIETY FOR PROTECTIVE COATINGS (SSPC)	
SSPC 7/NACE No.4	(2007) Brush-Off Blast Cleaning
SSPC Glossary	(2011) SSPC Protective Coatings Glossary
SSPC Guide 6	(2015) Guide for Containing Surface Preparation Debris Generated During Paint Removal Operations
SSPC Guide 7	(2015) Guide to the Disposal of Lead-Contaminated Surface Preparation Debris
SSPC PA 1	(2016) Shop, Field, and Maintenance Coating of Metals
SSPC QP 1	(2019) Standard Procedure for Evaluating the Qualifications of Industrial/Marine Painting Contractors (Field Application to Complex Industrial Steel Structures and Other Metal Components)
SSPC SP 1	(2015) Solvent Cleaning
SSPC SP 2	(2018) Hand Tool Cleaning
SSPC SP 3	(2018) Power Tool Cleaning
SSPC SP 6/NACE No.3	(2007) Commercial Blast Cleaning
SSPC SP 10/NACE No. 2	(2007) Near-White Blast Cleaning
SSPC VIS 1	(2002; E 2004) Guide and Reference Photographs for Steel Surfaces Prepared by Dry Abrasive Blast Cleaning
SSPC VIS 3	(2004) Guide and Reference Photographs for Steel Surfaces Prepared by Hand and Power Tool Cleaning
SSPC VIS 4/NACE VIS 7	(1998; E 2000; E 2004) Guide and Reference Photographs for Steel Surfaces Prepared by Waterjetting
SSPC-SP WJ-1/NACE WJ-1	(2012) Clean to Bare Substrate, Waterjet Cleaning of Metals

SSPC-SP WJ-2/NACE WJ-2	(2012) Very Thorough Cleaning, Waterjet Cleaning of Metals
SSPC-SP WJ-3/NACE WJ-3	(2012) Thorough Cleaning, Waterjet Cleaning of Metals
SSPC-SP WJ-4/NACE WJ-4	(2012) Light Cleaning, Waterjet Cleaning of Metals

SOCIETY OF AUTOMOTIVE ENGINEERS INTERNATIONAL (SAE)

SAE AMS-STD-595A	(2017) Colors used in Government Procurement
------------------	--

U.S. ARMY CORPS OF ENGINEERS (USACE)

EM 385-1-1	(2014) Safety and Health Requirements Manual
------------	--

U.S. DEPARTMENT OF DEFENSE (DOD)

MIL-PRF-680	(2010; Rev C; Notice 1 2015) Degreasing Solvent
-------------	---

MIL-STD-101	(2014; Rev C) Color Code for Pipelines and for Compressed Gas Cylinders
-------------	---

U.S. ENVIRONMENTAL PROTECTION AGENCY (EPA)

EPA Method 24	(2000) Determination of Volatile Matter Content, Water Content, Density, Volume Solids, and Weight Solids of Surface Coatings
---------------	---

U.S. FEDERAL AVIATION ADMINISTRATION (FAA)

FAA AC 70/7460-1	(2016; Rev L; Change 2) Obstruction Marking and Lighting
------------------	--

U.S. GENERAL SERVICES ADMINISTRATION (GSA)

FED-STD-313	(2018) Material Safety Data, Transportation Data and Disposal Data for Hazardous Materials Furnished to Government Activities
-------------	---

U.S. NATIONAL ARCHIVES AND RECORDS ADMINISTRATION (NARA)

29 CFR 1910.1000	Air Contaminants
29 CFR 1910.1001	Asbestos
29 CFR 1910.1025	Lead
29 CFR 1926.62	Lead

1.3 DEFINITIONS

1.3.1 Qualification Testing

Qualification testing is the performance of all test requirements listed in the product specification. This testing is accomplished by MPI to qualify each product for the MPI Approved Product List, and may also be accomplished by Contractor's third-party testing lab if an alternative to Batch Quality Conformance Testing by MPI is desired.

1.3.2 Batch Quality Conformance Testing

Batch quality conformance testing determines that the product provided is the same as the product qualified to the appropriate product specification. This testing must be accomplished by an MPI testing lab.

1.3.3 Coating

SSPC Glossary; (1) A liquid, liquefiable, or mastic composition that is converted to a solid protective, decorative, or functional adherent film after application as a thin layer; (2) Generic term for paint, lacquer, enamel.

1.3.4 DFT or dft

Dry film thickness, the film thickness of the fully cured, dry paint or coating.

1.3.5 DSD

Degree of Surface Degradation, the MPI system of defining degree of surface degradation. Five levels are generically defined under the Assessment sections in the **MPI MRM**, MPI Maintenance Repainting Manual.

1.3.6 EXT

MPI short term designation for an exterior coating system.

1.3.7 INT

MPI short term designation for an interior coating system.

1.3.8 Loose Paint

Paint or coating that can be removed with a dull putty knife.

1.3.10 mil / mils

The English measurement for 0.001 in or one one-thousandth of an inch.

1.3.12 MPI Gloss Levels

MPI system of defining gloss. Seven gloss levels (G1 to G7) are generically defined under the Evaluation sections of the MPI Manuals. Traditionally, Flat refers to G1/G2, Eggshell refers to G3, Semigloss refers to G5, and Gloss refers to G6.

Gloss levels are defined by MPI as follows:

Gloss Level	Description	Units at 60 degree angle	Units at 80 degree angle
G1	Matte or Flat	0 to 5	10 max
G2	Velvet	0 to 10	10 to 35
G3	Eggshell	10 to 25	10 to 35
G4	Satin	20 to 35	35 min
G5	Semi-Gloss	35 to 70	
G6	Gloss	70 to 85	
G7	High Gloss		

Gloss is tested in accordance with ASTM D523. Historically, the Government has used Flat (G1 / G2), Eggshell (G3), Semi-Gloss (G5), and Gloss (G6).

1.3.13 MPI System Number

The MPI coating system number in each MPI Division found in either the MPI Architectural Painting Specification Manual or the Maintenance Repainting Manual and defined as an exterior (EXT/REX) or interior system (INT/RIN).

1.3.14 Paint

SSPC Glossary; (1) Any pigmented liquid, liquefiable, or mastic composition designed for application to a substrate in a thin layer that is converted to an opaque solid film after application. Used for protection, decoration, identification, or to serve some other functional purposes; (2) Application of a coating material.

1.3.15 REX

MPI short term designation for an exterior coating system used in repainting projects or over existing coating systems.

1.3.16 RIN

MPI short term designation for an interior coating system used in repainting projects or over existing coating systems.

1.4 SUBMITTALS

Government approval is required for submittals with a "G" classification. Submittals not having a "G" classification are for Contractor Quality Control approval. Submit non-G submittals to the Government for their record. The Government reserves the right to provide additional comments, request resubmittal, rejection and re-submittal to all the non-G submittals.

When used, a code following the "G" classification identifies the office that will review the submittal for the Government. Submit the following in accordance with Section 01 33 00 SUBMITTAL PROCEDURES:

Samples of specified materials may be taken and tested for compliance with

specification requirements.

SD-02 Shop Drawings

Piping Identification

SD-03 Product Data

Coating; G

Product Data Sheets

Sealant

SD-04 Samples

Color; G

Textured Wall Coating System; G

SD-07 Certificates

Indoor Air Quality for Paints and Primers

Indoor Air Quality for Consolidated Latex Paints

SD-08 Manufacturer's Instructions

Application Instructions

Mixing

Manufacturer's Safety Data Sheets

SD-10 Operation and Maintenance Data

Coatings, Data Package 1; G

1.5 QUALITY ASSURANCE

1.5.1 Regulatory Requirements

1.5.1.1 Environmental Protection

In addition to requirements specified elsewhere for environmental protection, provide coating materials that conform to the restrictions of the local Air Pollution Control District and regional jurisdiction. Notify Contracting Officer of any paint specified herein which fails to conform.

1.5.1.2 Lead Content

Do not use coatings having a lead content over 0.06 percent by weight of nonvolatile content.

1.5.1.3 Chromate Content

Do not use coatings containing zinc-chromate or strontium-chromate.

1.5.1.4 Asbestos Content

Provide asbestos-free materials.

1.5.1.5 Mercury Content

Provide materials free of mercury or mercury compounds.

1.5.1.6 Silica

Provide abrasive blast media containing no free crystalline silica.

1.5.1.7 Human Carcinogens

Provide materials that do not contain ACGIH 0100 confirmed human carcinogens (A1) or suspected human carcinogens (A2).

1.5.1.8 Carbon Based Fibers / Tubes

Materials must not contain carbon based fibers such as carbon nanotubes or carbon nanofibers. Intelligence Bulletin 65 ranks toxicity of carbon nanotubes on a par with asbestos.

1.5.2 Approved Products List

The current MPI, "Approved Product List" which lists paint by brand, label, product name and product code as of the date of Contract award, will be used to determine compliance with the submittal requirements of this specification. The Contractor may choose to use a subsequent MPI "Approved Product List", however, only one list may be used for the entire Contract and each coating system is to be from a single manufacturer. Provide all coats on a particular substrate from a single manufacturer. No variation from the MPI Approved Products List is acceptable.

1.5.3 Paints and Coatings Indoor Air Quality Certifications

Provide paint and coating products certified to meet indoor air quality requirements by MPI GPS-1-14, MPI GPS-2-14 or provide certification by other third-party programs. Provide current product certification documentation from certification body.

Provide certification of Indoor Air Quality for Paints and Primers. Submit required indoor air quality certifications in one submittal package.

1.5.4 Field Samples and Tests

The Contracting Officer may choose up to two coatings that have been delivered to the site to be tested at no cost to the Government. Take samples of each chosen product as specified in the paragraph SAMPLING PROCEDURE. Test each chosen product as specified in the paragraph TESTING PROCEDURE. Remove products from the job site which do not conform, and replace with new products that conform to the referenced specification. Test replacement products that failed initial testing as specified in the paragraph TESTING PROCEDURE at no cost to the Government.

1.5.4.1 Sampling Procedure

Select paint at random from the products that have been delivered to the job site for sample testing. The Contractor must provide one quart samples of the selected paint materials. Take samples in the presence of the Contracting Officer, and label, and identify each sample. Provide labels in accordance with the paragraph PACKAGING, LABELING, AND STORAGE.

1.5.4.2 Testing Procedure

Provide Batch Quality Conformance Testing for specified products, as defined by and performed by MPI. As an alternative to Batch Quality Conformance Testing, the Contractor may provide Qualification Testing for specified products above to the appropriate MPI product specification, using the third-party laboratory approved under the paragraph QUALIFICATION TESTING laboratory for coatings. Include the backup data and summary of the test results within the qualification testing lab report. Provide a summary listing of all the reference specification requirements and the result of each test. Clearly indicate in the summary whether the tested paint meets each test requirement. Note that Qualification Testing may take 4 to 6 weeks to perform, due to the extent of testing required.

Submit name, address, telephone number, FAX number, and e-mail address of the independent third party laboratory selected to perform testing of coating samples for compliance with specification requirements. Submit documentation that laboratory is regularly engaged in testing of paint samples for conformance with specifications, and that employees performing testing are qualified. If MPI is chosen to perform the Batch Quality Conformance testing, the above submittal information is not required, only a letter is required from the Contractor stating that MPI will perform the testing.

1.6 PACKAGING, LABELING, AND STORAGE

Provide paints in sealed containers that legibly show the Contract specification number, designation name, formula or specification number, batch number, color, quantity, date of manufacture, manufacturer's formulation number, manufacturer's directions including any warnings and special precautions, and name and address of manufacturer. Furnish pigmented paints in containers not larger than 5 gallons. Store paints and thinners in accordance with the manufacturer's written directions, and as a minimum, stored off the ground, under cover, with sufficient ventilation to prevent the buildup of flammable vapors, and at temperatures between 40 to 95 degrees F. Do not store paint, polyurethane, varnish, or wood stain products with materials that have a high capacity to absorb VOC emissions. Do not store paint, polyurethane, varnish, or wood stain products in occupied spaces.

1.7 SAFETY AND HEALTH

Comply with applicable Federal, State, and local laws and regulations, and with the ACCIDENT PREVENTION PLAN, including the Activity Hazard Analysis as specified in Section 01 35 26 GOVERNMENTAL SAFETY REQUIREMENTS and in Appendix A of EM 385-1-1. Include in the Activity Hazard Analysis the potential impact of painting operations on painting personnel and on others involved in and adjacent to the work zone.

1.7.1 Toxic Materials

To protect personnel from overexposure to toxic materials, conform to the most stringent guidance of:

- a. The applicable [manufacturer's Safety Data Sheets](#) (SDS) or local regulation.
- b. [29 CFR 1910.1000](#).
- c. [ACGIH 0100](#), threshold limit values.
- d. The appropriate OSHA standard in [29 CFR 1910.1025](#) and [29 CFR 1926.62](#) for surface preparation on painted surfaces containing lead. Removal and disposal of coatings which contain lead is specified in Section [02 83 00 LEAD REMEDIATION](#). Additional guidance is given in [SSPC Guide 6](#) and [SSPC Guide 7](#). Refer to drawings for list of hazardous materials located on this project. Coordinate paint preparation activities with this specification section.
- e. The appropriate OSHA standards in [29 CFR 1910.1001](#) for surface preparation of painted surfaces containing asbestos. Removal and disposal of coatings which contain asbestos materials is specified in Section [02 82 00 ASBESTOS REMEDIATION](#). Refer to drawings for list of hazardous materials located on this project. Coordinate paint preparation activities with this specification section.

Submit manufacturer's Safety Data Sheets for coatings, solvents, and other potentially hazardous materials, as defined in [FED-STD-313](#).

1.8 ENVIRONMENTAL REQUIREMENTS

Comply, at minimum, with manufacturer recommendations for space ventilation during and after installation.

1.8.1 Coatings

Do not apply coating when air or substrate conditions are:

- a. Less than [5 degrees F](#) above dew point;
- b. Below [50 degrees F](#) or over [95 degrees F](#), unless specifically pre-approved by the Contracting Officer and the product manufacturer. Do not, under any circumstances, violate the manufacturer's application recommendations.

1.8.2 Post-Application

Vacate space for as long as possible after application. Wait a minimum of 48 hours before occupying freshly painted rooms. Maintain one of the following ventilation conditions during the curing period, or for 72 hours after application:

- a. Supply 100 percent outside air 24 hours a day.
- b. Supply airflow at a rate of 6 air changes per hour, when outside temperatures are between [55 degrees F](#) and [85 degrees F](#) and humidity is between 30 percent and 60 percent.

- c. Supply airflow at a rate of 1.5 air changes per hour, when outside air conditions are not within the range stipulated above.

PART 2 PRODUCTS

2.1 MATERIALS

Conform to the coating specifications and standards referenced in PART 3. Submit Product Data Sheets for specified coatings and solvents. Provide preprinted cleaning and maintenance instructions for all coating systems. Submit Manufacturer's Instructions on Mixing: Detailed mixing instructions, minimum and maximum application temperature and humidity, pot life, and curing and drying times between coats.

2.2 COLOR SELECTION OF FINISH COATS

Provide colors of finish coats as indicated or specified. Allow Contracting Officer to select colors not indicated or specified. Manufacturers' names and color identification are used for the purpose of color identification only. Named products are acceptable for use only if they conform to specified requirements. Products of other manufacturers are acceptable if the colors are approximately the colors indicated and the product conforms to specified requirements.

Provide color, texture, and pattern of wall coating systems as indicated. Submit manufacturer's samples of paint colors. Cross reference color samples to color scheme as indicated. Submit color stencil codes. Tint each coat progressively darker to enable confirmation of the number of coats.

PART 3 EXECUTION

3.1 PROTECTION OF AREAS AND SPACES NOT TO BE PAINTED

Prior to surface preparation and coating applications, remove, mask, or otherwise protect hardware, hardware accessories, machined surfaces, radiator covers, plates, lighting fixtures, public and private property, and other such items not to be coated that are in contact with surfaces to be coated. Following completion of painting, reinstall removed items by workmen skilled in the trades. Restore surfaces contaminated by coating materials, to original condition and repair damaged items.

3.2 RESEALING OF EXISTING EXTERIOR JOINTS

3.2.1 Surface Condition

Begin with surfaces that are clean, dry to the touch, and free from frost and moisture; remove grease, oil, wax, lacquer, paint, defective backstop, or other foreign matter that would prevent or impair adhesion. Where adequate grooves have not been provided, clean out to a depth of 1/2 inch and grind to a minimum width of 1/4 inch without damage to adjoining work. Grinding is not required on metal surfaces.

3.2.2 Backstops

In joints more than 1/2 inch deep, install glass fiber roving or neoprene, butyl, polyurethane, or polyethylene foams free of oil or other staining

elements as recommended by sealant manufacturer. Provide backstop material compatible with sealant. Do not use oakum and other types of absorptive materials as backstops.

3.2.3 Primer and Bond Breaker

Install the type recommended by the sealant manufacturer.

3.2.4 Ambient Temperature

Between 38 degrees F and 95 degrees F when applying sealant.

3.2.5 Exterior Sealant

For joints in vertical surfaces, provide ASTM C920, Type S or M, Grade NS, Class 25, Use NT. For joints in horizontal surfaces, provide ASTM C920, Type S or M, Grade P, Class 25, Use T. Color(s) will be selected by the Contracting Officer. Apply the sealant in accordance with the manufacturer's printed instructions. Force sealant into joints with sufficient pressure to fill the joints solidly. Apply sealant uniformly smooth and free of wrinkles.

3.2.6 Cleaning

Immediately remove fresh sealant from adjacent areas using a solvent recommended by the sealant manufacturer. Upon completion of sealant application, remove remaining smears and stains and leave the work in a clean condition. Allow sealant time to cure, in accordance with manufacturer's recommendations, prior to coating.

3.3 SURFACE PREPARATION

Remove dirt, splinters, loose particles, grease, oil, disintegrated coatings, and other foreign matter and substances deleterious to coating performance as specified for each substrate before application of paint or surface treatments. Remove oil and grease prior to mechanical cleaning. Schedule cleaning so that dust and other contaminants will not fall on wet, newly painted surfaces. Spot-prime exposed ferrous metals such as nail heads on or in contact with surfaces to be painted with water-thinned paints, with a suitable corrosion-inhibitive primer capable of preventing flash rusting and compatible with the coating specified for the adjacent areas. Refer to MPI ASM and MPI MRM for additional more specific substrate preparation requirements.

3.3.1 Additional Requirements for Preparation of Surfaces With Existing Coatings

Before application of coatings, perform the following on surfaces covered by soundly-adhered coatings, defined as those which cannot be removed with a putty knife:

- a. Test existing finishes for lead before sanding, scraping, or removing. If lead is present, refer to paragraph Toxic Materials.
- b. Wipe previously painted surfaces to receive solvent-based coatings, except stucco and similarly rough surfaces clean with a clean, dry cloth saturated with mineral spirits, ASTM D235 or as specified in

MPI MRM. Wipe the surfaces dry with a clean, dry, lint free cloth. Wipe immediately preceding the application of the first coat of any coating, unless specified otherwise.

- c. Sand existing glossy surfaces to be painted to reduce gloss. Brush, and wipe clean with a damp cloth to remove dust.
- d. The requirements specified are minimum. Comply also with the **application instructions** of the paint manufacturer and specific surface preparation requirements as outlined in **MPI MRM Exterior Surface Preparation and Interior Surface Preparation**.
- e. Thoroughly clean previously painted surfaces specified to be repainted damaged during construction of all grease, dirt, dust or other foreign matter.
- f. Remove blistering, cracking, flaking and peeling or otherwise deteriorated coatings.
- g. Remove chalk so that when tested in accordance with **ASTM D4214**, the chalk resistance rating is no less than 8.
- h. Roughen slick surfaces. Repair damaged areas such as, but not limited to, nail holes, cracks, chips, and spalls with suitable material to match adjacent undamaged areas.
- i. Feather and sand smooth edges of chipped paint.
- j. Clean rusty metal surfaces in accordance with SSPC requirements. Use solvent, mechanical, or chemical cleaning methods to provide surfaces suitable for painting.
- k. Provide new, proposed coatings that are compatible with existing coatings.

3.3.2 Existing Coated Surfaces with Minor Defects

Sand, spackle, and treat minor defects to render them smooth. Minor defects are defined as scratches, nicks, cracks, gouges, spalls, alligatoring, chalking, and irregularities due to partial peeling of previous coatings. Remove chalking by sanding or blasting so that when tested in accordance with **ASTM D4214**, the chalk rating is not less than 8.

3.3.3 Removal of Existing Coatings

Remove existing coatings from the following surfaces:

- a. As indicated.

3.3.4 Substrate Repair

- a. Repair substrate surface damaged during coating removal;
- b. Sand edges of adjacent soundly-adhered existing coatings so they are tapered as smooth as practical to areas involved with coating removal; and

- c. Clean and prime the substrate as specified.

3.4 PREPARATION OF METAL SURFACES

3.4.1 Existing and New Ferrous Surfaces

- a. Ferrous Surfaces including Shop-coated Surfaces and Small Areas That Contain Rust, Mill Scale and Other Foreign Substances: Solvent clean in accordance with SSPC SP 1 to remove oil and grease. Where shop coat is missing or damaged, clean according to SSPC SP 2, SSPC SP 3, SSPC SP 6/NACE No.3, or SSPC SP 10/NACE No. 2. Brush-off blast remaining surface in accordance with SSPC 7/NACE No.4]; Water jetting to SSPC-SP WJ-4/NACE WJ-4 may be used to remove loose coating and other loose materials. Use inhibitor as recommended by coating manufacturer to prevent premature rusting. Protect shop-coated ferrous surfaces from corrosion by treating and touching up corroded areas immediately upon detection.

3.4.2 Final Ferrous Surface Condition:

3.4.2.1 Tool Cleaned Surfaces

Comply with SSPC SP 2 and SSPC SP 3. Use as a visual reference, photographs in SSPC VIS 3 for the appearance of cleaned surfaces.

3.4.2.2 Abrasive Blast Cleaned Surfaces

Comply with SSPC 7/NACE No.4, SSPC SP 6/NACE No.3, and SSPC SP 10/NACE No. 2. Use as a visual reference, photographs in SSPC VIS 1 for the appearance of cleaned surfaces.

3.4.2.3 Waterjet Cleaned Surfaces

Comply with SSPC-SP WJ-1/NACE WJ-1, SSPC-SP WJ-2/NACE WJ-2, SSPC-SP WJ-3/NACE WJ-3 or SSPC-SP WJ-4/NACE WJ-4. Use as a visual reference, photographs in SSPC VIS 4/NACE VIS 7 for the appearance of cleaned surfaces.

3.4.3 Galvanized Surfaces

- a. New or Existing Galvanized Surfaces With Only Dirt and Zinc Oxidation Products: Clean with solvent, or non-alkaline detergent solution in accordance with SSPC SP 1. Completely remove coating by brush-off abrasive blast if the galvanized metal has been passivated or stabilized. Do not "passivate" or "stabilize" new galvanized steel to be coated. If the absence of hexavalent stain inhibitors is not documented, test as described in ASTM D6386, Appendix X2, and remove by one of the methods described therein.
- b. Galvanized with Slight Coating Deterioration or with Little or No Rusting: Water jetting to SSPC-SP WJ-3/NACE WJ-3 to remove loose coating from surfaces with less than 20 percent coating deterioration and no blistering, peeling, or cracking. Use inhibitor as recommended by the coating manufacturer to prevent rusting.

3.4.4 Non-Ferrous Metallic Surfaces

Aluminum and aluminum-alloy, lead, copper, and other nonferrous metal surfaces.

Surface Cleaning: Solvent clean in accordance with SSPC SP 1 and wash with mild non-alkaline detergent to remove dirt and water soluble contaminants.

3.4.5 Existing Surfaces with a Bituminous or Mastic-Type Coating

Remove chalk, mildew, and other loose material by washing with a solution of 1/2 cup trisodium phosphate, 1/4 cup household detergent, one quart 5 percent sodium hypochlorite solution and 3 quarts of warm water.

3.5 PREPARATION OF CONCRETE AND CEMENTITIOUS SURFACE

3.5.1 Concrete and Masonry

- a. Curing: Allow concrete, stucco and masonry surfaces to cure at least 30 days before painting, and concrete slab on grade to cure at least 90 days before painting.
- b. Surface Cleaning: Remove the following deleterious substances.
 - (1) Dirt, Chalking, Grease, and Oil: Wash new and existing surfaces with a solution composed of 1/2 cup trisodium phosphate, 1/4 cup household detergent, and 4 quarts of warm water. Then rinse thoroughly with fresh water. Wash existing coated surfaces with a suitable detergent and rinse thoroughly. For large areas, water blasting may be used.
 - (2) Fungus and Mold: Wash surfaces with a solution composed of 1/2 cup trisodium phosphate, 1/4 cup household detergent, one quart 5 percent sodium hypochlorite solution and 3 quarts of warm water. Rinse thoroughly with fresh water.
 - (3) Paint and Loose Particles: Remove by wire brushing.
 - (4) Efflorescence: Remove by scraping or wire brushing followed by washing with a 5 to 10 percent by weight aqueous solution of hydrochloric (muriatic) acid. Do not allow acid to remain on the surface for more than five minutes before rinsing with fresh water. Do not acid clean more than 4 square feet of surface, per workman, at one time.
- c. Cosmetic Repair of Minor Defects: Repair or fill mortar joints and minor defects, including but not limited to spalls, in accordance with manufacturer's recommendations and prior to coating application.
- d. Allowable Moisture Content: Latex coatings may be applied to damp surfaces, but not to surfaces with droplets of water. Do not apply epoxies to damp vertical surfaces as determined by ASTM D4263 or horizontal surfaces that exceed 3 lbs of moisture per 1000 square feet in 24 hours as determined by ASTM F1869. In all cases follow manufacturer's recommendations. Allow surfaces to cure a minimum of 30 days before painting.

3.5.2 Gypsum Board, Plaster, and Stucco

3.5.2.1 Surface Cleaning

Verify that plaster and stucco surfaces are free from loose matter and that gypsum board is dry. Remove loose dirt and dust by brushing with a soft brush, rubbing with a dry cloth, or vacuum-cleaning prior to application of the first coat material. A damp cloth or sponge may be used if paint is water-based.

3.5.2.2 Repair of Minor Defects

Prior to painting, repair joints, cracks, holes, surface irregularities, and other minor defects with patching plaster or spackling compound and sand smooth.

3.5.2.3 Allowable Moisture Content

Latex coatings may be applied to damp surfaces, but not surfaces with droplets of water. Do not apply epoxies to damp surfaces as determined by [ASTM D4263](#). Verify that new plaster to be coated has a maximum moisture content of 8 percent, when measured in accordance with [ASTM D4444](#), Method A, unless otherwise authorized. In addition to moisture content requirements, allow new plaster to age a minimum of 30 days before preparation for painting.

3.6 APPLICATION

3.6.1 Coating Application

- a. Comply with applicable federal, state and local laws enacted to ensure compliance with Federal Clean Air Standards. Apply coating materials in accordance with [SSPC PA 1](#). [SSPC PA 1](#) methods are applicable to all substrates, except as modified herein.
- b. At the time of application, paint must show no signs of deterioration. Maintain uniform suspension of pigments during application.
- c. Unless otherwise specified or recommended by the paint manufacturer, paint may be applied by brush, roller, or spray. Use trigger operated spray nozzles for water hoses. Use rollers for applying paints and enamels of a type designed for the coating to be applied and the surface to be coated. Wear protective clothing and respirators when applying oil-based paints or using spray equipment with any paints.
- d. Only apply paints, except water-thinned types, to surfaces that are completely free of moisture as determined by sight or touch.
- e. Thoroughly work coating materials into joints, crevices, and open spaces. Pay special attention to ensure that all edges, corners, crevices, welds, and rivets receive a film thickness equal to that of adjacent painted surfaces.
- f. Apply each coat of paint so that dry film is of uniform thickness and free from runs, drops, ridges, waves, pinholes or other voids, laps, brush marks, and variations in color, texture, and finish. Completely hide all blemishes.
- g. Touch up damaged coatings before applying subsequent coats. Broom

clean and clear dust from interior areas before and during the application of coating material.

- h. Drying Time: Allow time between coats, as recommended by the coating manufacturer, to permit thorough drying, but not to present topcoat adhesion problems. Provide each coat in specified condition to receive next coat.
- i. Primers, and Intermediate Coats: Do not allow primers or intermediate coats to dry more than 30 days, or longer than recommended by manufacturer, before applying subsequent coats. Follow manufacturer's recommendations for surface preparation if primers or intermediate coats are allowed to dry longer than recommended by manufacturers of subsequent coatings. Cover each preceding coat or surface completely by ensuring visually perceptible difference in shades of successive coats.
- j. Finished Surfaces: Provide finished surfaces free from runs, drops, ridges, waves, laps, brush marks, and variations in colors.
- kp. Thermosetting Paints: Apply topcoats over thermosetting paints (epoxies and urethanes) within the overcoat window recommended by the manufacturer.

3.6.2 Mixing and Thinning of Paints

Reduce paints to proper consistency by adding fresh paint, except when thinning is mandatory to suit surface, temperature, weather conditions, application methods, or for the type of paint being used. Obtain written permission from the Contracting Officer to use thinners. Verify that the written permission includes quantities and types of thinners to use.

When thinning is allowed, thin paints immediately prior to application with not more than one pint of suitable thinner per gallon. The use of thinner does not relieve the Contractor from obtaining complete hiding, full film thickness, or required gloss. Thinning cannot cause the paint to exceed limits on volatile organic compounds. Do not mix paints of different manufacturers.

3.6.3 Two-Component Systems

Mix two-component systems in accordance with manufacturer's instructions. Follow recommendation by the manufacturer for any thinning of the first coat to ensure proper penetration and sealing for each type of substrate.

3.6.4 Coating Systems

- a. Systems by Substrates: Apply coatings that conform to the respective specifications listed in the following Tables:

Table for Exterior Applications	
MPI Division	Substrate Application
MPI Division 3	Exterior Concrete Paint Table

Table for Exterior Applications	
MPI Division 4	Exterior Concrete Masonry Units Paint Table
MPI Division 5	Exterior Metal, Ferrous and Non-Ferrous Paint Table
MPI Division 6	Exterior Wood; Dressed Lumber, Paneling, Decking, Shingles Paint Table
MPI Division 9	Exterior Stucco Paint Table
MPI Division 10	Exterior Cloth Coverings and Bituminous Coated Surfaces Paint Table
Table for Interior Applications	
MPI Division	Substrate Application
MPI Division 3	Interior Concrete Paint Table
MPI Division 4	Interior Concrete Masonry Units Paint Table
MPI Division 5	Interior Metal, Ferrous and Non-Ferrous Paint Table
MPI Division 6	Interior Wood Paint Table
MPI Division 9	Interior Plaster, Gypsum Board, Textured Surfaces Paint Table

- b. Minimum Dry Film Thickness (DFT): Apply paints, primers, varnishes, enamels, undercoats, and other coatings to a minimum dry film thickness of 1.5 mil each coat unless specified otherwise in the Tables. Coating thickness, where specified, refers to the minimum dry film thickness.
- c. Coatings for Surfaces Not Specified Otherwise: Coat unspecified surfaces the same as surfaces having similar conditions of exposure.
- d. Existing Surfaces Damaged During Performance of the Work, Including New Patches In Existing Surfaces: Coat surfaces with the following:
 - (1) One coat of primer.
 - (2) One coat of undercoat or intermediate coat.
 - (3) One topcoat to match adjacent surfaces.
- e. Existing Coated Surfaces To Be Painted: Apply coatings conforming to the respective specifications listed in the Tables herein, except that pretreatments, sealers and fillers need not be provided on surfaces where existing coatings are soundly adhered and in good condition. Do not omit undercoats or primers.

3.7 COATING SYSTEMS FOR METAL

Apply coatings of Tables in MPI Division 5 for Exterior and Interior.

- a. Apply specified ferrous metal primer to steel surfaces on the same day that surface is cleaned, to surfaces that meet all specified surface preparation requirements at time of application.
- b. Inaccessible Surfaces: Prior to erection, use one coat of specified primer on metal surfaces that will be inaccessible after erection.
- c. Shop-primed Surfaces: Touch up exposed substrates and damaged coatings to protect from rusting prior to applying field primer.
- d. Surface Previously Coated with Epoxy or Urethane: Apply MPI 101, 1.5 mils DFT immediately prior to application of epoxy or urethane coatings.
- e. Pipes and Tubing: The semitransparent film applied to some pipes and tubing at the mill is not to be considered a shop coat. Overcoat these items with the specified ferrous-metal primer prior to application of finish coats.
- f. Exposed Nails, Screws, Fasteners, and Miscellaneous Ferrous Surfaces. On surfaces to be coated with water thinned coatings, spot prime exposed nails and other ferrous metal with latex primer MPI 107.

3.8 COATING SYSTEMS FOR CONCRETE AND CEMENTITIOUS SUBSTRATES

Apply coatings of Tables in MPI Division 3, 4 and 9 for Exterior and Interior.

3.9 COATING SYSTEMS FOR WOOD AND PLYWOOD

- a. Apply coatings of Tables in MPI Division 6 for Exterior and Interior.
- b. Prior to erection, apply two coats of specified primer to treat and prime wood and plywood surfaces which will be inaccessible after erection.
- c. Apply stains in accordance with manufacturer's printed instructions.

3.10 INSPECTION AND ACCEPTANCE

In addition to meeting previously specified requirements, demonstrate mobility of moving components, including swinging and sliding doors, cabinets, and windows with operable sash, for inspection by the Contracting Officer. Perform this demonstration after appropriate curing and drying times of coatings have elapsed and prior to invoicing for final payment.

3.11 WASTE MANAGEMENT

As specified in the Waste Management Plan and as follows. Do not use kerosene or any such organic solvents to clean up water based paints. Properly dispose of paints or solvents in designated containers. Close and seal partially used containers of paint to maintain quality as necessary for reuse. Store in protected, well-ventilated, fire-safe area at moderate temperature. Place materials defined as hazardous or toxic waste in designated containers. Set aside extra paint for future color matches or

reuse by the Government.

3.12 PAINT TABLES

All DFT's are minimum values. Use only materials with a MPI GPS-1-14 green check mark having a minimum MPI "Environmentally Friendly" E1 E2 E3 rating based on VOC (EPA Method 24) content levels. Acceptable products are listed in the MPI Green Approved Products List, available at <http://www.specifygreen.com/APL/ProductIdxByMPInum.asp>.

3.12.1 Exterior Paint Tables

3.12.1.1 MPI Division 3: Exterior Concrete Paint Table

A. Concrete; Vertical Surfaces, Undersides of Balconies and Soffits

(1) New and uncoated existing and Existing, previously painted concrete; vertical surfaces, including undersides of balconies and soffits but excluding tops of slabs

Latex					
New and uncoated existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI EXT 3.1A-G1 (Flat)	MPI REX 3.1A-G1 (Flat)	MPI 3	MPI 10	MPI 10	3.5 mils
MPI EXT 3.1A-G2 (Velvet)	MPI REX 3.1A-G2 (Velvet)	MPI 3	MPI 214	MPI 214	3.5 mils
MPI EXT 3.1A-G5 (Semigloss)	MPI REX 3.1A-G5 (Semigloss)	MPI 3	MPI 11	MPI 11	3.5 mils
MPI EXT 3.1A-G6 (Gloss)	MPI REX 3.1A-G6 (Gloss)	MPI 3	MPI 119	MPI 119	3.5 mils
Primer as recommended by manufacturer. Topcoat: Coating to match adjacent surfaces.					

(2) New and uncoated existing and Existing, previously painted concrete, textured system; vertical surfaces, including undersides of balconies and soffits but excluding tops of slabs

Latex Aggregate					
New and uncoated existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT

MPI EXT 3.1B-G2 (Flat)	MPI REX 3.1A-G1 (Flat)	MPI 42	MPI 10	MPI 10	N/A
MPI EXT 3.1B-G5 (Semigloss)	MPI REX 3.1A-G5 (Semigloss)	MPI 42	MPI 11	MPI 11	N/A
MPI EXT 3.1B-G6 (Gloss)	MPI REX 3.1A-G6 (Gloss)	MPI 42	MPI 119	MPI 119	N/A
Texture - Fine Surface preparation and number of coats in accordance with manufacturer's instructions. Topcoat: Coating to match adjacent surfaces.					

(3) New and uncoated existing and Existing, previously painted concrete, elastomeric system; vertical surfaces, including undersides of balconies and soffits but excluding tops of slabs

Elastomeric Coating					
New and uncoated existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI EXT 3.1F-G1 (Flat)	MPI REX 3.1F-G1 (Flat)	Per Manufacturer	MPI 113	MPI 113	16 mils
MPI EXT 3.1F-G2/3 (Velvet)	MPI REX 3.1F-G2/3 (Velvet)	Per Manufacturer	MPI 38	MPI 38	16 mils
Primer as recommended by manufacturer. Topcoat: Coating to match adjacent surfaces. Surface preparation and number of coats in accordance with manufacturer's instructions. NOTE: Apply sufficient coats to achieve a minimum dry film thickness of 16 mils.					

3.12.1.2 MPI Division 4: Exterior Concrete Masonry Units Paint Table

A. New and Existing concrete masonry on uncoated surface

Latex						
New	Existing	Block Filler	Primer	Intermediate	Topcoat	System DFT
MPI EXT 4.2A-G1 (Flat)	MPI REX 4.2A-G1 (Flat)	MPI 4	N/A	MPI 10	MPI 10	11 mils

MPI EXT 4.2A-G5 (Semigloss)	MPI REX 4.2A-G5 (Semigloss)	MPI 4	N/A	MPI 11	MPI 11	11 mils
MPI EXT 4.2A-G6 (Gloss)	MPI REX 4.2A-G6 (Gloss)	MPI 4	N/A	MPI 119	MPI 119	11 mils
Topcoat: Coating to match adjacent surfaces.						

B. New and Existing concrete masonry, textured system; on uncoated surface

Latex Aggregate					
New	Existing	Primer	Intermediate	Topcoat	System DFT
MPI EXT 4.2B-G1 (Flat)	MPI REX 3.1A-G1 (Flat)	MPI 42	MPI 42	MPI 10	N/A
MPI EXT 4.2B-G5 (Semigloss)	MPI REX 3.1A-G5 (Semigloss)	MPI 42	MPI 42	MPI 11	N/A
MPI EXT 4.2B-G6 (Gloss)	MPI REX 3.1A-G6 (Gloss)	MPI 42	MPI 42	MPI 119	N/A
Texture - Fine Medium Coarse. Surface preparation and number of coats in accordance with manufacturer's instructions. Topcoat: Coating to match adjacent surfaces.					

C. New and Existing concrete masonry, elastomeric system; on uncoated surfaces

Elastomeric Coating					
New and uncoated existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI EXT 3.1F-G1 (Flat)	MPI REX 3.1F-G1 (Flat)	Per Manufacturer	MPI 113	MPI 113	16 mils
Primer as recommended by manufacturer. Topcoat: Coating to match adjacent surfaces. Surface preparation and number of coats in accordance with manufacturer's instructions. NOTE: Apply sufficient coats of MPI 113 to achieve a minimum dry film thickness of 16 mils.					

3.12.1.3 MPI Division 5: Exterior Metal, Ferrous and Non-Ferrous Paint Table

A. Steel / Ferrous Surfaces

(1) New Steel that has been hand or power tool cleaned to SSPC SP 2 or SSPC SP 3

Alkyd					
New	Existing, uncoated	Primer	Intermediate	Topcoat	System DFT
MPI EXT 5.1Q-G5 (Semigloss)	MPI REX 5.1D-G5 (Semigloss)	MPI 23	MPI 94	MPI 94	5.25 mils
MPI EXT 5.1Q-G6 (Gloss)	MPI REX 5.1D-G6 (Gloss)	MPI 23	MPI 9	MPI 9	5.25 mils
Topcoat: Coating to match adjacent surfaces.					

(2) New Steel that has been blast-cleaned to SSPC SP 6/NACE No.3

Alkyd					
New	Existing, uncoated	Primer	Intermediate	Topcoat	System DFT
MPI EXT 5.1D-G5 (Semigloss)	MPI REX 5.1D-G5 (Semigloss)	MPI 79	MPI 94	MPI 94	5.25 mils
MPI EXT 5.1D-G6 (Gloss)	MPI REX 5.1D-G6 (Gloss)	MPI 79	MPI 9	MPI 9	5.25 mils
Topcoat: Coating to match adjacent surfaces.					

(3) Existing steel that has been spot-blasted to SSPC SP 6/NACE No.3

(a) Surface previously coated with alkyd or latex

Waterborne Light Industrial Coating				
Existing, previously coated with alkyd or latex	Primer	Intermediate	Topcoat	System DFT
MPI REX 5.1C-G5 (Semigloss)	MPI 79	MPI 163	MPI 163	5 mils
MPI REX 5.1C-G6 (Gloss)	MPI 79	MPI 164	MPI 164	5 mils
Topcoat: Coating to match adjacent surfaces.				

(b) Surfaces previously coated with epoxy

Waterborne Light Industrial Coating				
Existing, previously coated with epoxy	Primer	Intermediate	Topcoat	System DFT
MPI REX 5.1L-G5 (Semigloss)	MPI 101	MPI 163	MPI 163	5 mils
MPI REX 5.1L-G6 (Gloss)	MPI 101	MPI 164	MPI 164	5 mils
Topcoat: Coating to match adjacent surfaces.				

Pigmented Polyurethane				
Existing, previously coated with epoxy	Primer	Intermediate	Topcoat	System DFT
MPI REX 5.1H-G6 (Gloss)	MPI 101	MPI 108	MPI 72	8.5 mils
Topcoat: Coating to match adjacent surfaces.				

(4) New and existing steel blast cleaned to SSPC SP 10/NACE No. 2

Waterborne Light Industrial					
New	Existing	Primer	Intermediate	Topcoat	System DFT
MPI EXT 5.1R-G5 (Semigloss)	MPI EXT 5.1R-G5 (Semigloss)	MPI 101	MPI 108	MPI 163	8.5 mils
MPI EXT 5.1R-G6 (Gloss)	MPI EXT 5.1R-G6 (Gloss)	MPI 101	MPI 108	MPI 164	8.5 mils
Topcoat: Coating to match adjacent surfaces.					

Pigmented Polyurethane

New	Existing	Primer	Intermediate	Topcoat	System DFT
MPI EXT 5.1J-G6 (Gloss)	MPI EXT 5.1J-G6 (Gloss)	MPI 101	MPI 108	MPI 72	8.5 mils
Topcoat: Coating to match adjacent surfaces.					

(5) Metal floors (non-shop-primed surfaces or non-slip deck surfaces) with non-skid additive (NSA), load at manufacturer's recommendations

Epoxy					
New	Existing	Primer	Intermediate	Topcoat	System DFT
MPI EXT 5.1S-G5 (Semi Gloss)	MPI EXT 5.1S-G5 (Semi Gloss)	MPI 120	MPI 177	MPI 177	5.25 mils
MPI EXT 5.1S-G6 (Gloss)	MPI EXT 5.1S-G6 (Gloss)	MPI 120	MPI 77	MPI 77	5.25 mils
Topcoat: Coating to match adjacent surfaces. Load Non-Skid Additive at manufacturer's recommendations.					

B. Exterior Galvanized Surfaces

(1) New Galvanized surfaces

Waterborne Primer / Latex				
New Galvanized Surfaces	Primer	Intermediate	Topcoat	System DFT
MPI EXT 5.3H-G1 (Flat)	MPI 134	MPI 10	MPI 10	4.5 mils
EXT 5.3H-G5 (Semigloss)	MPI 134	MPI 11	MPI 11	4.5 mils
MPI EXT 5.3H-G6 (Gloss)	MPI 134	MPI 119	MPI 119	4.5 mils
Topcoat: Coating to match adjacent surfaces.				

Waterborne Primer / Waterborne Light Industrial Coating

New Galvanized Surfaces	Primer	Intermediate	Topcoat	System DFT
MPI EXT 5.3J-G5 (Semigloss)	MPI 134	MPI 163	MPI 163	4.5 mils
MPI EXT 5.3J-G6 (Gloss)	MPI 134	MPI 164	MPI 164	4.5 mils
Topcoat: Coating to match adjacent surfaces.				

Epoxy Primer / Waterborne Light Industrial Coating				
New Galvanized Surfaces	Primer	Intermediate	Topcoat	System DFT
MPI EXT 5.3K-G5 (Semigloss)	MPI 101	MPI 163	MPI 163	5 mils
MPI EXT 5.3K-G6 (Gloss)	MPI 101	MPI 164	MPI 164	5 mils
Topcoat: Coating to match adjacent surfaces.				

Pigmented Polyurethane				
New Galvanized Surfaces	Primer	Intermediate	Topcoat	System DFT
MPI EXT 5.3L-G6 (Gloss)	MPI 101	N/A	MPI 72	5 mils
Topcoat: Coating to match adjacent surfaces.				

(2) Galvanized surfaces with slight coating deterioration; little or no rusting

Waterborne Light Industrial Coating				
Galvanized Surfaces with slight coating deterioration	Primer	Intermediate	Topcoat	System DFT

MPI REX 5.3J-G5 (Semigloss)	MPI 134	N/A	MPI 163	4.5 mils
Topcoat: Coating to match adjacent surfaces.				

Pigmented Polyurethane				
Galvanized Surfaces with slight coating deterioration	Primer	Intermediate	Topcoat	System DFT
MPI REX 5.3D-G6 (Gloss)	MPI 101	N/A	MPI 72	5 mils
Topcoat: Coating to match adjacent surfaces.				

(3) Galvanized surfaces with severely deteriorated coating or rusting

Waterborne Light Industrial Coating				
Galvanized surfaces with severely deteriorated coating or rusting	Primer	Intermediate	Topcoat	System DFT
MPI REX 5.3L-G5 (Semigloss)	MPI 101	MPI 108	MPI 163	8.5 mils
MPI REX 5.3L-G6 (Gloss)	MPI 101	MPI 108	MPI 164	8.5 mils
Topcoat: Coating to match adjacent surfaces.				

Pigmented Polyurethane				
Galvanized surfaces with severely deteriorated coating or rusting	Primer	Intermediate	Topcoat	System DFT

MPI REX 5.3D-G6 (Gloss)	MPI 101	MPI 72	MPI 72	5 mils
Topcoat: Coating to match adjacent surfaces.				

C. Exterior Surfaces, Other Metals (Non-Ferrous)

(1) Aluminum, aluminum alloy and other miscellaneous non-ferrous metal items not otherwise specified except hot metal surfaces, roof surfaces, and new prefinished equipment

Alkyd				
New Galvanized Surfaces	Primer	Intermediate	Topcoat	System DFT
MPI EXT 5.4F-G1 (Flat	MPI 95	MPI 8	MPI 8	5 mils
MPI EXT 5.4F-G5 (Semigloss)	MPI 95	MPI 94	MPI 94	5 mils
MPI EXT 5.4F-G6 (Gloss)	MPI 95	MPI 9	MPI 9	5 mils
Topcoat: Coating to match adjacent surfaces.				

Waterborne Light Industrial Coating				
New Galvanized Surfaces	Primer	Intermediate	Topcoat	System DFT
MPI EXT 5.4F-G1 (Flat	MPI 95	MPI 161	MPI 161	5 mils
MPI EXT 5.4F-G5 (Semigloss)	MPI 95	MPI 163	MPI 163	5 mils
MPI EXT 5.4F-G6 (Gloss)	MPI 95	MPI 164	MPI 164	5 mils
Topcoat: Coating to match adjacent surfaces.				

(2) Existing roof surfaces previously coated

Aluminum Pigmented Asphalt Roof Coating				
Existing roof surfaces previously coated	N/A	Intermediate	Topcoat	System DFT
Non-MPI System	ASTM D2824/D2825	N/A	N/A	8 mils
Sufficient coats to provide not less than 8 mils of finished coating system (without asbestos fibers).				

Aluminum Paint				
Existing roof surfaces previously coated	Primer	Intermediate	Topcoat	System DFT
MPI REX 10.2D	MPI 107	MPI 1	MPI 1	3.5 mils
Topcoat: Coating to match adjacent surfaces.				

(3) Surfaces adjacent to painted surfaces; Mechanical, Electrical, Fire extinguishing sprinkler systems including valves, conduit, hangers, supports, exposed copper piping, and miscellaneous metal items not otherwise specified except floors, hot metal surfaces, and new prefinished equipment

Alkyd				
New	Primer	Intermediate	Topcoat	System DFT
MPI EXT 5.1D-G1 (Flat)	MPI 79	MPI 8	MPI 8	5.25 mils
MPI EXT 5.1D-G5 (Semigloss)	MPI 79	MPI 94	MPI 94	5.25 mils
MPI EXT 5.1D-G6 (Gloss)	MPI 79	MPI 9	MPI 9	5.25 mils
Topcoat: Coating to match adjacent surfaces.				

Waterborne Light Industrial Coating

New	Primer	Intermediate	Topcoat	System DFT
MPI EXT 5.1C-G3 (Eggshell)	MPI 79	MPI 161	MPI 161	5 mils
MPI EXT 5.1C-G5 (Semigloss)	MPI 79	MPI 163	MPI 163	5 mils
MPI EXT 5.1C-G6 (Gloss)	MPI 79	MPI 164	MPI 164	5 mils
Primer as recommended by manufacturer. Topcoat: Coating to match adjacent surfaces.				

D. Exterior Hot Surfaces

(1) Hot metal surfaces subject to temperatures up to 400 degrees F

Heat Resistant Enamel				
New	N/A	Intermediate	Topcoat	System DFT
MPI EXT 5.2A	MPI 21	N/A	N/A	Per Manufacturer
Surface preparation and number of coats per manufacturer's instructions.				

(2) Ferrous metal subject to high temperature, up to 750 degrees F

Inorganic Zinc Rich Coating				
New	N/A	Intermediate	Topcoat	System DFT
MPI EXT 5.2C	MPI 19	N/A	N/A	Per Manufacturer
Surface preparation and number of coats per manufacturer's instructions.				

Heat Resistant Aluminum Enamel				
New	N/A	Intermediate	Topcoat	System DFT

MPI EXT 5.2B	MPI 2	N/A	N/A	Per Manufacturer
Surface preparation and number of coats per manufacturer's instructions.				

(3) New surfaces and Existing surfaces made bare subject to temperatures up to 1100 degrees F

(1) New surfaces and Existing surfaces made bare cleaning to SSPC SP 10/NACE No. 2 subject to temperatures up to 1100 degrees F

Heat Resistant Coating					
New	Existing	N/A	Intermediate	Topcoat	System DFT
MPI EXT 5.2D	MPI REX 5.2D	MPI 22	N/A	N/A	Per Manufacturer
Surface preparation and number of coats per manufacturer's instructions.					

3.12.1.4 MPI Division 6: Exterior Wood; Dressed Lumber, Paneling, Decking, Shingles Paint Table

A. New and Existing, uncoated Dressed lumber, Wood and plywood, trim, including top, bottom and edges of doors not otherwise specified

Alkyd					
New	Existing, uncoated	Primer	Intermediate	Topcoat	System DFT
MPI EXT 6.3B-G5 (Semigloss)	MPI EXT 6.3B-G5 (Semigloss)	MPI 5	MPI 94	MPI 94	5 mils
MPI EXT 6.3B-G6 (Gloss)	MPI EXT 6.3B-G6 (Gloss)	MPI 5	MPI 9	MPI 9	5 mils
Topcoat: Coating to match adjacent surfaces.					

Latex					
New	Existing, uncoated	Primer	Intermediate	Topcoat	System DFT
MPI EXT 6.3A-G1 (Flat)	MPI EXT 6.3A-G1 (Flat)	MPI 5	MPI 10	MPI 10	5 mils
MPI EXT 6.3A-G5 (Semigloss)	MPI EXT 6.3B-G5 (Semigloss)	MPI 5	MPI 11	MPI 11	5 mils

MPI EXT 6.3A-G6 (Gloss)	MPI EXT 6.3B-G6 (Gloss)	MPI 5	MPI 119	MPI 119	5 mils
Topcoat: Coating to match adjacent surfaces.					

Waterborne Solid Color Stain					
New	Existing, uncoated	Primer	Intermediate	Topcoat	System DFT
MPI EXT 6.3K	MPI EXT 6.3K	MPI 5	MPI 16	MPI 16	4.25 mils
Topcoat: Coating to match adjacent surfaces.					

B. Existing, dressed lumber, Wood and plywood, trim, including top, bottom and edges of doors previously coated with an alkyd / oil based finish coat not otherwise specified

Alkyd				
Existing, previously coated	Primer	Intermediate	Topcoat	System DFT
MPI REX 6.3B-G5 (Semigloss)	MPI 5	MPI 94	MPI 94	5 mils
MPI REX 6.3B-G6 (Gloss)	MPI 5	MPI 9	MPI 9	5 mils

Latex				
Existing, previously coated	Primer	Intermediate	Topcoat	System DFT
MPI REX 6.3A-G1 (Flat)	MPI 5	MPI 10	MPI 10	5 mils
MPI REX 6.3B-G5 (Semigloss)	MPI 5	MPI 11	MPI 11	5 mils
MPI REX 6.3B-G6 (Gloss)	MPI 5	MPI 119	MPI 119	5 mils

C. Existing, dressed lumber, Wood and plywood, trim, including top, bottom and edges of doors previously coated with a latex / waterborne finish coat not otherwise specified

Latex

Existing, previously coated	Primer	Intermediate	Topcoat	System DFT
MPI REX 6.3L-G1 (Flat)	MPI 6	MPI 10	MPI 10	4.5 mils
MPI REX 6.3L-G5 (Semigloss)	MPI 6	MPI 11	MPI 11	4.5 mils
MPI REX 6.3L-G6 (Gloss)	MPI 6	MPI 119	MPI 119	4.5 mils
Topcoat: Coating to match adjacent surfaces.				

Waterborne Solid Color Stain				
Existing, previously coated	Primer	Intermediate	Topcoat	System DFT
MPI EXT 6.3K	MPI 6	MPI 16	MPI 16	4 mils
Topcoat: Coating to match adjacent surfaces.				

D. Wood Siding

(1) New, Uncoated wood siding

Semi-Transparent Stain				
New	Primer	Intermediate	Topcoat	System DFT
MPI EXT 6.3D	N/A	MPI 13	MPI 13	N/A
Topcoat: Coating to match adjacent surfaces.				

(2) Existing, previously stained wood siding

Latex				
Existing, previously stained	Primer	Intermediate	Topcoat	System DFT
MPI REX 6.2K-G1 (Flat)	MPI 5	MPI 10	MPI 10	4.5 mils

MPI REX 6.2K-G5 (Semigloss)	MPI 5	MPI 11	MPI 11	4.5 mils
Topcoat: Coating to match adjacent surfaces.				

(3) Existing Uncoated or previously semitransparent stained wood siding

Semi-Transparent Stain				
Existing	Primer	Intermediate	Topcoat	System DFT
MPI REX 6.3D	N/A	MPI 13	MPI 13	Per Manufacturer
Topcoat: Coating to match adjacent surfaces.				

E. Wood:

Latex Floor Paint				
New	Primer	Intermediate	Topcoat	System DFT
MPI EXT 6.5A-G2 (Flat)	MPI 5	MPI 60 plus NSA	MPI 60 plus NSA	4.5 mils
MPI EXT 6.5A-G6 (Gloss)	MPI 5	MPI 68 plus NSA	MPI 68 plus NSA	4.5 mils
Topcoat: Coating to match adjacent surfaces. Load non-skid additive (NSA) at manufacturer's recommendations.				

Alkyd Floor Paint				
New	Primer	Intermediate	Topcoat	System DFT
MPI EXT 6.5B-G2 (Flat)	MPI 59	MPI 59 plus NSA	MPI 59 plus NSA	5 mils
MPI EXT 6.5B-G6 (Gloss)	MPI 27	MPI 27 plus NSA	MPI 27 plus NSA	5 mils
Topcoat: Coating to match adjacent surfaces. Load non-skid additive (NSA) at manufacturer's recommendations.				

3.12.1.5 MPI Division 9: Exterior Stucco Paint Table

A. New and Existing stucco

Latex					
New	Existing	Primer	Intermediate	Topcoat	System DFT
MPI EXT 9.1A-G1 (Flat)	MPI REX 9.1A-G2 (Flat)	MPI 10	MPI 10	MPI 10	4.5 mils
MPI EXT 9.1A-G5 (Semigloss)	MPI REX 9.1A-G5 (Semigloss)	MPI 11	MPI 11	MPI 11	4.5 mils
MPI EXT 9.1A-G6 (Gloss)	MPI REX 9.1A-G6 (Gloss)	MPI 119	MPI 119	MPI 119	4.5 mils
Primer as recommended by manufacturer. Topcoat: Coating to match adjacent surfaces. On existing stucco, apply primer based on surface condition.					

B. New and Existing stucco, elastomeric system

Elastomeric Coating					
New	Existing	Primer	Intermediate	Topcoat	System DFT
MPI EXT 9.1C-G1 (Flat)	MPI REX 9.1C-G1 (Flat)	N/A	MPI 113	MPI 113	16 mils
Primer as recommended by manufacturer. Topcoat: Coating to match adjacent surfaces. Surface preparation and number of coats in accordance with manufacturer's instructions Apply sufficient coats of MPI 113 to achieve a minimum dry film thickness of 16 mils.					

3.12.1.6 MPI Division 10: Exterior Cloth Coverings and Bituminous Coated Surfaces Paint Table

A. Insulation and surfaces of insulation coverings (canvas, cloth, paper):
(Interior and Exterior Applications)

Latex				
New	Primer	Intermediate	Topcoat	System DFT
MPI EXT 10.1A-G1 (Flat)	N/A	MPI 10	MPI 10	3.2 mils
MPI EXT 10.1A-G5 (Semigloss)	N/A	MPI 11	MPI 11	3.2 mils
MPI EXT 10.1A-G6 (Gloss)	N/A	MPI 119	MPI 119	3.2 mils

Topcoat: Coating to match adjacent surfaces.

3.12.2 Interior Paint Tables

3.12.2.1 MPI Division 3: Interior Concrete Paint Table

A. New and uncoated existing and Existing, previously painted Concrete, vertical surfaces, not specified otherwise

Latex					
New, uncoated Existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI INT 3.1A-G2 (Flat)	MPI RIN 3.1A-G2 (Flat)	MPI 3	MPI 44	MPI 44	4 mils
MPI INT 3.1A-G3 (Eggshell)	MPI RIN 3.1A-G3 (Eggshell)	MPI 3	MPI 52	MPI 52	4 mils
MPI INT 3.1A-G5	MPI RIN 3.1A-G5 (Semigloss)	MPI 3	MPI 54	MPI 54	4 mils
Topcoat: Coating to match adjacent surfaces.					

High Performance Architectural Latex					
New, uncoated Existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI INT 3.1C-G2 (Flat)	MPI RIN 3.1J-G2 (Flat)	MPI 3	MPI 138	MPI 138	4 mils
MPI INT 3.1C-G3 (Eggshell)	MPI RIN 3.1J-G3 (Eggshell)	MPI 3	MPI 139	MPI 139	4 mils
MPI INT 3.1C-G4 (satin)	MPI RIN 3.1J-G4	MPI 3	MPI 140	MPI 140	4 mils
MPI INT 3.1C-G5 (Semigloss)	MPI RIN 3.1J-G5 (Semigloss)	MPI 3	MPI 141	MPI 141	4 mils
Topcoat: Coating to match adjacent surfaces.					

Institutional Low Odor / Low VOC Latex					
New, uncoated Existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI INT 3.1M-G2 (Flat)	MPI RIN 3.1L-G2 (Flat)	MPI 149	MPI 144	MPI 144	4 mils
MPI INT 3.1M-G3 (Eggshell)	MPI RIN 3.1L-G3 (Eggshell)	MPI 149	MPI 145	MPI 145	4 mils
MPI INT 3.1M-G4 (satin)	MPI RIN 3.1L-G4	MPI 149	MPI 146	MPI 146	4 mils
MPI INT 3.1M-G5 (Semigloss)	MPI RIN 3.1L-G5 (Semigloss)	MPI 149	MPI 147	MPI 147	4 mils
Topcoat: Coating to match adjacent surfaces.					

B. Concrete Ceilings, Uncoated

Latex Aggregate				
New, uncoated	Primer	Intermediate	Topcoat	System DFT
MPI INT 3.1N-G1 (Flat)	N/A	N/A	MPI 42	Per Manufacturer
Texture - Fine Medium Coarse. Surface preparation, number of coats, and primer in accordance with manufacturer's instructions. Topcoat: Coating to match adjacent surfaces.				

C. New and uncoated existing and Existing, previously painted Concrete in not otherwise specified except floors

Waterborne Light Industrial Coating					
New, uncoated Existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI INT 3.1L-G3 (Eggshell)	MPI RIN 3.1C-G3 (Eggshell)	MPI 3	MPI 151	MPI 151	4.8 mils
MPI INT 3.1L-G5 (Semigloss)	MPI RIN 3.1C-G5 (Semigloss)	MPI 3	MPI 153	MPI 153	4.8 mils

MPI INT 3.1L-G6 (Gloss)	MPI RIN 3.1C-G6 (Gloss)	MPI 3	MPI 154	MPI 154	4.8 mils
Topcoat: Coating to match adjacent surfaces.					

Alkyd					
New, uncoated Existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI INT 3.1D-G3 (Eggshell)	MPI RIN 3.1D-G3 (Eggshell)	MPI 3	MPI 51	MPI 51	4.5 mils
MPI INT 3.1D-G5 (Semigloss)	MPI RIN 3.1D-G5 (Semigloss)	MPI 3	MPI 47	MPI 47	4.5 mils
MPI INT 3.1D-G6 (Gloss)	MPI RIN 3.1D-G6 (Gloss)	MPI 3	MPI 48	MPI 48	4.5 mils
Topcoat: Coating to match adjacent surfaces.					

Epoxy					
New, uncoated Existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI INT 3.1F-G6 (Gloss)	MPI RIN 3.1E-G6 (Gloss)	MPI 77	MPI 77	MPI 77	4 mils
Note: Primer may be reduced for penetration per manufacturer's					

D. New and uncoated existing and Existing, previously painted concrete walls and bottom of swimming pools

Chlorinated Rubber					
New and uncoated existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
Chlorinated Rubber	Per Manufacturer	Per Manufacturer	Per Manufacturer	Per Manufacturer	Per Manufacturer

Note: Primer may be reduced for penetration per manufacturer's instructions.

Epoxy					
New, uncoated Existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI INT 3.1F	MPI RIN 3.1E	MPI 77	MPI 77	MPI 77	4 mils
Note: Primer may be reduced for penetration per manufacturer's instructions.					

E. New and uncoated existing and Existing, previously painted concrete floors in following areas

Latex Floor Paint					
New, uncoated Existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI INT 3.2A-G2 (Flat)	MPI RIN 3.2A-G2 (Flat)	MPI 60	MPI 60	MPI 60	5 mils

Alkyd Floor Paint					
New, uncoated Existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI INT 3.2B-G2 (Flat)	MPI RIN 3.2B-G2 (Flat)	MPI 59	MPI 59	MPI 59	5 mils
Note: Primer may be reduced for penetration per manufacturer's instructions.					

Epoxy					
New, uncoated Existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI INT 3.2C-G6 (Gloss)	MPI RIN 3.2C-G6 (Gloss)	MPI 77	MPI 77	MPI 77	5 mils

Note: Primer may be reduced for penetration per manufacturer's instructions.

3.12.2.2 MPI Division 4: Interior Concrete Masonry Units Paint Table

A. New and uncoated Existing Concrete Masonry

High Performance Architectural Latex					
New, uncoated Existing	Filler	Primer	Intermediate	Topcoat	System DFT
MPI INT 4.2D-G2 (Flat)	MPI 4	N/A	MPI 139	MPI 138	11 mils
MPI INT 4.2D-G3 (Eggshell)	MPI 4	N/A	MPI 139	MPI 139	11 mils
MPI INT 4.2D-G4 (Satin)	MPI 4	N/A	MPI 140	MPI 140	11 mils
MPI INT 4.2D-G5 (Semigloss)	MPI 4	N/A	MPI 141	MPI 141	11 mils
Fill all holes in masonry surface					

Institutional Low Odor / Low VOC Latex					
New, uncoated Existing	Filler	Primer	Intermediate	Topcoat	System DFT
MPI INT 4.2E-G2 (Flat)	MPI 4	N/A	MPI 144	MPI 144	4 mils
MPI INT 4.2E-G3 (Eggshell)	MPI 4	N/A	MPI 145	MPI 145	4 mils
MPI INT 4.2E-G4 (Satin)	MPI 4	N/A	MPI 146	MPI 146	4 mils
MPI INT 4.2E-G5 (Semigloss)	MPI 4	N/A	MPI 147	MPI 147	4 mils
Fill all holes in masonry surface					

B. Existing, Previously Painted Concrete Masonry

High Performance Architectural Latex

Existing, previously painted	Filler	Primer	Intermediate	Topcoat	System DFT
MPI RIN 4.2K-G2 (Flat)	N/A	MPI 138	MPI 138	MPI 138	4.5 mils
MPI RIN 4.2K-G3 (Eggshell)	N/A	MPI 139	MPI 139	MPI 139	4.5 mils
MPI RIN 4.2K-G4	N/A	MPI 140	MPI 140	MPI 140	4.5 mils
MPI RIN 4.2K-G5 (Semigloss)	N/A	MPI 141	MPI 141	MPI 141	4.5 mils

Institutional Low Odor / Low VOC Latex					
Existing, previously painted	Filler	Primer	Intermediate	Topcoat	System DFT
MPI RIN 4.2L-G2 (Flat)	N/A	MPI 144	MPI 144	MPI 144	4 mils
MPI RIN 4.2L-G3 (Eggshell)	N/A	MPI 145	MPI 145	MPI 145	4 mils
MPI RIN 4.2L-G4 (Satin)	N/A	MPI 146	MPI 146	MPI 146	4 mils
MPI RIN 4.2L-G5 (Semigloss)	N/A	MPI 147	MPI 147	MPI 147	4 mils

C. New and uncoated Existing Concrete masonry units in unless otherwise specified

Waterborne Light Industrial Coating					
New, uncoated Existing	Filler	Primer	Intermediate	Topcoat	System DFT
MPI INT 4.2K-G3 (Eggshell)	MPI 4	N/A	MPI 151	MPI 151	11 mils
MPI INT 4.2K-G5 (Semigloss)	MPI 4	N/A	MPI 153	MPI 153	11 mils
MPI INT 4.2K-G6 (Gloss)	MPI 4	N/A	MPI 154	MPI 154	11 mils

Fill all holes in masonry surface

Alkyd					
New, uncoated Existing	Filler	Primer	Intermediate	Topcoat	System DFT
MPI INT 4.2K-G3 (Eggshell)	MPI 4	MPI 50	MPI 51	MPI 51	12 mils
MPI INT 4.2K-G5 (Semigloss)	MPI 4	MPI 50	MPI 47	MPI 47	12 mils
MPI INT 4.2K-G6 (Gloss)	MPI 4	MPI 50	MPI 48	MPI 48	12 mils
Fill all holes in masonry surface					

Epoxy					
New, uncoated Existing	Filler	Primer	Intermediate	Topcoat	System DFT
MPI INT 4.2G-G6 (Gloss)	MPI 116	N/A	MPI 77	MPI 77	10 mils
Fill all holes in masonry surface					

D. Existing, previously painted, concrete masonry units in unless otherwise specified

Waterborne Light Industrial Coating					
Existing, previously painted	Filler	Primer	Intermediate	Topcoat	System DFT
MPI RIN 4.2G-G3 (Eggshell)	N/A	MPI 151	MPI 151	MPI 151	4.5 mils
MPI RIN 4.2G-G5 (Semigloss)	N/A	MPI 153	MPI 153	MPI 153	4.5 mils
MPI RIN 4.2G-G6 (Gloss)	N/A	MPI 154	MPI 154	MPI 154	4.5 mils

Alkyd					
Existing, previously painted	Filler	Primer	Intermediate	Topcoat	System DFT
MPI RIN 4.2C-G3 (Eggshell)	N/A	MPI 17	MPI 51	MPI 51	4.5 mils
MPI RIN 4.2C-G5 (Semigloss)	N/A	MPI 17	MPI 47	MPI 47	4.5 mils
MPI RIN 4.2C-G6 (Gloss)	N/A	MPI 17	MPI 48	MPI 48	4.5 mils

Epoxy					
Existing, previously painted	Filler	Primer	Intermediate	Topcoat	System DFT
MPI RIN 4.2D-G6 (Gloss)	N/A	MPI 77	MPI 77	MPI 77	5 mils

3.12.2.3 MPI Division 5: Interior Metal, Ferrous and Non-Ferrous Paint Table

A. Interior Steel / Ferrous Surfaces

(1) Metal, not otherwise specified except floors, hot metal surfaces, and new prefinished equipment

High Performance Architectural Latex				
New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT
MPI INT 5.1R-G2 (Flat)	MPI 76	MPI 138	MPI 138	5 mils
MPI INT 5.1R-G3 (Eggshell)	MPI 76	MPI 139	MPI 139	5 mils
MPI INT 5.1R-G5 (Semigloss)	MPI 76	MPI 141	MPI 141	5 mils
Topcoat: Coating to match adjacent surfaces.				

Alkyd

New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT
MPI INT 5.1E-G2 (Flat)	MPI 76	MPI 49	MPI 49	5.25 mils
MPI INT 5.1E-G3 (Eggshell)	MPI 76	MPI 51	MPI 51	5.25 mils
MPI INT 5.1E-G5 (Semigloss)	MPI 76	MPI 47	MPI 47	5.25 mils
MPI INT 5.1E-G6 (Gloss)	MPI 76	MPI 48	MPI 48	5.25 mils
Topcoat: Coating to match adjacent surfaces.				

(2) Metal floors (non-shop-primed surfaces or non-slip deck surfaces) with non-skid additive (NSA), load at manufacturer's recommendations

Alkyd (over q.d. Alkyd Primer)				
New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT
MPI INT 5.1E-G5 (Semi-Gloss)	MPI 76	MPI 47	MPI 47	5.25 mils
Topcoat: Coating to match adjacent surfaces.				

Epoxy				
New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT
MPI INT 5.1L-G6 (Gloss)	MPI 101	MPI 101	MPI 101	5.25 mils
Topcoat: Coating to match adjacent surfaces.				

(3) Metal in not otherwise specified except floors, hot metal surfaces, and new prefinished equipment

Alkyd				
New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT

MPI INT 5.1E-G3 (Eggshell)	MPI 76	MPI 51	MPI 51	5.25 mils
MPI INT 5.1E-G5 (Semigloss)	MPI 76	MPI 47	MPI 47	5.25 mils
MPI INT 5.1E-G6 (Gloss)	MPI 76	MPI 48	MPI 48	5.25 mils
Topcoat: Coating to match adjacent surfaces.				

Alkyd; For Hand Tool Cleaning				
New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT
MPI INT 5.1T-G3 (Eggshell)	MPI 23	MPI 51	MPI 51	5.25 mils
MPI INT 5.1T-G5 (Semigloss)	MPI 23	MPI 47	MPI 47	5.25 mils
MPI INT 5.1T-G6 (Gloss)	MPI 23	MPI 48	MPI 48	5.25 mils
Topcoat: Coating to match adjacent surfaces.				

(4) Ferrous metal in concealed damp spaces or in exposed areas having unpainted adjacent surfaces as follows:

Aluminum Paint				
New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT
MPI INT 5.1M	MPI 76	MPI 1	MPI 1	4.25 mils
Topcoat: Coating to match adjacent surfaces.				

(5) Miscellaneous non-ferrous metal items not otherwise specified except floors, hot metal surfaces, and new prefinished equipment. Match surrounding finish

High Performance Architectural Latex				
New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT

MPI INT 5.4F-G2 (Flat)	MPI 95	MPI 138	MPI 138	5 mils
MPI INT 5.4F-G3 (Eggshell)	MPI 95	MPI 139	MPI 139	5 mils
MPI INT 5.4F-G4 (Satin)	MPI 95	MPI 140	MPI 140	5 mils
MPI INT 5.4F-G5 (Semigloss)	MPI 95	MPI 141	MPI 141	5 mils
Topcoat: Coating to match adjacent surfaces.				

Alkyd				
New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT
MPI INT 5.4J-G2 (Flat)	MPI 95	MPI 49	MPI 49	5 mils
MPI INT 5.4J-G3 (Eggshell)	MPI 95	MPI 51	MPI 51	5 mils
MPI INT 5.4J-G5 (Semigloss)	MPI 95	MPI 47	MPI 47	5 mils
MPI INT 5.4J-G6 (Gloss)	MPI 95	MPI 48	MPI 48	5 mils
Topcoat: Coating to match adjacent surfaces.				

B. Hot Surfaces

(1) Hot metal surfaces subject to temperatures up to 400 degrees F

Heat Resistant Enamel				
New	N/A	Intermediate	Topcoat	System DFT
MPI INT 5.2A	MPI 21	N/A	N/A	Per Manufacturer
Surface preparation and number of coats per manufacturer's instructions.				

(2) Ferrous metal subject to high temperature, up to 750 degrees F

Inorganic Zinc Rich Coating				
New	N/A	Intermediate	Topcoat	System DFT
MPI INT 5.2C	MPI 19	N/A	N/A	Per Manufacturer
Surface preparation and number of coats per manufacturer's instructions.				

Heat Resistant Aluminum Enamel				
New	N/A	Intermediate	Topcoat	System DFT
MPI INT 5.2B (Aluminum Finish)	MPI 2	N/A	N/A	Per Manufacturer
Surface preparation and number of coats per manufacturer's instructions.				

(3) New and Existing Surfaces made bare subject to temperatures up to 1100 degrees F

(1) New surfaces and Existing surfaces made bare cleaning to SSPC SP 10/NACE No. 2 subject to temperatures up to 1100 degrees F:

Heat Resistant Coating					
New	Existing	N/A	Intermediate	Topcoat	System DFT
MPI INT 5.2D	MPI RIN 5.2D	MPI 22	N/A	N/A	Per Manufacturer
Surface preparation and number of coats per manufacturer's instructions.					

3.12.2.4 MPI Division 6: Interior Wood Paint Table

A. Interior Wood and Plywood

(1) New and Existing, uncoated Wood and plywood not otherwise specified

High Performance Architectural Latex				
New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT

MPI INT 6.4S-G3 (Eggshell)	MPI 39	MPI 139	MPI 139	4.5 mils
MPI INT 6.4S-G4 (Satin)	MPI 39	MPI 140	MPI 140	4.5 mils
MPI INT 6.4S-G5 (Semigloss)	MPI 39	MPI 141	MPI 141	4.5 mils
Topcoat: Coating to match adjacent surfaces.				

Alkyd				
New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.4B-G3 (Eggshell)	MPI 45	MPI 51	MPI 51	4.5 mils
MPI INT 6.4B-G5 (Semigloss)	MPI 45	MPI 47	MPI 47	4.5 mils
MPI INT 6.4B-G6 (Gloss)	MPI 45	MPI 48	MPI 48	4.5 mils
Topcoat: Coating to match adjacent surfaces.				

Institutional Low Odor / Low VOC Latex				
New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.3V-G2 (Flat)	MPI 39	MPI 144	MPI 144	4 mils
MPI INT 6.3V-G3 (Eggshell)	MPI 39	MPI 145	MPI 145	4 mils
MPI INT 6.3V-G4 (Satin)	MPI 39	MPI 146	MPI 146	4 mils
MPI INT 6.3V-G5 (Semigloss)	MPI 39	MPI 147	MPI 147	4 mils

(2) Existing, previously painted Wood and plywood not otherwise specified

High Performance Architectural Latex

Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI RIN 6.4B-G3 (Eggshell)	MPI 39	MPI 139	MPI 139	4.5 mils
MPI RIN 6.4B-G4 (Satin)	MPI 39	MPI 140	MPI 140	4.5 mils
MPI RIN 6.4B-G5 (Semigloss)	MPI 39	MPI 141	MPI 141	4.5 mils
Topcoat: Coating to match adjacent surfaces.				

Alkyd				
Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI RIN 6.4C-G3 (Eggshell)	MPI 46	MPI 51	MPI 51	4.5 mils
MPI RIN 6.4C-G5 (Semigloss)	MPI 46	MPI 47	MPI 47	4.5 mils
MPI RIN 6.4C-G6 (Gloss)	MPI 46	MPI 48	MPI 48	4.5 mils
Topcoat: Coating to match adjacent surfaces.				

Institutional Low Odor / Low VOC Latex				
Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI RIN 6.4D-G2 (Flat)	MPI 39	MPI 144	MPI 144	4 mils
MPI RIN 6.4D-G3 (Eggshell)	MPI 39	MPI 145	MPI 145	4 mils
MPI RIN 6.4D-G4 (Satin)	MPI 39	MPI 146	MPI 146	4 mils
MPI RIN 6.4D-G5 (Semigloss)	MPI 39	MPI 147	MPI 147	4 mils

B. Interior New and Existing, previously finished or stained Wood and

Plywood, except floors; natural finish or stained

Natural finish, oil-modified polyurethane					
New	Existing	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.4J-G4	MPI RIN 6.4L-G4	MPI 57	MPI 57	MPI 57	4 mils
MPI INT 6.4J-G6 (Gloss)	MPI RIN 6.4L-G6 (Gloss)	MPI 56	MPI 56	MPI 56	4 mils

Stained, oil-modified polyurethane						
New	Existing	Stain	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.4E-G4	MPI RIN 6.4G-G4	MPI 90	MPI 57	MPI 57	MPI 57	4 mils
MPI INT 6.4E-G6 (Gloss)	MPI RIN 6.4G-G6 (Gloss)	MPI 90	MPI 56	MPI 56	MPI 56	4 mils

Stained, Moisture Cured Urethane						
New	Existing	Stain	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.4V-G2 (Flat)	MPI RIN 6.4V-G2 (Flat)	MPI 90	MPI 71	MPI 71	MPI 71	4 mils
MPI INT 6.4V-G6 (Gloss)	MPI RIN 6.4V-G6 (Gloss)	MPI 90	MPI 31	MPI 31	MPI 31	4 mils

C. Interior New and Existing, previously finished or stained Wood Floors; Natural finish or stained

Natural finish, oil-modified polyurethane					
New	Existing, previously finished or stained	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.5C-G6 (Gloss)	MPI RIN 6.5C-G6 (Gloss)	MPI 56	MPI 56	MPI 56	4 mils

Natural finish, Moisture Cured Polyurethane					
New	Existing, previously finished or stained	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.5K-G6 (Gloss)	MPI RIN 6.5D-G6 (Gloss)	MPI 31	MPI 31	MPI 31	4 mils

Stained, oil-modified polyurethane						
New	Existing, previously finished or stained	Stain	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.5B-G6 (Gloss)	MPI RIN 6.5B-G6 (Gloss)	MPI 90	MPI 56	MPI 56	MPI 56	4 mils

Stained, Moisture Cured Urethane						
New	Existing, previously finished or stained	Stain	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.4V-G6 (Gloss)	MPI RIN 6.4V-G6 (Gloss)	MPI 90	MPI 31	MPI 31	MPI 31	4 mils

D. New and Existing, previously coated Wood floors; pigmented finish

Latex Floor Paint					
New	Existing, previously finished	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.5G-G2 (Flat)	MPI RIN 6.5J-G2 (Flat)	MPI 45	MPI 60	MPI 60	4.5 mils

MPI INT 6.5G-G6 (Gloss)	MPI RIN 6.5J-G6 (Gloss)	MPI 45	MPI 68	MPI 68	4.5 mils
Topcoat: Coating to match adjacent surfaces.					

Alkyd Floor Paint					
New	Existing, previously finished	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.5A-G2 (Flat)	MPI RIN 6.5A-G2 (Flat)	MPI 59	MPI 59	MPI 59	4.5 mils
MPI INT 6.5A-G6 (Gloss)	MPI RIN 6.5A-G6 (Gloss)	MPI 27	MPI 27	MPI 27	4.5 mils
Topcoat: Coating to match adjacent surfaces.					

E. Interior New and Existing, uncoated wood surfaces in not otherwise specified

High-Build Glaze Coatings
As specified in Section 09 96 59 HIGH-BUILD GLAZE COATINGS.

Waterborne Light Industrial				
New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.3P-G5 (Semigloss)	MPI 45	MPI 153	MPI 153	4.5 mils
MPI INT 6.3P-G6 (Gloss)	MPI 45	MPI 154	MPI 154	4.5 mils
Topcoat: Coating to match adjacent surfaces.				

Alkyd				
New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.3B-G5 (Semigloss)	MPI 45	MPI 47	MPI 47	4.5 mils
MPI INT 6.3B-G6 (Gloss)	MPI 45	MPI 48	MPI 48	4.5 mils
Topcoat: Coating to match adjacent surfaces.				

F. Existing, previously painted wood surfaces in not otherwise specified

High-Build Glaze Coatings
As specified in Section 09 96 59 HIGH-BUILD GLAZE COATINGS.

Waterborne Light Industrial				
Existing, previously finished	Primer	Intermediate	Topcoat	System DFT
MPI RIN 6.3P-G5 (Semigloss)	MPI 39	MPI 153	MPI 153	4.5 mils
MPI RIN 6.3P-G6 (Gloss)	MPI 39	MPI 154	MPI 154	4.5 mils
Topcoat: Coating to match adjacent surfaces.				

Alkyd				
Existing, previously finished	Primer	Intermediate	Topcoat	System DFT
MPI RIN 6.3B-G5 (Semigloss)	MPI 46	MPI 47	MPI 47	4.5 mils
MPI RIN 6.3B-G6 (Gloss)	MPI 46	MPI 48	MPI 48	4.5 mils
Topcoat: Coating to match adjacent surfaces.				

G. Interior New and Existing, previously finished or stained Wood Doors;

Natural Finish or Stained

Natural finish, oil-modified polyurethane					
New	Existing, previously finished or stained	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.3K-G4	MPI RIN 6.3K-G4	MPI 57	MPI 57	MPI 57	4 mils
MPI INT 6.3K-G6 (Gloss)	MPI RIN 6.3K-G6 (Gloss)	MPI 56	MPI 56	MPI 56	4 mils
Note: Sand between all coats per manufacturers recommendations.					

Stained, oil-modified polyurethane						
New	Existing, previously finished or stained	Stain	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.3E-G4	MPI RIN 6.3E-G4	MPI 90	MPI 57	MPI 57	MPI 57	4 mils
MPI INT 6.5B-G6 (Gloss)	MPI RIN 6.5B-G6 (Gloss)	MPI 90	MPI 56	MPI 56	MPI 56	4 mils
Note: Sand between all coats per manufacturers recommendations.						

Stained, Moisture Cured Urethane						
New	Existing, previously finished or stained	Stain	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.4V-G2 (Flat)	MPI RIN 6.4V-G2 (Flat)	MPI 90	MPI 71	MPI 71	MPI 71	4 mils
MPI INT 6.4V-G6 (Gloss)	MPI RIN 6.4V-G6 (Gloss)	MPI 90	MPI 31	MPI 31	MPI 31	4 mils
Note: Sand between all coats per manufacturers recommendations.						

H. New and Existing, uncoated Wood Doors; Pigmented finish

Alkyd				
New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.3B-G5 (Semigloss)	MPI 45	MPI 47	MPI 47	4.5 mils
MPI INT 6.3B-G6 (Gloss)	MPI 45	MPI 48	MPI 48	4.5 mils
Note: Sand between all coats per manufacturers recommendations.				

Pigmented Polyurethane				
New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT
MPI INT 6.1E-G6 (Gloss)	MPI 72	MPI 72	MPI 72	4.5 mils
Note: Sand between all coats per manufacturers recommendations.				

I. Existing, previously painted Wood Doors; Pigmented finish

Alkyd				
Existing, previously finished	Primer	Intermediate	Topcoat	System DFT
MPI RIN 6.3B-G5 (Semigloss)	MPI 46	MPI 47	MPI 47	4.5 mils
MPI RIN 6.3B-G6 (Gloss)	MPI 46	MPI 48	MPI 48	4.5 mils
Note: Sand between all coats per manufacturers recommendations.				

3.12.2.5 MPI Division 9: Interior Plaster, Gypsum Board, Textured Surfaces
Paint Table

A. Interior New and Existing, previously painted Plaster and Wallboard not
otherwise specified

Latex					
New	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT

MPI INT 9.2A-G2 (Flat)	RIN 9.2A-G2 (Flat)	MPI 50	MPI 44	MPI 44	4 mils
MPI INT 9.2A-G3 (Eggshell)	RIN 9.2A-G3 (Eggshell)	MPI 50	MPI 52	MPI 52	4 mils
MPI INT 9.2A-G5 (Semigloss)	RIN 9.2A-G5 (Semigloss)	MPI 50	MPI 54	MPI 54	4 mils
Topcoat: Coating to match adjacent surfaces.					

High Performance Architectural Latex - High Traffic Areas					
New	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI INT 9.2B-G2 (Flat)	MPI RIN 9.2B-G2 (Flat)	MPI 50	MPI 138	MPI 138	4 mils
MPI INT 9.2B-G3 (Eggshell)	MPI RIN 9.2B-G3 (Eggshell)	MPI 50	MPI 139	MPI 139	4 mils
MPI INT 9.2B-G5 (Semigloss)	MPI RIN 9.2B-G5 (Semigloss)	MPI 50	MPI 141	MPI 141	4 mils
Topcoat: Coating to match adjacent surfaces.					

Institutional Low Odor / Low VOC Latex, New

Institutional Low Odor / Low VOC Latex				
New	Primer	Intermediate	Topcoat	System DFT
MPI INT 9.2M-G2 (Flat)	MPI 149	MPI 144	MPI 144	4 mils
MPI INT 9.2M-G3 (Eggshell)	MPI 149	MPI 145	MPI 145	4 mils
MPI INT 9.2M-G4 (Satin)	MPI 149	MPI 146	MPI 146	4 mils
MPI INT 9.2M-G5 (Semigloss)	MPI 149	MPI 147	MPI 147	4 mils
Topcoat: Coating to match adjacent surfaces.				

Institutional Low Odor / Low VOC Latex, Existing, previously painted

Institutional Low Odor / Low VOC Latex				
Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI RIN 9.2M-G2 (Flat)	MPI 144	MPI 144	MPI 144	4 mils
MPI RIN 9.2M-G3 (Eggshell)	MPI 144	MPI 145	MPI 145	4 mils
MPI RIN 9.2M-G4 (Satin)	MPI 144	MPI 146	MPI 146	4 mils
MPI RIN 9.2M-G5 (Semigloss)	MPI 144	MPI 147	MPI 147	4 mils
Topcoat: Coating to match adjacent surfaces.				

B. Interior New and Existing, previously painted Plaster and Wallboard in not otherwise specified

Waterborne Light Industrial Coating					
New, uncoated Existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI INT 9.2L-G5 (Semigloss)	MPI RIN 9.2L-G5 (Semigloss)	MPI 50	MPI 153	MPI 153	4 mils
Topcoat: Coating to match adjacent surfaces.					

Alkyd					
New, uncoated Existing	Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI INT 9.2C-G5 (Semigloss)	MPI RIN 9.2C-G5 (Semigloss)	MPI 50	MPI 47	MPI 47	4 mils
Topcoat: Coating to match adjacent surfaces.					

Epoxy, New, uncoated Existing

Epoxy

New, uncoated Existing	Primer	Intermediate	Topcoat	System DFT
MPI INT 9.2E-G6 (Gloss)	MPI 50	MPI 77	MPI 77	4 mils
Topcoat: Coating to match adjacent surfaces.				

Epoxy, Existing, previously painted

Epoxy				
Existing, previously painted	Primer	Intermediate	Topcoat	System DFT
MPI RIN 9.2D-G6 (Gloss)	MPI 17	MPI 77	MPI 77	4 mils
Topcoat: Coating to match adjacent surfaces.				

-- End of Section --