Pune Packaging Test Laboratory (fictional)

Test Report No: PPTL/26/0388 Date: 05-08-2026

Customer: Shree Ganesh Corrugators, Chakan, Pune

Test: Bursting factor (IS 1060) and grammage of corrugated board samples

Ply	Flute	Liner GSM	BF
3	B	120	16.5
3	B	150	18.4
5	BC	120	16.2
5	BC	150	18.5
5	BC	180	22.3
7	BCB	200	24.6

Result: Samples tested as received. Results relate only to the samples tested.