Sabarmati Board Testing Centre (fictional)

Test Report No: SBTC/26/1021 Date: 12-05-2026

Customer: Ahmedabad Packwell Industries, GIDC Vatva, Ahmedabad

Test: Bursting factor (IS 1060) and grammage of corrugated board samples

Ply	Flute	Liner GSM	BF
3	B	150	18.7
5	BC	180	22.6
7	BCB	200	24.4

Result: Samples tested as received. Results relate only to the samples tested.