Hosur Paperboard Testing Centre (fictional)

Test Report No: HPTC/2026/0631 Date: 14-07-2026

Customer: Southern Flute Packaging, SIPCOT Phase II, Hosur

Test: Bursting factor (IS 1060) and grammage of corrugated board samples

Ply	Flute	Liner GSM	BF
3	B	150	17.6
5	BC	180	22.5
7	BCB	200	24.3

Result: Samples tested as received. Results relate only to the samples tested.