



Mikrosize®

Salt Spray Test Chamber



Testing Interface

- 1. Salt spray test: NSS, ACSS
 - (1.) Laboratory: $35^{\circ}\text{C} \pm 1^{\circ}\text{C}$
 - (2.) Saturated air tank: $47^{\circ}\text{C} \pm 1^{\circ}\text{C}$
- 2. Acetic acid mist test: NSS, ACSS
 - (1.) Laboratory: $50^{\circ}\text{C} \pm 1^{\circ}\text{C}$
 - (2.) Saturated air chamber: $63^{\circ}\text{C} \pm 1^{\circ}\text{C}$

Add glacial acetic acid to make the pH of the test solution 3.1~3.3

- 3. Copper speed test: CASS

(1.) Laboratory: $58^{\circ}\text{C} \pm 1$

(2.) Saturated air tank: $65^{\circ}\text{C} \pm 1^{\circ}\text{C}$

Add glacial acetic acid to make the pH of the test solution 3.1~3.3, and prepare 0.02%~0.025% copper chloride.



บริการติดตั้ง สอนการใช้งาน



รับประกัน 1 ปี (ภายใต้การใช้งาน)

Model	MS-60M	MS-90M	MS-120M
Volume (L)	108L	270L	576L
Analysis Accuracy	$\pm 0.1^{\circ}\text{C}$		
Control Accuracy	$\pm 1.0^{\circ}\text{C}$		
Distribution Accuracy	$\pm 2.0^{\circ}\text{C}$		
Opening Method	Manual Opening	Manual Opening	Auto Opening
Case Temperature	$35^{\circ}\text{C} \pm 1^{\circ}\text{C} / 50^{\circ}\text{C} \pm 1^{\circ}\text{C}$		
Pressure Tank	$47^{\circ}\text{C} \pm 1^{\circ}\text{C} / 63^{\circ}\text{C} \pm 1^{\circ}\text{C}$		
Temperature Uniformity	$\leq \pm 2^{\circ}\text{C}$		
Temperature Fluctuation	$\leq \pm 0.5^{\circ}\text{C}$		
Salt Spray Deposition	1~2ml/h.80cm ²		
Spray Pressure	1.00 $\pm$ 0.01kgf/cm ²		
Spray Pattern	Continuous spray + alternating spray		
Maximum Load Capacity	3.0KVA		
Maximum Operating Current	15A		
Chamber Dimensions (mm)	L600*W400*H450mm	L900*W600*H500mm	L1200*W800*H600mm
Weight	60kg	90kg	200kg
Power	1.8kw	3kw	3kw
Power Supply Voltage	AC220V $\pm$ 10%/50Hz/60Hz		