

Project: InstaDust Gloss

Date: 2026-06-08

Formulation: ID-007

Ingredients: PVA 46%

Water 45%

Dibutyl phthalate 4%

Polyvinyl alcohol 4%

Defoamer 1%

Block Shear Strength Test ASTM D905

Wood: Hard Maple

Dry Shear Strength: 3000 psi

Wood Failure: 80%