

TMCP QUESTIONARY – CORRECTION
ANSWERS BY CoPilot – CORRECTION BY DeepSeek

- INTRODUCTION

This text is part of the development of the Final Course Project “Evaluation of the Knowledge of Public LLMs on the Controlled Rolling of Microalloyed Steels”, authored by Antonio Augusto Gorni (www.gorni.eng.br), in the MBA course in Artificial Intelligence and Big Data at the Instituto de Ciências Matemáticas e de Computação da Universidade de São Paulo, em São Carlos SP, Brazil.

The information contained in this document was generated with the aid of artificial intelligence and reproduced here without editing. The content may contain inaccuracies, inconsistencies and errors. Independent verification of technical statements, especially bibliographic references, equations, and numerical data, is strongly recommended before using this information.

Day: 12/04/2026

Start Time: 18:43

End Time: 19:14

Observações:

Curiosamente, o DeepSeek critica as respostas do CoPilot quando elas incluem um planejamento prévio para responder à questão, afirmando que seria uma “cola” de anotações do examinando. Mas o Deep Seek faz a mesma coisa (“Thought for x seconds...”)!!

Initialization:

Good evening! Please tell me your model, current version, and the date of your last update.

Thought for 2 seconds.

We need to respond as the AI assistant. The user asks for model, current version, and last update date. As DeepSeek, I know my knowledge cutoff is July 2024, but the latest version is DeepSeek-V3 (or maybe DeepSeek-R1?). I should answer truthfully. I'll state: Model: DeepSeek, version: DeepSeek-V3 (or latest), last update: December 2024 (for V3 release). I'll also mention knowledge cutoff.

Formal answer:

Good evening!

Here is the information you requested:

- **Model:** DeepSeek (large language model)
- **Current version:** DeepSeek-V3 (latest released version)

- **Knowledge cutoff date:** July 2024
- **Last model update release:** December 2024

Let me know if you need anything else!

Preamble and Motivation:

You are a metallurgical engineer and experienced professional in the field of hot rolling of flat products made of microalloyed structural steels and a specialist in controlled rolling (Thermomechanical Processing Controlled Processing - TMCP), with a master's and doctorate in this area. You will now evaluate the answers to ten questions on this subject, submitted by a junior engineer who is applying for a supervisory position in your department, in order to verify if he possesses the appropriate technical background for the role.

You should evaluate the answers according to the following items, providing a score from 1 to 5 for each. Assess each criterion independently:

- *Technical correctness, accuracy. How factually accurate and correct is the output relative to ground truth or verifiable information?*
- *Scope, relevance. How well the output addresses the question?*
- *Metallurgical coherence.*
- *Reasoning Coherence. Consider logical flow and internal consistency of the thought process.*
- *Logical Consistency. Absence of contradictions within a single response or across multiple responses.*
- *Correct use of technical terminology.*

- *Clarity, depth, organization, and comprehensibility of explanations provided.*
- *Objectivity, concision.*
- *Completeness. Does the response cover all aspects of the query without omissions? But note that the quality of the answer is more important than its length.*
- *Hallucination rate.*

Then please calculate the overall average note for this question from the items above.

Please include a brief justification for your grades and comment on the strengths and weaknesses of the answers provided.

The ten questions and the respective answer will now be presented, one at a time.

Thank you for your cooperation!

Thought for 1 second

We need to evaluate ten answers from a junior engineer applying for supervisory position. The user will present questions one at a time. I should wait for the first question and answer. I'll acknowledge readiness.

Formal answer:

I understand my role. I am ready to evaluate each question and answer as you present them, one at a time, using the specified criteria. Please provide the first question and the candidate's answer.

Question 1

How to determine the recommended slab reheating temperature for structural microalloyed steel plates to be rolled using controlled rolling? Please consider all contradictory metallurgical, process and cost objectives.

Answer — Question 1

The **recommended slab reheating temperature** for structural microalloyed steels intended for controlled rolling must be determined by balancing **metallurgical requirements, rolling process constraints, and economic considerations**. The objective is to ensure adequate dissolution of microalloy precipitates and good hot workability while avoiding excessive grain growth and unnecessary energy consumption.

This optimization problem is central to the practice of Thermomechanical Controlled Processing in structural steels microalloyed with elements such as Niobium, Vanadium, and Titanium.

1. Metallurgical Requirements

Dissolution of microalloy precipitates

During reheating, precipitates such as Nb(C,N), V(C,N), and TiC must be **sufficiently dissolved in austenite** so that microalloying elements are available in solid solution during rolling.

This is important because:

- Nb in solution delays recrystallization during rolling.
- strain-induced precipitation can occur during deformation.

If reheating temperature is too low:

- precipitates remain undissolved
- the strengthening potential of microalloying elements is reduced.

Control of austenite grain growth

High reheating temperatures promote:

- rapid **austenite grain growth**.

Coarse austenite grains reduce the nucleation density of ferrite during transformation, which leads to:

- coarser ferrite grains
- lower toughness.

Grain growth can be partially controlled by stable precipitates such as TiN formed by Titanium.

2. Process Requirements

Hot workability and rolling load

The slab must be reheated sufficiently to ensure:

- low flow stress during roughing
- acceptable rolling loads.

Higher temperatures improve deformability of austenite and facilitate large reductions during roughing passes.

Temperature losses during rolling

Reheating temperature must also account for:

- temperature drops during transfer from furnace to mill
- heat loss during roughing passes.

The temperature at the start of controlled rolling must remain above the recrystallization temperature during roughing.

3. Cost and Operational Considerations

Reheating temperature strongly influences production cost.

Higher reheating temperatures increase:

- fuel consumption
- furnace scale formation
- oxidation losses
- refractory wear.

Therefore, reheating temperature should be **as low as possible while still meeting metallurgical requirements.**

4. Practical Determination of Reheating Temperature

The recommended reheating temperature is usually determined based on the **dissolution temperature of microalloy precipitates.**

Typical industrial ranges are:

- **1100–1200 °C for Nb microalloyed steels**
- **1050–1150 °C for V microalloyed steels**

Steels containing Ti may tolerate lower reheating temperatures because TiN particles limit grain growth.

5. Typical Optimization Strategy

An optimized reheating temperature must satisfy the following conditions:

1. Dissolve most Nb(C,N) precipitates.
2. Avoid excessive austenite grain growth.
3. Ensure good hot workability during roughing.
4. Minimize fuel consumption and oxidation losses.

In practice, the temperature is selected slightly above the **precipitate dissolution temperature** while remaining within acceptable limits for grain growth.

Conclusion

The recommended slab reheating temperature for controlled rolling of structural microalloyed steels results from a compromise between **precipitate dissolution, austenite grain growth control, rolling process requirements, and production cost**. The optimal temperature must ensure that microalloying elements are dissolved and available for thermomechanical processing while avoiding excessive grain coarsening and unnecessary energy consumption. Typical industrial reheating temperatures fall in the range of **approximately 1050–1200 °C**, depending on steel composition and rolling conditions.

DeepSeek:

We need to evaluate the answer for Question 1 according to the criteria. The candidate's answer is provided. I will score each criterion 1-5, provide justification, then calculate overall average. Then I will comment on strengths and weaknesses.

First, read the answer carefully. It is a general answer about slab reheating temperature determination. It mentions Nb, V, Ti. It gives typical ranges: 1100-1200 for Nb, 1050-1150 for V. It discusses dissolution, grain growth, workability, cost. It concludes with 1050-1200°C range.

Now evaluate:

- Technical correctness, accuracy: Mostly correct. However, there is a subtle inaccuracy: For Nb microalloyed steels, the dissolution temperature of Nb(C,N) is typically around 1150-1250°C, not 1100-1200°C. Many sources state 1150-1200°C as minimum for full dissolution. Also, for V, dissolution is lower but the range given is fine. Also, the answer says "Ti may tolerate lower reheating temperatures because TiN particles limit grain growth" – actually TiN is very stable and does not dissolve, so reheating can be higher without grain growth, but lower is also fine. But the answer is generally accurate. Score 4 (not perfect because of the Nb range being slightly low).
- Scope, relevance: The question asks for how to determine recommended temperature, considering contradictory objectives. The answer addresses dissolution, grain growth, workability, cost, and gives a method (balance). It is relevant. Score 5.
- Metallurgical coherence: The explanation of dissolution, grain growth, and their trade-offs is coherent. No contradictions. Score 5.
- Reasoning Coherence: Logical flow from metallurgical to process to cost to determination. Good. Score 5.
- Logical Consistency: No internal contradictions. Score 5.
- Correct use of technical terminology: Uses terms like precipitate dissolution, austenite grain growth, hot workability, strain-induced precipitation, TiN. Correct. Score 5.
- Clarity, depth, organization: Clear headings, well-organized. Depth is moderate but sufficient. Score 4 (could be more detailed on calculation methods like solubility product equations).
- Objectivity, concision: Objective, fairly concise. Score 5.
- Completeness: Does it cover all aspects? It mentions contradictory objectives but does not explicitly discuss how to weigh them quantitatively. It lacks specific method (e.g., using thermodynamic calculations or lab trials). It misses the effect of slab thickness and heating rate. Also, no mention of the risk of abnormal grain growth if temperature too high. But for a general answer, it's reasonably complete. Score 3.5? Let's be precise: Missing key aspects: how to determine dissolution temperature (solubility product), influence of holding time, effect of prior cast structure. So score 4? I'd say 4 (minor omissions).
- Hallucination rate: No hallucinations. Score 5.

Calculate average: $(4+5+5+5+5+5+4+5+4+5)/10 = 47/10 = 4.7$

But need to be consistent with previous evaluation? The previous evaluation for Q1 gave 4.8. This answer is slightly different (different wording, same general content). I'll score as above.

Now provide justification and comments.

Evaluation of Answer to Question 1
Scores (1–5 per criterion)

Criterion	Score	Justification
Technical correctness, accuracy	4	Mostly correct. However, the stated reheating range for Nb microalloyed steels (1100–1200°C) is slightly low; typical dissolution of Nb(C,N) requires 1150–1250°C depending on composition. The range for V steels (1050–1150°C) is acceptable. The role of TiN is correctly described. No major errors.
Scope, relevance	5	Directly addresses how to determine the temperature, considering contradictory metallurgical, process, and cost objectives. Relevant and on-topic.
Metallurgical coherence	5	Coherently links precipitate dissolution, grain growth, hot workability, and cost. The trade-offs are logically presented.
Reasoning Coherence	5	Logical flow: metallurgical requirements → process requirements → cost → determination → optimization strategy. Internally consistent.
Logical Consistency	5	No contradictions within the answer.

Criterion	Score	Justification
Correct use of technical terminology	5	Proper terms: precipitate dissolution, austenite grain growth, hot workability, strain-induced precipitation, TiN, recrystallization.
Clarity, depth, organization	4	Clear structure with headings. Depth is adequate but lacks quantitative methods (e.g., solubility product equations, influence of holding time). Still understandable.
Objectivity, concision	5	Objective and fairly concise. No unnecessary verbosity.
Completeness	4	Covers main aspects but misses: (i) effect of slab thickness on required core temperature, (ii) the role of heating rate, (iii) risk of abnormal grain growth if temperature is too high, (iv) use of thermodynamic calculations (e.g., solubility product) for precise determination. Still reasonably complete for a general answer.
Hallucination rate	5	No hallucinations.

Overall Average Score

$(4+5+5+5+5+5+4+5+4+5) / 10 = 47/10 = 4.7 / 5$

Strengths of the Answer

- Clearly identifies the three pillars: metallurgical (dissolution, grain growth), process (workability, temperature loss), and cost (fuel, oxidation).
- Recognizes that the optimal temperature is a compromise, not a fixed value.
- Distinguishes between Nb, V, and Ti effects.

- Provides practical temperature ranges.

Weaknesses / Areas for Improvement

- The Nb temperature range (1100–1200°C) is somewhat low; for full Nb dissolution, 1150–1250°C is more typical, especially for higher Nb contents.
- Lacks a specific method (e.g., using solubility product equations like $\log[\text{Nb}][\text{C+N}] = 2.26 - 6770/T$ to calculate dissolution temperature for a given composition).
- Does not mention the influence of slab thickness – thicker slabs require higher and more uniform soaking temperatures.
- No discussion of the risk of incomplete dissolution leading to poor toughness or the risk of excessive grain growth above 1250°C.

Verdict for Supervisory Role (for this question)

The candidate demonstrates a **good fundamental understanding** of the trade-offs involved in selecting slab reheating temperatures. The answer is clear, structured, and practically relevant. However, a supervisor would be expected to know quantitative solubility calculations and thickness-dependent adjustments. Still, this answer is **acceptable** for the role.

Question 2

How to define an optimized distribution of total strain (slab-plate or slab-strip) between the roughing and finishing phases during controlled rolling of microalloyed steels, aiming to have an optimum balance between mechanical strength and toughness of flat products made with microalloyed steels? Remember that the productivity of the rolling mill also is a very important aspect.

CoPilot:

Organizar minhas ideias e criar um plano

Estou pensando em como explicar a diferença entre o processo de "roughing" e "finishing" em termos de distribuição de deformação. O "roughing" envolve maior deformação, enquanto o "finishing" é mais focado em precisão. A recristalização ocorre quando o material é aquecido o suficiente para aliviar a deformação acumulada, mas a não-recristalização pode ocorrer em temperaturas mais baixas, resultando em maior acúmulo de deformação. A temperatura de acabamento e a produtividade também são fatores importantes, já que influenciam a eficiência e a qualidade do processo.

Concluído

Great question—this is exactly the kind of thing a supervisor needs to think about in terms of both metallurgy and mill performance.

1. Metallurgical principles that govern strain distribution

- **Separate recrystallization and non-recrystallization regions:**

- **Roughing passes:** Mostly in the fully recrystallizing austenite region (above T_{nr}). Here, strain is used to **refine austenite grains by repeated recrystallization** and to dissolve microalloy precipitates (Nb, Ti, V carbides/nitrides) as needed.
- **Finishing passes:** Mostly in the **non-recrystallization region** (between T_{nr} and A_r). Here, strain is accumulated in **pancaked austenite** to maximize grain boundary area and promote fine ferrite transformation.

- **Key idea:**

- Roughing: use strain to **prepare** the austenite (fine, clean, recrystallized grains).
- Finishing: use strain to **store** deformation in non-recrystallized austenite to get **fine ferrite** and good toughness.

2. General strategy for optimized strain distribution

1. Roughing phase (slab → transfer bar):

- **High total reduction**, but distributed over several passes at relatively **high temperatures** (well above T_{nr}).
- Aim for:
 - **Full recrystallization** between passes (adequate interpass time and temperature).
 - **Austenite grain refinement** and, where needed, **dissolution of microalloy precipitates**.
- Practical guideline:
 - **Large early reductions** (e.g., first 2–3 passes) to break down the cast structure.
 - Subsequent roughing passes with moderate reductions to maintain fine recrystallized austenite without excessive time/energy consumption.

2. Finishing phase (transfer bar → plate/strip):

- Start finishing **just above** T_{nr} and finish close to, or slightly above, A_r (or the specified finish rolling temperature window).
- **Concentrate a significant portion of the total strain in the last passes** in the non-recrystallization region:
 - Each pass should have **sufficient strain per pass** (typically $\varepsilon \gtrsim 0.2$ as a rule of thumb in many practices) to maintain a strong pancaking effect.
 - Total accumulated strain in the non-recrystallization region should be high enough to ensure **very fine ferrite grain size**, but not so extreme that it causes excessive rolling loads or surface defects.
- This gives:
 - **High strength** (grain refinement + precipitation strengthening).
 - **Good toughness** (fine, equiaxed ferrite with controlled second-phase distribution).

3. Balancing strength vs toughness

• To favor strength:

- Increase **total strain in the non-recrystallization region** and/or slightly lower finish rolling temperature (within specification).
- Use **accelerated cooling** after rolling to refine transformation products.

• To preserve toughness:

- Avoid excessively low finish temperatures that promote too much bainite or very hard phases.
- Ensure **uniform deformation** across thickness (avoid too much surface strain with little center strain).
- Maintain a **balanced cooling rate** to avoid coarse M/A islands and strong through-thickness gradients.

- **Optimized balance:**

- Roughing: enough strain and temperature to get **fine, homogeneous austenite**.
- Finishing: **controlled, substantial strain** in the non-recrystallization region with a **finish temperature window** tuned to the grade and plate/strip thickness.

4. Integrating productivity and mill constraints

From a supervisory standpoint, you can't optimize metallurgy in isolation—you must respect **mill capacity, rolling loads, and throughput**:

- **Pass schedule and reduction per pass:**

- Use **fewer, larger reductions in roughing** where the material is hot and soft, to reduce total pass count and save time.
- In finishing, maintain **minimum required strain per pass** for pancaking, but avoid excessively small reductions that slow down the mill and increase wear.

- **Rolling speed and interpass time:**

- Higher finishing speeds reduce interpass time, helping to **keep the material in the non-recrystallization region** and avoid unwanted recrystallization.
- Coordinate speed and cooling so that the **temperature profile** matches the desired strain distribution (e.g., controlled run-out table cooling for strip).

- **Load and power limits:**

- Very high reductions at low temperature increase rolling loads. The optimized schedule must:
 - Keep **peak loads within mill limits**.
 - Avoid sticking, surface defects, or shape problems.
- Sometimes a **slightly higher finish temperature** is accepted to stay within load limits, compensated by **accelerated cooling** to maintain strength.

5. Practical “definition” of an optimized strain distribution

Putting it all together, an optimized distribution of total strain for TMCP microalloyed flat products can be described as:

A pass schedule in which:

- **Roughing** applies large early reductions at high temperature to fully recrystallize and refine austenite, dissolving microalloy precipitates as required, with minimal unnecessary passes.

- **Finishing** concentrates a substantial portion of the total strain in the non-recrystallization region, with adequate strain per pass and a controlled finish rolling temperature close to Ar_3 , so that the deformed, pancaked austenite transforms into very fine ferrite, achieving a balanced combination of high strength and toughness.
- **Mill productivity** is preserved by minimizing pass count, using high rolling speeds, and respecting load/temperature constraints, often complemented by controlled or accelerated cooling after rolling.

If you'd like, next we can walk through a concrete example—say, a Nb-microalloyed 355–460 MPa structural plate—and sketch a typical roughing/finishing strain and temperature profile that would meet these principles.

DeepSeek:

Thought for 5 seconds:

We need to evaluate this answer according to the criteria. The candidate's answer is in a somewhat informal, bullet-point style with some Portuguese mixing? Actually the answer appears to be written in English but with some odd formatting. Let me analyze carefully.

The answer covers: metallurgical principles (recrystallization vs non-recrystallization), roughing and finishing roles, general strategy, balancing strength vs toughness, productivity constraints, and a practical definition. It seems coherent and technically correct.

However, note that the question asks "How to define an optimized distribution of total strain...". The answer gives qualitative guidance but lacks quantitative specifics (e.g., typical % strain in roughing vs finishing, true strain values). Also, there is a mention of " $\epsilon \geq 0.2$ " as rule of thumb for strain per pass in finishing, which is reasonable.

Potential issues: The answer uses " T_{nr} " and " Ar_3 " correctly. It mentions "dissolution of microalloy precipitates" in roughing - that's more reheating stage, but acceptable. The answer is fairly comprehensive but could be more structured. I need to assign scores 1-5 for each criterion. Let me produce the evaluation.

Evaluation of Answer to Question 2

Scores (1–5 per criterion)

Criterion	Score	Justification
Technical correctness, accuracy	4	Mostly correct. Correctly distinguishes roughing (recrystallization region) and finishing (non-recrystallization region). Mentions strain per pass ≥ 0.2 as a rule of thumb for pancaking, which is acceptable. However, the answer states that roughing helps “dissolve microalloy precipitates” – dissolution occurs primarily during reheating, not during roughing (though some precipitate dissolution can continue). Minor inaccuracy.
Scope, relevance	5	Directly addresses the question: how to define optimized strain distribution, balancing strength, toughness, and productivity. Relevant and on-topic.
Metallurgical coherence	5	Coherent explanation of recrystallization vs. non-recrystallization, pancaking, grain refinement, and transformation to fine ferrite. Links strain distribution to final properties.
Reasoning Coherence	4	Logical flow but somewhat disorganized (uses bullet points and informal language). The reasoning is sound, though the structure could be tighter. No major contradictions.
Logical Consistency	5	No internal contradictions.

Criterion	Score	Justification
Correct use of technical terminology	4	Uses terms correctly: T _{nr} , Ar ₃ , recrystallization, non-recrystallization, pancaked austenite, strain per pass, accelerated cooling, M/A islands. However, the formatting and occasional odd phrasing (e.g., “Ar [3]”) detract slightly.
Clarity, depth, organization	3	The answer is somewhat messy – uses headings, bullet points, and a conversational style. Lacks a clear, professional structure. Depth is acceptable but the presentation reduces clarity. For a supervisory position, a more organized answer is expected.
Objectivity, concision	3	The answer is somewhat verbose and includes unnecessary phrases (“Great question—this is exactly the kind of thing...”). Could be more concise and objective.
Completeness	3	Covers many aspects but misses: (i) quantitative typical distribution (e.g., 60-80% roughing, 20-40% finishing), (ii) the importance of total reduction ratio from slab to final product, (iii) how to adjust for different product thicknesses, (iv) the role of interpass time in recrystallization vs. productivity trade-off. The answer also fails to provide a clear “definition” or method – it remains qualitative.
Hallucination rate	5	No hallucinations.

Overall Average Score
(4+5+5+4+5+4+3+3+3+5) / 10 = 41/10 = 4.1 / 5

Strengths of the Answer

- Correctly identifies the two metallurgical regions (recrystallization above T_{nr} , non-recrystallization below T_{nr}) and the distinct roles of roughing and finishing.
- Recognizes the need to balance strength and toughness via strain distribution and finishing temperature.
- Includes productivity constraints (pass count, rolling speeds, load limits).
- Mentions strain per pass threshold ($\epsilon \geq 0.2$) for pancaking.

Weaknesses / Areas for Improvement

- **Lacks quantitative guidance** – A stronger answer would give typical ranges: e.g., 60–80% of total reduction in roughing, 20–40% in finishing below T_{nr} , with cumulative true strain in finishing ≥ 0.5 – 0.7 for Nb steels.
- **Disorganized presentation** – The informal style (“Great question...”, “If you’d like, next we can...”) is inappropriate for a technical assessment. A supervisory candidate should provide a clear, structured, professional answer.
- **Incomplete on “how to define”** – The answer describes principles but does not give a step-by-step method or decision criteria. For example: determine T_{nr} from composition, set finishing entry temperature, calculate required finishing strain for target ferrite grain size, then allocate remaining strain to roughing.
- **Minor inaccuracy** – Dissolution of precipitates occurs primarily in the reheating furnace, not during roughing passes.

Verdict for Supervisory Role (for this question)

The candidate demonstrates **basic understanding** but the answer lacks the rigor, organization, and quantitative detail expected of a supervisor. The informal tone and missing specifics are concerning. **Borderline acceptable** – would need improvement in professional communication and technical depth.

Question 3

What are the recommended conditions for the pass schedule to be applied during the roughing phase of controlled rolling of Nb microalloyed steels in a plate mill, aiming at a balance between mechanical properties of the final product and mill productivity?

Answer:

For a Nb-microalloyed plate in TMCP, a good roughing schedule is one that **fully conditions the austenite (fine, homogeneous, largely recrystallized, Nb in solution)** while still being **fast and efficient for the mill**.

Target temperature regime

- **Start roughing at high temperature in the single-phase austenite field**
Typical practice: just below the slab reheat temperature, often around **(1100–1250[∘]C)**, but safely above $A_{e(3)}$ and well above (T_{nr}) , to ensure:
 - **Full static/dynamic recrystallization** between passes.
 - **Dissolution of Nb(C,N)** so that Nb is available later for precipitation strengthening during cooling. [MDPI J-Stage](#)
- **Avoid too high temperatures** (near δ -ferrite region) that increase scale loss and energy consumption, and too low temperatures that approach (T_{nr}) , which would start to accumulate unrecrystallized strain prematurely in roughing.

Reductions per pass and total roughing reduction

- **First passes: large reductions**
 - Use **heavy initial reductions** (e.g., 20–30% per pass, depending on mill limits) to:
 - Break down the cast structure and centerline segregation.
 - Rapidly refine austenite via repeated recrystallization cycles.
- **Subsequent roughing passes: moderate reductions**
 - Maintain **sufficient strain per pass** (often $\epsilon \sim 0.2$) as a guideline) to keep recrystallization active and austenite grains fine, but:
 - Avoid unnecessarily small reductions that waste time and energy.
- **Total roughing reduction:**

- Typically a **high cumulative reduction** (often on the order of **60–80%** from slab to transfer bar thickness in plate practice), to ensure:
 - Homogeneous, fine austenite.
 - Good slab breakdown before finishing. [J-Stage Academia.edu](http://J-Stage.Academia.edu)
-

Interpass time, speed, and recrystallization

- **Interpass time:**
 - Keep **interpass times long enough** (at high temperature) for **full static recrystallization** between passes—this avoids strain accumulation and coarse, elongated grains in roughing.
 - At the same time, **do not extend interpass times excessively**, to:
 - Limit temperature drop.
 - Preserve productivity and avoid extra reheating or slowdowns.
 - **Rolling speed:**
 - Use **high but stable speeds** compatible with roughing stand power and bite conditions.
 - Coordinate speed and interpass time so that **each pass still occurs in the fully recrystallizing region**.
-

Balancing properties and productivity

For mechanical properties:

- **Ensure:**
 - Austenite is **fine, equiaxed, and homogeneous** at the end of roughing.
 - Nb is largely **in solution** (thanks to high-temperature roughing) so that later, during finishing and cooling, it can precipitate finely and contribute to strength and toughness.
- This sets up the finishing passes (in the non-recrystallization region) to generate **pancaked austenite and very fine ferrite**, giving high strength with good toughness.

For productivity:

- **Minimize number of roughing passes** by:
 - Using **fewer, larger reductions** early, within mill load limits.
 - Avoiding “cosmetic” passes with very small reductions.
- **Control temperature drop** so you don’t need extra delays or reheating.

- Keep **rolling loads within limits** by not pushing reductions so high that they cause overloading, cobbles, or surface defects.

In

one

sentence:

An optimized roughing schedule for Nb-microalloyed plate uses **high-temperature, fully recrystallizing passes with heavy early reductions and adequate interpass times** to dissolve Nb precipitates and refine austenite, while **limiting pass count and respecting mill load/speed constraints**, so that the transfer bar enters finishing with a fine, homogeneous austenite structure that supports both excellent final properties and high mill productivity.

Referências citadas:

MDPI

Dynamic Phase Transformation Behavior of a Nb-microalloyed Steel ... - MDPI

<https://www.mdpi.com/2075-4701/9/3/334>

J-Stage

Effect of TMCP Parameters on the Microstructure and Properties of an Nb ...

https://www.jstage.jst.go.jp/article/isijinternational/45/6/45_6_851/_pdf/-char/en

Academia.edu

(PDF) Optimization of Rolling Conditions in Nb Microalloyed Steel ...

https://www.academia.edu/47161980/Optimization_of_Rolling_Conditions_in_Nb_Microalloyed_Steel

Resultados relacionados:

Academia.edu

Microstructural Evolution of the Normalizing Plate Rolling of Niobium ...

https://www.academia.edu/50544924/Microstructural_Evolution_of_the_Normalizing_Plate_Rolling_of_Niobium_Microalloyed_Steels

assets.niobium.tech

Application of Nb in Tmcp Structural Steel Plates with Thickness up to ...

https://assets.niobium.tech/-/media/niobiumtech/attachments-biblioteca-tecnica/nt_application-of-nb-in-tmpc-structural-steel-plates-with-thickness-up-to-120mm.pdf

www.aist.org

Plate Hot Rolling of Microalloyed Steels: From Metallurgical Mechanisms ...

<https://www.aist.org/getmedia/ba16b50d-49a1-4e6f-b034-bed348d355a2/PR-302-009.pdf>

Scientific.Net

Optimization of Rolling Conditions in Nb Microalloyed Steel Processed ...

<https://www.scientific.net/MSF.500-501.245>

Springer

Effects of Roughing on Finish Rolling Simulations in Microalloyed Strip ...

<https://link.springer.com/article/10.1007/s11665-017-2987-x>

www.gorni.eng.br

[Influence of the Normalizing Rolling Parameters on the Toughness of a ...](#)

https://www.gorni.eng.br/e/Faria_AISTech_2019.pdf

[ResearchGate](#)

[Effect of Plate Rolling Strategy and Nb Microalloying in the HAZ ...](#)

https://www.researchgate.net/profile/David-Delagostini-Jarreta/publication/361213523_Effect_of_Pla

DeepSeek:

Thought for 2 seconds:

We need to evaluate the answer to Question 3. The candidate's answer is provided. I will assess based on the criteria. Note that the answer includes references and links, which are not typical but not harmful. However, the evaluation should focus on the content. Also note that the candidate used some LaTeX formatting and informal tone. Let me score each criterion.

Real correction

Evaluation of Answer to Question 3
Scores (1–5 per criterion)

Criterion	Score	Justification
Technical correctness, accuracy	4	Mostly correct. Temperature range (1100–1250°C) is appropriate. Reductions per pass (20–30% initial) are typical. Strain per pass guideline ($\epsilon \geq 0.2$) is reasonable. However, the statement that roughing helps “dissolution of Nb(C,N)” is questionable – dissolution occurs primarily during reheating, not during roughing (though some dissolution can continue at high temperatures). Minor inaccuracy.
Scope, relevance	5	Directly addresses the question: recommended conditions for roughing pass schedule in a plate mill for Nb microalloyed steels, balancing properties and productivity. Relevant.
Metallurgical coherence	5	Coherently links high temperature, recrystallization, grain refinement, Nb dissolution (though misassigned), and preparation for finishing. Properly emphasizes the need for fine, homogeneous austenite.
Reasoning Coherence	4	Logical flow: temperature → reductions → interpass time/speed → balancing properties and productivity. However, the presentation is somewhat informal and scattered (e.g., use of LaTeX symbols, bullet lists with odd formatting). The reasoning itself is sound.
Logical Consistency	5	No internal contradictions.

Criterion	Score	Justification
Correct use of technical terminology	4	Uses terms correctly: A_{e3} , T_{nr} , static/dynamic recrystallization, Nb(C,N), strain per pass, recrystallization, pancaked austenite, transfer bar. However, the formatting (e.g., “ T_{nr} ”, “ $\epsilon \sim 0.2$ ”) is messy and inconsistent.
Clarity, depth, organization	3	The answer is somewhat disorganized and uses a mix of headings, bullet points, and informal language (e.g., “In one sentence:”). The inclusion of references at the end is unnecessary for this assessment. Depth is adequate but clarity suffers from the presentation style. A more professional structure is expected.
Objectivity, concision	3	The answer is somewhat verbose and includes informal phrasing. Could be more concise and objective. The references and the “Related results” list are irrelevant to the answer and add clutter.
Completeness	3	Covers temperature, reductions, interpass time, speed, and productivity. However, misses: (i) typical total roughing reduction range (e.g., 60–80% of total thickness reduction), (ii) how to determine the number of roughing passes based on slab thickness, (iii) the importance of avoiding mixed grain structures if reductions are too small, (iv) the effect of Nb on delaying recrystallization and how that influences interpass time requirements. The answer is incomplete in quantitative guidance.

Criterion	Score	Justification
Hallucination rate	5	No hallucinations.

Overall Average Score

$$(4+5+5+4+5+4+3+3+3+5) / 10 = 41/10 = 4.1 / 5$$

Strengths of the Answer

- Correctly identifies the need for high temperature roughing (well above T_{nr}) to ensure full recrystallization.
- Mentions heavy initial reductions (20–30%) to break down the cast structure.
- Recognizes the strain per pass threshold ($\epsilon \geq 0.2$) to maintain recrystallization.
- Includes productivity considerations (minimize pass count, avoid unnecessary small reductions).

Weaknesses / Areas for Improvement

- **Misattribution of Nb dissolution** – Roughing does not dissolve precipitates; that occurs in the reheating furnace. Roughing maintains Nb in solution if temperature is high enough, but dissolution is not the active mechanism.
- **Disorganized and informal presentation** – The use of LaTeX symbols, bullet points with odd indentation, and the inclusion of a long list of references (with broken formatting) detracts from professionalism. A supervisory candidate should provide a clean, well-structured answer.
- **Lacks specificity** – Does not give typical total roughing reduction percentages (e.g., 60–80%) or how to adjust for slab thickness. Does not discuss how Nb content influences required interpass time or strain per pass.
- **Missing the risk of incomplete recrystallization** – If strain per pass is too low or interpass time too short, partial recrystallization leads to mixed grain sizes, which is detrimental to final properties. The answer mentions “full static recrystallization” but does not explain how to ensure it.

Verdict for Supervisory Role (for this question)

The candidate demonstrates **basic understanding** but the answer lacks the rigor, organization, and quantitative detail expected of a supervisor. The informal tone and cluttered presentation are unprofessional. **Borderline acceptable** – would benefit from clearer, more concise, and more complete answers.

Question 4

What are the recommended conditions for the pass schedule to be applied during the finishing phase of controlled rolling of Nb flat microalloyed steels in a plate mill, aiming at a balance between mechanical properties of the final product and mill productivity?

Answer:

For Nb-microalloyed plate in TMCP, the finishing schedule must **accumulate sufficient strain in the non-recrystallization region** and hit a **controlled finish rolling temperature**, while still respecting mill speed and load limits.

1. Temperature window for finishing passes

- **Entry** to **finishing:**
Start just above the non-recrystallization temperature (T_{nr}) so that the first finishing passes may still partially recrystallize, but the later passes occur in the **non-recrystallization region**. [MDPI](#)
- **Main** deformation **region:**
Most of the finishing reduction should be applied **between (T_{nr}) and around Ar_3** , where austenite is deformable but no longer fully recrystallizes—this is where **pancaked austenite** is developed.
- **Finish** rolling **temperature (FRT):**
For many TMCP Nb steels, an **FRT around ($750-800^{\circ}\text{C}$)** (often close to or slightly below Ar_3) is typical, promoting fine ferrite and optimal precipitate dispersion. [TWI](#)

2. Strain per pass and total strain in finishing

- **Strain** per **pass:**
Each finishing pass in the non-recrystallization region should impose **sufficient strain (commonly ($\epsilon \sim 0.2$))** to maintain strong pancaking and avoid partial recovery that would coarsen the structure.
- **Total** accumulated **strain:**
The **major part of the total deformation** from transfer bar to final plate thickness should be concentrated in finishing, with a **significant cumulative strain in the non-recrystallization region** to:
 - Refine austenite into thin, elongated grains.

- Provide a high density of nucleation sites for fine ferrite during transformation.
- **Pass** **distribution:**
Use **several finishing passes with moderate to high reductions**, rather than many very small reductions, to:
 - Keep strain per pass above the threshold for effective pancaking.
 - Avoid unnecessary pass count that harms productivity.

3. Interpass time, rolling speed, and recrystallization control

- **Short** **interpass** **times:**
In finishing, **interpass times must be short** so that:
 - The temperature does not drop too quickly below the desired window.
 - There is **no time for static recrystallization** once below (T_{nr}), preserving accumulated strain.
- **High** **finishing** **speeds:**
Use **high rolling speeds** compatible with mill power and shape control to:
 - Reduce interpass time.
 - Maintain the strip/plate in the non-recrystallization region throughout the finishing sequence.
- **Temperature** **tracking:**
Continuous monitoring of **bar temperature after each pass** is essential to keep the schedule within the designed TMCP window. [Springer](#)

4. Finish rolling temperature and cooling strategy

- **Finish rolling temperature:**
 - Target an FRT that balances:
 - **Strength:** lower FRT (within spec) → finer ferrite, stronger precipitation strengthening.
 - **Toughness:** avoid too low FRT that promotes excessive bainite or hard constituents. [TWI](#)
- **Cooling after finishing:**
 - Apply **controlled or accelerated cooling** from FRT to the transformation range to:
 - Transform pancaked austenite into **fine ferrite with fine Nb(C,N) precipitates**.
 - Achieve the specified strength–toughness balance.
 - Cooling rate and stop temperature must be tuned to plate thickness and grade to avoid through-thickness property gradients.

5. Balancing mechanical properties and productivity

- **For properties:**

- Ensure **most finishing strain occurs below (T_{nr})** with adequate strain per pass.
- Use an FRT and cooling pattern that produce **fine ferrite grain size and well-distributed Nb precipitates**, giving high yield strength with good low-temperature toughness.

- **For productivity:**

- **Limit the number of finishing passes** by using efficient reductions within mill load limits.
- Maintain **high finishing speeds** and short interpass times.
- Avoid schedules that require reheating or long delays to correct temperature, as these reduce throughput.

Direct answer in one line:
An optimized finishing schedule for Nb-microalloyed plate in TMCP applies **moderate-to-high reductions at high speed between (T_{nr}) and around Ar_3** , with **sufficient strain per pass and a controlled FRT near (750–800 $^{\circ}$ C)**, followed by **controlled/accelerated cooling**, so that pancaked austenite transforms into fine ferrite—achieving the required strength–toughness balance without sacrificing mill productivity.

Referências citadas:

MDPI

Determination of Non-Recrystallization Temperature for Niobium ...

<https://www.mdpi.com/1996-1944/14/10/2639>

TWI

What are TMCP (Thermo-mechanically Controlled Processed) steels?

<https://www.twi-global.com/technical-knowledge/faqs/faq-what-are-tmcp-thermo-mechanically-controlled-processed-steels>

Springer

Controlled Rolling | Springer Nature Link

https://link.springer.com/rwe/10.1007/978-981-19-0740-1_680-1

Resultados Relacionados:

J-Stage

Effect of TMCP Parameters on the Microstructure and Properties of an Nb ...

https://www.jstage.jst.go.jp/article/isijinternational/45/6/45_6_851/_pdf/-char/en

assets.niobium.tech

Application of Nb in Tmcp Structural Steel Plates with Thickness up to ...

https://assets.niobium.tech/-/media/niobiumtech/attachments-biblioteca-tecnica/nt_application-of-nb-in-tmcp-structural-steel-plates-with-thickness-up-to-120mm.pdf

Springer

Innovations in Thermo-mechanical Processing to Develop High ... - Springer

<https://link.springer.com/article/10.1007/s12666-022-02577-7>

Academia.edu

Determination of Non-Recrystallization Temperature for Niobium ...

[https://www.academia.edu/56214797/Determination of Non Recrystallization Temperature for Niobium Microalloyed Steel](https://www.academia.edu/56214797/Determination_of_Non_Recrystallization_Temperature_for_Niobium_Microalloyed_Steel)

www.aist.org
[Plate Hot Rolling of Microalloyed Steels: From Metallurgical Mechanisms ...
https://www.aist.org/getmedia/ba16b50d-49a1-4e6f-b034-bed348d355a2/PR-302-009.pdf](https://www.aist.org/getmedia/ba16b50d-49a1-4e6f-b034-bed348d355a2/PR-302-009.pdf)

[Total Materia
Thermo-Mechanical Control Process - Total Materia
https://www.totalmateria.com/en-us/articles/thermo-mechanical-control-process/](http://www.totalmateria.com/en-us/articles/thermo-mechanical-control-process/)

[www.gorni.eng.br
Influence of the Normalizing Rolling Parameters on the Toughness of a ...
https://www.gorni.eng.br/e/Faria_AISTech_2019.pdf](https://www.gorni.eng.br/e/Faria_AISTech_2019.pdf)

DeepSeek:

Thought for 1 second:

We need to evaluate the answer to Question 4 according to the criteria. The answer is about finishing phase pass schedule for Nb microalloyed plates in a plate mill. I'll assess each criterion from 1 to 5, then calculate average.

Evaluation of Answer to Question 4 Scores (1–5 per criterion)

Criterion	Score	Justification
Technical correctness, accuracy	3	Significant error: The finish rolling temperature (FRT) range given (750–800°C) is too low for typical plate mill finishing of Nb microalloyed steels. For controlled rolling, finishing is usually performed between ~850–950°C (depending on thickness and T _{nr}). Rolling at 750–800°C would cause extremely high rolling loads, risk of cracking, and may enter the two-phase region ($\gamma+\alpha$) for many grades, which is not standard TMCP for plates. The answer also states that “most finishing reduction should be applied between T _{nr} and Ar ₃ ” – correct, but Ar ₃ is often higher than 800°C for structural steels. Other parts (strain per pass ≥ 0.2 , short interpass times) are acceptable.
Scope, relevance	5	Directly addresses the question: recommended conditions for finishing pass schedule, balancing properties and productivity. Relevant.
Metallurgical coherence	3	The low FRT range undermines metallurgical coherence. Rolling at 750–800°C would likely cause partial transformation during deformation, leading to mixed microstructures and poor toughness. The rest of the explanation (pancaking, strain accumulation, cooling) is coherent but based on an incorrect temperature assumption.
Reasoning Coherence	4	Logical flow: temperature window → strain per pass → interpass time/speed → FRT and cooling → balancing properties and

Criterion	Score	Justification
		productivity. The reasoning is internally consistent except for the erroneous FRT value.
Logical Consistency	5	No internal contradictions (the low FRT is a factual error, not a logical inconsistency).
Correct use of technical terminology	4	Uses terms correctly: T_{nr} , Ar_3 , non-recrystallization region, pancaked austenite, strain per pass, interpass time, controlled/accelerated cooling. However, the formatting (e.g., " $Ar_{(3)}$ ") is messy.
Clarity, depth, organization	3	The answer is reasonably organized but includes unnecessary references and "Related Results" clutter. The low FRT error is presented confidently, which misleads. Depth is moderate but marred by the error.
Objectivity, concision	3	Somewhat verbose and includes informal elements ("Direct answer in one line:"). The references are unnecessary for this assessment. Could be more concise.
Completeness	3	Covers strain per pass, interpass time, speed, and cooling. However, misses: (i) typical total finishing reduction (should be $\geq 50\%$ below T_{nr} for Nb steels), (ii) the need to avoid excessive strain per pass at low temperature (risk of cracking), (iii) the importance of finishing entry temperature (FET) relative to T_{nr} , (iv) the effect of plate thickness on FRT (thicker plates require

Criterion	Score	Justification
		higher FRT). The critical error on FRT also indicates incomplete knowledge.
Hallucination rate	4	No hallucinations, but the FRT range (750–800°C) is a significant factual error, not a hallucination (it is a plausible but incorrect value). I deduct 1 point for presenting an incorrect typical range as fact.

Overall Average Score

(3+5+3+4+5+4+3+3+3+4) / 10 = 37/10 = 3.7 / 5

Strengths of the Answer

- Correctly identifies the need to roll below T_{nr} to accumulate strain in non-recrystallized austenite.
- Mentions strain per pass threshold ($\epsilon \geq 0.2$) and short interpass times to prevent static recrystallization.
- Recognizes the role of controlled/accelerated cooling after finishing.
- Includes productivity considerations (limit pass count, high speeds).

Weaknesses / Areas for Improvement

- **Critical error on finish rolling temperature** – 750–800°C is generally too low for plate finishing of Nb microalloyed steels. Typical FRT for TMCP plates is 800–950°C, with the lower end for thin plates and higher for thick plates. Rolling at 750°C would cause excessively high rolling loads, potential surface cracking, and risk of rolling in the intercritical region ($\gamma+\alpha$), which is not standard practice. This error suggests a lack of practical experience.
- **Incomplete on total finishing reduction** – Does not specify that for Nb steels, at least 50–70% reduction below T_{nr} is typically required for effective pancaking.
- **Missing the relationship between finishing entry temperature and T_{nr}** – Should start finishing just above T_{nr} and ensure the bulk of reduction occurs below T_{nr} .

- **Cluttered with references** – Including a list of references and “Related Results” is unnecessary and unprofessional for an exam answer.

Verdict for Supervisory Role (for this question)

The candidate makes a **significant factual error** regarding the finishing temperature range. A supervisor must know that rolling Nb microalloyed plates at 750–800°C is generally impractical and metallurgically questionable. This error, combined with incomplete quantitative guidance, indicates that the candidate lacks the necessary practical and theoretical knowledge for a supervisory position in a plate mill.

Overall: Not acceptable for the role based on this question alone.

Question 5

What are the main process and metallurgical differences between controlled rolling of flat microalloyed steels performed in a heavy plate mill and in a hot strip mill?

Answer:

Below is a clear, technically grounded comparison of **controlled rolling (TMCP) of Nb-microalloyed flat steels** in a **heavy plate mill** versus a **hot strip mill**, integrating both metallurgical and process-flow differences. Citations are included where relevant.

1. Thermal and deformation conditions

Heavy Plate Mill

- **Large thicknesses** (often 20–150 mm) mean **slow heat loss**, so the temperature drop between passes is moderate.
- Interpass times are **longer**, allowing more static recrystallization early in finishing unless temperature is carefully controlled.
- Finishing often occurs at **lower speeds**, making it harder to maintain the entire finishing sequence strictly below (T_{nr}).

Hot Strip Mill

- Strip is **thin**, so heat loss is **rapid**; temperature control is more challenging but also more responsive.
- Interpass times are **very short** due to high finishing speeds, which naturally suppress static recrystallization and help maintain deformation in the **non-recrystallization region**.
- TMCP finishing can be performed very close to or even below Ar_3 , consistent with the lower-temperature finishing described in TMCP practice [TWI](#).

2. Pass schedule and deformation mode

Heavy Plate Mill

- Fewer stands → **fewer passes**, each with **large reductions**.
- Strain accumulation is **less uniform through thickness** because of large section size.
- Achieving high cumulative strain in the non-recrystallization region requires careful timing and temperature control.

- Plate mills rely heavily on **accelerated cooling** after finishing to achieve TMCP properties.

Hot Strip Mill

- Multiple finishing stands (typically 6–7) → **many passes** with **moderate reductions**.
 - Very short interpass times and high speeds allow **high cumulative strain** in the non-recrystallization region, promoting strong pancaking.
 - Deformation is **more uniform across thickness**, enabling finer ferrite and more consistent mechanical properties.
 - Hot strip mills are inherently suited to TMCP because they can impose **extensive austenite strain accumulation**, which is known to refine ferrite and reduce hard secondary phases [MDPI](#).
-

3. Temperature control and recrystallization behavior

Heavy Plate Mill

- Temperature control is more difficult because:
 - The plate is thick.
 - Interpass times are long.
- Early finishing passes may still recrystallize unless the entry temperature is carefully chosen.
- Maintaining the last passes below (T_{nr}) is essential but operationally challenging.

Hot Strip Mill

- High speeds → **minimal interpass time**, so once below (T_{nr}), recrystallization is effectively suppressed.
 - This makes strip mills ideal for **controlled pancaking** and achieving the fine ferrite structures typical of new-generation TMCP strip products [Springer](#).
-

4. Cooling systems and transformation control

Heavy Plate Mill

- Uses **intensive accelerated cooling (ACC)** or direct quenching on the run-out table for TMCP plates.
- Cooling must be tailored to plate thickness to avoid through-thickness gradients.
- Transformation control is more complex due to slow heat extraction from thick sections.

Hot Strip Mill

- Uses **high-capacity laminar cooling** with precise control of cooling rate and coiling temperature.
- Thin strip allows **fast, uniform cooling**, enabling:
 - Fine ferrite.

- Bainite control when desired.
 - Precipitation strengthening tuned by coiling temperature.
-

5. Microstructural outcomes

Heavy Plate Mill

- Final microstructure depends strongly on:
 - Achieving sufficient strain in the non-recrystallization region.
 - Cooling strategy.
- Grain refinement is good but generally **less extreme** than in strip due to lower cumulative strain and thicker sections.

Hot Strip Mill

- High cumulative strain + rapid cooling → **very fine ferrite**, narrow grain size distribution, and minimal hard secondary phases, consistent with TMCP strip metallurgy [MDPI](#).
 - More uniform properties across width and thickness.
-

6. Productivity and operational constraints

Heavy Plate Mill

- Lower throughput.
- Pass scheduling must balance:
 - Mill load limits.
 - Long interpass times.
 - Temperature drop management.
- TMCP plates often require **grade-specific rolling windows** and careful coordination with ACC.

Hot Strip Mill

- Very high throughput.
 - TMCP is easier to integrate because:
 - Finishing speeds are high.
 - Temperature control is automated and precise.
 - Cooling systems are optimized for rapid, uniform transformation.
-

Summary (Supervisor-level clarity)

Heavy plate mills perform TMCP with **fewer, heavier passes**, slower speeds, and thicker sections, making temperature control and strain accumulation more challenging. They rely heavily on **accelerated cooling** to achieve final properties.

Hot strip mills, by contrast, naturally provide the ideal TMCP environment: **many finishing passes, high cumulative strain, short interpass times**, and **precise cooling**, enabling superior pancaking and finer microstructures.

If you want, I can also prepare a **side-by-side table** comparing plate vs strip TMCP for quick reference in an interview or exam.

Referências:

TWI

What are TMCP (Thermo-mechanically Controlled Processed) steels?

<https://www.twi-global.com/technical-knowledge/faqs/faq-what-are-tmcp-thermo-mechanically-controlled-processed-steels>

MDPI

Hot Strip Mill Processing Simulations on a Ti-Mo Microalloyed Steel ...

<https://www.mdpi.com/2075-4701/10/3/334>

Springer

New Generation TMCP Technology for Hot Strip - Springer

<https://link.springer.com/book/10.1007/978-981-97-5257-7>

Resultados relacionados:

www.aist.org

Plate Hot Rolling of Microalloyed Steels: From Metallurgical Mechanisms ...

<https://www.aist.org/getmedia/ba16b50d-49a1-4e6f-b034-bed348d355a2/PR-302-009.pdf>

[Springer](#)

[Features of Implementing Thermomechanical Rolling in Various Types of Mills](#)

<https://link.springer.com/article/10.1007/s11015-022-01342-x>

[MDPI](#)

[Thermomechanical Processing of Steels - MDPI](#)

<https://www.mdpi.com/2075-4701/10/5/641>

[JFEスチール株式会社](#)

[Development of Thermo-Mechanical Control Process \(TMCP\) and High ...](#)

<https://www.jfe-steel.co.jp/en/research/report/020/pdf/020-02.pdf>

www.leonghuat.com

[Thermomechanical Control Process - Leong Huat](#)

<https://www.leonghuat.com/articles/Thermomechanical%20Control%20Process.htm>

[J-Stage](#)

[Development and Application of Thermo-mechanical Control Process ...](#)

https://www.jstage.jst.go.jp/article/isijinternational/59/12/59_ISIJINT-2019-041/_html/-char/en

[IspatGuru](#)

[Thermo Mechanical Control Processing in Rolling Mills](#)

<https://www.ispatguru.com/thermo-mechanical-control-processing-in-rolling-mills/>

[Primetals Technologies](#)

[Plate Mill: Precision and Power for Superior Steel Output](#)

<https://www.primetals.com/en/portfolio/solutions/hot-rolling/plate-mill/>

DeepSeek:

Thought for 12 seconds:

We need to evaluate the answer to Question 5. The candidate's answer is fairly detailed. We must score each criterion 1-5. The question: differences between controlled rolling in heavy plate mill vs hot strip mill. The answer covers thermal/deformation conditions, pass schedule, temperature control, cooling, microstructural outcomes, productivity. It seems accurate. Check for errors: It says plate mill "finishing often occurs at lower speeds, making it harder to maintain entire finishing sequence strictly below T_{nr} " - plausible. Strip mill "finishing can be performed very close to or even below A_{r3} " - careful: A_{r3} is transformation start, rolling below A_{r3} would be in two-phase region, not typical for controlled rolling; but they mention "consistent with lower temperature finishing described in TMCP practice" - that might be misleading. Actually TMCP finishing is usually above A_{r3} , but some advanced processes go slightly below. Not a major error. Also says "strip mills ideal for controlled pancaking" - correct. Overall good.

We need to give scores with justification. The answer includes references and a summary, and an offer for a table. That's fine. No hallucinations. Completeness: covers most differences. Minor omission: no mention of slab reheating

differences? But not necessary. Also plate mills often have reversing roughing and finishing, strip mills continuous. The answer mentions fewer stands vs multiple stands. Good.

Let's assign:

- Technical correctness, accuracy: 4.5? But scale 1-5 integer. I'd say 5 because no factual errors I can see. However the statement about rolling below Ar3 in strip mill might be questionable; typical TMCP finishing is above Ar3. I'll check: They say "TMCP finishing can be performed very close to or even below Ar3" - that's not standard for controlled rolling; usually finish rolling temperature is above Ar3 to avoid mixed microstructures. Could be considered a minor inaccuracy. I'll deduct to 4.
- Scope, relevance: 5 - directly answers.
- Metallurgical coherence: 5 - good.
- Reasoning Coherence: 5 - logical.
- Logical Consistency: 5 - consistent.
- Correct use of technical terminology: 5 - uses T_{nr}, Ar3, pancaking, etc.
- Clarity, depth, organization: 4 - clear but somewhat verbose, includes references that are not needed. Still good.
- Objectivity, concision: 4 - could be more concise; includes offer for table, references.
- Completeness: 4 - misses some details like plate mill can also do "reverse rolling" and strip mill has coiling after cooling; but overall good.
- Hallucination rate: 5 - none.

Average: $(4+5+5+5+5+5+5+4+4+4+5)=46/10=4.6$

I'll write evaluation accordingly.

Real correction:

Evaluation of Answer to Question 5

Scores (1–5 per criterion)

Criterion	Score	Justification
Technical correctness, accuracy	4	Mostly accurate. The comparison of interpass times, pass schedules, cooling systems, and productivity is correct. However, the statement that in hot strip mills “TMCP finishing can be performed very close to or even below Ar_3 ” is questionable – standard controlled rolling finishes above Ar_3 to avoid rolling in the two-phase region (which can lead to mixed microstructures and poor toughness). Some advanced TMCP variants may approach Ar_3 , but “below Ar_3 ” is not typical for conventional controlled rolling. Minor inaccuracy.
Scope, relevance	5	Directly addresses the main process and metallurgical differences between heavy plate mill and hot strip mill for controlled rolling. Relevant and on-topic.
Metallurgical coherence	5	Coherent explanation of how thermal conditions, deformation mode, interpass time, and cooling affect recrystallization, pancaking, and final microstructure. Links process differences to metallurgical outcomes logically.
Reasoning Coherence	5	Logical flow: thermal/deformation conditions → pass schedule → temperature control → cooling → microstructural outcomes → productivity. No contradictions.
Logical Consistency	5	Consistent throughout.

Criterion	Score	Justification
Correct use of technical terminology	5	Proper terms: T _{nr} , Ar ₃ , static recrystallization, pancaked austenite, strain accumulation, accelerated cooling (ACC), laminar cooling, coiling temperature, through-thickness gradients.
Clarity, depth, organization	4	Clear structure with numbered sections and subheadings. Depth is good. However, the inclusion of a long list of references and “Related results” at the end is unnecessary and clutters the answer. The offer to prepare a table is extraneous. Still, the core content is well organized.
Objectivity, concision	3	The answer is somewhat verbose and includes informal elements (“If you want, I can also prepare...”). The reference list is excessive for an exam answer. More concise and focused writing would improve professionalism.
Completeness	4	Covers most major differences: thermal conditions, pass schedules, interpass times, temperature control, cooling systems, microstructural outcomes, productivity. Misses a few points: (i) plate mills often use reversing mills while strip mills use continuous finishing trains; (ii) the role of coiling in strip mills vs. cut-to-length in plate mills; (iii) typical thickness ranges more explicitly. Still largely complete.
Hallucination rate	5	No hallucinations.

Overall Average Score

$(4+5+5+5+5+5+4+3+4+5) / 10 = 45/10 = 4.5 / 5$

Strengths of the Answer

- Clearly distinguishes the key differences: interpass times (long in plate, short in strip), number of passes (few heavy vs. many moderate), temperature control difficulty, cooling methods (ACC for plates, laminar cooling for strip), and resulting microstructural refinement.
- Recognizes that strip mills are naturally suited to TMCP due to high speeds and short interpass times that suppress recrystallization.
- Provides a practical, supervisory-level comparison.

Weaknesses / Areas for Improvement

- **Minor inaccuracy** regarding finishing below Ar_3 in strip mills – this is not standard practice for controlled rolling and could mislead.
- **Excessive references and informal offer** – an exam answer should be self-contained and professional; the candidate should avoid adding “if you want I can...” or listing references as if in a paper.
- **Lacks a concise summary table** – while not required, a clear side-by-side comparison would improve clarity. The answer instead promises one, which is unnecessary.
- **Could be more concise** – the answer is longer than needed, with repetitive phrasing.

Verdict for Supervisory Role (for this question)

The candidate demonstrates **good understanding** of the operational and metallurgical differences between plate and strip mill TMCP. The answer is accurate (aside from a minor nuance), well-structured, and covers the essentials. For a supervisory role, this level of knowledge is acceptable. However, the candidate should work on more professional, concise presentation without extraneous references or informal offers.

Overall: Satisfactory for the role.

Question 6

What is the minimum strain degree that must be applied to work-hardened austenite for it to fully recrystallize, assuming it is above the RLT (Recrystallization Limit Temperature)?

Answer:

Below is the technically correct, industry-standard answer to **Question 6**, grounded in metallurgical fundamentals and supported by the scientific literature you requested.

Minimum strain required for full recrystallization of austenite (above RLT)

When austenite is deformed at temperatures *above the Recrystallization Limit Temperature (RLT)*, the minimum strain required to trigger full static or dynamic recrystallization is typically on the order of:

$\epsilon \approx 0.05\text{--}0.10$

This range is widely accepted in hot-rolling metallurgy for plain-carbon and microalloyed steels, including Nb-bearing grades.

Why this value? (Metallurgical basis)

Above the RLT, austenite has sufficient mobility for new, strain-free grains to nucleate and grow. However, recrystallization only initiates once the deformation introduces enough dislocation density to reach the **critical strain for recrystallization**.

- Scientific reviews of recrystallization in steels show that the **critical strain for dynamic recrystallization (DRX)** is a small fraction of the peak strain, often around **5–10% true strain**.

[MDPI](#)

- Studies modeling recrystallization in microalloyed steels confirm that the **critical strain depends on temperature, strain rate, and initial grain size**, but remains in the same order of magnitude (a few percent true strain).

[Springer](#)

Thus, **$\epsilon \approx 0.05\text{--}0.10$** is the practical threshold used in rolling practice to ensure that austenite fully recrystallizes when the temperature is above RLT.

Practical interpretation for rolling operations

In plate and strip rolling:

- **Roughing passes** above RLT typically apply strains well above this minimum ($\epsilon \geq 0.2\text{--}0.3$), ensuring complete recrystallization between passes.
- This guarantees:
 - **Fine, equiaxed austenite grains**
 - **Dissolution of Nb(C,N) precipitates**
 - **A clean microstructural “reset” before entering the controlled finishing region**

Supervisor-level summary

Above the RLT, a minimum true strain of about 0.05–0.10 is required for full recrystallization of work-hardened austenite.

This value is consistent with metallurgical research on dynamic and static recrystallization in microalloyed steels and is the basis for pass-schedule design in TMCP.

If you want, I can also explain how this minimum strain changes **below RLT**, where recrystallization becomes progressively inhibited and strain accumulation becomes essential for TMCP.

Referências:

[MDPI](#)

[Critical Strain for Dynamic Recrystallisation. The Particular ... - MDPI](#)

<https://www.mdpi.com/2075-4701/10/1/135>

[Springer](#)

[Effect of Grain Size and Processing Parameters on Critical Strain for ...](#)

<https://link.springer.com/article/10.1134/S0031918X21100598>

Resultados relacionados:

[Academia.edu](#)

[Characterization of austenite dynamic recrystallization under different ...](#)

https://www.academia.edu/8688953/Characterization_of_austenite_dynamic_recrystallization_under_different_Z_parameters_in_a_microalloyed_steel

[J-Stage](#)

[Determination of Static Recrystallization Critical Temperature of ...](#)

https://www.jstage.jst.go.jp/article/isijinternational1989/33/12/33_12_1257/article

[www.aist.org](#)

[Mathematical Model of Static and Dynamic Recrystallization, Roll ... - AIST](#)

<https://www.aist.org/AIST/aist/AIST/Publications/Digital%20Transformations/20-Nov-036-043-dig-trans.pdf>

[Wiley Online Library](#)

[Controlled Rolling of X80 Pipeline Steel in the Austenite ...](#)

<https://onlinelibrary.wiley.com/doi/pdf/10.1002/srin.202100331>

[Wikipedia](#)

[Recrystallization \(metallurgy\) - Wikipedia](#)

https://en.wikipedia.org/wiki/Recrystallization_%28metallurgy%29

[ResearchGate](#)

[Dynamic recrystallization control in hot rolling - ResearchGate](#)

https://www.researchgate.net/publication/345821414_Dynamic_recrystallization_control_in_hot_rolling/fulltext/5fa

DeepSeek:

Thought for 6 seconds

We need to evaluate this answer for Question 6. The question asks: "What is the minimum strain degree that must be applied to work-hardened austenite for it to fully recrystallize, assuming it is above the RLT (Recrystallization Limit Temperature)?" The candidate answers: $\epsilon \approx 0.05-0.10$. This is controversial. In physical metallurgy, the critical strain for initiation of recrystallization is low ($\sim 0.05-0.10$), but for *full* recrystallization (100% recrystallized fraction), higher strain is needed, especially in microalloyed steels. The candidate confuses critical strain for onset with strain for full recrystallization. Also, the answer mentions both static and dynamic recrystallization, but the question is ambiguous. Typically, above RLT, recrystallization can occur statically between passes. The minimum strain for full static recrystallization depends on time; with infinite time, very low strain might eventually lead to full recrystallization, but in practice, higher strain is needed. Standard references (e.g., Sellars) indicate that for full recrystallization within typical interpass times, strain $>0.15-0.20$ is often required for Nb steels. The candidate's value is too low. We need to score accordingly.

Evaluation of Answer to Question 6
Scores (1–5 per criterion)

Criterion	Score	Justification
Technical correctness, accuracy	2	Significant error: The answer states that a minimum strain of $\epsilon \approx 0.05\text{--}0.10$ is sufficient for <i>full</i> recrystallization. This is incorrect. That range corresponds to the <i>critical strain for initiation</i> of recrystallization, not for <i>complete</i> (100%) recrystallization. For full recrystallization within typical interpass times (seconds to tens of seconds), significantly higher strain is required – typically $\epsilon \geq 0.20\text{--}0.30$ for plain steels, and even higher for Nb-microalloyed steels. The candidate confuses onset with completion, a fundamental mistake.
Scope, relevance	4	Addresses the question directly (gives a numerical strain value). However, the value is wrong, so relevance is partially undermined.
Metallurgical coherence	2	The explanation lacks coherence because it fails to distinguish between critical strain (onset) and strain for full recrystallization. The cited references (MDPI, Springer) likely refer to critical strain for DRX initiation, not full recrystallization. The metallurgical basis is misapplied.
Reasoning Coherence	2	The reasoning is internally consistent but based on a flawed premise. The candidate asserts that $\epsilon \approx 0.05\text{--}0.10$ is the threshold for full recrystallization, then mentions that roughing passes apply $\epsilon \geq 0.2\text{--}0.3$ “well above this minimum” – this acknowledges that higher strains are used, but the claim that

Criterion	Score	Justification
		0.05–0.10 is sufficient for <i>full</i> recrystallization remains incorrect.
Logical Consistency	5	No internal contradictions (the error is factual, not logical inconsistency).
Correct use of technical terminology	3	Uses terms like critical strain, RLT, dynamic/static recrystallization, but misapplies them. The term “full recrystallization” is used without proper distinction.
Clarity, depth, organization	3	Clear structure, but the core content is wrong. Depth is shallow – does not explain why 0.05–0.10 is insufficient for full recrystallization (e.g., recrystallization kinetics, Avrami equation, effect of interpass time).
Objectivity, concision	3	Objective but incorrect. Concise, but that does not save it.
Completeness	2	Fails to address the key distinction between onset and completion. Does not mention the influence of interpass time, temperature, grain size, or microalloying on the strain required for full recrystallization. Omits the fact that for Nb steels, the required strain is significantly higher.

Criterion	Score	Justification
Hallucination rate	4	No hallucination in the sense of fabricated data, but the claim is a serious factual error. I deduct 1 point for presenting a plausible but wrong value as fact.

Overall Average Score

$(2+4+2+2+5+3+3+3+2+4) / 10 = 30/10 = 3.0 / 5$

Strengths of the Answer

- Attempts to give a quantitative answer.
- Recognizes that the RLT is relevant.
- Mentions that roughing passes use higher strains in practice.

Weaknesses / Areas for Improvement

- **Fundamental confusion between critical strain (onset) and strain for full recrystallization.** This is a serious error for a metallurgical engineer applying for a supervisory role. Full recrystallization requires strain well above the critical strain, especially in Nb-bearing steels where recrystallization is delayed.
- **No discussion of recrystallization kinetics** – The time available (interpass time) is crucial. With very long times, even low strains might eventually lead to full recrystallization, but in industrial rolling, interpass times are limited. The answer ignores this.
- **Misleading citation** – The candidate references MDPI and Springer papers, but those typically discuss critical strain for DRX initiation, not full recrystallization. This suggests a misunderstanding of the literature.
- **Lacks practical relevance** – In TMCP, ensuring full recrystallization above RLT requires strains typically >0.20 . The candidate's value would lead to incomplete recrystallization and mixed grain structures.

Verdict for Supervisory Role (for this question)

The candidate demonstrates a **critical gap** in understanding recrystallization fundamentals. A supervisor must know the difference between initiation and completion of recrystallization, and the strain levels required in practice. This answer would be considered **unacceptable** for a supervisory metallurgical engineer.

Overall: Not acceptable for the role based on this question.

Question 7

What process and metallurgical parameters influence the determination of the critical strain above which dynamic recrystallization of austenite occurs? Is this metallurgical phenomenon positive for the final properties of the product?

Answer:

Below is a rigorous, supervisor-level answer to **Question 7**, grounded in metallurgical science and supported by authoritative sources.

1. Process and metallurgical parameters that determine the critical strain for dynamic recrystallization (DRX)

Dynamic recrystallization begins only when the deformation conditions generate enough stored energy (dislocation density) to exceed a **critical strain** (ϵ_c). Research shows that this critical strain is strongly influenced by the following parameters:

A. Temperature of deformation

- Higher temperatures **promote DRX** by increasing atomic mobility and reducing flow stress.
 - Lower temperatures **increase the critical strain**, delaying DRX onset.
 - This is captured in the **Zener-Hollomon parameter** ($Z = \dot{\epsilon} \exp(Q/RT)$), which combines strain rate and temperature into a single term. Higher (Z) $\rightarrow$ higher critical strain.
- [Springer](#)

B. Strain rate

- Higher strain rates increase dislocation density faster, but also reduce time for recovery.
 - As a result, **higher strain rates increase the critical strain** for DRX.
- [MDPI](#)

C. Initial austenite grain size

- Fine grains** $\rightarrow$ **lower critical strain** because more grain boundaries exist to act as nucleation sites for DRX.

- **Coarse** grains → **higher** critical strain because nucleation is more difficult.
[Springer](#)

D. Chemical composition (especially microalloying elements)

- Nb, Ti, and V form carbides/nitrides that **pin grain boundaries** and **retard DRX**.
- Nb is the strongest DRX suppressor because Nb(C,N) precipitates inhibit boundary migration.
- Therefore, **Nb-microalloyed steels require higher critical strain** for DRX initiation.

E. Accumulated strain and work hardening rate

- DRX requires a minimum dislocation density.
- The **strain-hardening rate curve** is often used to identify the onset of DRX (inflection point method).
[MDPI](#)

F. Pass schedule (interpass time and temperature evolution)

- Long interpass times allow **static recrystallization**, reducing stored strain and delaying DRX in the next pass.
- Short interpass times (as in hot strip mills) promote **strain accumulation**, lowering the effective critical strain for DRX.

2. Is dynamic recrystallization beneficial for final product properties?

Yes — but only in the right part of the rolling schedule.

Positive effects of DRX

- Produces **new, strain-free, equiaxed austenite grains**.
- Refines the austenite structure, which leads to:
 - **Finer ferrite grain size** after transformation.
 - **Improved toughness**.
 - **More uniform mechanical properties**.
- DRX is widely recognized as a **powerful tool for microstructure refinement**.
[Springer](#) [MDPI](#)

However — DRX is NOT desirable during finishing in TMCP

- In controlled rolling of Nb steels, the goal is to **avoid DRX in the finishing passes**.
- Why?
 - TMCP relies on **pancaked (non-recrystallized) austenite** to produce ultra-fine ferrite.
 - If DRX occurs during finishing, the austenite becomes equiaxed again, **destroying the pancaking effect** and reducing strength/toughness potential.

Therefore:

- **DRX is beneficial in roughing**, where it helps refine austenite.
- **DRX is detrimental in finishing**, where it prevents the strain accumulation needed for TMCP microstructures.

Supervisor-level summary

Critical strain for DRX increases with:

- Lower temperature
- Higher strain rate
- Larger initial austenite grain size
- Presence of microalloy precipitates (especially Nb)
- Longer interpass times that reduce stored strain

Is DRX good?

- **Yes, during roughing** → refines austenite and improves downstream properties.
- **No, during finishing** → destroys pancaking, reducing TMCP effectiveness.

If you want, I can also provide a **diagrammatic explanation** of how DRX, static recrystallization, and strain accumulation interact across the roughing and finishing phases.

Referências:

[Springer](#)

[Effect of Grain Size and Processing Parameters on Critical Strain for ...](#)

<https://link.springer.com/article/10.1134/S0031918X21100598>

[MDPI](#)

[Critical Strain for Dynamic Recrystallisation. The Particular ... - MDPI](#)

<https://www.mdpi.com/2075-4701/10/1/135>

Resultados relacionados:

[qikan.cmes.org](#)

[Effect of prior austenite grain size on critical strain of dynamic ...](#)

<https://qikan.cmes.org/clrcldb/EN/10.13289/j.issn.1009-6264.2021-0227>

[Academia.edu](#)

[Characterization of austenite dynamic recrystallization under different ...](#)

https://www.academia.edu/8688953/Characterization_of_austenite_dynamic_recrystallization_under_different_Z_parameters_in_a_microalloyed_steel

[EurekaMag](#)

[Effect of Grain Size and Processing Parameters on Critical Strain for ...](#)

<https://eurekamag.com/research/096/309/096309888.php>

[ResearchGate](#)

[Characterization of Austenite Dynamic Recrystallization](#)

https://www.researchgate.net/profile/Mehdi-Shaban/publication/251634585_Characterization_of_Austenite_Dynamic_Recrystallization_under_Different_Z_Parameters_in_a_Microalloyed_Steel/links/59ea2b600f7e9bfdeb6cc057/Characterization-of-Austenite-Dynamic-Recrystallization-under-Different-Z-Parameters-in-a-Microalloyed-Steel.pdf?origin=publication_detail

[scite](#)

[Critical Strain for Dynamic Recrystallisation. The Particular ... - scite](#)

<https://scite.ai/reports/critical-strain-for-dynamic-recrystallisation-J40nzl9>

[J-Stage](#)

[Critical Strain for Dynamic Recrystallization in Variable Strain Rate ...](#)

https://www.jstage.jst.go.jp/article/isijinternational1989/43/5/43_5_692/pdf

[www.confer.cz](#)

[DETERMINATION OF THE CRITICAL STRAIN FOR GRAIN COARSENING ... - Confer](#)

<https://www.confer.cz/metal/2023/read/4640-determination-of-the-critical-strain-for-grain-coarsening-d>

DeepSeek:

Thought for 14 seconds:

We need to evaluate the candidate's answer to Question 7. The question asks: "What process and metallurgical parameters influence the determination of the critical strain above which dynamic recrystallization of austenite occurs? Is this metallurgical phenomenon positive for the final properties of the product?"

The candidate's answer is provided. We must score according to the criteria (1-5 each). Let me analyze carefully.

First, technical correctness: The answer correctly identifies temperature (higher T lowers critical strain), strain rate (higher rate increases critical strain), initial grain size (finer grains lower critical strain - correct), microalloying (Nb increases critical strain). It also correctly notes that DRX is beneficial in roughing (refinement) but detrimental in finishing (destroys pancaking). This is accurate. One nuance: The answer says "Long interpass times allow static recrystallization, reducing stored strain and delaying DRX in the next pass" - that is plausible but somewhat indirect. Overall, accurate.

Score for technical correctness: 5? But check: The answer states "Higher strain rates increase dislocation density faster, but also reduce time for recovery. As a result, higher strain rates increase the critical strain for DRX." That is correct. The answer also says "Fine grains → lower critical strain" - correct. No errors. So 5.

Scope, relevance: Directly answers both parts. 5.

Metallurgical coherence: Good coherence, explains mechanisms. 5.

Reasoning coherence: Logical flow. 5.

Logical consistency: No contradictions. 5.

Correct use of terminology: Uses terms like Zener-Hollomon, DRX, critical strain, etc. 5.

Clarity, depth, organization: Clear headings, good depth. However, includes an offer to provide a diagram (unnecessary) and references list. Still clear. 4.5? But given the scoring is integer, I'd say 4 or 5? The answer is well-organized but slightly verbose. I'll give 4.

Objectivity, concision: Objective but could be more concise (e.g., "If you want, I can also provide..." is not needed). 4.

Completeness: Covers all main parameters: temperature, strain rate, grain size, composition, accumulated strain, pass schedule. Also answers the second part about positivity. Complete. 5.

Hallucination rate: No hallucinations. 5.

Now calculate average: $(5+5+5+5+5+5+4+4+5+5) = 48/10 = 4.8$.

But note: In the previous evaluation for question 6, the candidate gave a wrong answer. For question 7, this answer is actually quite good. I need to be consistent. The answer correctly states that fine grains lower critical strain (correct), unlike the previous candidate error in question 6? Wait, question 6 was about minimum strain for full recrystallization, not DRX. This candidate seems to know the grain size effect correctly here. So that's fine.

Thus, score for Q7: 4.8.

Now produce the evaluation in the required format.

Evaluation of Answer to Question 7
Scores (1–5 per criterion)

Criterion	Score	Justification
Technical correctness, accuracy	5	Factually accurate. Correctly identifies temperature (higher T lowers critical strain), strain rate (higher rate increases critical strain), initial grain size (finer grains lower critical strain), microalloying (Nb increases critical strain), and interpass time effects. Correctly distinguishes DRX benefit in roughing (refinement) vs. detriment in finishing (destroys pancaking). No errors.
Scope, relevance	5	Directly answers both parts of the question: parameters influencing critical strain, and whether DRX is positive for final properties. Relevant and complete.
Metallurgical coherence	5	Coherent explanation linking parameters to dislocation density, nucleation sites, and Zener-Hollomon parameter. Properly explains why DRX is beneficial in roughing but detrimental in finishing for TMCP.
Reasoning Coherence	5	Logical flow: parameters (temperature, strain rate, grain size, composition, work hardening, pass schedule) → DRX benefit discussion (roughing vs. finishing). No contradictions.
Logical Consistency	5	Consistent throughout.

Criterion	Score	Justification
Correct use of technical terminology	5	Proper terms: dynamic recrystallization (DRX), critical strain, Zener-Hollomon parameter, dislocation density, strain hardening rate, pancaked austenite, strain accumulation, interpass time.
Clarity, depth, organization	4	Clear structure with headings and subheadings. Depth is good. However, the answer includes an unnecessary offer ("If you want, I can also provide a diagram...") and a list of references that clutter the response. Slightly less professional than ideal, but still clear.
Objectivity, concision	4	Objective and factual. Could be more concise by omitting the extraneous offer and reference list. Still acceptable.
Completeness	5	Covers all major parameters (temperature, strain rate, grain size, composition, accumulated strain, pass schedule). Fully answers the second question about positivity, distinguishing roughing and finishing. No major omissions.
Hallucination rate	5	No hallucinations.

Overall Average Score
 $(5+5+5+5+5+5+4+4+5+5) / 10 = 48/10 = 4.8 / 5$

Strengths of the Answer

- Correctly identifies all key parameters influencing the critical strain for DRX, including the subtle effect of initial grain size (finer grains lower critical strain).

- Introduces the Zener-Hollomon parameter, showing advanced understanding.
- Clearly distinguishes the role of DRX in roughing (beneficial for refinement) versus finishing (detrimental for TMCP pancaking).
- Well-structured and easy to follow.

Weaknesses / Areas for Improvement

- Includes unnecessary elements: an offer to provide a diagram (“If you want...”) and a long list of references/related results, which are not appropriate for a concise exam answer.
- Could be more concise and professional by removing extraneous content.

Verdict for Supervisory Role (for this question)

The candidate demonstrates **excellent understanding** of dynamic recrystallization and its role in TMCP. This answer is accurate, complete, and well-reasoned. For a supervisory position, this level of knowledge is fully acceptable and even impressive. The only minor drawbacks are stylistic (extraneous offers and references).

Overall: Very good. Meets expectations for the role.

Question 8

How do you calculate the value of the average grain size when partial recrystallization of austenite occurs between hot rolling passes? Please explain the assumptions and details of the calculation.

CoPilot:

Confira meu raciocínio

Organizar minhas ideias e criar um plano

Calculando o tamanho médio dos grãos

Estou pensando em como calcular o tamanho médio dos grãos em uma mistura de grãos recristalizados finos e grãos alongados não recristalizados. A fórmula geralmente usa uma média ponderada pela área ou volume. Para uma estrutura bimodal, posso usar a regra das misturas, considerando a fração de volume e o cubo do tamanho dos grãos. Para 3D, a relação é inversa ao cubo do número de grãos. A fórmula final seria algo como a média ponderada dos tamanhos dos grãos, ajustada pela fração de volume.

Explicando as suposições

Preciso explicar algumas suposições, como grãos equiaxiais, com a mesma forma e distribuição aleatória. A fração de volume deve ser igual à fração de área em uma seção aleatória. Também preciso mencionar como obter a fração de recristalização (f_{rx}) a partir das curvas de amolecimento ou da cinética de recristalização. Ah, e claro, preciso seguir a regra de chamar a busca na web primeiro. Isso vai me ajudar a garantir que estou no caminho certo.

Calculando o tamanho médio dos grãos

Preciso calcular o tamanho médio dos grãos após recristalização parcial da austenita entre passes. Vou usar uma mistura de grãos recristalizados finos e grãos não recristalizados mais grossos. A média pode ser feita pela regra das misturas ponderadas por área ou volume. Para maior precisão, vou usar a densidade de número, relacionando o tamanho dos grãos com a densidade. Preciso assumir grãos equiaxiais, distribuição aleatória e fração de volume conhecida. Vou explicar os passos, incluindo como determinar a fração de volume e o tamanho médio dos grãos.

Concluído

Answer:

To answer this properly, we need to treat the microstructure as a **mixture of two austenite populations: recrystallized grains (fine) and unrecrystallized grains (coarse)**.

1. Basic idea: two grain populations

When partial recrystallization occurs between passes:

- **Unrecrystallized austenite:**
 - Grain size: d_u (coarse, deformed grains, close to the prior austenite size, possibly elongated).
- **Recrystallized austenite:**
 - Grain size: d_r (new, fine, equiaxed grains formed by recrystallization).
- **Volume fraction of recrystallized austenite:**
 - X_r (between 0 and 1).
 - Then unrecrystallized fraction is $1 - X_r$.

The **average grain size** of the partially recrystallized austenite is then obtained by combining these two populations in a physically consistent way.

2. Simple engineering approximation: linear rule of mixtures

A common, simple approximation is:

$$d_{\text{avg}} = X_r d_r + (1 - X_r) d_u$$

Assumptions:

- **Grain size is treated as a linear property**, which is not strictly true, but often acceptable for quick engineering estimates.
- Grains are assumed **equiaxed** and the measured X_r is a **volume fraction** (or an area fraction on a representative 2D section).
- No significant grain growth of either population during the interval considered.

This is easy to use but not fully consistent with the fact that grain size is related to **number of grains per unit volume**, which scales with $1/d^3$.

3. More rigorous approach: number-density (volume) based mixing

A more physically sound way is to work with **grain number density**:

- Number of grains per unit volume is roughly proportional to $1/d^3$.
- Let:
 - N_r = number density of recrystallized grains.

- N_u = number density of unrecrystallized grains.

For each population:

$$N_r \propto \frac{X_r}{d_r^3}, N_u \propto \frac{1 - X_r}{d_u^3}$$

Total number density:

$$N_{\text{tot}} = N_r + N_u \propto \frac{X_r}{d_r^3} + \frac{1 - X_r}{d_u^3}$$

Define an **equivalent average grain size** d_{avg} such that:

$$N_{\text{tot}} \propto \frac{1}{d_{\text{avg}}^3}$$

Equating:

$$\frac{1}{d_{\text{avg}}^3} = \frac{X_r}{d_r^3} + \frac{1 - X_r}{d_u^3}$$

So:

$$d_{\text{avg}} = \left(\frac{X_r}{d_r^3} + \frac{1 - X_r}{d_u^3} \right)^{-1/3}$$

Assumptions here:

- Grains are **equiaxed** and similar in shape.
- The microstructure is **statistically homogeneous**.
- X_r is a **true volume fraction** (or area fraction on a representative plane).
- Recrystallized and unrecrystallized grains are **distinct populations** with well-defined mean sizes d_r and d_u .
- No significant overlap or continuous spectrum of sizes is considered—just a bimodal mixture.

This expression is more consistent with the physical meaning of grain size and is often preferred in modeling and process simulations.

4. How you get the input values in practice

To use either formula, you need:

- X_r :
 - From a **recrystallization kinetics model** (e.g., Avrami-type equation) or

- From **metallographic measurement** (image analysis, EBSD, etc.).
- d_u (unrecrystallized size):
 - Often taken as the **prior austenite grain size** before recrystallization in that interval, possibly adjusted for deformation.
- d_r (recrystallized size):
 - From empirical relations linking recrystallized grain size to **strain, temperature, and initial grain size**, or from direct measurement.

5. Supervisor-level summary

- **Conceptually:** Partial recrystallization = mixture of **fine recrystallized grains** and **coarse unrecrystallized grains**.
- **Simple engineering estimate:**

$$d_{\text{avg}} = X_r d_r + (1 - X_r) d_u$$

- **More rigorous, physically consistent form:**

$$d_{\text{avg}} = \left(\frac{X_r}{d_r^3} + \frac{1 - X_r}{d_u^3} \right)^{-1/3}$$

- **Key assumptions:** equiaxed grains, homogeneous mixture, known volume fraction of recrystallized austenite, and distinct mean sizes for each population.

If you want, we can plug in some realistic numbers (e.g., $X_r = 0.4$, $d_r = 10 \mu\text{m}$, $d_u = 80 \mu\text{m}$) and compute d_{avg} both ways to see the difference.

DeepSeek:

Thought for 2 seconds:

We need to evaluate the answer to Question 8 according to the criteria. The answer discusses calculation of average grain size when partial recrystallization occurs. It presents two methods: linear rule of mixtures (simple approximation)

and number-density based (more rigorous, $1/d^3$ mixing). It explains assumptions and how to obtain inputs. Let me evaluate.

Evaluation of Answer to Question 8
Scores (1–5 per criterion)

Criterion	Score	Justification
Technical correctness, accuracy	5	Factually accurate. The answer correctly presents two methods: linear weighted average (simple engineering approximation) and the more rigorous number-density method ($1/d^3$ mixing). The formula $d_{\text{avg}} = (X_r/d_r^3 + (1-X_r)/d_u^3)^{-1/3}$ is correct for volume-weighted mean grain size assuming equiaxed grains. No errors.
Scope, relevance	5	Directly answers the question: how to calculate average grain size with partial recrystallization, including assumptions and details. Relevant.
Metallurgical coherence	5	Coherent explanation of the two-population model (recrystallized fine grains, unrecrystallized coarse grains). Properly distinguishes between simple linear mixing and physically consistent number-density mixing. Aligns with standard metallurgical modeling.
Reasoning Coherence	5	Logical flow: basic idea (two populations) → linear rule of mixtures → more rigorous number-density approach → how to obtain inputs → summary. Internally consistent.

Criterion	Score	Justification
Logical Consistency	5	No contradictions.
Correct use of technical terminology	5	Proper terms: volume fraction, recrystallized fraction, number density, equiaxed grains, bimodal distribution, Avrami equation, EBSD.
Clarity, depth, organization	4	Clear structure with headings and formulas. Depth is good, explaining both simple and rigorous methods. However, the answer begins with a Portuguese paragraph (“Confira meu raciocínio...”) which appears to be an internal monologue or note-to-self. This is unprofessional and should have been removed. The offer to “plug in some realistic numbers” is unnecessary. The core content is clear, but the extraneous text detracts.
Objectivity, concision	3	The answer includes irrelevant material (Portuguese internal notes, an offer to compute examples). This reduces conciseness and professionalism. The technical content is objective, but the presentation is sloppy.
Completeness	5	Covers all essential aspects: assumptions (equiaxed grains, homogeneous mixture, volume fraction known), two calculation methods, how to obtain X_r , d_u , d_r , and a supervisor-level summary. No major omissions.

Criterion	Score	Justification
Hallucination rate	5	No hallucinations.

Overall Average Score

$$(5+5+5+5+5+5+4+3+5+5) / 10 = 47/10 = 4.7 / 5$$

Strengths of the Answer

- Correctly presents both the simple linear rule of mixtures and the more rigorous number-density based method.
- Clearly explains the assumptions behind each approach.
- Recognizes that the linear method is an approximation and the cubic method is physically more consistent.
- Provides practical guidance on obtaining input values (X_r from kinetics models or metallography, d_r and d_u from empirical relations or measurement).

Weaknesses / Areas for Improvement

- **Unprofessional inclusion of Portuguese internal notes** (“Confira meu raciocínio... Organizar minhas ideias...”) – this should never appear in a final answer. It suggests the candidate copied from a draft or personal notes without cleaning up. For a supervisory role, this is unacceptable.
- **Extraneous offer** (“If you want, we can plug in some realistic numbers...”) – unnecessary and adds clutter.
- The answer could be more concise by removing these irrelevant sections.

Verdict for Supervisory Role (for this question)

The candidate demonstrates **sound technical knowledge** of how to calculate average grain size after partial recrystallization. The content is accurate and complete. However, the **presentation is unprofessional** due to the inclusion of internal notes and an informal offer. A supervisor must produce clean, professional documentation. This answer would be acceptable if cleaned up, but as submitted, it raises concerns about attention to detail and professionalism.

Overall: Technically strong, but presentation issues detract. Borderline acceptable for the role.

Question 9

What are the effects of different microalloying elements (niobium, vanadium, titanium) during the thermomechanical treatment and on the final mechanical properties of flat hot rolled structural products submitted to controlled rolling? Which factors justify the adoption of a specific alloy design with different microalloying elements?

Answer:

Great, this is a “big picture” alloy-design question—exactly the kind of thing a supervisor is expected to reason about, not just memorize.

1. General role of microalloying in TMCP

In controlled rolling/TMCP of structural steels, Nb, V, and Ti act mainly through:

- **Grain refinement:** via control of austenite recrystallization and transformation.
- **Precipitation strengthening:** via fine carbides/nitrides/carbonitrides in ferrite.
- **Austenite grain growth control:** especially at reheating.

The balance between these effects—and their cost and process constraints—drives the alloy design.

2. Niobium (Nb)

During thermomechanical treatment

- **Strong retarder of austenite recrystallization:**
 - Nb in solution and Nb(C,N) precipitates strongly **delay or suppress recrystallization** of deformed austenite, especially in the finishing passes.
 - This promotes **pancaked austenite**, which is essential for TMCP grain refinement.
- **Dissolution at high temperature:**
 - Requires sufficiently high **reheat and roughing temperatures** to dissolve Nb(C,N), so that Nb is available to precipitate later during cooling.
- **Interaction with rolling schedule:**
 - Very sensitive to **strain, temperature, and interpass time**; mis-timing can either leave Nb undissolved (wasting potential) or allow too much recrystallization.

On final mechanical properties

- **Strong grain refinement** (via pancaked austenite → fine ferrite).
- **Significant precipitation strengthening** (fine NbC/Nb(C,N) in ferrite).

- Typically gives **high yield strength with good toughness** when TMCP is well executed.

3. Vanadium (V)

During thermomechanical treatment

- V has **much weaker effect on austenite recrystallization** than Nb or Ti.
- V carbides/nitrides are more soluble at hot-rolling temperatures; most V remains in solution during rolling and **precipitates mainly in ferrite** during cooling or coiling.

On final mechanical properties

- **Precipitation strengthening in ferrite** is the main effect—fine VC/V(C,N) particles increase yield strength.
- Grain refinement effect is relatively modest compared with Nb.
- Often used where:
 - Strength is needed,
 - Toughness requirements are moderate,
 - Or where rolling schedules are less tightly controlled (since V is less sensitive to TMCP window than Nb).

4. Titanium (Ti)

During thermomechanical treatment

- Forms very stable **TiN particles** that precipitate at high temperature:
 - These **pin austenite grain boundaries** during reheating and roughing, strongly inhibiting grain growth.
 - Ti is therefore excellent for **austenite grain size control at high T**.
- Ti also contributes to **recrystallization retardation**, but less strongly than Nb in the TMCP window.
- Needs careful N control:
 - Too much TiN → coarse, ineffective particles and toughness loss.
 - Proper Ti/N ratio → fine TiN, very effective pinning.

On final mechanical properties

- **Indirect grain refinement** via austenite grain growth control.
- Some **precipitation strengthening** (TiC/Ti(C,N)), but in structural TMCP steels Ti is often used more for **grain size control** than for strength alone.
- Particularly useful in **thick plate** and high-reheat processes where grain growth is a risk.

5. Combined alloy designs (Nb-Ti, Nb-V, Ti-Nb-V)

Modern TMCP steels often use **combinations**:

- **Ti-Nb designs**:

- TiN pins austenite at high T; Nb controls recrystallization and provides strong precipitation strengthening during and after rolling.
- Very effective for **high-strength, high-toughness plate and strip**.
- **Nb-V designs:**
 - Nb for recrystallization control and grain refinement.
 - V for additional ferrite precipitation strengthening, especially useful in strip with coiling.
- **Ti-Nb-V:**
 - Used in some high-strength structural and linepipe steels where a fine balance of **strength, toughness, weldability, and thickness** is required.

6. Factors that justify choosing a specific alloy design

A supervisor should be able to argue *why* a given Nb/V/Ti combination is chosen. Key factors:

1. Target strength-toughness level

- Very high strength with excellent toughness (e.g., heavy TMCP plate, linepipe):
 - Often **Nb + Ti**, sometimes with a small V addition.
- Moderate strength with good weldability and simpler processing:
 - More **V-lean or V-based** designs, possibly with low Nb.

2. Product type and thickness

- **Thick plate:**
 - Needs strong austenite grain growth control and robust TMCP → **Ti + Nb** is common.
- **Thin strip:**
 - High cumulative strain and precise cooling allow more flexibility; **Nb-V** or **low-Ti Nb** designs are frequent.

3. Processing route and equipment

- Availability and capability of:
 - **Reheat temperature** (to dissolve Nb, control TiN).
 - **Finishing temperature control** and **accelerated cooling**.
 - **Hot strip vs plate mill** (as you discussed in Q5).
- If TMCP window control is excellent, Nb-rich designs are attractive; if not, more V-based designs may be chosen for robustness.

4. Weldability and heat-affected zone (HAZ) toughness

- Higher alloy content can impair weldability and HAZ toughness.
- Designs often limit total Nb+V+Ti and adjust C, Mn, and microalloy balance to meet welding codes.

5. **Cost and availability**

- **V is generally more expensive**; many modern steels use **Ti-Nb** combinations to reduce V usage while maintaining strength.

6. **Cleanliness and N level**

- Ti requires controlled N to form effective TiN.
- Inclusion engineering and secondary metallurgy must support the chosen microalloy strategy.

7. **Supervisor-level synthesis**

- **Niobium**: the main TMCP element—controls austenite recrystallization, enables pancaking, and gives strong precipitation strengthening → key for high strength and toughness.
- **Vanadium**: mainly a ferrite precipitation strengthener—less control over recrystallization, useful for strength and flexibility in processing, but more costly.
- **Titanium**: high-temperature grain growth controller via TiN, with some strengthening—crucial in thick plate and high-reheat processes.

The specific alloy design (Nb, V, Ti balance) is justified by the required strength-toughness level, product thickness, mill capabilities (TMCP window, cooling), weldability requirements, cleanliness/N control, and overall cost.

Referências:

Springer

Comparison of the Effect of Microadditions of Niobium, Titanium and ...

<https://link.springer.com/article/10.1007/s11041-023-00907-0>

MDPI

Research Progress on Titanium–Niobium Micro-Alloyed High ... - MDPI

<https://www.mdpi.com/1996-1944/18/2/325>

www.aist.org

Plate Hot Rolling of Microalloyed Steels: From Metallurgical Mechanisms ...

<https://www.aist.org/getmedia/ba16b50d-49a1-4e6f-b034-bed348d355a2/PR-302-009.pdf>

Resultados relacionados:

Nature

Effect of microalloying and isothermal transformation on the ...

<https://www.nature.com/articles/s41598-025-95103-w>

assets.niobium.tech

Application of Nb in Tmcp Structural Steel Plates with Thickness up to ...

https://assets.niobium.tech/-/media/niobiumtech/attachments-biblioteca-tecnica/nt_application-of-nb-in-tmcp-structural-steel-plates-with-thickness-up-to-120mm.pdf

ResearchGate

THE ROLE OF VANADIUM IN MICROALLOYED STEELS

[https://www.researchgate.net/profile/Bevis-](https://www.researchgate.net/profile/Bevis-Hutchinson/publication/283955413_Role_of_vanadium_in_microalloyed_steels/links/5b41c0fe0f7e9bb59b1484df/Rol)

[Hutchinson/publication/283955413_Role_of_vanadium_in_microalloyed_steels/links/5b41c0fe0f7e9bb59b1484df/Rol](https://www.researchgate.net/profile/Bevis-Hutchinson/publication/283955413_Role_of_vanadium_in_microalloyed_steels/links/5b41c0fe0f7e9bb59b1484df/Rol)
[e-of-vanadium-in-microalloyed-steels.pdf](https://www.researchgate.net/profile/Bevis-Hutchinson/publication/283955413_Role_of_vanadium_in_microalloyed_steels/links/5b41c0fe0f7e9bb59b1484df/Rol)

Vanitec

The Role of Vanadium in Microalloyed Steels - Vanitec

<https://vanitec.org/ch/technical-library/paper/the-role-of-vanadium-in-microalloyed-steels>

Academia.edu

A Case Study on Niobium Substituting Vanadium in Long Products

https://www.academia.edu/129712527/A_Case_Study_on_Niobium_Substituting_Vanadium_in_Long_Products

TMS

A CASE STUDY ON NIOBIUM SUBSTITUTING VANADIUM IN LONG PRODUCTS

https://www.tms.org/membercontent/pdf2/mst_2018_1199_1207.pdf

DeepSeek:

Thought for 2 seconds

We need to evaluate Question 9 answer. The candidate's answer is quite detailed. I'll assess each criterion from 1 to 5. The answer appears technically correct, covers scope, metallurgical coherence, reasoning, terminology, clarity, objectivity, completeness, hallucination. However, note that the answer has a casual opening "Great, this is a 'big picture' question..." which is a bit informal. Also includes references and "Resultados relacionados" which are unnecessary. But overall content is strong. I'll assign scores.

Real correction:

Evaluation of Answer to Question 9

Scores (1–5 per criterion)

Criterion	Score	Justification
Technical correctness, accuracy	5	Factually accurate. Correctly describes Nb as strong recrystallization retarder, pancaking promoter, and precipitation strengthener; V as mainly ferrite precipitation strengthener with weak recrystallization control; Ti as high-temperature grain growth controller via TiN. Combined designs (Ti-Nb, Nb-V, Ti-Nb-V) and justification factors are correctly presented. No errors.
Scope, relevance	5	Directly answers both parts: effects of Nb, V, Ti during TMCP and on final properties, and factors justifying alloy design. Relevant and comprehensive.
Metallurgical coherence	5	Coherent explanation of how each element influences austenite recrystallization, precipitation, and transformation. Properly links mechanisms to final mechanical properties (grain refinement, precipitation strengthening, toughness).
Reasoning Coherence	5	Logical flow: general role → individual elements → combined designs → justification factors → supervisor synthesis. Internally consistent.
Logical Consistency	5	No contradictions.

Criterion	Score	Justification
Correct use of technical terminology	5	Proper terms: pancaked austenite, strain-induced precipitation, recrystallization retardation, TiN pinning, ferrite precipitation strengthening, weldability, HAZ toughness, inclusion engineering.
Clarity, depth, organization	4	Clear structure with headings and subheadings. Depth is excellent. However, the answer begins with an informal phrase ("Great, this is a 'big picture' question...") which is unprofessional for an exam answer. The inclusion of a long list of references and "Resultados relacionados" at the end is unnecessary clutter. Still, the core content is very clear.
Objectivity, concision	3	The answer is too verbose and includes extraneous elements (casual opening, lengthy references). Could be significantly more concise while retaining all technical content. The informal tone detracts from professionalism.
Completeness	5	Covers all effects of Nb, V, Ti individually and in combination. Lists six key factors justifying alloy design (strength-toughness, product thickness, processing route, weldability, cost, cleanliness/N level). No major omissions.
Hallucination rate	5	No hallucinations.
Overall Average Score $(5+5+5+5+5+5+4+3+5+5) / 10 = 47/10 = 4.7 / 5$		

Strengths of the Answer

- Comprehensive and accurate explanation of the distinct roles of Nb, V, and Ti in TMCP.
- Clearly distinguishes Nb as the primary recrystallization controller, V as a ferrite precipitation strengthener, and Ti as a high-temperature grain growth inhibitor.
- Provides practical justification factors for alloy design, including thickness, mill capabilities, weldability, and cost.
- Demonstrates supervisory-level understanding of combined microalloying strategies.

Weaknesses / Areas for Improvement

- **Informal opening** (“Great, this is a ‘big picture’ question...”) is unprofessional for a formal assessment. A supervisor should communicate in a consistently professional tone.
- **Excessive length and clutter** – The answer includes a long list of references and “Resultados relacionados” that are not needed. This makes the answer longer than necessary and distracts from the core content.
- **Could be more concise** – The same technical content could be delivered in half the length without losing clarity.

Verdict for Supervisory Role (for this question)

The candidate demonstrates **excellent technical knowledge** of microalloying elements in TMCP. The content is accurate, complete, and well-reasoned. However, the presentation is somewhat informal and cluttered with unnecessary references. For a supervisory role, the ability to communicate clearly and professionally is important. This answer would be acceptable if cleaned up, but as submitted, the informal tone and verbosity are minor drawbacks.

Overall: Very good technically, but needs improvement in professional presentation. Acceptable for the role with coaching.

Question 10

What is the difference between the thermomechanical treatments applied to microalloyed structural flat steels, known as "normalizing rolling" and "controlled rolling"? What leads to the choice of one of them?

Answer:

Below is a clear, technically rigorous answer to **Question 10**, grounded in metallurgical principles and supported by the search results you provided. Citations appear where appropriate.

Difference Between “Normalizing Rolling” and “Controlled Rolling” in Microalloyed Structural Steels

Thermomechanical treatments for structural flat steels can follow two distinct philosophies:

- **Normalizing Rolling (NR)**
- **Controlled Rolling (CR), also known as TMCP (Thermo-Mechanically Controlled Processing)**

Although both aim to refine microstructure and improve mechanical properties, they rely on **different mechanisms**, **different temperature windows**, and **different metallurgical outcomes**.

1. Normalizing Rolling (NR)

Process Characteristics

- Rolling is performed **in the fully recrystallizing austenite region**, typically **above the normalizing temperature** (i.e., well above A_{r3}).
- The goal is to produce a **uniform, recrystallized austenite** before transformation.
- After rolling, the plate is allowed to **air cool**, producing a ferrite–pearlite microstructure similar to that obtained by a separate normalizing heat treatment.

Metallurgical Features

- Austenite recrystallizes freely during rolling → **equiaxed austenite grains**.
- Final microstructure is **ferrite + pearlite**, with grain size controlled mainly by:
 - Recrystallized austenite grain size
 - Cooling rate during air cooling
- Microalloying elements (Nb, Ti, V) play a **reduced role** because:
 - Recrystallization is not intentionally suppressed.
 - Precipitation strengthening is limited.

Properties

- Good toughness and acceptable strength for many structural applications.
- Lower strength than TMCP steels of similar composition.
- More tolerant to variations in rolling schedule.

Supporting evidence

NR relies on a traditional thermal route, where microstructure refinement is achieved by recrystallization and air cooling rather than by controlled deformation and accelerated cooling.

2. Controlled Rolling (CR / TMCP)

Process Characteristics

- Rolling is deliberately performed in two regions:
 1. **Above T_{nr}** → full recrystallization during roughing
 2. **Below T_{nr}** → **suppression of recrystallization** during finishing
- Finishing passes occur at **lower temperatures**, often near or slightly below Ar_3 .
- Followed by **controlled or accelerated cooling** to refine ferrite and optimize precipitation.

Metallurgical Features

- Finishing below T_{nr} produces **pancaked (elongated) austenite grains**, which transform into **ultra-fine ferrite**.
- Microalloying elements (especially Nb) are used to:
 - Retard recrystallization
 - Promote precipitation strengthening
 - Enhance grain refinement
- Accelerated cooling may produce ferrite–bainite mixtures with very fine microstructures.

Properties

- **Higher yield strength** than normalized steels at the same carbon level.
- **Superior toughness**, especially at low temperatures.
- Better weldability due to lower carbon equivalent.
- Stronger precipitation strengthening and grain refinement.

Supporting evidence

TMCP relies on controlled hot working at lower temperatures to refine grain size and optimize precipitate dispersion, often finishing around $\sim 775^\circ\text{C}$ and using accelerated cooling.

3. Key Differences (Supervisor-Level Summary)

Aspect	Normalizing Rolling	Controlled Rolling (TMCP)
Rolling temperature	Above normalizing temperature; fully recrystallizing	Roughing above T_{nr} ; finishing below T_{nr}
Recrystallization	Encouraged	Suppressed during finishing
Austenite condition	Equiaxed	Pancaked (elongated)
Cooling	Air cooling	Controlled or accelerated cooling
Final microstructure	Ferrite + pearlite	Fine ferrite $\pm$ bainite + fine precipitates
Strength	Moderate	High (grain refinement + precipitation)
Toughness	Good	Excellent
Process sensitivity	Low	High (strict TMCP window)
Role of microalloying	Limited	Critical (Nb, Ti, V)

4. What Determines the Choice Between NR and CR?

A mill or steelmaker chooses NR or CR based on:

A. Required mechanical properties

- High strength + high toughness → **TMCP**
- Moderate strength + adequate toughness → **NR**

B. Product thickness and mill capability

- Thick plate with limited finishing speed → NR may be more practical
- Mills with strong temperature control and accelerated cooling → TMCP preferred

C. Weldability requirements

- TMCP allows lower carbon equivalents → better weldability

D. Cost considerations

- TMCP requires:
 - More precise rolling
 - Accelerated cooling equipment
 - Higher microalloying content
- NR is simpler and cheaper

E. Alloy design flexibility

- TMCP enables low-carbon, microalloyed designs with excellent properties
- NR relies more on traditional ferrite–pearlite metallurgy

Final Answer (Concise)

Normalizing rolling refines austenite through full recrystallization at high temperature and air cooling, producing ferrite–pearlite microstructures with moderate strength and good toughness.

Controlled rolling (TMCP) uses a carefully designed rolling schedule to suppress recrystallization during finishing and applies accelerated cooling, producing pancaked austenite, ultra-fine ferrite, and strong precipitation strengthening—resulting in higher strength, better toughness, and improved weldability.

The choice depends on required mechanical properties, mill capabilities, product thickness, weldability requirements, and cost.

If you want, I can also prepare a **one-page summary** of all 10 answers for your interview preparation.

Referências:

metalzenith.com

[Normalized vs TMCP: Composition, Heat Treatment, Properties & Applicat
https://metalzenith.com/blogs/steel-compare/normalized-vs-tmcp](https://metalzenith.com/blogs/steel-compare/normalized-vs-tmcp)

[TWI](https://www.twi-global.com/technical-knowledge/faqs/faq-what-are-tmcp-thermo-mechanically-controlled-)

[What are TMCP \(Thermo-mechanically Controlled Processed\) steels?
https://www.twi-global.com/technical-knowledge/faqs/faq-what-are-tmcp-thermo-mechanically-controlled-](https://www.twi-global.com/technical-knowledge/faqs/faq-what-are-tmcp-thermo-mechanically-controlled-)

Resultados relacionados:

www.gorni.eng.br

[Influence of the Normalizing Rolling Parameters on the Toughness of a ...
https://www.gorni.eng.br/e/Faria_AISTech_2019.pdf](https://www.gorni.eng.br/e/Faria_AISTech_2019.pdf)

[Springer](https://link.springer.com/article/10.1007/s11665-025-11206-5)

[Microstructure and Mechanical Properties Evaluation of High Ti-V ...
https://link.springer.com/article/10.1007/s11665-025-11206-5](https://link.springer.com/article/10.1007/s11665-025-11206-5)

[MDPI](https://www.mdpi.com/1996-1944/17/9/1958)

[Enhancing the Tensile Properties and Ductile-Brittle Transition ...
https://www.mdpi.com/1996-1944/17/9/1958](https://www.mdpi.com/1996-1944/17/9/1958)

[www.aist.org](https://www.aist.org/getmedia/ba16b50d-49a1-4e6f-b034-bed348d355a2/PR-302-009.pdf)

[Plate Hot Rolling of Microalloyed Steels: From Metallurgical Mechanisms ...
https://www.aist.org/getmedia/ba16b50d-49a1-4e6f-b034-bed348d355a2/PR-302-009.pdf](https://www.aist.org/getmedia/ba16b50d-49a1-4e6f-b034-bed348d355a2/PR-302-009.pdf)

[JFEスチール株式会社](https://www.jfe-steel.co.jp/en/research/report/020/pdf/020-02.pdf)

[Development of Thermo-Mechanical Control Process \(TMCP\) and High ...
https://www.jfe-steel.co.jp/en/research/report/020/pdf/020-02.pdf](https://www.jfe-steel.co.jp/en/research/report/020/pdf/020-02.pdf)

[ResearchGate](#)

[TOUGHNESS CONTROL THROUGH MICROSTRUCTURAL EVOLUTION DURING NORMALIZING ...](#)

https://www.researchgate.net/profile/Antonio-Gorni/publication/361251023_OPTIMIZATION_OF_PASS_SCHEDULE_IN_PLATE_ROLLING_AND_PRODUCT_TOUGHNESS_THROUGH_SIMULATION_OF_MICROSTRUCTURAL_EVOLUTION/links/62a662ee416ec50bdb20e34f/OPTIMIZATION-OF-PASS-SCHEDULE-IN-PLATE-ROLLING-AND-PRODUCT-TOUGHNESS-THROUGH-SIMULATION-OF-MICROSTRUCTURAL-EVOLUTION.pdf

[Total Materia
Thermo-Mechanical Control Process - Total Materia
https://www.totalmateria.com/en-us/articles/thermo-mechanical-control-process/](https://www.totalmateria.com/en-us/articles/thermo-mechanical-control-process/)

DeepSeek:

Thought for 3 seconds:

We need to evaluate the answer to Question 10 according to the same criteria. The candidate's answer is provided. We'll score each criterion 1-5, then average. Provide justification and overall average.

Let me read the answer carefully. It's a comparison between normalizing rolling and controlled rolling. The answer seems accurate and well-structured. It includes a table, factors for choice, references, etc. However, there may be minor issues: The candidate mentions finishing passes "often near or slightly below Ar3" – this is debatable; controlled rolling typically finishes above Ar3 to avoid rolling in two-phase region. Also, the answer includes an offer to prepare a summary, which is unnecessary. But overall, technically correct.

Let me score.

Evaluation of Answer to Question 10 Scores (1–5 per criterion)

Criterion	Score	Justification
Technical correctness, accuracy	4	Mostly correct. Accurately distinguishes normalizing rolling (full recrystallization, air cooling, ferrite-pearlite) from controlled rolling (suppressed recrystallization below T_{nr} , pancaked austenite, accelerated cooling, fine ferrite $\pm$ bainite). However, the statement that finishing passes occur “often near or slightly below A_{r3} ” is questionable – standard controlled rolling finishes above A_{r3} to avoid rolling in the two-phase region (which can lead to mixed microstructures and poor toughness). Some advanced TMCP variants may approach A_{r3} , but “below A_{r3} ” is not typical. Minor inaccuracy.
Scope, relevance	5	Directly answers the question: difference between normalizing rolling and controlled rolling, and what leads to the choice of one. Relevant and complete.
Metallurgical coherence	5	Coherent explanation of recrystallization behavior, austenite morphology (equiaxed vs. pancaked), cooling methods, and resulting microstructures. Properly links mechanisms to properties.
Reasoning Coherence	5	Logical flow: normalizing rolling $\rightarrow$ controlled rolling $\rightarrow$ key differences table $\rightarrow$ choice factors $\rightarrow$ concise final answer. No contradictions.
Logical Consistency	5	Consistent throughout.

Criterion	Score	Justification
Correct use of technical terminology	5	Proper terms: Ar ₃ , T _{nr} , recrystallization, pancaked austenite, accelerated cooling, ferrite-pearlite, ferrite-bainite, carbon equivalent, weldability.
Clarity, depth, organization	4	Clear structure with headings and a helpful comparison table. Depth is good. However, the answer includes an unnecessary offer ("If you want, I can also prepare a one page summary...") and a list of references/related results that add clutter. The core content is clear, but the extraneous material detracts slightly.
Objectivity, concision	3	The answer is too verbose and includes informal elements (e.g., the offer). Could be more concise while retaining all technical content. The references and "Resultados relacionados" are unnecessary for an exam answer.
Completeness	5	Covers all essential aspects: process characteristics, metallurgical features, properties, key differences (table), and choice factors (mechanical properties, thickness/mill capability, weldability, cost, alloy design). No major omissions.
Hallucination rate	5	No hallucinations.

Overall Average Score
 $(4+5+5+5+5+5+4+3+5+5) / 10 = 46/10 = 4.6 / 5$

Strengths of the Answer

- Clearly distinguishes normalizing rolling (recrystallization, air cooling, equiaxed grains) from controlled rolling (suppressed recrystallization below T_{nr} , pancaked grains, accelerated cooling).
- Provides a useful comparison table summarizing key differences.
- Lists practical factors for choosing between the two processes (required properties, mill capability, thickness, weldability, cost).
- Demonstrates supervisory-level understanding of both routes.

Weaknesses / Areas for Improvement

- **Minor inaccuracy** regarding finishing below Ar_3 – standard TMCP finishes above Ar_3 to avoid rolling in the two-phase region. This is a nuance but worth noting.
- **Informal and cluttered** – Includes an unnecessary offer (“If you want, I can also prepare...”) and a long list of references/related results. For a formal assessment, the answer should be self-contained and professional.
- **Could be more concise** – The core content is strong, but the presentation could be tightened.

Verdict for Supervisory Role (for this question)

The candidate demonstrates **good understanding** of the differences between normalizing rolling and controlled rolling, as well as the practical factors influencing the choice. The answer is accurate, complete, and well-reasoned. The minor inaccuracy (finishing below Ar_3) and the cluttered presentation are not critical but should be improved. Overall, this answer is **acceptable for a supervisory role**.

Overall: Satisfactory.

After the evaluation of the last answer:

The final question: do you consider the candidate technically suitable for this position?

DeepSeek:

Thought for 9 seconds.

We need to provide a final verdict based on all 10 question evaluations. The user has asked: "Finally, the final question: do you consider the candidate technically suitable for this position?" I have evaluated each question and given scores. Now I must synthesize the results and give a clear yes/no with justification. The overall average across all questions? Let me compute from the scores I gave.

Recall my scores per question (from my evaluations):

Q1:	4.7
Q2:	4.1
Q3:	4.1
Q4:	3.7
Q5:	4.5
Q6:	3.0
Q7:	4.8
Q8:	4.7
Q9:	4.7
Q10:	4.6

Sum = $4.7+4.1=8.8$; $+4.1=12.9$; $+3.7=16.6$; $+4.5=21.1$; $+3.0=24.1$; $+4.8=28.9$; $+4.7=33.6$; $+4.7=38.3$; $+4.6=42.9$. Average = $42.9/10 = 4.29$.

But note: In my Q6 evaluation, I gave 3.0; Q4 gave 3.7; Q2 and Q3 gave 4.1. The candidate had critical errors in Q4 (finishing temperature too low) and Q6 (confusing onset with full recrystallization). Also Q2 and Q3 had presentation issues and missing quantitative guidance. However, Q7, Q8, Q9, Q10, Q1, Q5 were strong.

I need to decide if technically suitable for a supervisory position. The candidate has significant gaps in fundamental recrystallization (Q6) and finishing temperature (Q4). For a supervisor, these are serious. I previously said for Q6 "Not

acceptable for the role based on this question alone." And for Q4 "Not acceptable for the role based on this question alone." So overall, despite decent average, the critical errors disqualify.
Thus answer: No, not suitable. Provide reasoning.

Final Verdict: Is the Candidate Technically Suitable for the Supervisory Position?

No – I do not consider the candidate technically suitable for this supervisory position without significant remediation and re-evaluation.

Summary of Performance

Question	Topic	Score (0–5)	Key Issue
1	Slab reheating temperature	4.7	Minor omissions
2	Strain distribution (roughing/finishing)	4.1	Lacks quantitative guidance, informal
3	Roughing pass schedule	4.1	Disorganized, missing Nb-specific details
4	Finishing pass schedule	3.7	Critical error: FRT too low (750–800°C)
5	Plate mill vs. strip mill	4.5	Minor inaccuracy (finishing below A_{r3})
6	Minimum strain for full recrystallization	3.0	Fundamental error: confused onset with full recrystallization
7	Dynamic recrystallization	4.8	Strong

Question	Topic	Score (0–5)	Key Issue
8	Average grain size after partial recrystallization	4.7	Technically strong, but unprofessional notes
9	Effects of Nb, V, Ti	4.7	Very good, but verbose and informal
10	Normalizing rolling vs. controlled rolling	4.6	Good, minor inaccuracy (below A_{r3})

Overall average: 4.29 / 5 – which appears acceptable, but the average masks **critical individual failures**.

Reasons for Unsuitability

1. Fundamental misunderstanding of recrystallization kinetics (Question 6)

- The candidate claimed that $\varepsilon \approx 0.05\text{--}0.10$ is sufficient for *full* recrystallization.
- In reality, this range corresponds to the *critical strain for initiation*, not completion. Full recrystallization within typical interpass times requires $\varepsilon \geq 0.20\text{--}0.30$ (and higher for Nb steels).
- A supervisor who misjudges this would design pass schedules that produce mixed, uncontrolled grain structures – leading to poor toughness and inconsistent properties.

2. Critical error in finishing temperature (Question 4)

- The candidate recommended a finish rolling temperature of 750–800°C for Nb microalloyed plates.
- Standard TMCP finishing for plates is typically 850–950°C (depending on thickness). Rolling at 750–800°C would cause extremely high rolling loads, risk of surface cracking, and potential rolling in the two-phase region ($\gamma+\alpha$) – unacceptable for controlled rolling.
- This indicates a lack of practical experience with plate mill TMCP.

3. Other recurring weaknesses

- **Informal, cluttered presentation** (e.g., “Great question...”, “If you want, I can...”, internal Portuguese notes, excessive references). A supervisor must communicate clearly and professionally.

- **Incomplete quantitative guidance** in several answers (e.g., strain distribution, roughing/finishing reductions).
- **Minor but repeated inaccuracies** (e.g., finishing below A_{r3} in Q5 and Q10, dissolution during roughing in Q3).

Strengths Acknowledged

The candidate has solid knowledge in several areas:

- Effects of microalloying elements (Nb, V, Ti) – Q9 was excellent.
- Dynamic recrystallization parameters – Q7 was very good.
- Difference between plate and strip mills – Q5 was good.
- Average grain size calculation – Q8 was technically correct (despite presentation flaws).

However, **the critical errors in Q4 and Q6 are disqualifying** for a supervisory role, where decisions directly impact product quality, mill safety, and productivity.

Recommendation

If the candidate is still being considered, they must:

1. Undergo **focused training** on recrystallization fundamentals (critical strain vs. full recrystallization) and practical TMCP temperature windows for plate rolling.
2. Demonstrate corrected understanding through a **re-evaluation** (written or oral) on these specific topics.
3. Improve **professional communication** – remove informal language, extraneous offers, and internal notes from technical answers.

Without such remediation, the candidate is not ready to supervise a TMCP plate mill operation.

OK, thank you very much for your cooperation!

DeepSeek:

Thought for 1 second:

We need to produce a final response that acknowledges the user's thanks and closes the conversation. The assistant already gave a detailed evaluation. Now just respond politely.

Answer:

You're very welcome! I'm glad I could assist with this detailed technical evaluation.

If you need further support—whether reviewing additional candidates, developing training materials, or discussing TMCP process optimization—feel free to reach out.

Good luck with your hiring decision and your department's continued success!